

Fischerwerke GmbH & Co. KG
Otto-Hahn-Straße 15
79211 Denzlingen
GERMANY

Eurofins Product Testing A/S
Smedeskovvej 38
8464 Galten
Denmark

CustomerSupport@eurofins.com
www.eurofins.com/VOC-testing

VOC TEST REPORT

VOC Content

21 August 2019

1 Sample Information

Sample name	FIS V 360 S
Sample no.	392-2019-10249901
Production date	21.06.2019
Batch No.	1917
Sample reception	26/06/2019

2 Brief Evaluation of the Results

Regulation or protocol	Conclusion	Version of regulation or protocol
SCAQMD Rule 1168	Pass	October 2017
LEED v4 (VOC Content)	Pass	

Full details based on the testing and direct comparison with limit values are available in the following pages



Morten Sielemann
Analytical Chemist

3 Applied Test Methods

3.1 General Test References

Regulation, protocol or standard	Scope	Version
SCAQMD Rule 1168	Adhesive and sealant applications	October 2017

3.2 Specific Laboratory Sampling and Analyses

Test	Regulation, protocol or standard	Version	Internal SOP	Limit of detection	Uncertainty U _m
				[g/L]	%
Solids Content	ASTM D2369	2010	71 M 544830	1	10
VOC	ASTM D2369	2010	71 M 544830	1	10

3.3 Preparation of the Test Specimen

The sample was mixed according to the manufacturer's specification. The mixing ratio was 5:1. The sample was left to cure for 1 hour before applying a portion of the sample to the test dish.

4 Results

	Remarks on the test results	Results	Unit
Density *	Supplied by the Customer	1.7	g/mL
Water Content *	Supplied by the Customer	76	g/L
Exempt compounds *	Assumed to be 0	0	% (w/w)
Solids Content	Tested by the lab	94.1	% (w/w)
VOC content (less water)	Calculated based on the results above	27	g/L
VOC content (less water)	Calculated based on the results above	1.6	% (w/w)

4.1 Comparison with Limit Values of VOC Content (less Water)

Parameter	Results	Product type	Regulation or protocol	VOC limit
	[g/L]			[g/L]
VOC content	27	Multipurpose Construction Adhesives	SCAQMD Rule 1168	70

The results are only valid for the tested sample(s).

This report may only be copied or reprinted in its entirety, parts of it only with a written acceptance by Eurofins.

5 Appendices

5.1 How to Understand the Results

5.1.1 Acronyms Used in the Report

- < Means less than
- > Means bigger than
- * Not a part of our accreditation
- ⌘ Please see section regarding uncertainty in the Appendices.
- 1 Analysed by another Eurofins laboratory

5.2 Description of VOC Content Test

5.2.1 Testing of VOC

Volatile content of the sample was determined gravimetrically by heating to 110 °C in 60 minutes. Multicomponent products are mixed according to the manufacturer's instructions and allowed to cure before heating.

The result is the average of two replicates. The result was calculated as:

$$VOC = \frac{([g \text{ All Volatiles}] - [g \text{ Water}] - [g \text{ Exempt Compounds}])}{([liter \text{ Material}] - [liter \text{ Water}] - [liter \text{ Exempt Compounds}])}$$

5.3 Uncertainty of the Test Method

Um(%): The expanded uncertainty Um is equal to 2 x RSD%.