



Independent Expert Report

on the assessment of the adhesive injection anchor fischer FIS EM Plus
for anchoring in uncracked and cracked concrete for a
working life up to 120 years
based on EAD 330499-02-0601

Client: fischerwerke GmbH & Co. KG
Otto-Hahn-Straße 15
79211 Denzlingen

Contract dated: March 26, 2024

Report No.: 24-053-1

Date: June 16, 2024

Validity of this Expert Report: 5 years

This Expert Report comprises 4 pages.

The injection system fischer FIS EM Plus of company fischerwerke GmbH & Co. KG is an adhesive anchor consisting of a cartridge with injection mortar fischer FIS EM Plus and steel elements. It received a Technical Assessment Document (ETA) in 2019 [1]. The ETA covers fastenings in uncracked and cracked concrete of strength classes C20/25 to C50/60 with threaded rods M8 to M30 of different strength classes and corrosion resistance classes and with deformed reinforcing bars $\varnothing 8$ to $\varnothing 40$. The allowable use conditions and characteristic strength values for steel, concrete and bond between steel parts and concrete were evaluated in [6] based on EAD 330499-00-0601 [3]. The characteristic bond strength values are given for temperature ranges T1: 35°C/60°C (maximum long- term temperature / maximum short- term temperature) and T2: 50 °C/72 °C.

The EAD [3] is valid for a working life of fastenings up to 50 years. The next edition EAD 330499-01-0601 [4] covers also an extended working life of 100 years. The characteristic bond strength values of bonded anchors FIS EM Plus for a working life of 100 years were assessed in [7] based on [4]. These values are also given in the ETA [1].

To improve some service conditions and to cover an additional temperature range (24 °C/40 °C), additional tests were performed, which were evaluated in [9] based on EAD 330499-02-0601 [5]. The results are incorporated in [2]. Furthermore, fractional sizes of threaded rods and reinforcing bars are incorporated in [2] based on [8].

The company fischerwerke GmbH & Co. KG has commissioned the Engineering Office IEA to derive the characteristic resistances and admissible service conditions of the system fischer FIS EM Plus as approved in [2] for a working life up to 120 years based on EAD 330499-02-0601 [5].

For the assessment of the behaviour of bonded anchors FIS EM Plus for a working life of 120 years the results of sustained load tests [10] with a test duration of 6000 hours and tests in opening and closing cracks [11], [12] with 2400 crack opening cycles as well as information given in literature ([13] to [18]) on the behaviour of bonded anchors under sustained load and during crack cycling were taken into account. The tests [10] and [12] were performed by company fischerwerke. They were supervised by an

independent engineer on behalf of the engineering office IEA. Because [5] is valid for a working life of 100 years, the test conditions and assessment criteria given in [5] were adjusted to a design working life of 120 years. The evaluation of the test results and of the use conditions for a working life up to 120 years are described in detail in the Expert Report [19].

The bond strength $\tau_{\text{Rk},120}$ for a working life of 120 years is calculated according to Equation (1)

$$\tau_{\text{Rk},120} = \alpha_{120} \cdot \tau_{\text{Rk},100} \quad (1)$$

where

$\tau_{\text{Rk},100}$ = bond strength for a working life of 100 years given in [2]

α_{120} = reduction factor.

For bonded anchors FIS EM Plus in uncracked and cracked concrete the following reduction factors are recommended [19]:

$\alpha_{120} = 0,8$ Temperature range T1 (24 °C/40 °C),


$\alpha_{120} = 0,9$ Temperature ranges T2 (35 °C/60 °C) and T3 (50 °C/72 °C).

The factors ψ_{sus}^0 given in [2] may also be used for a working life of 120 years:

T1: $\psi_{\text{sus}}^0 = 0,77$, T2: $\psi_{\text{sus}}^0 = 0,60$, T3: $\psi_{\text{sus}}^0 = 0,71$.

Note, that indications given on the working life cannot be interpreted as a guarantee given by the producer but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

All other design provisions given in [2] are valid for a working life up to 120 years.



Prof. Dr. Ing. R. Eligehausen

Literature

- [1] ETA-17/0979, 'fischer injection system FIS EM PLUS; bonded fastener for use in concrete'. June 17, 2020
- [2] ETA-17/0979 ,fischer injection system FIS EM Plus, bonded fastener for use in concrete'. April 22, 2024
- [2] EAD 330499-00-0601 'Bonded fasteners for use in concrete', Sept. 2015
- [3] EAD 330499-01-0601 'Bonded fasteners for use in concrete', Dec. 2018
- [5] EAD 330499-02-0601 ,'Bonded fasteners for use in concrete'. Dec. 2023
- [6] IEA GmbH & Co. KG: Evaluation Report 17-053 on the 'Upgrade of fischer FIS EM PLUS adhesive anchors using additional tests for the assessment according to draft EAD 330499-00-0601 and ETAG 001, Part 5', Stuttgart, Oct. 10, 2017.
- [7] IEA GmbH & Co. KG: Evaluation Report 18-038 on 'Assessment of adhesive anchors fischer FIS EM Plus for anchoring in uncracked and cracked concrete for a design service life of 100 years based on EAD 330499-01-0601', Stuttgart, Nov. 7, 2018, Rev. 1: March 3, 2019.
- [8] IEA GmbH & Co. KG, Evaluation Report 19-040, Rev. 1: Assessment of bonded anchors FIS EM Plus with threaded rods and rebars (inch and metric sizes) for anchoring in uncracked and cracked concrete in accordance with AC308 and ACI 355.4-11. Stuttgart, Feb. 02, 2021.
- [9] Fixing solutions GmbH: Evaluation Report for Fischer FIS EM Plus Improving of Performance, Stuttgart, 04.03.2024.
- [10] fischerwerke: Test report: E-C 1692-2019, Dauerstandversuche mit FIS EM Plus für Service life time 120 years, Entwicklung Chemie, Denzlingen, 05.03.2019.
- [11] Universität für Bodenkultur Wien, Institut für konstruktiven Ingenieurbau, Akkreditierte Prüfstelle: Test Report Nr. 875-19-004, Versuche am fischer Verbundanker FIS EM Plus mit Gewindestangen M10 und M16 nach EAD 330499-00-0601 inkl. TR 048 unter Berücksichtigung von EAD 332077-00-0601, Wien, 14.03.2019.
- [12] fischerwerke: Test Report: E-C 1695-2019, Risswechselfersuche mit FIS EM Plus für Service life time 120 years mit den Größen M8 und M12', Entwicklung Chemie, Denzlingen, 15.03.2019.
- [13] Silva, J., Eligehausen, R.: Assessment and design of adhesive anchors in concrete for sustained loading. Hilti corporation, Schaan, Principality of Liechtenstein, 2008.
- [14] Davis, T.M.: Sustained Load Performance of Adhesive Anchor Systems in Concrete. PhD Thesis, University of Florida, 2012.
- [15] Eligehausen, R.; Blochwitz, R., Fuchs, W.: Behavior and design of adhesive anchors under sustained loading. ACI Special Publication SP-283, Understanding Adhesive Anchors: Behavior, Materials, Installation, Design. 2012. Pages 9.1 – 9.14.
- [16] Cook, R.A.; Douglas E.P. Davis, T.M.; Liu, C.: Long-Term Performance of Epoxy Adhesive Anchor Systems. Transportation Research Board, Washington, D.C., 2013.
- [17] Davis, T.M.; Cook, R.A.: Sustained Load Performance of Adhesive Anchor Systems in Concrete. ACI Structural Journal, July-August 2017. Pages 951 – 957.
- [18] Blochwitz, R.: Verbunddübelssysteme unter dauerhafter Lasteinwirkung. Dissertation, Universität Stuttgart, 2019.
- [19] IEA GmbH & Co. KG: Expert Report 24-053, Rev.1 on Assessment of adhesive anchors fischer FIS EM Plus for anchoring in uncracked and cracked concrete for a working life of 120 years based on EAD 330499-02-0601, Stuttgart, June 61, 2024