

DECLARACIÓN DE PRESTACIONES

DoP 0201

para el sistema de inyección de Upat UPM44 (Anclaje químico para uso en hormigón)

ES

1. <u>Código de identificación única del producto tipo:</u>	DoP 0201
2. <u>Usos previstos:</u>	Fijación a posteriori en hormigón fisurado y no fisurado. Véase el apéndice, especialmente los anexos B1- B10
3. <u>Fabricante:</u>	Upat Vertriebs GmbH, Bebelstraße 11, 79108 Freiburg im Breisgau, Alemania
4. <u>Representante autorizado:</u>	-
5. <u>Sistemas de evaluación y verificación de la constancia de las prestaciones (EVCP):</u>	1
6. <u>Documento de evaluación europeo:</u> Evaluación técnica europea: Organismo de evaluación técnica: Organismos notificados:	EAD 330499-01-0601, Edition 04/2020 ETA-02/0022; 2020-07-28 DIBt- Deutsches Institut für Bautechnik 2873 TU Darmstadt
7. <u>Prestaciones declaradas:</u> Resistencia mecánica y estabilidad (BWR 1) Resistencia característica a tracción (carga estática y cuasi-estática):	Resistencia de rotura del acero: Anexos C1-C3 $E_S = 210\ 000 \text{ MPa}$ Resistencia para la combinación de rotura por cono de hormigón y extracción: Anexos C5-C8 $\tau_{RK,100} = \text{NPD}$ Resistencia de rotura por cono de hormigón: Anexo C4 Distancia al borde para evitar la rotura del acero sometido a carga: Anexo C4 Robustez: Anexos C4-C8,C13,C14 Par máximo de montaje: Anexos B3, B4, B6 Distancia mínima entre el borde y el centro: Anexos B3- B6
Resistencia característica a cortante (carga estática y cuasi-estática):	Resistencia de rotura del acero: Anexos C1- C3 Resistencia falla por arrancamiento lateral: Anexo C4 Resistencia de rotura del hormigón al borde: Anexo C4
Resistencia y desplazamientos característicos para las categorías sísmicas C1 y C2:	Resistencia a carga de tracción, desplazamientos, categoría C1: Anexos C11-C13 Resistencia a carga de tracción, desplazamientos, categoría C2: Anexos C11,C12,C14 Resistencia a esfuerzo cortante, desplazamientos, categoría C1: Anexos C11,C12 Resistencia a esfuerzo cortante, desplazamientos, categoría C2: Anexos C11,C12,C14 Factor espacio anular: Anexo C11
Desplazamientos bajo carga a corto y largo plazo:	Desplazamientos bajo carga a corto y largo plazo: Anexos C9, C10
Higiene, salud y medio ambiente (BWR 3) Contenido, emisión y/o desprendimiento de sustancias peligrosas:	NPD



Einfach. Sicher. Upat

8. Documentación técnica adecuada o documentación técnica específica: -

Las prestaciones del producto identificado anteriormente son conformes con el conjunto de prestaciones declaradas. La presente declaración de prestaciones se emite, de conformidad con el Reglamento (UE) no 305/2011, bajo la sola responsabilidad del fabricante arriba identificado.

Firmado por y en nombre del fabricante por:

Dr. Oliver Geibig, Director General Unidades de Negocio e Ingeniería
Tumlingen, 2020-08-11

Jürgen Grün, Director General de Química y Calidad

Esta DdR se ha preparado en distintos idiomas. En caso de que haya alguna controversia sobre la interpretación prevalecerá siempre la versión inglesa.

El Apéndice incluye información voluntaria y complementaria en idioma inglés que excede los requisitos legales (de idioma neutral).

Specific Part

1 Technical description of the product

The "injection system UPM 44" is a bonded fastener consisting of a cartridge with injection mortar UPM 44, UPM 44 Relax or UPM 44 Express and a steel element according to Annex A5.

The steel element is placed into a drilled hole filled with injection mortar and is anchored via the bond between metal part, injection mortar and concrete.

The product description is given in Annex A.

2 Specification of the intended use in accordance with the applicable European Assessment Document

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the anchor of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment

3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Characteristic resistance to tension load (static and quasi-static loading)	See Annex B 3 to B 6, C 1 to C 8
Characteristic resistance to shear load (static and quasi-static loading)	See Annex C 1 to C 4
Displacements under short-term and long-term loading	See Annex C 9 and C 10
Characteristic resistance and displacements for seismic performance categories C1 and C2	See Annex C 11 to C 14

3.2 Hygiene, health and the environment (BWR 3)

Essential characteristic	Performance
Content, emission and/or release of dangerous substances	No performance assessed

4

Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base


In accordance with the European Assessment Document EAD 330499-01-0601 the applicable European legal act is: [96/582/EC].

The system to be applied is: 1


Installation conditions part 1

Upat anchor rod


Pre-positioned installation



Push through installation (annular gap filled with mortar)



Pre-positioned or push through installation with subsequently injected filling disc (annular gap filled with mortar)



Figures not to scale

h_0 = drill hole depth

h_{ef} = effective embedment depth

t_{fix} = thickness of fixture

injection system UPM 44

Product description

Installation conditions part 1


Annex A 1

Appendix 3 / 32


Installation conditions part 2

Upat Internal threaded anchor IST

Pre-positioned installation



Pre-positioned installation with subsequently injected filling disc (annular gap filled with mortar)



Figures not to scale

h_0 = drill hole depth

h_{ef} = effective embedment depth

t_{fix} = thickness of fixture

injection system UPM 44

Product description


Installation conditions part 2

Annex A 2

Appendix 4 / 32


Installation conditions part 3

Reinforcing bar




Upat rebar anchor FRA

Pre-positioned installation



Push through installation (annular gap filled with mortar)



Figures not to scale

h_0 = drill hole depth

h_{ef} = effective embedment depth

t_{fix} = thickness of fixture

injection system UPM 44

Product description



Installation conditions part 3

Annex A 3



Appendix 5 / 32

Overview system components part 1



Injection cartridge (shuttle cartridge) with sealing cap; Sizes: 350 ml, 360 ml, 390 ml, 550 ml, 1100 ml, 1500 ml




Injection cartridge (coaxial cartridge) with sealing cap; Sizes: 100 ml, 150 ml, 300 ml, 380 ml, 400 ml, 410 ml



Static mixer Upat MR Plus or UMR



Injection adapter and Extension tube for static mixer



Cleaning brush UP BS



Blow-out pump UPM or ABP



Figures not to scale

injection system UPM 44

Product description

Overview system components part 1;
cartridges / static mixer / accessories

Annex A 4

Overview system components part 2

Upat anchor rod

Size: M6, M8, M10, M12, M16, M20, M24, M27, M30




Upat internal threaded anchor IST


Size: M8, M10, M12, M16, M20



Screw / threaded rod / washer / hexagon nut



Filling disc with injection adapter



Reinforcing bar

Nominal diameter: $\phi 8, \phi 10, \phi 12, \phi 14, \phi 16, \phi 20, \phi 25, \phi 28$



Upat rebar anchor FRA

Size: M12, M16, M20, M24



Figures not to scale

injection system UPM 44

Product description

Overview system components part 2;
steel components

Annex A 5

Appendix 7 / 32

Table A6.1: Materials

Part	Designation	Material		
1	Injection cartridge	Mortar, hardener, filler		
Steel grade	Steel	Stainless steel R	High corrosion resistant steel HCR	
	zinc plated	acc. to EN 10088-1:2014 Corrosion resistance class CRC III acc. to EN 1993-1-4:2015	acc. to EN 10088-1:2014 Corrosion resistance class CRC V acc. to EN 1993-1-4:2015	
2	Anchor rod	Property class 4.8, 5.8 or 8.8; EN ISO 898-1:2013 zinc plated $\geq 5 \mu\text{m}$, ISO 4042:2018/Zn5/An(A2K) or hot dip galvanised $\geq 40 \mu\text{m}$ EN ISO 10684:2004 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 12\%$ fracture elongation	Property class 50, 70 or 80 EN ISO 3506-1:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; 1.4062, 1.4662, 1.4462; EN 10088-1:2014 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 12\%$ fracture elongation	Property class 50 or 80 EN ISO 3506-1:2009 or property class 70 with $f_{yk} = 560 \text{ N/mm}^2$ 1.4565; 1.4529; EN 10088-1:2014 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 12\%$ fracture elongation
		Fracture elongation $A_5 > 8\%$, for applications without requirements for seismic performance category C2		
3	Washer ISO 7089:2000	zinc plated $\geq 5 \mu\text{m}$, ISO 4042:2018/Zn5/An(A2K) or hot dip galvanised $\geq 40 \mu\text{m}$ EN ISO 10684:2004	1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2014	1.4565; 1.4529; EN 10088-1:2014
4	Hexagon nut	Property class 4, 5 or 8; EN ISO 898-2:2012 zinc plated $\geq 5 \mu\text{m}$, ISO 4042:2018/Zn5/An(A2K) or hot dip galvanised $\geq 40 \mu\text{m}$ EN ISO 10684:2004	Property class 50, 70 or 80 EN ISO 3506-1:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2014	Property class 50, 70 or 80 EN ISO 3506-1:2009 1.4565; 1.4529; EN 10088-1:2014
5	Upat internal threaded anchor IST	Property class 5.8 ISO 898-1:2013 zinc plated $\geq 5 \mu\text{m}$, ISO 4042:2018/Zn5/An(A2K)	Property class 70 EN ISO 3506-1:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2014	Property class 70 EN ISO 3506-1:2009 1.4565; 1.4529; EN 10088-1:2014
6	Commercial standard screw or threaded rod for Upat internal threaded anchor IST	Property class 5.8 or 8.8; EN ISO 898-1:2013 zinc plated $\geq 5 \mu\text{m}$, ISO 4042:2018/Zn5/An(A2K) $A_5 > 8\%$ fracture elongation	Property class 70 EN ISO 3506-1:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2014 $A_5 > 8\%$ fracture elongation	Property class 70 EN ISO 3506-1:2009 1.4565; 1.4529; EN 10088-1:2014 $A_5 > 8\%$ fracture elongation
7	filling disc similar to DIN 6319-G	zinc plated $\geq 5 \mu\text{m}$, ISO 4042:2018/Zn5/An(A2K) or hot dip galvanised $\geq 40 \mu\text{m}$ EN ISO 10684:2004	1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2014	1.4565; 1.4529; EN 10088-1:2014
8	Reinforcing bar EN 1992-1-1:2004 and AC:2010, Annex C	Bars and de-coiled rods, class B or C with f_{yk} and k according to NDP or NCL of according to EN 1992-1-1/NA $f_{uk} = f_{tk} = k \cdot f_{yk}$		
9	Upat rebar anchor FRA	Rebar part: Bars and de-coiled rods class B or C with f_{yk} and k according to NDP or NCL of EN 1992-1-1:2004+AC:2010 $f_{uk} = f_{tk} = k \cdot f_{yk}$	Threaded part: Property class 70 or 80 EN ISO 3506-1:2009 1.4401, 1.4404, 1.4571, 1.4578, 1.4439, 1.4362, 1.4062 acc. to EN 10088-1:2014 Corrosion resistance class CRC III acc. to EN 1993-1-4:2015 1.4565; 1.4529 acc. to EN 10088-1:2014 Corrosion resistance class CRC V acc. to EN 1993-1-4:2015	

injection system UPM 44

Product description
Materials
Annex A 6

Appendix 8 / 32

Specifications of intended use (part 1)

Table B1.1: Overview use and performance categories

Anchorage subject to		UPM 44 with ...													
		Anchor rod	Upat internal threaded anchor IST	Reinforcing bar		Upat rebar anchor FRA									
Hammer drilling with standard drill bit															
Hammer drilling with hollow drill bit (fischer "FHD", Heller "Duster Expert"; Bosch „Speed Clean“; Hilti "TE-CD, TE-YD"), DreBo D-Plus, DreBo D-Max															
		all sizes													
		Nominal drill bit diameter (d_0) 12 mm to 35 mm													
Static and quasi static load, in	uncracked concrete	all sizes	Tables: C1.1 C4.1 C5.1 C9.1	all sizes	Tables: C2.1 C4.1 C6.1 C9.2	all sizes	Tables: C3.1 C4.1 C7.1 C10.1	all sizes	Tables: C3.2 C4.1 C8.1 C10.2						
	cracked concrete	M8 to M30		- ²⁾		ϕ 10 to ϕ 28									
Seismic performance category (only hammer drilling with standard / hollow drill bits)	C1 ¹⁾	M10 to M30	Tables: C11.1 C12.1 C13.1	- ²⁾		- ²⁾		- ²⁾							
	C2 ¹⁾	M12 M16 M20 M24	Tables: C11.1 C12.1 C14.1	- ²⁾		- ²⁾		- ²⁾							
Use category	I1	dry or wet concrete	all sizes												
	I2	water filled hole	M 12 to M 30	all sizes		- ²⁾		- ²⁾							
Installation direction	D3 (downward and horizontal and upwards (e.g. overhead) installation)														
Installation temperature	$T_{i,\min} = -10 \text{ }^{\circ}\text{C}$ to $T_{i,\max} = +40 \text{ }^{\circ}\text{C}$														
In-service temperature	Temperature range I	-40 $\text{ }^{\circ}\text{C}$ to +80 $\text{ }^{\circ}\text{C}$		(max. short term temperature +80 $\text{ }^{\circ}\text{C}$; max. long term temperature +50 $\text{ }^{\circ}\text{C}$)											
	Temperature range II	-40 $\text{ }^{\circ}\text{C}$ to +120 $\text{ }^{\circ}\text{C}$		(max. short term temperature +120 $\text{ }^{\circ}\text{C}$; max. long term temperature +72 $\text{ }^{\circ}\text{C}$)											

¹⁾ Not for UPM 44 Relax or UPM 44 Express

²⁾ No performance assessed

injection system UPM 44

Intended use
Specifications (part 1)

Annex B 1

Appendix 9 / 32

Specifications of intended use (part 2)

Base materials:

- Compacted reinforced or unreinforced normal weight concrete without fibres of strength classes C20/25 to C50/60 according to EN 206:2013+A1:2016

Use conditions (Environmental conditions):

- Structures subject to dry internal conditions (zinc coated steel, stainless steel or high corrosion resistant steel).
- For all other conditions according to EN1993-1-4:2015 corresponding to corrosion resistance classes to Annex A 6 table A6.1.

Design:

- Anchorages have to be designed by a responsible engineer with experience of concrete anchor design.
- Verifiable calculation notes and drawings are to be prepared taking account of the loads to be anchored. The position of the anchor is indicated on the design drawings (e. g. position of the anchor relative to reinforcement or to supports, etc.).
- Anchorages are designed in accordance with:
EN 1992-4:2018 and EOTA Technical Report TR 055, Edition February 2018.

Installation:

- Anchor installation is to be carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters of the site
- In case of aborted hole: The hole shall be filled with mortar
- Anchorage depth should be marked and adhered to on installation
- Overhead installation is allowed

injection system UPM 44

Intended use
Specifications (part 2)


Annex B 2

Appendix 10 / 32

Table B3.1: Installation parameters for anchor rods

Anchor rods	Thread	M6	M8	M10	M12	M16	M20	M24	M27	M30	
Width across flats	SW [mm]	10	13	17	19	24	30	36	41	46	
Nominal drill hole diameter		8	10	12	14	18	24	28	30	35	
Drill hole depth		$h_0 = h_{\text{ef}}$									
Effective embedment depth		50	60	60	70	80	90	96	108	120	
embedment depth		72	160	200	240	320	400	480	540	600	
Minimum spacing and minimum edge distance		40	40	45	55	65	85	105	125	140	
Diameter of the clearance hole of the fixture		7	9	12	14	18	22	26	30	33	
pre-positioned installation		9	12	14	16	20	26	30	33	40	
push through installation		$h_{\text{ef}} + 30 (\geq 100)$				$h_{\text{ef}} + 2d_0$					
Minimum thickness of concrete member		h_{min}									
Maximum installation torque	max T_{inst}	[Nm]	5	10	20	40	60	120	150	200	300


Upat anchor rod



Marking (on random place) Upat anchor rod:

Steel zinc plated PC ¹⁾ 8.8	• or +	Steel hot-dip PC ¹⁾ 8.8	●
High corrosion resistant steel HCR PC ¹⁾ 50	•	High corrosion resistant steel HCR PC ¹⁾ 70	-
High corrosion resistant steel HCR PC ¹⁾ 80	(Stainless steel R property class 50	~
Stainless steel R property class 80	*		
Alternatively: Colour coding according to DIN 976-1: 2016			¹⁾ PC = property class

Installation conditions:



Commercial standard threaded rods, washers and hexagon nuts may also be used if the following requirements are fulfilled

- Materials, dimensions and mechanical properties according to Annex A 6, Table A6.1
- Inspection certificate 3.1 according to EN 10204:2004, the documents have to be stored
- Setting depth is marked

Figures not to scale

injection system UPM 44

Intended use
Installation parameters anchor rods


Annex B 3

Appendix 11 / 32

Table B4.1: Installation parameters for Upat internal threaded anchors IST

Internal threaded anchors IST	Thread	M8	M10	M12	M16	M20
Diameter of anchor	d _{nom} = d _H [mm]	12	16	18	22	28
Nominal drill hole diameter		14	18	20	24	32
Drill hole depth		$h_0 = h_{ef} = L_H$				
Effective embedment depth (h _{ef} = L _H)		90	90	125	160	200
Minimum spacing and minimum edge distance		55	65	75	95	125
Diameter of clearance hole in the fixture		9	12	14	18	22
Minimum thickness of concrete member		120	125	165	205	260
Maximum screw-in depth l _{E,max}		18	23	26	35	45
Minimum screw-in depth l _{E,min}		8	10	12	16	20
Maximum installation torque max T _{inst}	[Nm]	10	20	40	80	120

Upat internal threaded anchor IST




Marking: Anchor size e. g.: **M10**

Stainless steel → additional **R**; e.g.: **M10 R**

High corrosion resistant steel → additional **HCR**; e.g.: **M10 HCR**

Retaining bolt or threaded rods (including nut and washer) must comply with the appropriate material and strength class of Annex A 6, Table A6.1

Installation conditions:



Figures not to scale

injection system UPM 44

Intended use

Installation parameters Upat internal threaded anchors IST

Annex B 4

Table B5.1: Installation parameters for reinforcing bars

Nominal diameter of the bar	ϕ	8 ¹⁾	10 ¹⁾	12 ¹⁾	14	16	20	25	28
Nominal drill hole diameter	d_0	10	12	12	14	14	16	18	20
Drill hole depth	h_0							$h_0 = h_{\text{ef}}$	
Effective embedment depth	$h_{\text{ef,min}}$	60	60	70	75	80	90	100	112
	$h_{\text{ef,max}}$	160	200	240	280	320	400	500	560
Minimum spacing and minimum edge distance	$s_{\text{min}} = c_{\text{min}}$	40	45	55	60	65	85	110	130
Minimum thickness of concrete member	h_{min}	$h_{\text{ef}} + 30$ (≥ 100)			$h_{\text{ef}} + 2d_0$				


¹⁾ Both drill hole diameters can be used

Reinforcing bar



- The minimum value of related rib area $f_{R,\text{min}}$ must fulfil the requirements of EN 1992-1-1:2004+AC:2010
- The rib height must be within the range: $0,05 \cdot \phi \leq h_{\text{rib}} \leq 0,07 \cdot \phi$
(ϕ = Nominal diameter of the bar, h_{rib} = rib height)

Installation conditions:



Figures not to scale

injection system UPM 44

Intended use
Installation parameters reinforcing bars


Annex B 5

Table B6.1: Installation parameters for Upat rebar anchor FRA

Rebar anchor FRA	Thread	M12 ¹⁾	M16	M20	M24
Nominal diameter of the bar ϕ		12	16	20	25
Width across flats SW		19	24	30	36
Nominal drill hole diameter d_0		14	16	20	25
Drill hole depth h_0				$h_{ef} + l_e$	
Effective embedment depth $h_{ef,min}$		70	80	90	96
Effective embedment depth $h_{ef,max}$		140	220	300	380
Distance concrete surface to welded joint l_e				100	
Minimum spacing and minimum edge distance $s_{min} = c_{min}$	[mm]	55	65	85	105
Diameter of clearance hole in the fixture pre-positioned anchorage $\leq d_f$		14	18	22	26
Diameter of clearance hole in the fixture push through anchorage $\leq d_f$		18	22	26	32
Minimum thickness of concrete member h_{min}		$h_0 + 30$		$h_0 + 2d_0$	
Maximum installation torque max T_{inst}	[Nm]	40	60	120	150

¹⁾ Both drill hole diameters can be used


Upat rebar anchor FRA



Marking frontal e. g.:

 FRA (for stainless steel);
 FRA HCR (for high corrosion resistant steel)

Installation conditions:



Figures not to scale

injection system UPM 44


Intended use
Installation parameters rebar anchor FRA

Annex B 6

Table B7.1: Parameters of the **cleaning brush UP BS** (steel brush with steel bristles)

The size of the cleaning brush refers to the drill hole diameter

Nominal drill hole diameter	d_0	[mm]	8	10	12	14	16	18	20	24	25	28	30	35
Steel brush diameter	d_b		9	11	14	16		20		25	26	27	30	40

**Table B7.2 Maximum processing time of the mortar and minimum curing time**

(During the curing time of the mortar the concrete temperature may not fall below the listed minimum temperature)

Temperature at anchoring base [°C]	Maximum processing time t_{work}			Minimum curing time ¹⁾ t_{cure}		
	UPM 44 Express	UPM 44	UPM 44 Relax	UPM 44 Express	UPM 44	UPM 44 Relax
-10 to -5 ²⁾	-	-	-	12 h	-	-
> -5 to 0 ²⁾	5 min	-	-	3 h	24 h	-
> 0 to 5 ²⁾	5 min	13 min	-	3 h	3 h	6 h
> 5 to 10	3 min	9 min	20 min	50 min	90 min	3 h
> 10 to 20	1 min	5 min	10 min	30 min	60 min	2 h
> 20 to 30	-	4 min	6 min	-	45 min	60 min
> 30 to 40	-	2 min	4 min	-	35 min	30 min

¹⁾ In wet concrete or water filled holes the curing times must be doubled²⁾ Minimal cartridge temperature +5°C

injection system UPM 44

Intended use





Cleaning brush (steel brush)

Processing time and curing time

Annex B 7



Installation instructions part 1

Drilling and cleaning the hole (hammer drilling with standard drill bit)

1		Drill the hole. Nominal drill hole diameter d_0 and drill hole depth h_0 see tables B3.1, B4.1, B5.1, B6.1
2		Clean the drill hole: For $h_{ef} \leq 12d$ and $d_0 < 18$ mm blow out the hole four times by hand
3		Brush the drill hole four times. For deep holes use an extension. Corresponding brushes see table B7.1
4		Clean the drill hole: For $h_{ef} \leq 12d$ and $d_0 < 18$ mm blow out the hole four times by hand

Go to step 5

Drilling and cleaning the hole (hammer drilling with hollow drill bit)

1		Check a suitable hollow drill (see table B1.1) for correct operation of the dust extraction
2		Use a suitable dust extraction system, e. g. fischer FVC 35 M or a comparable dust extraction system with equivalent performance data Drill the hole with hollow drill bit. The dust extraction system has to extract the drill dust nonstop during the drilling process and must be adjusted to maximum power. Nominal drill hole diameter d_0 and drill hole depth h_0 see tables B3.1, B4.1, B5.1, B6.1

Go to step 5




injection system UPM 44

Intended use
Installation instructions part 1

Annex B 8




Installation instructions part 2

Preparing the cartridge

5		Remove the sealing cap Screw on the static mixer (the spiral in the static mixer must be clearly visible)
6		 Place the cartridge into the dispenser
7		 Extrude approximately 10 cm of material out until the resin is evenly grey in colour. Do not use mortar that is not uniformly grey

Go to step 8

Injection of the mortar

8			
	Fill approximately 2/3 of the drill hole with mortar. Always begin from the bottom of the hole and avoid bubbles	For drill hole depth ≥ 150 mm use an extension tube	For overhead installation, deep holes ($h_0 > 250$ mm) or drill hole diameter ($d_0 \geq 40$ mm) use an injection adapter

Go to step 9

injection system UPM 44

Intended use
Installation instructions part 2

Annex B 9

Appendix 17 / 32

Installation instructions part 3

Installation of anchor rods or Upat internal threaded anchors IST

9		Only use clean and oil-free metal parts. Mark the setting depth of the metal part. Push the anchor rod or Upat internal threaded IST anchor down to the bottom of the hole, turning it slightly while doing so. After inserting the metal parts, excess mortar must be emerged around the anchor element.
		For overhead installations support the metal part with wedges (e.g. centering wedges) or fischer overhead clips.
10		Wait for the specified curing time t_{cure} see table B7.2
Option		After the minimum curing time is reached, the gap between metal part and fixture (annular clearance) may be filled with mortar via the filling disc. Compressive strength $\geq 50 \text{ N/mm}^2$ (e.g. injection mortars UPM 33, UPM 44, UPM 55). ATTENTION: Using filling disc reduces t_{fix} (usable length of the anchor)

Installation reinforcing bars and Upat rebar anchor FRA

9		Only use clean and oil-free reinforcing bars or Upat rebar anchor FRA. Mark the setting depth. Turn while using force to push the reinforcement bar or the Upat rebar anchor FRA into the filled hole up to the setting depth mark
10		Wait for the specified curing time t_{cure} see table B7.2
11		Mounting the fixture max T_{inst} see tables B3.1 and B4.1

injection system UPM 44

Intended use
Installation instructions part 3

Annex B 10

Table C1.1: Characteristic values for steel failure under tension / shear load of Upat anchor rods and standard threaded rods

Anchor rod / standard threaded rod			M6	M8	M10	M12	M16	M20	M24	M27	M30				
Bearing capacity under tension load, steel failure ³⁾															
Characteristic resistance $N_{Rk,s}$	Steel zinc plated	Property class	4.8	8	15(13)	23(21)	33	63	98	141	184	224			
			5.8	10	19(17)	29(27)	43	79	123	177	230	281			
			8.8	16	29(27)	47(43)	68	126	196	282	368	449			
	Stainless steel R and high corrosion resistant steel HCR		50	10	19	29	43	79	123	177	230	281			
			70	14	26	41	59	110	172	247	322	393			
			80	16	30	47	68	126	196	282	368	449			
Partial factors ¹⁾															
Partial factor $\gamma_{Ms,N}$	Steel zinc plated	Property class	4.8	[-]	1,50										
			5.8		1,50										
			8.8		1,50										
			50		2,86										
			70		1,50 ²⁾ / 1,87										
			80		1,60										
Bearing capacity under shear load, steel failure ³⁾															
without lever arm															
Characteristic resistance $V_{Rk,s}^0$	Steel zinc plated	Property class	4.8	[kN]	4	9(8)	14(13)	20	38	59	85	110	135		
			5.8		6	11(10)	17(16)	25	47	74	106	138	168		
			8.8		8	15(13)	23(21)	34	63	98	141	184	225		
	Stainless steel R and high corrosion resistant steel HCR		50		5	9	15	21	39	61	89	115	141		
			70		7	13	20	30	55	86	124	161	197		
			80		8	15	23	34	63	98	141	184	225		
Ductility factor			k_7		1,0										
with lever arm															
Charact. resistance $M_{Rk,s}^0$	Steel zinc plated	Property class	4.8	[Nm]	6	15(13)	30(27)	52	133	259	448	665	899		
			5.8		7	19(16)	37(33)	65	166	324	560	833	1123		
			8.8		12	30(26)	60(53)	105	266	519	896	1333	1797		
	Stainless steel R and high corrosion resistant steel HCR		50		7	19	37	65	166	324	560	833	1123		
			70		10	26	52	92	232	454	784	1167	1573		
			80		12	30	60	105	266	519	896	1333	1797		
Partial factors ¹⁾															
Partial factor $\gamma_{Ms,V}$	Steel zinc plated	Property class	4.8	[-]	1,25										
			5.8		1,25										
			8.8		1,25										
	Stainless steel R and high corrosion resistant steel HCR		50		2,38										
			70		1,25 ²⁾ / 1,56										
			80		1,33										
¹⁾ In absence of other national regulations															
²⁾ Only admissible for high corrosion resist. steel HCR, with $f_yk / f_{uk} \geq 0,8$ and $A_s > 12\%$ (e.g. Upat anchor rods)															
³⁾ Values in brackets are valid for undersized threaded rods with smaller stress area A_s for hot dip galvanised standard threaded rods according to EN ISO 10684:2004+AC:2009															
injection system UPM 44										Annex C 1					
Performances Characteristic values for steel failure under tension / shear load of Upat anchor rods and standard threaded rods										Appendix 19 / 32					

Table C2.1: Characteristic values for steel failure under tension / shear load of Upat internal threaded anchors IST

Upat internal threaded anchors IST		M8	M10	M12	M16	M20		
Bearing capacity under tension load, steel failure								
Charact. resistance with screw	N _{Rk,s}	Property class 5.8	[kN]	19	29	43	79	123
		Property class 8.8		29	47	68	108	179
		Property class R		26	41	59	110	172
		Property class 70		26	41	59	110	172
Partial factors¹⁾								
Partial factors	γ _{Ms,N}	Property class 5.8	[-]		1,50			
		Property class 8.8			1,50			
		Property class R			1,87			
		Property class 70			1,87			
Bearing capacity under shear load, steel failure								
Without lever arm								
Charact. resistance with screw	V ⁰ _{Rk,s}	Property class 5.8	[kN]	9,2	14,5	21,1	39,2	62,0
		Property class 8.8		14,6	23,2	33,7	54,0	90,0
		Property class R		12,8	20,3	29,5	54,8	86,0
		Property class 70		12,8	20,3	29,5	54,8	86,0
Ductility factor		k ₇	[-]		1,0			
With lever arm								
Charact. resistance with screw	M ⁰ _{Rk,s}	Property class 5.8	[Nm]	20	39	68	173	337
		Property class 8.8		30	60	105	266	519
		Property class R		26	52	92	232	454
		Property class 70		26	52	92	232	454
Partial factors¹⁾								
Partial factors	γ _{Ms,V}	Property class 5.8	[-]		1,25			
		Property class 8.8			1,25			
		Property class R			1,56			
		Property class 70			1,56			

¹⁾ In absence of other national regulations

Table C3.1: Characteristic values for steel failure under tension / shear load of reinforcing bars

Nominal diameter of the bar	ϕ	8	10	12	14	16	20	25	28							
Bearing capacity under tension load, steel failure																
Characteristic resistance	$N_{Rk,s}$	[kN]	$A_s \cdot f_{uk}^{1)}$													
Bearing capacity under shear load, steel failure																
Without lever arm																
Characteristic resistance	$V_{Rk,s}^0$	[kN]	$0,5 \cdot A_s \cdot f_{uk}^{1)}$													
Ductility factor	k_7	[-]	1,0													
With lever arm																
Characteristic resistance	$M_{Rk,s}^0$	[Nm]	$1,2 \cdot W_{el} \cdot f_{uk}^{1)}$													

¹⁾ f_{uk} or f_{yk} respectively must be taken from the specifications of the reinforcing bar

Table C3.2: Characteristic values for steel failure under tension / shear load of Upat rebar anchors FRA

Upat rebar anchor FRA		M12	M16	M20	M24			
Bearing capacity under tension load, steel failure								
Characteristic resistance	$N_{Rk,s}$	[kN]	63	111	173			
Partial factor¹⁾								
Partial factor	$\gamma_{Ms,N}$	[-]	1,4					
Bearing capacity under shear load, steel failure								
Without lever arm								
Characteristic resistance	$V_{Rk,s}^0$	[kN]	30	55	86			
Ductility factor	k_7	[-]	1,0					
With lever arm								
Characteristic resistance	$M_{Rk,s}^0$	[Nm]	92	233	454			
Partial factor¹⁾								
Partial factor	$\gamma_{Ms,V}$	[-]	1,56					

¹⁾ In absence of other national regulations

injection system UPM 44

Performances

Characteristic values for steel failure under tension / shear load of reinforcing bars and Upat rebar anchors FRA

Annex C 3

Table C4.1: Characteristic values for concrete failure under tension / shear load

Size	All sizes										
Tension load											
Installation factor	γ_{inst}	[-]	See annex C 5 to C 8 and C 13 to C14								
Factors for the compressive strength of concrete > C20/25											
Increasing factor for τ_{RK}	C25/30	Ψ_c [-]	1,05								
	C30/37		1,10								
	C35/45		1,15								
	C40/50		1,19								
	C45/55		1,22								
	C50/60		1,26								
Splitting failure											
Edge distance	$h / h_{ef} \geq 2,0$	$C_{cr,sp}$ [mm]	1,0 h_{ef}								
	$2,0 > h / h_{ef} > 1,3$		4,6 h_{ef} - 1,8 h								
	$h / h_{ef} \leq 1,3$		2,26 h_{ef}								
Spacing	$S_{cr,sp}$		2 $C_{cr,sp}$								
Concrete cone failure											
Uncracked concrete	$k_{ucr,N}$	[-]	11,0								
Cracked concrete	$k_{cr,N}$		7,7								
Edge distance	$C_{cr,N}$	[mm]	1,5 h_{ef}								
Spacing	$S_{cr,N}$		2 $C_{cr,N}$								
Factors for sustained tension load											
Temperature range		[-]	50 °C / 80 °C				72 °C / 120 °C				
Factor	Ψ_{sus}^0	[-]	0,74				0,87				
Shear load											
Installation factor	γ_{inst}	[-]	1,0								
Concrete pry-out failure											
Factor for pry-out failure	k_8	[-]	2,0								
Concrete edge failure											
Effective length of fastener in shear loading	l_f	[mm]	for $d_{nom} \leq 24$ mm: min (h_{ef} ; 12 d_{nom}) for $d_{nom} > 24$ mm: min (h_{ef} ; 8 d_{nom} ; 300 mm)								
Calculation diameters											
Size			M6	M8	M10	M12	M16	M20	M24	M27	M30
Upat anchor rods and standard threaded rods	d_{nom}	[mm]	6	8	10	12	16	20	24	27	30
Upat internal threaded anchors IST	d_{nom}		- ¹⁾	12	16	18	22	28	- ¹⁾	- ¹⁾	- ¹⁾
Upat rebar anchor FRA	d_{nom}		- ¹⁾	- ¹⁾	- ¹⁾	12	16	20	25	- ¹⁾	- ¹⁾
Size (nominal diameter of the bar)	ϕ		8	10	12	14	16	20	25	28	
Reinforcing bar	d_{nom}	[mm]	8	10	12	14	16	20	25	28	
1) Anchortyp not part of the assessment											
injection system UPM 44								Annex C 4			
Performances Characteristic values for concrete failure under tension / shear load								Appendix 22 / 32			

Table C5.1: Characteristic values for combined pull-out and concrete failure for **Upat anchor rods and standard threaded rods** in hammer drilled holes; uncracked or cracked concrete

Anchor rod / standard threaded rod		M6	M8	M10	M12	M16	M20	M24	M27	M30
Combined pullout and concrete cone failure										
Calculation diameter	d [mm]	6	8	10	12	16	20	24	27	30
Uncracked concrete										
Characteristic bond resistance in uncracked concrete C20/25										
Hammer-drilling with standard drill bit or hollow drill bit (dry or wet concrete)										
Temperature range	I: 50 °C / 80 °C	$\tau_{Rk,ucr}$ [N/mm ²]	9,0	11,0	11,0	11,0	10,0	9,5	9,0	8,5
	II: 72 °C / 120 °C		6,5	9,5	9,5	9,0	8,5	8,0	7,5	7,0
Hammer-drilling with standard drill bit or hollow drill bit (water filled hole) ¹⁾										
Temperature range	I: 50 °C / 80 °C	$\tau_{Rk,ucr}$ [N/mm ²]	-2)	-2)	-2)	9,5	8,5	8,0	7,5	7,0
	II: 72 °C / 120 °C		-2)	-2)	-2)	7,5	7,0	6,5	6,0	6,0
Installation factors										
Dry or wet concrete	γ_{inst} [-]						1,0			
Water filled hole			-2)	-2)	-2)			1,2 ¹⁾		
Cracked concrete										
Characteristic bond resistance in cracked concrete C20/25										
Hammer-drilling with standard drill bit or hollow drill bit (dry or wet concrete)										
Temperature range	I: 50 °C / 80 °C	$\tau_{Rk,cr}$ [N/mm ²]	-2)	5,5	6,0	6,0	6,0	5,5	4,5	4,0
	II: 72 °C / 120 °C		-2)	4,5	5,0	6,0	6,0	5,0	4,0	3,5
Hammer-drilling with standard drill bit or hollow drill bit (water filled hole) ¹⁾										
Temperature range	I: 50 °C / 80 °C	$\tau_{Rk,cr}$ [N/mm ²]	-2)	-2)	-2)	5,0	5,0	4,5	4,0	3,5
	II: 72 °C / 120 °C		-2)	-2)	-2)	4,0	4,0	4,0	3,5	3,0
Installation factors										
Dry or wet concrete	γ_{inst} [-]						1,0			
Water filled hole			-2)	-2)	-2)			1,2 ¹⁾		
1) Only with coaxial cartridges: 380ml, 400 ml, 410 ml										
2) No performance assessed										
injection system UPM 44								Annex C 5		
Performances Characteristic values for combined pull-out and concrete failure for Upat anchor rod and standard threaded rods								Appendix 23 / 32		

Table C6.1: Characteristic values for combined pull-out and concrete failure for **Upat internal threaded anchors IST** in hammer drilled holes; **uncracked concrete**

Upat Internal threaded anchor IST		M8	M10	M12	M16	M20
Combined pullout and concrete cone failure						
Calculation diameter	d [mm]	12	16	18	22	28
Uncracked concrete						
Characteristic bond resistance in uncracked concrete C20/25						
Hammer-drilling with standard drill bit or hollow drill bit (dry or wet concrete)						
Temperature range	I: 50 °C / 80 °C	$\tau_{Rk,ucr}$ [N/mm ²]	10,5	10,0	9,5	9,0
	II: 72 °C / 120 °C		9,0	8,0	8,0	7,5
Hammer-drilling with standard drill bit or hollow drill bit (water filled hole) ¹⁾						
Temperature range	I: 50 °C / 80 °C	$\tau_{Rk,ucr}$ [N/mm ²]	10,0	9,0	9,0	8,5
	II: 72 °C / 120 °C		7,5	6,5	6,5	6,0
Installation factors						
Dry or wet concrete	γ_{inst} [-]		1,0			
Water filled hole			1,2 ¹⁾			

¹⁾ Only with coaxial cartridges: 380 ml, 400 ml, 410 ml

injection system UPM 44

Performances

Characterstic values for combined pull-out and concrete failure for Upat internal threaded anchors IST

Annex C 6

Table C7.1: Characteristic values for combined pull-out and concrete failure for **reinforcing bars** in hammer drilled holes; **uncracked or cracked concrete**

Nominal diameter of the bar	ϕ	8	10	12	14	16	20	25	28		
Combined pullout and concrete cone failure											
Calculation diameter	d [mm]	8	10	12	14	16	20	25	28		
Uncracked concrete											
Characteristic bond resistance in uncracked concrete C20/25											
Hammer-drilling with standard drill bit or hollow drill bit (dry or wet concrete)											
Tem- peratur range	I: 50 °C / 80 °C II: 72 °C / 120 °C	$\tau_{Rk,ucr}$	[N/mm ²]	11,0 9,5	11,0 9,5	11,0 9,0	10,0 8,5	10,0 8,5	9,5 8,0	9,0 7,5	8,5 7,0
Installation factor											
Dry or wet concrete	γ_{inst}	[\cdot]								1,0	
Cracked concrete											
Characteristic bond resistance in cracked concrete C20/25											
Hammer-drilling with standard drill bit or hollow drill bit (dry or wet concrete)											
Tem- peratur range	I: 50 °C / 80 °C II: 72 °C / 120 °C	$\tau_{Rk,cr}$	[N/mm ²]	- ¹⁾ - ¹⁾	3,0 3,0	5,0 4,5	5,0 4,5	5,0 4,5	4,5 4,0	4,0 3,5	4,0 3,5
Installation factor											
Dry or wet concrete	γ_{inst}	[\cdot]								1,0	

¹⁾ No performance assessed

injection system UPM 44

Performances

Characteristic values for combined pull-out and concrete failure for reinforcing bars

Annex C 7

Table C8.1: Characteristic values for combined pull-out and concrete failure for **Upat rebar anchors FRA** in hammer drilled holes; **uncracked or cracked concrete**

Upat rebar anchor FRA	M12	M16	M20	M24		
Combined pullout and concrete cone failure						
Calculation diameter d [mm]	12	16	20	25		
Uncracked concrete						
Characteristic bond resistance in uncracked concrete C20/25						
Hammer-drilling with standard drill bit or hollow drill bit (dry or wet concrete)						
Temperature range	I: 50 °C / 80 °C II: 72 °C / 120 °C	$\tau_{Rk,ucr}$ [N/mm ²]	11,0 9,0	10,0 8,5	9,5 8,0	9,5 7,5
Installation factors						
Dry or wet concrete	γ_{inst}	[-]	1,0			
Cracked concrete						
Characteristic bond resistance in cracked concrete C20/25						
Hammer-drilling with standard drill bit or hollow drill bit (dry or wet concrete)						
Temperature range	I: 50 °C / 80 °C II: 72 °C / 120 °C	$\tau_{Rk,cr}$ [N/mm ²]	5,0 4,5	5,0 4,5	4,5 4,0	4,0 3,5
Installation factors						
Dry or wet concrete	γ_{inst}	[-]	1,0			
injection system UPM 44						
Performances Characteristic values for combined pull-out and concrete failure for Upat rebar anchors FRA						
				Annex C 8		
				Appendix 26 / 32		

Table C9.1: Displacements for anchor rods

Anchor rod	M6	M8	M10	M12	M16	M20	M24	M27	M30
Displacement-Factors for tension load¹⁾									
Uncracked concrete; Temperature range I, II									
δ_{N0} -Factor	[mm/(N/mm ²)]	0,09	0,09	0,09	0,10	0,10	0,10	0,11	0,12
$\delta_{N\infty}$ -Factor		0,10	0,10	0,10	0,12	0,12	0,12	0,13	0,14
Cracked concrete; Temperature range I, II									
δ_{N0} -Factor	[mm/(N/mm ²)]	- ³⁾	0,12	0,12	0,12	0,13	0,13	0,14	0,15
δ_{N0} -Factor		- ³⁾	0,25	0,27	0,30	0,30	0,35	0,35	0,40
Displacement-Factors for shear load²⁾									
Uncracked or cracked concrete; Temperature range I, II									
δ_{V0} -Factor	[mm/kN]	0,11	0,11	0,11	0,10	0,10	0,09	0,09	0,08
$\delta_{V\infty}$ -Factor		0,12	0,12	0,12	0,11	0,11	0,10	0,09	0,09

¹⁾ Calculation of effective displacement:

$$\delta_{N0} = \delta_{N0}\text{-Factor} \cdot \tau_{Ed}$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-Factor} \cdot \tau_{Ed}$$

(τ_{Ed} : Design value of the applied tensile stress)

³⁾ No performance assessed

²⁾ Calculation of effective displacement:

$$\delta_{V0} = \delta_{V0}\text{-Factor} \cdot V_{Ed}$$

$$\delta_{V\infty} = \delta_{V\infty}\text{-Factor} \cdot V_{Ed}$$

(V_{Ed} : Design value of the applied shear force)

Table C9.2: Displacements for Upat internal threaded anchors IST

Upat Internal threaded anchor IST	M8	M10	M12	M16	M20
Displacement-Factors for tension load¹⁾					
Uncracked concrete; Temperature range I, II					
δ_{N0} -Factor	[mm/(N/mm ²)]	0,10	0,11	0,12	0,13
$\delta_{N\infty}$ -Factor		0,13	0,14	0,15	0,16
Displacement-Factors for shear load²⁾					
Uncracked concrete; Temperature range I, II					
δ_{V0} -Factor	[mm/kN]	0,12	0,12	0,12	0,12
$\delta_{V\infty}$ -Factor		0,14	0,14	0,14	0,14

¹⁾ Calculation of effective displacement:

$$\delta_{N0} = \delta_{N0}\text{-Factor} \cdot \tau_{Ed}$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-Factor} \cdot \tau_{Ed}$$

(τ_{Ed} : Design value of the applied tensile stress)

²⁾ Calculation of effective displacement:

$$\delta_{V0} = \delta_{V0}\text{-Factor} \cdot V_{Ed}$$

$$\delta_{V\infty} = \delta_{V\infty}\text{-Factor} \cdot V_{Ed}$$

(V_{Ed} : Design value of the applied shear force)

injection system UPM 44

Performances

Displacements for anchor rods and Upat internal threaded anchors IST

Annex C 9

Table C10.1: Displacements for reinforcing bars

Nominal diameter of the bar	ϕ	8	10	12	14	16	20	25	28
Displacement-Factors for tension load¹⁾									
Uncracked concrete; Temperature range I, II									
δ_{N0} -Factor	[mm/(N/mm ²)]	0,09	0,09	0,10	0,10	0,10	0,10	0,10	0,11
$\delta_{N\infty}$ -Factor		0,10	0,10	0,12	0,12	0,12	0,12	0,13	0,13
Cracked concrete; Temperature range I, II									
δ_{V0} -Factor	[mm/(N/mm ²)]	³⁾	0,12	0,13	0,13	0,13	0,13	0,13	0,14
$\delta_{V\infty}$ -Factor		³⁾	0,27	0,30	0,30	0,30	0,30	0,35	0,37
Displacement-Factors for shear load²⁾									
Uncracked or cracked concrete; Temperature range I, II									
δ_{V0} -Factor	[mm/kN]	0,11	0,11	0,10	0,10	0,10	0,09	0,09	0,08
$\delta_{V\infty}$ -Factor		0,12	0,12	0,11	0,11	0,11	0,10	0,10	0,09

¹⁾ Calculation of effective displacement:

$$\delta_{N0} = \delta_{N0}\text{-Factor} \cdot \tau_{Ed}$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-Factor} \cdot \tau_{Ed}$$

(τ_{Ed} : Design value of the applied tensile stress)

²⁾ Calculation of effective displacement:

$$\delta_{V0} = \delta_{V0}\text{-Factor} \cdot V_{Ed}$$

$$\delta_{V\infty} = \delta_{V\infty}\text{-Factor} \cdot V_{Ed}$$

(V_{Ed} : Design value of the applied shear force)

³⁾ No performance assessed

Table C10.2: Displacements for Upat rebar anchors FRA

Upat rebar anchor FRA	M12	M16	M20	M24	
Displacement-Factors for tension load¹⁾					
Uncracked concrete; Temperature range I, II					
δ_{N0} -Factor	[mm/(N/mm ²)]	0,10	0,10	0,10	0,10
$\delta_{N\infty}$ -Factor		0,12	0,12	0,12	0,13
Cracked concrete; Temperature range I, II					
δ_{N0} -Factor	[mm/(N/mm ²)]	0,12	0,13	0,13	0,13
$\delta_{N\infty}$ -Factor		0,30	0,30	0,30	0,35
Displacement-Factors for shear load²⁾					
Uncracked or cracked concrete; Temperature range I, II					
δ_{V0} -Factor	[mm/kN]	0,10	0,10	0,09	0,09
$\delta_{V\infty}$ -Factor		0,11	0,11	0,10	0,10

¹⁾ Calculation of effective displacement:

$$\delta_{N0} = \delta_{N0}\text{-Factor} \cdot \tau_{Ed}$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-Factor} \cdot \tau_{Ed}$$

(τ_{Ed} : Design value of the applied tensile stress)

²⁾ Calculation of effective displacement:

$$\delta_{V0} = \delta_{V0}\text{-Factor} \cdot V_{Ed}$$

$$\delta_{V\infty} = \delta_{V\infty}\text{-Factor} \cdot V_{Ed}$$

(V_{Ed} : Design value of the applied shear force)

injection system UPM 44

Performances

Displacements for reinforcing bars and Upat rebar anchors FRA

Annex C 10

Table C11.1: Characteristic values for steel failure under tension / shear load of Upat anchor rods and standard threaded rods under seismic action performance category C1 or C2

Anchor rod / standard threaded rod		M10	M12	M16	M20	M24	M27	M30		
Bearing capacity under tension load, steel failure¹⁾										
Upat anchor rods and standard threaded rods, performance category C1²⁾										
Characteristic resistance $N_{Rk,s,C1}$	Steel zinc plated	Property class [kN]	5.8	29(27)	43	79	123	177	230	281
			8.8	47(43)	68	126	196	282	368	449
			50	29	43	79	123	177	230	281
			70	41	59	110	172	247	322	393
			80	47	68	126	196	282	368	449
Upat anchor rods and standard threaded rods, performance category C2²⁾										
Characteristic resistance $N_{Rk,s,C2}$	Steel zinc plated	Property class [kN]	5.8	- ⁴⁾	39	72	108	- ⁴⁾	- ⁴⁾	- ⁴⁾
			8.8	- ⁴⁾	61	116	173	- ⁴⁾	- ⁴⁾	- ⁴⁾
			50	- ⁴⁾	39	72	108	- ⁴⁾	- ⁴⁾	- ⁴⁾
			70	- ⁴⁾	53	101	152	- ⁴⁾	- ⁴⁾	- ⁴⁾
			80	- ⁴⁾	61	116	173	- ⁴⁾	- ⁴⁾	- ⁴⁾
Bearing capacity under shear load, steel failure without lever arm¹⁾										
Upat anchor rods, performance category C1²⁾										
Characteristic resistance $V^0_{Rk,s,C1}$	Steel zinc plated	Property class [kN]	5.8	17(16)	25	47	74	106	138	168
			8.8	23(21)	34	63	98	141	184	225
			50	15	21	39	61	89	115	141
			70	20	30	55	86	124	161	197
			80	23	34	63	98	141	184	225
Standard threaded rods, performance category C1²⁾										
Characteristic resistance $V^0_{Rk,s,C1}$	Steel zinc plated	Property class [kN]	5.8	12(11)	17	33	52	74	97	118
			8.8	16(14)	24	44	69	99	129	158
			50	11	15	27	43	62	81	99
			70	14	21	39	60	87	113	138
			80	16	24	44	69	99	129	158
Upat anchor rods and standard threaded rods, performance category C2										
Characteristic resistance $V^0_{Rk,s,C2}$	Steel zinc plated	Property class [kN]	5.8	14	27	43	- ⁴⁾	- ⁴⁾	- ⁴⁾	- ⁴⁾
			8.8	22	44	69	- ⁴⁾	- ⁴⁾	- ⁴⁾	- ⁴⁾
			50	14	27	43	- ⁴⁾	- ⁴⁾	- ⁴⁾	- ⁴⁾
			70	20	39	60	- ⁴⁾	- ⁴⁾	- ⁴⁾	- ⁴⁾
			80	22	44	69	- ⁴⁾	- ⁴⁾	- ⁴⁾	- ⁴⁾
Factor for the annular gap	α_{gap}	[$-$]	0,5 (1,0) ³⁾							

¹⁾ Partial factors for performance category C1 or C2 see table C12.1;

for Upat anchor rods ASTA/UPM-A the factor for steel ductility is 1,0

²⁾ Values in brackets are valid for undersized threaded rods with smaller stress area A_s for hot dip galvanised standard threaded rods according to EN ISO 10684:2004+AC:2009.

³⁾ Values in brackets are valid for filled annular gaps between the anchor rod and the through-hole in the attachment. It is necessary to use the filling disc according to Annex A 1

⁴⁾ No performance assessed

injection system UPM 44

Performances

Characteristic values for steel failure under tension / shear load for Upat anchor rods and standard threaded rods under seismic action (performance category C1 / C2)

Annex C 11

Table C12.1: Partial factors for Upat anchor rods, standard threaded rods under seismic action performance category C1 or C2

Anchor rod / standard threaded rod		M10	M12	M16	M20	M24	M27	M30
Tension load, steel failure¹⁾								
γ_{M_N}	Steel zinc plated	Property class	5.8	1,50				
			8.8	1,50				
	Stainless steel R and high corrosion resistant steel HCR		50	2,86				
			70	1,50 ²⁾ / 1,87				
			80	1,60				
Shear load, steel failure¹⁾								
γ_{M_V}	Steel zinc plated	Property class	5.8	1,25				
			8.8	1,25				
	Stainless steel R and high corrosion resistant steel HCR		50	2,38				
			70	1,25 ²⁾ / 1,56				
			80	1,33				

¹⁾ In absence of other national regulations

²⁾ Only admissible for high corrosion resistant steel HCR, with $f_{y_k} / f_{u_k} \geq 0,8$ and $A_5 > 12\%$ (e.g. Upat anchor rods)

injection system UPM 44

Performances

Partial factors under seismic action (performance category C1 and C2) for Upat anchor rods and standard threaded rods

Annex C 12

Table C13.1: Characteristic values for combined pull-out and concrete failure for **Upat anchor rods and standard threaded rods** in hammer drilled holes under seismic action performance category **C1**

Anchor rod / standard threaded rod		M10	M12	M16	M20	M24	M27	M30
Characteristic bond resistance, combined pullout and concrete cone failure								
Hammer-drilling with standard drill bit or hollow drill bit (dry or wet concrete)								
Tem- perature range	I: 50 °C / 80 °C	$\tau_{Rk,C1}$	[N/mm ²]	4,5	5,5	5,5	5,5	4,5
	II: 72 °C / 120 °C			4,0	4,5	4,5	4,5	4,0
Hammer-drilling with standard drill bit or hollow drill bit (water filled hole ¹⁾								
Tem- perature range	I: 50 °C / 80 °C	$\tau_{Rk,C1}$	[N/mm ²]	- ²⁾	5,0	5,0	4,5	4,0
	II: 72 °C / 120 °C			- ²⁾	4,0	4,0	4,0	3,5
Installation factors								
Dry or wet concrete		γ_{inst}	[-]	1,0				
Water filled hole				- ²⁾	1,2 ¹⁾			

¹⁾ Only with coaxial cartridges: 380ml, 400 ml, 410 ml

²⁾ No performance assessed

injection system UPM 44

Performances

Characteristic values for combined pull-out and concrete failure under seismic action (performance category C1) for Upat anchor rods and standard threaded rods

Annex C 13

Table C14.1: Characteristic values for combined pull-out and concrete failure for **Upat anchor rods and standard threaded rods** in hammer drilled holes under seismic action performance category **C2**

Anchor rod / standard threaded rod		M12	M16	M20			
Characteristic bond resistance, combined pullout and concrete cone failure							
Hammer-drilling with standard drill bit or hollow drill bit (dry or wet concrete)							
Temperature range	I: 50 °C / 80 °C II: 72 °C / 120 °C	$\tau_{Rk,C2}$ [N/mm ²]	1,5 1,3	1,3 1,2			
				2,1 1,9			
Hammer-drilling with standard drill bit or hollow drill bit (water filled hole ³⁾)							
Temperature range	I: 50 °C / 80 °C II: 72 °C / 120 °C	$\tau_{Rk,C2}$ [N/mm ²]	1,3 1,1	1,1 1,0			
				1,8 1,6			
Installation factors							
Dry or wet concrete	γ_{inst}	[\cdot]	1,0				
Water filled hole			- ⁴⁾	1,2 ³⁾			
Displacement-Factors for tension load¹⁾							
$\delta_{N,C2}$ (DLS)-Factor	$[\text{mm}/(\text{N/mm}^2)]$		0,20	0,13			
$\delta_{N,C2}$ (ULS)-Factor			0,38	0,18			
Displacement-Factors for shear load²⁾							
$\delta_{V,C2}$ (DLS)-Factor	$[\text{mm/kN}]$		0,18	0,10			
$\delta_{V,C2}$ (ULS)-Factor			0,25	0,14			
¹⁾ Calculation of effective displacement:		²⁾ Calculation of effective displacement:					
$\delta_{N,C2}$ (DLS) = $\delta_{N,C2}$ (DLS)-Factor $\cdot \tau_{Ed}$		$\delta_{V,C2}$ (DLS) = $\delta_{V,C2}$ (DLS)-Factor $\cdot V_{Ed}$					
$\delta_{N,C2}$ (ULS) = $\delta_{N,C2}$ (ULS)-Factor $\cdot \tau_{Ed}$		$\delta_{V,C2}$ (ULS) = $\delta_{V,C2}$ (ULS)-Factor $\cdot V_{Ed}$					
(τ_{Ed} : Design value of the applied tensile stress)		(V_{Ed} : Design value of the applied shear force)					
³⁾ Only with coaxial cartridges: 380ml, 400 ml, 410 ml							
⁴⁾ No performance assessed							
injection system UPM 44							
Performances Characteristic values for combined pull-out and concrete failure under seismic action (performance category C2) for Upat anchor rods and standard threaded rods							
				Annex C 14			
				Appendix 32 / 32			