



ΔΗΛΩΣΗ ΕΠΙΔΟΣΕΩΝ

fischer 
innovative solutions

DoP: 0146

για fischer μπετόβιδα ULTRACUT FBS II (Εκτομούμενα αγκύρια για χρήση σε μπετόν (βαρέος τύπου)) – EL

1. Μοναδικός κωδικός ταυτοποίησης του τύπου του προϊόντος: **DoP: 0146**
2. Προβλεπόμενη(-ες) χρήση(-εις): **Εκ των υστέρων στερέωση σε ρηγματωμένο ή μη ρηγματωμένο σκυρόδεμα, δείτε το παράρτημα, ειδικά τα παραρτήματα B 1 - B 5**
3. Κατασκευαστής: **fischerwerke GmbH & Co. KG, Klaus-Fischer-Straße 1, 72178 Waldachtal, Γερμανία**
4. Εξουσιοδοτημένος αντιπρόσωπος: --
5. Σύστημα/συστήματα AVCP (αξιολόγηση και επαλήθευση της σταθερότητας της επίδοσης): **1**
6. Ευρωπαϊκό έγγραφο αξιολόγησης: **EAD 330232-00-0601**

Ευρωπαϊκή τεχνική αξιολόγηση: **ETA-15/0352; 2018-10-30**

Οργανισμός τεχνικής αξιολόγησης: **DIBt**

Κοινοποιημένος(-οι) οργανισμός(-οι): **1343 – MPA Darmstadt**

7. Δηλωθείσα(-ες) επίδοση(-εις):

Μηχανική αντιστάση και σταθερότητα (BWR 1)

- **χαρακτηριστική εφελκυστική αντοχή (για στατική και ημιστατική ενέργεια):**
δείτε το παράρτημα, συγκεκριμένα το παράρτημα C 1 και C 2
- **χαρακτηριστική διατμητική αντοχή (για στατική και ημιστατική ενέργεια):**
δείτε το παράρτημα, συγκεκριμένα το παράρτημα C 1 και C 2
- **μετατόπιση (για στατική και ημιστατική ενέργεια):** δείτε το παράρτημα, συγκεκριμένα τα παραρτήματα C 7
- **Χαρακτηριστική αντιστάση και μετατοπίσεις για κατηγορίες σεισμικών επιδόσεων C1 και C2:**
δείτε το παράρτημα, συγκεκριμένα το παράρτημα C 3, C 4 και C 7

Ασφάλεια σε περίπτωση φωτιάς (BWR 2)

- **Αντίδραση σε φωτιά :** Το Αγκύριο καλύπτει τις απαιτήσεις της Κατηγορίας A 1
- **Αντίσταση στη φωτιά:** δείτε το παράρτημα, συγκεκριμένα τα παραρτήματα C 5 και C 6

8. Κατάλληλη τεχνική τεκμηρίωση και/ή ειδική τεχνική τεκμηρίωση: ---

Η επίδοση του προϊόντος που ταυτοποιείται ανωτέρω είναι σύμφωνη με τη (τις) δηλωθείσα(-ες) επίδοση(-εις). Αυτή η δήλωση επιδόσεων εκδίδεται σύμφωνα με τον Κανονισμό (ΕΕ) Αρ. 305/2011 με αποκλειστική ευθύνη του κατασκευαστή που προσδιορίζεται παραπάνω.

Υπογραφή για λογαριασμό και εξ ονόματος του κατασκευαστή από:

Andreas Bucher, Dipl.-Ing.

Wolfgang Hengesbach, Dipl.-Ing., Dipl.-Wirtsch.-Ing.

Tumlingen, 2018-11-06

- Αυτή η Δήλωση Απόδοσης μεταφράστηκε σε διάφορες γλώσσες. σε περίπτωση που υπάρχει αμφιβολία για τη μετάφραση η αγγλική έκδοση θα υπερισχύει πάντα.
- Το παράρτημα περιλαμβάνει προαιρετικές και συμπληρωματικές πληροφορίες στα αγγλικά. Αυτές ξεπερνούν τις προβλεπόμενες από το νόμο (γλώσσα ουδέτερη) .

Specific Part**1 Technical description of the product**

The fischer concrete screw ULTRACUT FBS II is an anchor of sizes 6, 8, 10, 12 and 14 mm made of hardened carbon steel. The anchor is screwed into a predrilled cylindrical drill hole. The special thread of the anchor cuts an internal thread into the member while setting. The anchorage is characterised by mechanical interlock in the special thread.

The product description is given in Annex A.

2 Specification of the intended use in accordance with the applicable European Assessment Document

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the anchor of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment**3.1 Mechanical resistance and stability (BWR 1)**

Essential characteristic	Performance
Characteristic resistance to tension load (static and quasi-static loading)	See Annex C 1 and C 2
Characteristic resistance to shear load (static and quasi-static loading)	See Annex C 1 and C 2
Displacements (static and quasi-static loading)	See Annex C 7
Characteristic resistance and displacements for seismic performance categories C1 and C2	See Annex C 3, C 4 and C 7


3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire	Class A1
Resistance to fire	See Annex C 5 and C 6


4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

In accordance with European Assessment Document EAD No. 330232-00-0601 the applicable European legal act is: [96/582/EC].


The system to be applied is: 1

Product in the installed condition

FBS II US



FBS II SK



FBS II 6 M8

fischer concrete screw ULTRACUT FBS II

Product description

Product in the installed condition

Annex A 1

Table A2.1: Screw types FBS II 6










FBS II 6		
Hexagon head with formed washer (US)		
Hexagon head with formed washer and TX-drive (US TX)		
Countersunk Head (SK)		
Pan head (P)		
Large Pan head (LP)		
Hexagon head and connection thread M8 or M10 (M)		
Internal thread M8 / M10 combined (M8/M10 I)		
fischer concrete screw ULTRACUT FBS II		Annex A 2
Product description Screw types FBS II 6		

Table A3.1: Screw types FBS II 8 - 14

FBS II 8 - 14		
Hexagon head with formed washer (US)		
Hexagon head with formed washer and TX-drive (US TX)		
Countersunk Head (SK)		
Hexagon head (S)		
Hexagon head with TX-drive (S TX)		
fischer concrete screw ULTRACUT FBS II		Annex A 3
Product description Screw types FBS II 8 to 14		


Table A4.1: Geometry and material

Screw types / size		All head shapes				
		6	8	10	12	14
Thread outer diameter	d_a	[mm]	7,75	10,3	12,5	14,5
Core diameter	d_k		5,65	7,4	9,4	11,3
Shaft diameter	d_s		6,0	8,0	9,9	11,7
Material	[-]	Hardened carbon steel; $A_{5\%} \geq 8\%$				
Coating		galvanized				


**Head marking US, US TX, S; S TX, SK, P, LP**

FBS II: Product identification

XXX: Screw length L

**Marking at M8, M10, M8/M10 I**

Head marking:
XX: Screw length L



Rotary marking:
FBS II: Product identification
6: Screw size

fischer concrete screw ULTRACUT FBS II

Product description
Geometry and marking

Annex A 4

Specification of intended use**Table B1.1:** Anchorages subject to

Size	6	8		10			12			14		
Nominal embedment depth [mm]	40-55	50	65	55	65	85	60	75	100	65	85	115
Static and quasi-static loads in cracked and uncracked concrete	✓											
Fire exposure												
Seismic performance category C1	✓		✓		✓		✓		✓		✓	
Seismic performance category C2												

Base materials:

- Compacted reinforced or unreinforced normal weight concrete without fibres according to EN 206:2013
- Strength classes C20/25 to C50/60 according to EN 206:2013
- Uncracked or cracked concrete

Use conditions (Environmental conditions):

- Structures subjected to dry internal conditions

Design:

- Anchorages are to be designed under the responsibility of an engineer experienced in anchorages and concrete work
- Verifiable calculation notes and drawings are to be prepared taking account of the loads to be anchored. The position of the screw is indicated on the design drawings (e.g. position of the screw relative to reinforcement or to supports, etc.).
- Design of fastenings according to FprEN 1992-4: 2016 and EOTA Technical Report TR 055
- Seismic design according to EOTA Technical Report TR 049

Installation:

- Hammer drilling or hollow drilling:
All sizes and embedment depths
- Alternative diamond drilling: All sizes and embedment depths from diameter 8
- Screw installation carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters on site
- In case of aborted hole: New hole must be drilled at a minimum distance of twice the depth of the aborted hole or closer, if the hole is filled with a high strength mortar and only if the hole is not in the direction of the oblique tensile or shear load.
- Adjustability according to Annex B4 for: All sizes and embedment depths
- Cleaning of drill hole is not necessary when using a hollow drill with functional suction or:
 - If drilling vertically upwards
 - If drilling vertical downwards and the drill hole depth has been increased. It is recommended to increase the drill depth with additional $3 d_0$.
- After correct installation further turning of the screw head shall not be possible
- The head of the screw must be fully engaged on the fixture and show no signs of damage
- For seismic performance category C2 applications: The gap between screw shaft and fixture must be filled with mortar; mortar compressive strength $\geq 50 \text{ N/mm}^2$ (e. g. FIS V, FIS HB, FIS SB or FIS EM Plus).

fischer concrete screw ULTRACUT FBS II

Intended use
Specification**Annex B 1**


Table B2.1: Installation parameters FBS II 6 - drilling bore hole and setting tools

FBS II 6			All head shapes
Nominal embedment depth	h_{nom}	[mm]	$40 \leq h_{nom} \leq 55$
Nominal drill hole diameter	d_0		6
Cutting diameter of drill bits	$d_{cut} \leq$		6,4
Clearance hole diameter	$d_f \leq$		8
Drill hole depth			$h_{nom} + 10^{1)}$
Drill hole depth (with adjustable setting)	$h_1 \geq$		$h_{nom} + 20$
Torque impact screw driver	$T_{imp,max}$	[Nm]	450
Maximum installation torque with hexagon nut on head shapes M8, M10 and M8/M10 I	T_{max}	[Nm]	10

¹⁾ Value can be reduced to $h_{nom} + 5$ for installation vertically upwards

Table B2.2: Installation parameters FBS II 6 – drive and fixture

FBS II 6			US	US TX	SK	P	LP	M8	M10	M8/M10 I
Wrench size	SW	[mm]	10		-			10	13	
TX size	TX	[-]	-	30				-		
Head diameter	d _h	[mm]	17		13,5	14,4	17,5			
Thickness of fixture	t _{fix} ≤		L - h _{nom}							
Length of screw	L _{min} =		40							
	L _{max} =	325						55		



fischer concrete screw ULTRACUT FBS II


Intended use

Installation parameters FBS II 6

Annex B 2

Table B3.1: Installation parameters FBS II 8 - 14

Size			FBS II										
			8		10			12			14		
Nominal embedment depth	h_{nom}	[mm]	50	65	55	65	85	60	75	100	65	85	115
Nominal drill hole diameter	d_0		8		10			12			14		
Cutting diameter of drill bits	$d_{cut} \leq$		8,45		10,45			12,50			14,50		
Cutting diameter of diamond driller			8,10		10,30			12,30			14,30		
Clearance hole diameter			d_f	10,6 – 12,0		12,8 – 14,0			14,8 – 16,0			16,9 – 18,0	
Wrench size (US,S)	SW	13		15			17			21			
Tx size	Tx	[-]	40		50			-					
Head diameter	d_h	[mm]	18		21								
Countersunk diameter in fixture	d_c		20		23								
Drill hole depth	$h_1 \geq$		60	75	65	75	95	70	85	110	80	100	130
Drill hole depth (with adjustable setting)			70	85	75	85	105	80	95	120	90	110	140
Thickness of fixture	$t_{fix} \leq$		L - h_{nom}										
Length of screw	$L_{min} =$	50	65	55	65	85	60	75	100	65	85	115	
	$L_{max} =$	400	415	405	415	435	410	425	450	415	435	465	
Torque impact screw driver	$T_{imp,max}$	[Nm]	600			650							



fischer concrete screw ULTRACUT FBS II


Intended use

Installation parameters FBS II 8 - 14


Annex B 3

Adjustment


1)




2)



3)



4)



It is permissible to untighten the screw up to two times for adjustment purposes.
Therefore the screw may be untightened to a maximum of $L_{adj} = 20$ mm to the surface of the initial fixture.

The total permissible thickness of shims added during the adjustment process is $t_{adj} = 10$ mm

Table B4.1: Minimum thickness of concrete members, minimum spacing and edge distance

Size		FBS II											
		6	8		10			12			14		
Nominal embedment depth	h_{nom}	40 to 55	50	65	55	65	85	60	75	100	65	85	115
Minimum thickness of concrete member	h_{min}	max.(80; $h_1^{1)} + 30$)	100	120	100	120	140	110	130	150	120	140	180
Minimum spacing	s_{min}	35	35		40			50			60		
Minimum edge distance	c_{min}	35	35		40			50			60		

¹⁾ Drill hole depth according to table B3.1

fischer concrete screw ULTRACUT FBS II

Intended use

Adjustment

Minimum thickness of members, minimum spacing and edge distance

Annex B 4










Installation instruction		
		Drill the hole using hammer drill, hollow drill or diamond core drill. Drill hole diameter d_0 and drill hole depth h_1 according to table B2.1 and B3.1
a) 	b) 	Option a): Clean the drill hole Option b): Cleaning of drill hole is not necessary when using a hollow drill or a diamond drill or: - If drilling vertically upwards or - If drilling vertically downwards and the drill hole depth has been increased. It is recommended to increase the drill hole depth additional 3 times d_0 .
		Installation with any torque impact screw driver up to the maximum mentioned torque moment ($T_{imp,max}$ according to table B2.1 and B3.1). Alternatively, all other tools without an indicated torque moment are allowed (e.g. ratchet spanner). The indicated torque moments for impact screw driver are therefore not decisive.
		After installation a further turning of the screw must not be possible. The head of the screw must be in contact with the fixture and is not damaged
1. 	2. 	Optional: It is permissible to adjust the screw twice. Therefore the screw may be untightened to a maximum of $L_{adj} = 20 \text{ mm}$ off the surface of the initial fixture. The total permissible thickness of shims added during the adjustment process is $t_{adj} = 10 \text{ mm}$.
3. 		
		Filling of the annular gap: For seismic performance category C2 applications: The gap between screw shaft and fixture must be filled with mortar; mortar compressive strength $\geq 50 \text{ N/mm}^2$ (e. g. FIS V, FIS HB, FIS SB or FIS EM Plus). As an aid for filling the gap, the filling disc FFD is recommended.
fischer concrete screw ULTRACUT FBS II		Annex B 5
Intended use Installation instruction		

Table C1.1: Characteristic values for static and quasi-static action with FBS II 6							
FBS II 6							
Nominal embedment depth		h_{nom}	[mm]	40	45	50	55
Steel failure for tension load and shear load							
Characteristic resistance		$N_{Rk,s}$	[kN]	21			
Partial factor		γ_{Ms}	[-]	1,4			
Characteristic resistance		$V_{Rk,s}$	[kN]	9,0			13,3
Partial factor		γ_{Ms}	[-]	1,5			
Factor for ductility		k_7		1,0			
Characteristic bending resistance		$M^0_{Rk,s}$	[Nm]	17,1			
Pullout failure							
Characteristic resistance in concrete C20/25	uncracked	$N_{Rk,p}$	[kN]	8,0	10,0	12,0	13,5
	cracked	$N_{Rk,p}$		2,5	3,5	4,0	5,0
Increasing factors concrete	C25/30	ψ_c	[-]	1,12			
	C30/37			1,22			
	C35/45			1,32			
	C40/50			1,41			
	C45/55			1,50			
	C50/60			1,58			
Installation factor		γ_{inst}	[-]	1,0			
Concrete cone failure and splitting failure; concrete pryout failure							
Effective embedment depth		h_{ef}	[mm]	32	36	40	44
Factor for uncracked concrete		$k_{ucr,N}$	[-]	11,0			
Factor for cracked concrete		$k_{cr,N}$		7,7			
Characteristic edge distance		$c_{cr,N}$	[mm]	1,5 h_{ef}			
Characteristic spacing		$s_{cr,N}$		3 h_{ef}			
Charakt. resistance for splitting		$N^0_{Rk,sp}$	[kN]	$N_{Rk,c}$			
Charact. edge distance for splitting		$c_{cr,sp}$	[mm]	1,5 h_{ef}			
Charakt. spacing for splitting		$s_{cr,sp}$		3 h_{ef}			
Factor for pryout failure		k_8	[-]	2,0			
Installation factor		γ_{inst}		1,0			
Concrete edge failure							
Effective length in concrete		l_f	[mm]	40	45	50	55
Nominal diameter of screw		d_{nom}		6			
Adjustment							
Maximum thickness of shims		t_{adj}	[mm]	10			
Max. number of adjustments		n_a	[-]	2			
fischer concrete screw ULTRACUT FBS II						Annex C 1	
Performances Characteristic values for static and quasi-static action with FBS II 6							

Table C2.1: Characteristic values for static and quasi-static action with FBS II 8 - 14

Size			FBS II										
			8		10			12			14		
Nominal embedment depth h_{nom} [mm]			50	65	55	65	85	60	75	100	65	85	115
Steel failure for tension load and shear load													
Characteristic resistance $N_{Rk,s}$ [kN]			35		55			76			103		
Partial factor γ_{Ms} [-]			1,4										
Characteristic resistance $V_{Rk,s}$ [kN]			13,1	19,0	29,4		34,9	31,9		42,7	46,5		61,7
Partial factor γ_{Ms} [-]			1,5										
Factor for ductility k_7			1,0										
Characteristic bending resistance $M^0_{Rk,s}$ [Nm]			51		95			165			269		
Pullout failure													
Characteristic resistance in concrete C20/25	uncracked	$N_{Rk,p}$ [kN]	- ¹⁾										
	cracked	$N_{Rk,p}$ [kN]	6	12	9	12	- ¹⁾						
Increasing factors concrete	C25/30	ψ_c [-]	1,12										
	C30/37		1,22										
	C35/45		1,32										
	C40/50		1,41										
	C45/55		1,50										
	C50/60		1,58										
Installation factor γ_{inst} [-]			1,0										
Concrete cone failure and splitting failure; concrete pryout failure													
Effective embedment depth h_{ef} [mm]			40	52	43	51	68	47	60	81	50	67	93
Factor for uncracked concrete $k_{ucr,N}$ [mm]			11,0										
Factor for cracked concrete $k_{cr,N}$ [mm]			7,7										
Characteristic edge distance $c_{cr,N}$ [mm]			1,5 h_{ef}										
Characteristic spacing $s_{cr,N}$ [mm]			3 h_{ef}										
Charact. edge distance for splitting $c_{cr,sp}$ [mm]			1,5 h_{ef}										
Charakt. spacing for splitting $s_{cr,sp}$ [mm]			3 h_{ef}										
Factor for pryout failure k_8 [-]			1,0	2,0	1,0	2,0							
Installation factor γ_{inst} [-]			1,0										
Concrete edge failure													
Effective length in concrete l_f [mm]			50	65	55	65	85	60	75	100	65	85	115
Nominal diameter of screw d_{nom} [mm]			8		10			12			14		
Adjustment													
Maximum thickness of shims t_{adj} [mm]			10										
Max. number of adjustments n_a [-]			2										
1) Pullout failure not decisive													
fischer concrete screw ULTRACUT FBS II										Annex C 2			
Performances Characteristic values for static and quasi-static action with FBS II 8 - 14													

Table C3.1: Characteristic values for seismic performance category C1 with FBS II 6

FBS II 6						
Nominal embedment depth	h_{nom}	[mm]	40	45	50	55
Steel failure for tension load and shear load						
Characteristic resistance	$N_{Rk,s,eq}$	[kN]	21			
	$V_{Rk,s,eq}$		6,3			9,3
Without filling of the annular gap	α_{gap}	[-]	0,5			
With filling of the annular gap ¹⁾	α_{gap}		1,0			
Pullout failure						
Characteristic resistance in cracked concrete	$N_{Rk,p,eq}$	[kN]	2,5	3,5	4,0	5,0
Concrete cone failure						
Effective embedment depth	h_{ef}	[mm]	32	36	40	44
Characteristic edge distance	$c_{cr,N}$		1,5 h_{ef}			
Characteristic spacing	$s_{cr,N}$		3 h_{ef}			
Installation factor	γ_{inst}	[-]	1,0			
Concrete pryout failure						
Factor for pryout failure	k_8	[-]	2,0			
Concrete edge failure						
Effective length in concrete	l_f	[mm]	40	45	50	55
Nominal diameter of screw	d_{nom}		6			

Table C3.2: Characteristic values for seismic performance category C1 with FBS II 8 – 14 ¹⁾

Table C4.1: Characteristic values for seismic performance category C2 ¹⁾

Size			FBS II			
			8	10	12	14
Nominal embedment depth	h_{nom}	[mm]	65	85	100	115
Steel failure for tension load and shear load						
Characteristic resistance	$N_{\text{Rk,s,eq}}$	[kN]	35,0	55	76,0	103
	$V_{\text{Rk,s,eq}}$		13,3	20,4	29,9	35,2
With filling of the annular gap ¹⁾	α_{gap}	[-]	1,0			
Pullout failure						
Characteristic resistance in cracked concrete	$N_{\text{Rk,p,eq}}$	[kN]	2,1	6,0	8,9	17,1
Concrete cone failure						
Effective embedment depth	h_{ef}	[mm]	52	68	81	93
Characteristic edge distance	$c_{\text{cr,N}}$		1,5 h_{ef}			
Characteristic spacing	$s_{\text{cr,N}}$		3 h_{ef}			
Installation factor	γ_{inst}	[-]	1,0			
Concrete pryout failure						
Factor for pryout failure	k_8	[-]	2,0			
Concrete edge failure						
Effective length in concrete	l_f	[mm]	65	85	100	115
Nominal diameter of screw	d_{nom}		8	10	12	14

¹⁾ Filling of the annular gap according annex B 5. Application without filling of the annular gap not allowed.

fischer concrete screw ULTRACUT FBS II

Performances

Characteristic values for seismic performance category C2 with FBS II 8 - 14

Annex C 4

Table C5.1: Characteristic values for resistance to fire with FBS II 6 ¹⁾						
FBS II 6						
Nominal embedment depth	h_{nom}	[mm]	40	45	50	55
Steel failure for tension load and shear load ($F_{Rk,s,fi} = N_{Rk,s,fi} = V_{Rk,s,fi}$)						
Characteristic resistance for all head shapes	$F_{Rk,s,fi}$	R30	[kN]	1,00		
		R60		0,60		
		R90		0,50		
		R120		0,40		
Characteristic bending resistance for all head shapes	$M^0_{Rk,s,fi}$	R30	[Nm]	0,80		
		R60		0,50		
		R90		0,40		
		R120		0,35		
Edge distance						
R30 to R120	$c_{cr,fi}$	[mm]	2 h_{ef}			
In case of fire attack from more than one side, the minimum edge distance shall be ≥ 300 mm						
Spacing						
R30 to R120	$s_{cr,fi}$	[mm]	2 $c_{cr,fi}$			
¹⁾ The embedment depth has to be increased for wet concrete by at least 30 mm compared to the given value.						
fischer concrete screw ULTRACUT FBS II					Annex C 5	
Performances Characteristic values for resistance to fire with FBS II 6						

Table C6.1: Characteristic values for resistance to fire with FBS II 8 – 14 ¹⁾

Size				FBS II											
				8		10			12			14			
Nominal embedment depth h_{nom} [mm]				50	65	55	65	85	60	75	100	65	85	115	
Steel failure for tension load and shear load ($F_{Rk,s,fi} = N_{Rk,s,fi} = V_{Rk,s,fi}$)															
Characteristic resistance for the head shapes	US, S	$F_{Rk,s,fi}$	R30	[kN]	2,33		3,45		4,62			6,46			
			R60		1,82		2,73		3,66			5,11			
			R90		1,30		2,00		2,69			3,75			
			R120		1,04		1,64		2,20			3,08			
	SK, US TX, S TX	$F_{Rk,s,fi}$	R30	[kN]	2,12		2,96		-						
			R60		1,67		2,26								
			R90		1,21		1,56								
			R120		0,99		1,21								
	All head shapes	$M_{Rk,s,fi}^0$	[Nm]	R30	2,62		4,92		7,83			12,89			
				R60	2,05		3,89		6,20			10,19			
				R90	1,46		2,85		4,56			7,48			
				R120	1,17		2,34		3,73			6,14			
Pullout failure															
Characteristic resistance	$N_{Rk,p,fi}$	R30	[kN]	1,5	3,0	2,3	3,0	5,0	2,9	4,2	6,6	3,2	4,9	8,1	
		R60													
		R90													
		R120													
				1,2	2,4	1,8	2,4	4,0	2,3	3,3	5,2	2,5	3,9	6,5	
Edge distance															
R30 to R120 $c_{cr,fi}$ [mm]				2 h_{ef}											
In case of fire attack from more than one side, the minimum edge distance shall be ≥ 300 mm															
Spacing															
R30 to R120 $s_{cr,fi}$ [mm]				2 $c_{cr,fi}$											
¹⁾ The embedment depth has to be increased for wet concrete by at least 30 mm compared to the given value.															
fischer concrete screw ULTRACUT FBS II												Annex C 6			
Performances Characteristic values for resistance to fire with FBS II 8 - 14															

Table C7.1: Displacements due to tension loads (static)

Size			FBS II												
			6 ¹⁾		8		10			12			14		
Nominal embedment depth	h_{nom}	[mm]	40	55	50	65	55	65	85	60	75	100	65	85	115
Tension load in cracked concrete	N	[kN]	2,0	3,5	2,9	5,7	4,3	5,7	9,6	5,5	8,0	12,5	6,1	9,4	15,3
Displacement	$\frac{\delta_{N0}}{\delta_{N\infty}}$	[mm]	1,1	1,4	0,5	0,9	0,7	0,7	0,8	0,7	0,9	0,8	0,8	1,0	0,8
			2,5	2,5	1,3	1,0	0,7	0,7	0,8	1,3	0,9	0,8	1,1	1,0	1,1
Tension load in uncracked concrete	N	[kN]	4,0	7,0	7,9	12,0	6,8	8,8	13,5	7,7	11,0	17,4	8,5	13,2	21,6
Displacement	$\frac{\delta_{N0}}{\delta_{N\infty}}$	[mm]	1,0	1,8	0,9	1,4	0,9	0,9	1,4	0,9	1,1	1,4	1,0	1,3	1,1
			1,7	2,6	1,4	1,4	1,4	1,4	1,4	1,4	1,4	1,4	1,1	1,3	1,1

¹⁾ Intermediate values by linear interpolation**Table C7.2:** Displacements due to shear loads (static)

Size			FBS II												
			6 ¹⁾		8		10			12			14		
Nominal embedment depth	h_{nom}	[mm]	40	55	50	65	55	65	85	60	75	100	65	85	115
Shear load in cracked and uncracked concrete	V	[kN]	4,5	6,7	6,2	9,0	14,0	14,0	16,6	15,9	15,9	21,2	23,0	23,0	30,5
Displacement	$\frac{\delta_{V0}}{\delta_{V\infty}}$	[mm]	2,0	2,9	1,4	1,4	3,2	3,2	3,2	2,5	2,5	3,4	2,8	2,8	5,4
			2,9	4,4	2,0	2,1	4,9	4,9	4,9	3,8	3,8	5,1	4,2	4,2	8,1

¹⁾ Intermediate values by linear interpolation**Table C7.3:** Displacements due to tension loads (seismic performance category C2)

Size			FBS II			
			8	10	12	14
Nominal embedment depth	h_{nom}	[mm]	65	85	100	115
Displacement DLS	$\delta_{N,eq(DLS)}$		0,5	0,8	0,9	1,3
Displacement ULS	$\delta_{N,eq(ULS)}$		1,7	2,8	2,7	5,0

Table C7.4: Displacements due to shear loads (seismic performance category C2)

Size			FBS II			
			8	10	12	14
Nominal embedment depth	h_{nom}	[mm]	65	85	100	115
Displacement DLS	$\delta_{V,eq(DLS)}$		1,6	2,7	3,1	4,1
Displacement ULS	$\delta_{V,eq(ULS)}$		3,9	7,1	5,3	8,7

fischer concrete screw ULTRACUT FBS II

Performances

Displacements due to tension and shear loads

Annex C 7