

## DECLARATION OF PERFORMANCE

### DoP 0272

for fischer injection system FIS GREEN (Bonded fastener for use in concrete)

EN

1. Unique identification code of the product-type: **DoP 0272**
2. Intended use/es: **Post-installed fastening for use in uncracked concrete see appendix, especially annexes B1- B8.**
3. Manufacturer: **fischerwerke GmbH & Co. KG, Otto-Hahn-Straße 15, 79211 Denzlingen, Germany**
4. Authorised representative: **–**
5. System/s of AVCP: **1**
6. European Assessment Document: **ETAG 001, Part 5, April 2013, used as EAD**  
European Technical Assessment: **ETA-14/0408; 2014-12-19**  
Technical Assessment Body: **DIBt- Deutsches Institut für Bautechnik**  
Notified body/ies: **2873 TU Darmstadt**
7. Declared performance/s:  
**Mechanical resistance and stability (BWR 1)**  
**Characteristic resistance to tension load (static and quasi-static loading):**  
Resistance to steel failure: Annexes C2,C3 (TR 029); Annexes C6-C9 (CEN/TS 1992-4)  
Resistance to combined pull- out and concrete cone failure: Annexes C1-C3 (TR 029); Annexes C6-C9 (CEN/TS 1992-4)  $\psi_{sus}^0 = \text{NPD}$   
  
Resistance to concrete cone failure: NPD (see TR 029); Annexes C6-C9 (CEN/TS 1992-4)  
Edge distance to prevent splitting under load: Annexes C1-C3 (TR 029); Annexes C6-C9 (CEN/TS 1992-4)  
Robustness: Annexes C1-C3 (TR 029); Annexes C6-C11 (CEN/TS 1992-4)  
Maximum installation torque: Annexes B2,B3,B5  
Minimum edge distance and spacing: Annexes B2-B5  
  
**Characteristic resistance to shear load (static and quasi-static loading):**  
Resistance to steel failure: Annexes C4,C5 (TR 029); Annexes C10,C11 (CEN/TS 1992-4)  
Resistance to pry-out failure: Annexes C4,C5 (TR 029); Annexes C10,C11 (CEN/TS 1992-4)  
Resistance to concrete edge failure: NPD (see TR 029); Annexes C10, C11 (CEN/TS 1992-4)  
  
**Displacements under short-term and long-term loading:**  
Displacements under short-term and long-term loading: Annexes C12,C13  
  
**Characteristic resistance and displacements for seismic performance categories C1 and C2:**  
Resistance to tension load, displacements, category C1: NPD  
Resistance to tension load, displacements, category C2: NPD  
Resistance to shear load, displacements, category C1: NPD  
Resistance to shear load, displacements, category C2: NPD  
Factor for annular gap: NPD  
  
**Hygiene, health and the environment (BWR 3)**  
Content, emission and/or release of dangerous substances: NPD
8. Appropriate Technical Documentation and/or **–**  
Specific Technical Documentation:

The performance of the product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011, under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:



Dr.-Ing. Oliver Geibig, Managing Director Business Units & Engineering  
Tumlingen, 2021-01-11



Jürgen Grün, Managing Director Chemistry & Quality

This DoP has been prepared in different languages. In case there is a dispute on the interpretation the English version shall always prevail.

The Appendix includes voluntary and complementary information in English language exceeding the (language-neutrally specified) legal requirements.

## Specific Part

### 1 Technical description of the product

The fischer injection system FIS GREEN is a bonded anchor consisting of a cartridge with injection mortar fischer FIS GREEN and a steel element. The steel element consist of

- a fischer threaded rod with washer and hexagon nut of sizes M8 to M20 or
- internal threaded anchor RG MI of sizes M8 to M16 or
- a deformed reinforcing bar of sizes  $\phi = 8$  to 20 mm or
- a fischer rebar anchor FRA of sizes M12 to M20

The steel element is placed into a drilled hole filled with injection mortar and is anchored via the bond between metal part, injection mortar and concrete.

The product description is given in Annex A.

### 2 Specification of the intended use in accordance with the applicable European Assessment Document

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the anchor of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

### 3 Performance of the product and references to the methods used for its assessment

#### 3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Characteristic resistance for design according to TR 029	See Annex C 1 to C 5
Characteristic resistance for design according to CEN/TS 1992-4:2009	See Annex C 6 to C 11
Displacements under tension and shear loads	See Annex C 12 / C 13

#### 3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire	Anchors satisfy requirements for Class A1
Resistance to fire	No performance determined (NPD)

### **3.3 Hygiene, health and the environment (BWR 3)**

Regarding dangerous substances there may be requirements (e.g. transposed European legislation and national laws, regulations and administrative provisions) applicable to the products falling within the scope of this European Technical Assessment. In order to meet the provisions of Regulation (EU) No 305/2011, these requirements need also to be complied with, when and where they apply.

### **3.4 Safety in use (BWR 4)**

The essential characteristics regarding Safety in use are included under the Basic Works Requirement Mechanical resistance and stability.

### **3.5 Protection against noise (BWR 5)**

Not applicable.

### **3.6 Energy economy and heat retention (BWR 6)**

Not applicable.

### **3.7 Sustainable use of natural resources (BWR 7)**

The sustainable use of natural resources was not investigated.

### **3.8 General aspects**


The verification of durability is part of testing the essential characteristics. Durability is only ensured if the specifications of intended use according to Annex B are taken into account.

## **4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base**

According to Decision of the Commission of 24 June 1996 (96/582/EC) (OJ L 254 of 08.10.96 p. 62-65), the system of assessment and verification of constancy of performance (see Annex V and Article 65 Paragraph 2 to Regulation (EU) No 305/2011) given in the following table applies.

<b>Product</b>	<b>Intended use</b>	<b>Level or class</b>	<b>System</b>
Metal anchors for use in concrete (heavy-duty type)	For fixing and/or supporting concrete structural elements or heavy units such as cladding and suspended ceilings	—	1


## Installed condition



### fischer Injectionsystem FIS GREEN

**Product description**  
Installed condition

### Annex A 1



**Sealing cap**




1

**Shuttle cartridge**

(sizes: 345 ml; 360 ml; 390 ml; 950 ml; 1100ml; 1500 ml)

Imprint: fischer FIS GREEN, processing notes, shelf-life, piston travel scale, curing times and processing times (depending on temperature), hazard codes, size.



**Coaxial cartridge**

(sizes: 100 ml; 150 ml; 300 ml; 380 ml; 400ml; 410 ml)


Imprint: fischer FIS GREEN, processing notes, shelf-life, piston travel scale, curing times and processing times (depending on temperature), hazard codes, size



**fischer threaded rod**

(size: M8, M10, M12, M16, M20)

2



**Washer**

**Hexagon nut**

3


4



**fischer internal threaded anchor RG MI**

(size M8, M10, M12, M16)

5



**Screw**

**threaded rod**

**Washer**

**Hexagon nut**



6

**Reinforcing bar**

(size Ø8, Ø10, Ø12, Ø16, Ø20)

7



**fischer rebar anchor FRA**

(size M12, M16, M20)

8



**Washer**

**Hexagon nut**



**fischer Injectionsystem FIS GREEN**

**Product description**

Cartridges, Static mixer, Steel elements

**Annex A 2**

Appendix 4 / 26

**Table A1: Materials**

Part	Designation	Material		
1	Mortar cartridge	Bio based mortar, hardener; fillers		
		Steel, zinc plated	Stainless steel A4	High corrosion-resistant steel C
2	Threaded rod	Property class 5.8 or 8.8; ISO 898-1: 2013 zinc plated $\geq 5\mu\text{m}$ , ISO 4042:1999 A2K or hot-dip galvanised ISO 10684:2004 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 8\%$	Property class 50, 70 or 80 ISO 3506:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; 1.4062 EN 10088-1:2014 $f_{ik} \leq 1000 \text{ N/mm}^2$ $A_5 > 8\%$	Property class 50 or 80 ISO 3506:2009 or property class 70 with $f_{yk} = 560 \text{ N/mm}^2$ 1.4565; 1.4529 EN 10088-1:2014 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 8\%$
3	Washer ISO 7089:2000	zinc plated $\geq 5\mu\text{m}$ , EN ISO 4042:1999 A2K or hot-dip galvanised ISO 10684:2004	1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362 EN 10088-1:2014	1.4565; 1.4529 EN 10088-1:2014
4	Hexagon nut	Property class 5 or 8; ISO 898-2:2013 zinc plated $\geq 5\mu\text{m}$ , ISO 4042:1999 A2K or hot-dip galvanised ISO 10684:2004	Property class 50, 70 or 80 ISO 3506:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4571; 1.4439; 1.4362 EN 10088-1:2014	Property class 50, 70 or 80 ISO 3506:2009 1.4565; 1.4529 EN 10088-1:2014
5	Internal threaded anchor RG MI	Property class 5.8 or 8.8; EN 10277-1:2008-06 zinc plated $\geq 5\mu\text{m}$ , ISO 4042:1999 A2K	Property class 70 ISO 3506:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362 EN 10088-1:2014	Property class 70 ISO 3506-1:2009 1.4565; 1.4529 EN 10088-1:2014
6	Screw or threaded rod for internal threaded anchor	Property class 5.8 or 8.8; ISO 898-1:2013 zinc plated $\geq 5\mu\text{m}$ , ISO 4042:1999 A2K	Property class 70 ISO 3506:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362 EN 10088-1:2014	Property class 70 ISO 3506-1:2009 1.4565; 1.4529 EN 10088-1:2014
7	Rebar EN 1992-1-1:2004 + AC:2010, Annex C	Bars and decoiled rods class B or C with $f_{yk}$ and $k$ according to NDP or NCL of EN 1992-1-1/NA:2013 $f_{uk} = f_{tk} = k \cdot f_{yk}$		
8	Rebar anchor FRA	Bars and decoiled rods class B or C with $f_{yk}$ and $k$ according to NDP or NCL of EN 1992-1-1/NA:2013 $f_{uk} = f_{tk} = k \cdot f_{yk}$  Threaded part: Property class 70 ISO 3506:2009 1.4565; 1.4529 EN 10088-1:2014		

**fischer Injectionsystem FIS GREEN**
**Product description**  
Materials

**Annex A 3**

Appendix 5 / 26

## Specifications of intended use

### Anchorage subject to:

- Static and quasi-static loads.

### Base materials:

- Reinforced or unreinforced normal weight concrete according to EN 206:2013 .
- Strength classes C20/25 to C50/60 according to EN 206:2013.
- Non-cracked concrete.

### Temperature ranges:

	Max. long term temperature	Max. short term temperature
<b>Temperature range I</b> -40°C to +40°C	+24°C	+40°C
<b>Temperature range II</b> -40°C to +80°C	+50°C	+80°C

### Use conditions (Environmental conditions):

- Structures subject to dry internal conditions  
(zinc coated steel, stainless steel or high corrosion resistant steel)
- Structures subject to external atmospheric exposure (including industrial and marine environment) and to permanently damp internal condition, if no particular aggressive conditions exist  
(stainless steel or high corrosion resistant steel)
- Structures subject to external atmospheric exposure and to permanently damp internal condition, if other particular aggressive conditions (high corrosion resistant steel)  
Note: Particular aggressive conditions are e.g. permanent, alternating immersion in seawater or the splash zone of seawater, chloride atmosphere of indoor swimming pools or atmosphere with extreme chemical pollution (e.g. in desulphurization plants or road tunnels where de-icing materials are used).

### Design:

- Anchorages have to be designed under the responsibility of an engineer experienced in anchorages and concrete work.
- Verifiable calculation notes and drawings have to be prepared taking account of the loads to be anchored. The position of the anchor is indicated on the design drawings (e.g. position of the anchor relative to reinforcement or to supports, etc.).
- Anchorages under static or quasi-static actions have to be designed in accordance with TR 029 "Design of bonded anchors", Edition September 2010 or CEN/TS 1992-4:2009

### Installation:

- Anchor installation carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters of the site.
- Dry or wet concrete.
- Hole drilling by hammer mode.
- In case of aborted hole: The hole shall be filled with mortar
- Marking and keeping the effective anchorage depth
- Cleaning the drill hole and installation in accordance with Annexes B 7 to B 8
- During curing of the mortar the temperature of the concrete must not fall below 0°C
- The curing time until the anchor may be loaded as given in Annex B 6 Table B6

**fischer Injectionsystem FIS GREEN**

**Intended use**  
Specifications

**Annex B 1**


Appendix 6 / 26

**Table B1: Installation parameters threaded rods**

Anchor size			M8	M10	M12	M16	M20
Nominal drill hole diameter		d <sub>0</sub> [mm]	10	12	14	18	24
Width across flat		SW [mm]	13	17	19	24	30
Drill hole depth		h <sub>0</sub> [mm]	h <sub>0</sub> = h <sub>ef</sub>				
Effective anchorage depth		h <sub>ef,min</sub> [mm]	60	60	70	80	90
		h <sub>ef,max</sub> [mm]	160	200	240	320	400
Maximum torque moment		T <sub>inst,max</sub> [Nm]	10	20	40	60	120
Minimum spacing		s <sub>min</sub> [mm]	40	45	55	65	85
Minimum edge distance		c <sub>min</sub> [mm]	40	45	55	65	85
Diameter of clearance hole in the fixture <sup>1)</sup>	Pre-positioned anchorage	d <sub>f</sub> [mm]	9	12	14	18	22
	Push-through anchorage	d <sub>f</sub> [mm]	11	14	16	20	26
Minimum thickness of concrete member		h <sub>min</sub> [mm]	h <sub>ef</sub> + 30 (≥ 100)			h <sub>ef</sub> + 2d <sub>0</sub>	

<sup>1)</sup> For bigger clearance holes in fixture see TR 029, chapter 1.1 or CEN/TS 1992-4-1, chapter 1.2.3

#### fischer threaded rod FIS A and RGM



#### Marking:

Property class 8.8 or high corrosion-resistant steel C, property class 80: •

Stainless steel A4, property class 50 and high corrosion-resistant steel C, property class 50: ••

**Commercial standard threaded rods, washers and hexagon nuts may also be used if the following requirements are fulfilled:**

- Materials, dimensions and mechanical properties according Annex A 3, Table A1
- Inspection certificate 3.1 according to EN 10204:2004, the documents should be stored
- Marking of embedment depth

**fischer Injectionsystem FIS GREEN**

#### Intended use

Installation parameters threaded rods

**Annex B 2**

Appendix 7 / 26




Table B2: Installation parameters internal threaded anchors RG MI


Nominal size			M8	M10	M12	M16
Anchor size	$d_H$	[mm]	12	16	18	22
Nominal drill hole diameter	$d_0$	[mm]	14	18	20	24
Drill hole depth	$h_0$	[mm]	$h_0 = h_{ef}$			
Effective anchorage depth	$h_{ef}$	[mm]	90	90	125	160
Maximum torque moment	$T_{inst,max}$	[Nm]	10	20	40	80
Minimum spacing	$s_{min}$	[mm]	55	65	75	95
Minimum edge distance	$c_{min}$	[mm]	55	65	75	95
Diameter of clearance hole in the fixture <sup>1)</sup>	$d_f$	[mm]	9	12	14	18
Minimum thickness of concrete member	$h_{min}$	[mm]	120	126	165	208
Maximum screw-in depth	$l_{E,max}$	[mm]	18	23	26	35
Minimum screw-in depth	$l_{E,min}$	[mm]	8	10	12	16

<sup>1)</sup> For bigger clearance holes in fixture see TR 029, chapter 1.1 or CEN/TS 1992-4-1, chapter 1.2.3

fischer internal threaded anchor RG MI



Marking: anchor size e.g.: M10  
Stainless steel in addition A4 e.g.: M10  
A4High corrosion-resistant steel in addition C  
e.g.: M10 C




Fastening screw or threaded rods including washer and nuts must comply with the appropriate material and strength class of table A1

Rebar diameter			8 <sup>1)</sup>	10 <sup>1)</sup>	12 <sup>1)</sup>	14	16	20
Nominal drill hole diameter	d <sub>0</sub>	[mm]	(10)12	(12)14	(14) 16	18	20	25
Drill hole depth	h <sub>0</sub>	[mm]	h <sub>0</sub> = h <sub>ef</sub>					
Effective anchorage depth	h <sub>ef,min</sub>	[mm]	60	60	70	75	80	90
	h <sub>ef,max</sub>	[mm]	160	200	240	280	320	400
Minimum spacing	s <sub>min</sub>	[mm]	40	45	55	60	65	85
Minimum edge distance	c <sub>min</sub>	[mm]	40	45	55	60	65	85
Minimum thickness of concrete member	h <sub>min</sub>	[mm]	h <sub>ef</sub> + 30 ≥ 100			h <sub>ef</sub> + 2d <sub>0</sub>		

1) Both drill bit diameters can be used.

## Reinforcing bar



Properties of reinforcement: refer to EN 1992-1-1 Annex C, Table C.1 and C.2N

Product form			Non-zink-plated bars and decoiled rod	
Class			B	C
Characteristic yield strength $f_{yk}$ or $f_{0,2k}$ [MPa]			400 to 600	
Minimum value of $k = (f_t/f_y)_k$			≥ 1,08	≥ 1,15 < 1,35
Characteristic strain at maximum force $\epsilon_{uk}$ [%]			≥ 5,0	≥ 7,5
Bentability property			Bend / Rebendtest	
Maximum deviation from nominal mass (individual bar) [%]	Nominal bar size [mm]	≤ 8	± 6,0	
		> 8	± 4,5	
Bond: Minimum relative rib area, $f_{R,min}$ (determination acc. to EN 15630)	Nominal bar size [mm]	8 to 12	0,040	
		> 12	0,056	

## Rib height h:

The rib height h must be:

$$0,05 * d \leq h \leq 0,07 * d$$

d = nominal bar size

**fischer Injectionsystem FIS GREEN**

## Intended use

Installation parameters reinforcing bars

**Annex B 4**

Appendix 9 / 26


**Table B4: Installation parameters rebar anchor FRA**



Threaded diameter			M12 <sup>1)</sup>	M16	M20
Nominal bar size	d	[mm]	12	16	20
Width across flat	SW	[mm]	19	24	30
Nominal drill hole diameter	d <sub>0</sub>	[mm]	(14) 16	20	25
Drill hole depth	h <sub>0</sub>	[mm]	h <sub>ef</sub> + l <sub>e</sub>		
Distance concrete surface to welded joint	l <sub>e</sub>	[mm]	100		
Effective anchorage depth	h <sub>ef,min</sub>	[mm]	70	80	90
	h <sub>ef,max</sub>	[mm]	140	220	300
Maximum torque moment	T <sub>inst,max</sub>	[Nm]	40	60	120
Minimum spacing	s <sub>min</sub>	[mm]	55	65	85
Minimum edge distance	c <sub>min</sub>	[mm]	55	65	85
Diameter of clearance hole in the fixture <sup>2)</sup>	Pre-positioned anchorage	d <sub>f</sub>	14	18	22
	Push-through anchorage	d <sub>f</sub>	18	22	26
Minimum thickness of concrete member	h <sub>min</sub>	[mm]	h <sub>0</sub> + 30	h <sub>0</sub> + 2d <sub>0</sub>	

<sup>1)</sup> Both drill bit diameters can be used

<sup>2)</sup> For bigger clearance holes in fixture see TR 029, chapter 1.1 or CEN/TS 1992-4-1, chapter 1.2.3

**fischer rebar anchor FRA**



Marking:  FRA (for stainless steel)  
 FRA C (for high corrosion-resistant steel)

**fischer Injectionsystem FIS GREEN**


**Intended use**  
 Installation parameters rebar anchor FRA

**Annex B 5**

Appendix 10 / 26

**Table B5: Parameters of steel brush FIS BS**

Drill bit diameter	[mm]	10	12	14	16	18	20	24	25
Steel brush diameter $d_b$	[mm]	11	14	16	20	20	25	26	27







**Cleaning nozzle****Table B6: Maximum processing time of the mortar and minimum curing time**

(During the curing time of the mortar the concrete temperature may not fall below the listed minimum temperature).





Temperature at anchoring base [ °C ]	Minimum curing time <sup>1)</sup> $t_{\text{cure}}$ [ minutes ]	System temperature (mortar) [ °C ]	Maximum processing time $t_{\text{work}}$ [ minutes ]
±0 to +5	6 hours	+5	13
>+5 to +10	4 hours	+10	9
>+10 to +20	90	+20	5
>+20 to +30	60	+30	4
>+30 to +40	30	+40	2

<sup>1)</sup> For wet concrete the curing time must be doubled.

# Installation instructions part 1 Drilling and cleaning the hole

1		Drill the hole. Drill hole diameter $d_0$ and drill hole depth $h_0$ see Tables <b>B1</b> , <b>B2</b> , <b>B3</b> , <b>B4</b> .		
2		$h_{ef} \leq 10d$ and $d_0 < 18$ mm: Blow out the drill hole two times by hand.		$h_{ef} > 10d$ and/or $d_0 \geq 18$ mm: Blow out the drill hole two times, using oil-free pressure air ( $p > 6$ bar) with a cleaning nozzle.
3		Brush the drill hole two times using an adequate steel brush (see Table <b>B5</b> ).		
4		$h_{ef} \leq 10d$ and $d_0 < 18$ mm: Blow out the drill hole two times by hand.		$h_{ef} > 10d$ and/or $d_0 \geq 18$ mm: Blow out the drill hole two times, using oil-free pressure air ( $p > 6$ bar) with a cleaning nozzle.

## Preparing the cartridge

5		Twist off the sealing cap.
6		Twist on the static mixer. The spiral in the static mixer must be clearly visible.
7		Place the cartridge into the dispenser.
8		Press out approx. 10cm of mortar until the resin is permanent grey in colour. Mortar which is not grey in colour will not cure and must be disposed of.

fischer Injectionsystem FIS GREEN



Intended Use  
Installation instructions part 1

Annex B 7







Appendix 12 / 26

## Installation instructions part 2




### Injection of the mortar

9		Fill approx. 2/3 of the drill hole with mortar. Always begin from the bottom of the hole to eliminate voids.		For drill hole depth $\geq 150$ mm use an extension tube.
---	---	--	--	---

### Installation fischer anchor rods or internal threaded anchors RG MI

10			Only use clean and oil-free anchor elements. Press the anchor rod or internal threaded anchor RG MI down to the bottom of the hole, turning it slightly while doing so. After inserting the anchor element, excess mortar must emerge around the anchor element.	
		For overhead installation support the anchor element with wedges.		For push-through installation fill the annular gap also with mortar.
11		Wait for the specified curing time $t_{\text{cure}}$ see Table B6.		
12		Mounting the fixture $T_{\text{inst,max}}$ see Tables B1 or B6		

### Installing reinforcing bars and fischer rebar anchors FRA

10		Only use clean and oil-free rebars. Mark the reinforcing bar for setting depth. Using a turning movement, push the reinforcing bar or FRA vigorously into the filled hole up to the insertion depth marking. When reaching the setting depth marking surplus mortar must emerge around the anchor.	
11		Wait for the specified curing time $t_{\text{cure}}$ see Table B6.	
12		Mounting the fixture $T_{\text{inst,max}}$ see Table B4	

**fischer Injectionsystem FIS GREEN**

**Intended Use**  
Installation instructions part 2

**Annex B 8**

Appendix 13 / 26

**Table C1: Characteristic values of resistance for threaded rods under tension loads in non-cracked concrete (Design according to TR 029)**

Anchor size			M8	M10	M12	M16	M20
Installation safety factor	$\gamma_2$	[-]	1,2				
<b>Combined pullout and concrete cone failure</b>							
Diameter for calculation	d	[mm]	8	10	12	16	20
Characteristic bond resistance in non-cracked concrete C20/25							
Temperature range I <sup>1)</sup>	$\tau_{Rk,ucr}$	[N/mm <sup>2</sup> ]	10,5	10,0	9,5	8,5	7,5
Temperature range II <sup>1)</sup>	$\tau_{Rk,ucr}$	[N/mm <sup>2</sup> ]	9,5	9,0	8,5	7,5	6,5
Increasing factor $\Psi_c$	C25/30	[-]	1,02				
	C30/37	[-]	1,04				
	C35/45	[-]	1,07				
	C40/50	[-]	1,08				
	C45/55	[-]	1,09				
	C50/60	[-]	1,10				
<b>Splitting failure</b>							
Edge distance $c_{cr,sp}$	$h/h_{ef} \geq 2,0$	[mm]	$1,0 h_{ef}$				
	$2,0 > h/h_{ef} > 1,3$	[mm]	$4,6 h_{ef} - 1,8 h$				
	$h/h_{ef} \leq 1,3$	[mm]	$2,26 h_{ef}$				
Spacing	$s_{cr,sp}$	[mm]	$2 c_{cr,sp}$				

<sup>1)</sup> See Annex B1

**Table C2: Characteristic values of resistance for internal threaded anchors RG MI under tension loads in non-cracked concrete (Design according to TR 029)**

Anchor size				M8	M10	M12	M16
Installation safety factor		$\gamma_2$	[-]	1,2			
Steel failure							
Characteristic resistance with screw $N_{Rk,s}$	Property class	5.8	[kN]	19	29	43	79
		8.8	[kN]	29	47	68	108
	Property class 70	A4	[kN]	26	41	59	110
		C	[kN]	26	41	59	110
Partial safety factor $\gamma_{Ms,N}^{1)}$	Property class	5.8	[-]	1,50			
		8.8	[-]	1,50			
	Property class 70	A4	[-]	1,87			
		C	[-]	1,87			
Combined pullout and concrete cone failure							
Characteristic bond resistance in non-cracked concrete C20/25							
Temperature range I <sup>2)</sup>		$N_{Rk,p}^0$	[kN]	32	38	56	76
Temperature range II <sup>2)</sup>		$N_{Rk,p}^0$	[kN]	30	35	51	70
Increasing factor $\Psi_c$	C25/30		[-]	1,02			
	C30/37		[-]	1,04			
	C35/45		[-]	1,07			
	C40/50		[-]	1,08			
	C45/55		[-]	1,09			
	C50/60		[-]	1,10			
Splitting failure							
Edge distance $c_{cr,sp}$	$h/h_{ef} \geq 2,0$		[mm]	$1,0 h_{ef}$			
	$2,0 > h/h_{ef} > 1,3$		[mm]	$4,6 h_{ef} - 1,8 h$			
	$h/h_{ef} \leq 1,3$		[mm]	$2,26 h_{ef}$			
Spacing		$s_{cr,sp}$	[mm]	$2 c_{cr,sp}$			

<sup>1)</sup> In absence of other national regulations

<sup>2)</sup> See Annex B1



**Table C3: Characteristic values of resistance for reinforcing bars under tension loads in non-cracked concrete (Design according to TR 029)**

Size	Ø	[mm]	8	10	12	14	16	20
Installation safety factor	$\gamma_2$	[-]	1,2					
Combined pullout and concrete cone failure								
Diameter of calculation	d	[mm]	8	10	12	14	16	20
Characteristic bond resistance in non-cracked concrete C20/25								
Temperature range I <sup>2)</sup>	$\tau_{Rk,ucr}$	[N/mm <sup>2</sup> ]	7,5	7,5	7,5	7,5	7,5	7,5
Temperature range II <sup>2)</sup>	$\tau_{Rk,ucr}$	[N/mm <sup>2</sup> ]	6,5	6,5	6,5	6,5	6,5	6,5
Increasing factor $\Psi_c$	C25/30	[-]	1,02					
	C30/37	[-]	1,04					
	C35/45	[-]	1,07					
	C40/50	[-]	1,08					
	C45/55	[-]	1,09					
	C50/60	[-]	1,10					
Splitting failure								
Edge distance $c_{cr,sp}$	$h/h_{ef} \geq 2,0$	[mm]	$1,0 h_{ef}$					
	$2,0 > h/h_{ef} > 1,3$	[mm]	$4,6 h_{ef} - 1,8 h$					
	$h/h_{ef} \leq 1,3$	[mm]	$2,26 h_{ef}$					
Spacing	$s_{cr,sp}$	[mm]	$2 c_{cr,sp}$					

<sup>1)</sup> In absence of other national regulations

<sup>2)</sup> See Annex B1

**Table C4: Characteristic values of resistance for rebar anchors FRA under tension loads in non-cracked concrete (Design according to TR 029)**

Size			M12	M16	M20
Installation safety factor	$\gamma_2$	[-]	1,2		
Steel failure					
Characteristic resistance	$N_{Rk,s}$	[kN]	63	111	173
Partial safety factor	$\gamma_{Ms,N}$ <sup>1)</sup>	[-]	1,40		
Combined pullout and concrete cone failure					
Diameter of calculation	d	[mm]	12	16	20
Characteristic bond resistance in non-cracked concrete C20/25					
Temperature range I <sup>2)</sup>	$\tau_{Rk,ucr}$	[N/mm <sup>2</sup> ]	7,5	7,5	7,5
Temperature range II <sup>2)</sup>	$\tau_{Rk,ucr}$	[N/mm <sup>2</sup> ]	6,5	6,5	6,5
Increasing factor $\Psi_c$	C25/30	[-]	1,02		
	C30/37	[-]	1,04		
	C35/45	[-]	1,07		
	C40/50	[-]	1,08		
	C45/55	[-]	1,09		
	C50/60	[-]	1,10		
Splitting failure					
Edge distance $c_{cr,sp}$	$h/h_{ef} \geq 2,0$	[mm]	$1,0 h_{ef}$		
	$2,0 > h/h_{ef} > 1,3$	[mm]	$4,6 h_{ef} - 1,8 h$		
	$h/h_{ef} \leq 1,3$	[mm]	$2,26 h_{ef}$		
Spacing	$s_{cr,sp}$	[mm]	$2 c_{cr,sp}$		

<sup>1)</sup> In absence of other national regulations

<sup>2)</sup> See Annex B1

**fischer Injectionsystem FIS GREEN**

#### Performances

Characteristic values of resistance for reinforcing bars and rebar anchors FRA under tension load in non-cracked concrete. (Design according to TR 029)

**Annex C 3**

Appendix 16 / 26

**Table C5: Characteristic values of resistance for threaded rods under shear loads in non-cracked concrete (Design according to TR 029)**

Size		M8	M10	M12	M16	M20
<b>Concrete pryout failure</b>						
Factor k in equation (5.7) of Technical Report TR 029, Section 5.2.3.3	k	[-]				
		2,0				

**Table C6: Characteristic values of resistance for internal threaded rods RG MI under shear loads in non-cracked concrete (Design according to TR 029)**

Size		M8		M10	M12	M16	
Steel failure without lever arm							
Characteristic resistance $V_{Rk,s}$	Property class	5.8	[kN]	9,2	14,5	21,1	39,2
		8.8	[kN]	14,6	23,2	33,7	62,7
	Property class 70	A4	[kN]	12,8	20,3	29,5	54,8
		C	[kN]	12,8	20,3	29,5	54,8
Steel failure with lever arm							
Characteristic resistance $M^0_{Rk,s}$	Property class	5.8	[Nm]	20	39	68	173
		8.8	[Nm]	30	60	105	266
	Property class 70	A4	[Nm]	26	52	92	232
		C	[Nm]	26	52	92	232
Concrete pryout failure							
Factor k in equation (5.7) of Technical Report TR 029, Section 5.2.3.3		k	[-]	2,0			

**Table C7: Characteristic values of resistance for reinforcing bars under shear loads in non-cracked concrete (Design according to TR 029)**

Size	Ø	[mm]	8	10	12	14	16	20
<b>Concrete pryout failure</b>								
Factor k in equation (5.7) of Technical Report TR 029, Section 5.2.3.3	k	[-]	2,0					

**Table C8: Characteristic values of resistance rebar anchors FRA under shear loads in non-cracked concrete (Design according to TR 029)**

Size			M12	M16	M20
Steel failure without lever arm					
Characteristic resistance	V <sub>Rk,s</sub>	[kN]	30	55	86
Steel failure with lever arm					
Characteristic resistance	M <sup>0</sup> <sub>Rk,s</sub>	[Nm]	92	233	454
Partial safety factor	γ <sub>Ms,V</sub> <sup>1)</sup>	[-]	1,56		
Concrete pryout failure					
Factor k in equation (5.7) of Technical Report TR 029, Section 5.2.3.3	k	[-]	2,0		

<sup>1)</sup> In absence of other national regulations

**Table C9: Characteristic values of resistance for threaded rods under tension loads in non-cracked concrete (Design according to CEN/TS 1992-4)**

Anchor size			M8	M10	M12	M16	M20
Installation safety factor	$\gamma_{inst}$	[-]	1,2				
<b>Steel failure</b>							
Characteristic resistance	$N_{Rk,s}$	[kN]	$A_s \times f_{uk}$				
<b>Combined pullout and concrete cone failure</b>							
Diameter for calculation	d	[mm]	8	10	12	16	20
Characteristic bond resistance in non-cracked concrete C20/25							
Temperature range I <sup>1)</sup>	$\tau_{Rk,ucr}$	[N/mm <sup>2</sup> ]	10,5	10,0	9,5	8,5	7,5
Temperature range II <sup>1)</sup>	$\tau_{Rk,ucr}$	[N/mm <sup>2</sup> ]	9,5	9,0	8,5	7,5	6,5
Increasing factor $\Psi_c$	C25/30	[-]	1,02				
	C30/37	[-]	1,04				
	C35/45	[-]	1,07				
	C40/50	[-]	1,08				
	C45/55	[-]	1,09				
	C50/60	[-]	1,10				
Factor acc. CEN/TS-1992-4 Section 6.2.2.3	$k_8$	[-]	10,1				
<b>Splitting failure</b>							
Factor acc. CEN/TS-1992-4 Section 6.2.3.1	$k_{ucr}$	[-]	10,1				
Edge distance $c_{cr,sp}$	$h/h_{ef} \geq 2,0$	[mm]	$1,0 h_{ef}$				
	$2,0 > h/h_{ef} \geq 1,3$	[mm]	$4,6 h_{ef} - 1,8 h$				
	$h/h_{ef} \leq 1,3$	[mm]	$2,26 h_{ef}$				
Spacing	$s_{cr,sp}$	[mm]	$2 c_{cr,sp}$				

<sup>1)</sup> See Annex B1

**Table C10: Characteristic values of resistance for internal threaded anchors RG MI under tension loads in non-cracked concrete (Design according to CEN/TS 1992-4)**

Anchor size			M8	M10	M12	M16	
Installation safety factor		$\gamma_{inst}$	[-]	1,2			
<b>Steel failure</b>							
Characteristic resistance with screw $N_{Rk,s}$	Property class	5.8	[kN]	19	29	43	79
		8.8	[kN]	29	47	68	108
	Property class 70	A4	[kN]	26	41	59	110
		C	[kN]	26	41	59	110
Partial safety factor $\gamma_{Ms,N}^{1)}$	Property class	5.8	[-]	1,50			
		8.8	[-]	1,50			
	Property class 70	A4	[-]	1,87			
		C	[-]	1,87			
<b>Combined pullout and concrete cone failure</b>							
Characteristic bond resistance in non-cracked concrete C20/25							
Temperature range I <sup>2)</sup>		$N_{Rk,p}^0$	[kN]	32	38	56	76
Temperature range II <sup>2)</sup>		$N_{Rk,p}^0$	[kN]	30	35	51	70
Increasing factor $\Psi_c$	C25/30	[-]	1,02				
	C30/37	[-]	1,04				
	C35/45	[-]	1,07				
	C40/50	[-]	1,08				
	C45/55	[-]	1,09				
	C50/60	[-]	1,10				
Factor acc. CEN/TS-1992-4-5:2009 Section 6.2.2.3		$k_8$	[-]	10,1			
<b>Splitting failure</b>							
Factor acc. CEN/TS-1992-4-5:2009 Section 6.2.3.1		$k_{ucr}$	[-]	10,1			
Edge distance $c_{cr,sp}$	$h/h_{ef} \geq 2,0$	[mm]	$1,0 h_{ef}$				
	$2,0 > h/h_{ef} > 1,3$	[mm]	$4,6 h_{ef} - 1,8 h$				
	$h/h_{ef} \leq 1,3$	[mm]	$2,26 h_{ef}$				
Spacing		$s_{cr,sp}$	[mm]	$2 c_{cr,sp}$			

<sup>1)</sup> In absence of other national regulations

<sup>2)</sup> See Annex B1

**Table C11: Characteristic values of resistance for reinforcing bars under tension loads in non-cracked concrete (Design according to CEN/TS 1992-4)**

Size	Ø	[mm]	8	10	12	14	16	20
Installation safety factor	γ <sub>inst</sub>	[-]	1,2					
Steel failure								
Characteristic resistance	N <sub>Rk,s</sub>	[kN]	A <sub>s</sub> × f <sub>uk</sub>					
Combined pullout and concrete cone failure								
Diameter of calculation	d	[mm]	8	10	12	14	16	20
Characteristic bond resistance in non-cracked concrete C20/25								
Temperature range I <sup>1)</sup>	τ <sub>Rk,ucr</sub>	[N/mm <sup>2</sup> ]	7,5	7,5	7,5	7,5	7,5	7,5
Temperature range II <sup>1)</sup>	τ <sub>Rk,ucr</sub>	[N/mm <sup>2</sup> ]	6,5	6,5	6,5	6,5	6,5	6,5
Increasing factor Ψ <sub>c</sub>	C25/30	[-]	1,02					
	C30/37	[-]	1,04					
	C35/45	[-]	1,07					
	C40/50	[-]	1,08					
	C45/55	[-]	1,09					
	C50/60	[-]	1,10					
Factor acc. CEN/TS-1992-4-5:2009 Section 6.2.2.3	k <sub>8</sub>	[-]	10,1					
Splitting failure								
Factor acc. CEN/TS-1992-4-5:2009 Section 6.2.3.1	k <sub>ucr</sub>	[-]	10,1					
Edge distance c <sub>cr,sp</sub>	h/h <sub>ef</sub> ≥2,0	[mm]	1,0 h <sub>ef</sub>					
	2,0>h/h <sub>ef</sub> ≥1,3	[mm]	4,6 h <sub>ef</sub> – 1,8 h					
	h/h <sub>ef</sub> ≤1,3	[mm]	2,26 h <sub>ef</sub>					
Spacing	s <sub>cr,sp</sub>	[mm]	2 c <sub>cr,sp</sub>					

<sup>1)</sup> See Annex B1

**Table C12: Characteristic values of resistance for rebar anchors FRA under tension loads in non-cracked concrete (Design according to CEN/TS 1992-4)**

Size			M12	M16	M20
Installation safety factor	$\gamma_{inst}$	[-]	1,2		
<b>Steel failure</b>					
Characteristic resistance	$N_{Rk,s}$	[kN]	63	111	173
Partial safety factor	$\gamma_{Ms,N}$	[-]	1,40		
<b>Combined pullout and concrete cone failure</b>					
Diameter of calculation	d	[mm]	12	16	20
Characteristic bond resistance in non-cracked concrete C20/25					
Temperature range I <sup>2)</sup>	$\tau_{Rk,ucr}$	[N/mm <sup>2</sup> ]	7,5	7,5	7,5
Temperature range II <sup>2)</sup>	$\tau_{Rk,ucr}$	[N/mm <sup>2</sup> ]	6,5	6,5	6,5
Increasing factor $\Psi_c$	C25/30	[-]	1,02		
	C30/37	[-]	1,04		
	C35/45	[-]	1,07		
	C40/50	[-]	1,08		
	C45/55	[-]	1,09		
	C50/60	[-]	1,10		
Factor acc. CEN/TS-1992-4-5:2009 Section 6.2.2.3	$k_8$	[-]	10,1		
<b>Splitting failure</b>					
Factor acc. CEN/TS-1992-4-5:2009 Section 6.2.3.1	$k_{ucr}$	[-]	10,1		
Edge distance $c_{cr,sp}$	$h/h_{ef} \geq 2,0$	[mm]	$1,0 h_{ef}$		
	$2,0 > h/h_{ef} > 1,3$	[mm]	$4,6 h_{ef} - 1,8 h$		
	$h/h_{ef} \leq 1,3$	[mm]	$2,26 h_{ef}$		
Spacing	$s_{cr,sp}$	[mm]	$2 c_{cr,sp}$		

<sup>1)</sup> In absence of other national regulations

<sup>2)</sup> See Annex B1

**Table C13: Characteristic values of resistance for threaded rods under shear loads in non-cracked concrete (Design according to CEN/TS 1992-4)**

Size			M8	M10	M12	M16	M20
Installation safety factor	$\gamma_{inst}$	[-]	1,0				
Steel failure without lever arm							
Characteristic resistance	$V_{RK,s}$	[kN]	0,5 $A_s \times f_{uk}$				
Ductility factor acc. to CEN/TS 1992-4-5, Section 6.3.2.1	$k_2$	[-]	0,8				
Steel failure with lever arm							
Characteristic resistance	$M^0_{RK,s}$	[Nm]	1,2 x $W_{el} \times f_{uk}$				
Concrete pryout failure							
Factor in equation of CEN/TS 1992-4-5, Section 6.3.3	$k_3$	[-]	2,0				
Concrete edge failure							
Effective length of anchor	$l_f$	[mm]	$l_f = \min(h_{ef}; 8 d_{nom})$				
Outside diameter of anchor	$d_{nom}$	[mm]	8	10	12	16	20

**Table C14: Characteristic values of resistance for internal threaded rods RG MI under shear loads in non-cracked concrete (Design according to CEN/TS 1992-4)**

Size				M8	M10	M12	M16
Installation safety factor		$\gamma_{inst}$	[-]	1,0			
Steel failure without lever arm							
Characteristic resistance $V_{Rk,s}$	Property class	5.8	[kN]	9,2	14,5	21,1	39,2
		8.8	[kN]	14,6	23,2	33,7	62,7
	Property class 70	A4	[kN]	12,8	20,3	29,5	54,8
		C	[kN]	12,8	20,3	29,5	54,8
Ductility factor acc. to CEN/TS 1992-4-5, Section 6.3.2.1		$k_2$	[-]	0,8			
Steel failure with lever arm							
Characteristic resistance $M^0_{Rk,s}$	Property class	5.8	[Nm]	20	39	68	173
		8.8	[Nm]	30	60	105	266
	Property class 70	A4	[Nm]	26	52	92	232
		C	[Nm]	26	52	92	232
Concrete pryout failure							
Factor in equation of CEN/TS 1992-4-5, Section 6.3.3		$k_3$	[-]	2,0			
Concrete edge failure							
Effective length of anchor		$l_f$	[mm]	90	90	125	160
Outside diameter of anchor		$d_{nom}$	[mm]	12	16	18	22

**fischer Injectionsystem FIS GREEN**

**Performances**

Characteristic values of resistance for threaded rods and internal threaded anchors RG MI under shear loads in non-cracked concrete (Design according to CEN/TS

**Annex C 10**

Appendix 23 / 26



**Table C15: Characteristic values of resistance for reinforcing bars under shear loads in non-cracked concrete (Design according to CEN/TS 1992-4)**

Size	Ø d	[mm]	8	10	12	14	16	20
Installation safety factor	$\gamma_{inst}$	[-]	1,0					
Steel failure without lever arm								
Characteristic resistance	$V_{Rk,s}$	[kN]	0,5 A <sub>s</sub> x f <sub>uk</sub>					
Ductility factor acc. to CEN/TS 1992-4-5, Section 6.3.2.1	k <sub>2</sub>	[-]	0,8					
Steel failure with lever arm								
Characteristic resistance	$M^0_{Rk,s}$	[Nm]	1,2 x W <sub>el</sub> x f <sub>uk</sub>					
Concrete pryout failure								
Factor in equation of CEN/TS 1992-4-5, Section 6.3.3	k <sub>3</sub>	[-]	2,0					
Concrete edge failure								
Effective length of anchor	l <sub>f</sub>	[mm]	l <sub>f</sub> = min (h <sub>ef</sub> , 8d <sub>nom</sub> )					
Outside diameter of anchor	d <sub>nom</sub>	[mm]	8	10	12	14	16	20

**Table C16: Characteristic values of resistance rebar anchors FRA under shear loads in non-cracked concrete (Design according to CEN/TS 1992-4)**

Size			M12	M16	M20
Installation safety factor	$\gamma_{inst}$	[-]	1,0		
Steel failure without lever arm					
Characteristic resistance	$V_{Rk,s}$	[kN]	30	55	86
Ductility factor acc. to CEN/TS 1992-4-5, Section 6.3.2.1	$k_2$	[-]	0,8		
Steel failure with lever arm					
Characteristic resistance	$M^0_{Rk,s}$	[Nm]	92	233	454
Partial safety factor	$\gamma_{Ms,V}^{1)}$	[-]	1,56		
Concrete pryout failure					
Factor in equation of CEN/TS 1992-4-5, Section 6.3.3	$k_3$	[-]	2,0		
Concrete edge failure					
Effective length of anchor	$l_f$	[mm]			
Outside diameter of anchor	$d_{nom}$	[mm]	12	16	20

<sup>1)</sup> In absence of other national regulations

**Table C17: Displacements under tension load<sup>1)</sup> for threaded rods**

Size		M8	M10	M12	M16	M20
<b>Temperature range I and II</b>						
$\delta_{N0}$ -Factor	[mm/(N/mm <sup>2</sup> )]	0,09	0,09	0,10	0,11	0,11
$\delta_{N\infty}$ -Factor	[mm/(N/mm <sup>2</sup> )]	0,14	0,14	0,15	0,17	0,17

<sup>1)</sup> Calculation of the displacement

$$\delta_{N0} = \delta_{N0}\text{-Factor} \cdot \tau$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-Factor} \cdot \tau$$

**Table C18: Displacements under shear load<sup>1)</sup> for threaded rods**

Size		M8	M10	M12	M16	M20
<b>Temperature range I and II</b>						
$\delta_{V0}$ -Factor	[mm/kN]	0,18	0,15	0,12	0,09	0,07
$\delta_{V\infty}$ -Factor	[mm]	0,27	0,22	0,18	0,14	0,11

<sup>1)</sup> Calculation of the displacement

$$\delta_{N0} = \delta_{N0}\text{-Factor} \cdot V$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-Factor} \cdot V$$

**Table C19: Displacements under tension load<sup>1)</sup> for internal threaded anchors RG MI**

Size		M8	M10	M12	M16
<b>Temperature range I and II</b>					
$\delta_{N0}$ -Factor	[mm/(N/mm <sup>2</sup> )]	0,10	0,11	0,12	0,12
$\delta_{N\infty}$ -Factor	[mm/(N/mm <sup>2</sup> )]	0,15	0,17	0,18	0,18

<sup>1)</sup> Calculation of the displacement

$$\delta_{N0} = \delta_{N0}\text{-Factor} \cdot \tau$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-Factor} \cdot \tau$$

**Table C20: Displacements under shear load<sup>1)</sup> for internal threaded anchors RG MI**

Size		M8	M10	M12	M16
<b>Temperature range I and II</b>					
$\delta_{V0}$ -Factor	[mm/kN]	0,18	0,15	0,12	0,09
$\delta_{V\infty}$ -Factor	[mm/kN]	0,27	0,22	0,18	0,14

<sup>1)</sup> Calculation of the displacement

$$\delta_{N0} = \delta_{N0}\text{-Factor} \cdot V$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-Factor} \cdot V$$

**Table C21: Displacements under tension load<sup>1)</sup> for reinforcing bars**

Size	Ø	[mm]	8	10	12	14	16	20
<b>Temperature range I and II</b>								
$\delta_{N0}$ -Factor		[mm/(N/mm <sup>2</sup> )]	0,09	0,09	0,10	0,11	0,12	0,13
$\delta_{N\infty}$ -Factor		[mm/(N/mm <sup>2</sup> )]	0,13	0,14	0,16	0,16	0,18	0,20

<sup>1)</sup> Calculation of the displacement

$$\delta_{N0} = \delta_{N0}\text{-Factor} \cdot \tau$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-Factor} \cdot \tau$$

**Table C22: Displacements under shear load<sup>1)</sup> for reinforcing bars**

Size	Ø	[mm]	8	10	12	14	16	20
<b>Temperature range I (-40°C / +40°C) and temperature range II (-40°C / +80°C)</b>								
$\delta_{V0}$ -Factor		[mm/kN]	0,18	0,15	0,12	0,10	0,09	0,07
$\delta_{V\infty}$ -Factor		[mm/kN]	0,27	0,22	0,18	0,16	0,14	0,11

<sup>1)</sup> Calculation of the displacement

$$\delta_{N0} = \delta_{N0}\text{-Factor} \cdot V$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-Factor} \cdot V$$

**Table C23: Displacements under tension load<sup>1)</sup> for rebar anchor FRA**

Size	Ø	[mm]	M10	M12	M16
<b>Temperature range I and II</b>					
$\delta_{N0}$ -Factor		[mm/(N/mm <sup>2</sup> )]	0,09	0,10	0,12
$\delta_{N\infty}$ -Factor		[mm/(N/mm <sup>2</sup> )]	0,14	0,16	0,18

<sup>1)</sup> Calculation of the displacement

$$\delta_{N0} = \delta_{N0}\text{-Factor} \cdot \tau$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-Factor} \cdot \tau$$

**Table C24: Displacements under shear load<sup>1)</sup> for rebar anchor FRA**

Size	Ø	[mm]	M10	M12	M16
<b>Temperature range I and II</b>					
$\delta_{V0}$ -Factor		[mm/kN]	0,15	0,12	0,09
$\delta_{V\infty}$ -Factor		[mm/kN]	0,22	0,18	0,14

<sup>1)</sup> Calculation of the displacement

$$\delta_{N0} = \delta_{N0}\text{-Factor} \cdot V$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-Factor} \cdot V$$