



DECLARATION OF PERFORMANCE

DoP 0331

for fischer injection system FIS V Plus (Mortar for post-installed rebar connections)

1. <u>Unique identification code of the product-type:</u> DoP 0331

2. Intended use/es: System for post-installed rebar connection, see appendix, especially annexes B1-B11.

fischerwerke GmbH & Co. KG, Otto-Hahn-Straße 15, 79211 Denzlingen, Germany 3. Manufacturer:

4. Authorised representative:

5. System/s of AVCP:

6. European Assessment Document: EAD 330087-01-0601 Edition 06/2021

ETA-20/0728; 2022-12-16 European Technical Assessment:

Technical Assessment Body: DIBt- Deutsches Institut für Bautechnik

Notified body/ies: 2873 TU Darmstadt

7. Declared performance/s:

Mechanical resistance and stability (BWR 1)

Characteristic resistance under static and quasi-static loading:

Bond strength of post-installed rebar: Annex C1

Bond efficiency factor: Annex C1

Amplification factor for minimum anchorage length: Annex C1

Characteristic resistance to steel failure for rebar tension anchors: Annex C2

Characteristic resistance under seismic loading:

Bond strength under seismic loading, Seismic bond efficiency factor: NPD

Minimum concrete cover under seismic loading: NPD

Safety in case of fire (BWR 2)

Reaction to fire: Class (A1)

Resistance to fire:

Bond strength at increased temperature for post-installed rebar assessed for 50 years: Annex C3 Bond strength at increased temperature for post-installed rebar assessed for 100 years: NPD Characteristic resistance to steel failure for rebar tension anchors under fire exposure: Annex C2

8. Appropriate Technical Documentation and/or Specific -

Technical Documentation:

The performance of the product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011, under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:

Dr.-Ing. Oliver Geibig, Managing Director Business Units & Engineering

Tumlingen, 2023-01-02

Jürgen Grün, Managing Director Chemistry & Quality

This DoP has been prepared in different languages. In case there is a dispute on the interpretation the English version shall always prevail.

The Appendix includes voluntary and complementary information in English language exceeding the (language-neutrally specified) legal requirements.

Fischer DATA DOP_ECs_V84.xlsm 1/1

f_{bd.PIR.100v}= NPD $k_{b,100y}$ = NPD

 $\alpha_{lb,100y}$ = NPD

ΕN



Translation guidance Essential Characteristics and Performance Parameters for Annexes

Me	chanical resistance and stability (BWR 1)					
	Characteristic resistance under static and quasi-static loading:					
1	Bond strength of post-installed rebar:	$f_{bd,PIR}$ [N/mm ²], $f_{bd,PIR,100y}$ [N/mm ²]				
2	Bond efficiency factor:	k _b [-], k _{b,100y} [-]				
3	Amplification factor for minimum anchorage length:	α _{lb} [-], α _{lb,100y} [-]				
4	Characteristic resistance to steel failure for rebar tension anchors:	N _{Rk,s} [kN]				
	Characteristic resistance under seismic loading:					
5	Bond strength under seismic loading, Seismic bond efficiency factor:	$\begin{split} &f_{bd,PIR,seis}\left[N/mm^2\right],k_{b,seis}\left[\text{-}\right],f_{bd,PIR,seis,100y}\\ &\left[N/mm^2\right],k_{b,seis,100y}\left[\text{-}\right] \end{split}$				
6	Minimum concrete cover under seismic loading:	c _{min,seis} [mm]				
Sa	fety in case of fire (BWR 2)	<u> </u>				
7	Reaction to fire:	Class				
	Resistance to fire:					
8	Bond strength at increased temperature for post-installed rebar assessed for 50 years:	$f_{bd,fi}(\theta) [N/mm^2], k_{fi} (\theta) [\text{-}], \theta_{max} [^{\circ}C]$				
9	Bond strength at increased temperature for post-installed rebar assessed for 100 years:	$f_{bd,fi,100y}(\theta) \; [N/mm^2], \; k_{fi,100y}(\theta) \; [-], \qquad \theta_{max} \\ [^{\circ}C]$				
10	Characteristic resistance to steel failure for rebar tension anchors under fire exposure:	N _{Rk,s,fi} [kN]				

Specific Part

1 Technical description of the product

The subject of this European Technical Assessment is the post-installed connection, by anchoring or overlap connection joint, of reinforcing bars (rebars) in existing structures made of normal weight concrete, using the "Rebar connection with injection system FIS V Plus" in accordance with the regulations for reinforced concrete construction.

Reinforcing bars made of steel with a diameter ϕ from 8 to 28 mm or the fischer rebar anchor FRA or FRA HCR of sizes M12 to M24 according to Annex A and injection mortar FIS V Plus or FIS V Plus Low Speed are used for rebar connections. The rebar is placed into a drilled hole filled with injection mortar and is anchored via the bond between rebar, injection mortar and concrete.

The product description is given in Annex A.

2 Specification of the intended use in accordance with the applicable European assessment Document

The performances given in Section 3 are only valid if the rebar connection is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the rebar connections of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment

3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Characteristic resistance under static and quasi-static loading	See Annex C 1 and C2
Characteristic resistance under seismic loading	No performance assessed

3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire	Class A1
Resistance to fire	See Annex C 2 and C 3

Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

In accordance with European Assessment Document EAD No. 330087-01-0601, the applicable European legal act is: [96/582/EC].

The system to be applied is: 1

Installation conditions and application examples reinforcing bars, part 1

Figure A1.1:

Overlap joint with existing reinforcement for rebar connections of slabs and beams




Figure A1.2:

Overlap joint with existing reinforcement at a foundation of a column or wall where the rebars are stressed





Figure A1.3:

End anchoring of slabs or beams (e.g. designed as simply supported)



Rebar connection with injection system FIS V Plus	
Product description	Annex A 1
Installation conditions and application examples reinforcing bars, part 1	Appendix 2 / 21

Installation conditions and application examples reinforcing bars, part 2

Figure A2.1:

Rebar connection for stressed primarily in compression





Figure A2.2:

Anchoring of reinforcement to cover the enveloped line of acting tensile force in the bending member



(only post-installed rebar is plotted)

Key to Figure

- T Acting tensile force
- E Envelope of M_{ed} / z + N_{ed} (see EN 1992-1-1:2011)
- x Distance between the theoretical point of support and concrete joint

Note to figure A1.1 to A1.3 and figure A2.1 to A2.2

In the figures no traverse reinforcement is plotted, the transverse reinforcement as required by EN 1992-1-1:2011 shall be present.

The shear transfer between old and new concrete shall be designed according to EN 1992-1-1:2011

Preparation of joints according to **Annex B 3** of this document


Rebar connection with injection system FIS V Plus	
Product description	Annex A 2
Installation conditions and application examples reinforcing bars, part 2	Appendix 3 / 21

Installation conditions and application examples fischer rebar anchor FRA


Figure A3.1:

Lap to a foundation of a column under bending.

- Shear lug (or fastener loaded in shear)
- 2. fischer rebar anchor FRA (tension only)
- 3. Existing stirrup / reinforcement for overlap (lap splice)
- 4. Slotted hole



A-A




B-B

Figure A3.2:

Lap of the anchoring of guardrail posts or anchoring of cantilevered building components.


In the anchor plate, the drill holes for the fischer rebar anchors FRA have to be designed as slotted holes with axial direction to the shear force.

- 1. Fastener for shear load transfer
- fischer rebar anchor FRA (tension only)
- 3. Existing stirrup / reinforcement for overlap (lap splice)
- 4. Slotted hole



The required transverse reinforcement acc. to EN 1992-1-1:2011 is not shown in the figures. **The fischer rebar anchor FRA may be only used for axial tensile force.** The tensile force must be transferred by lap to the existing reinforcement of the building. The transfer of the shear force has to be ensured by suitable measure, e.g. by means of shear force or anchors with European Technical Assessment (ETA).

Rebar connection with injection system FIS V Plus	
Product description	Annex A 3
Installation conditions and application examples fischer rebar anchors FRA	Appendix 4 / 21



Properties of reinforcing bars (rebar)

Figure A5.1:



- The minimum value of related rib area f_{R,min} according to EN 1992-1-1:2011
- The maximum outer rebar diameter over the ribs shall be.
 - The nominal diameter of the bar with rib $\phi + 2 \cdot h$ (h ≤ 0.07 · ϕ)
 - ο (φ: Nominal diameter of the bar; h_{rib} = rib height of the bar)

Table A5.1: Installation conditions for rebars

Nominal diameter of the ba	ф	81)		10	10 ¹⁾ 1		21)	14	16	20	2	5 ¹⁾	28	
Nominal drill hole diameter	d₀		10	12	12	14	14	16	18	20	25	30	35	35
Drill hole depth	h_0	$h_0 = I_v$												
Effective embedment depth	Ιν	[mm]]				acc. to static calculation							
Minimum thickness of concrete member	h _{min}		l _v + 30 (≥ 100)			I _v + 2d ₀								

¹⁾ Both drill hole diameters can be used

Table A5.2: Materials of rebars

Designation	Reinforcing bar (rebar)
FN 1992-1-1:2011 Annex C	Bars and de-coiled rods class B or C with f_{yk} and k according to NDP or NCI of EN 1992-1-1/NA $f_{uk} = f_{tk} = k \cdot f_{yk}$

Rebar connection with injection system FIS V Plus	
Product description	Annex A 5
Properties and materials of reinforcing bars (rebar)	Appendix 6 / 21

Properties of fischer rebar anchors FRA Figure A6.1: head marking \mathbf{t}_{fix} l_{e,ges}

Head marking e.g.: FRA (for stainless steel)

FRA HCR (for high corrosion-resistant steel)

Table A6.1: Installation conditions for fischer rebar anchors FRA

Thread diameter		M1	2 ²⁾	M16	M20	M2	2 4 ²⁾	
Nominal diameter	[mm]	1:	12 16 20				25	
Nominal drill bit diameter	d ₀	[mm]	14	16	20	25	30	35
Drill hole depth ($h_0 = I_{e,ges}$) $I_{e,ges}$			l _v + l _e					
Effective embedment depth I _v			according to static calculation					
Distance concrete surface welded join	to I _e	[mm]			10	00		
Maximum Diameter of	Pre-positioned d _f	[mm]	14	4	18	22	2	6
clearance hole in the fixture ¹⁾	Push through d _f	[mm]	16	18	22	26	32	
Minimum thickness of concrete member	h _{min}	[mm]	h ₀ +	30		h ₀ + 2d ₀		
Maximum torque moment attachment of the fixture	for max T _{inst}	[Nm]	50	0	100	150	1:	50

¹⁾ For bigger clearance holes in the fixture see EN 1992-4:2018 ²⁾ Both drill bit diameters can be used

Materials of fischer rebar anchors FRA Table A6.2:

Part	Description	Materials							
		FRA	FRA HCR						
		Corrosion resistance class CRC III	Corrosion resistance class CRC V						
		acc. to EN 1993-1-4:2006+A1:2015	acc. to EN 1993-1-4: 2006+A1:2015						
1	Reinforcing bar	Bars and de-coiled rods class B or C with fyk and k according to NDP or NCI of							
_ '	Tellilorellig bai	EN 1992-1-1:NA; $f_{uk} = f_{tk} = k \cdot f_{yk}$; $(f_{yk} = 500 \text{ N})$	N/mm²)						
2	Round bar with partial or full thread	Stainless steel, strength class 80, according to EN 10088-1:2014	Stainless steel, strength class 80, according to EN 10088-1:2014						
3	Washer	Stainless steel,	Stainless steel,						
	ISO 7089:2000	according to EN 10088-1:2014	according to EN 10088-1:2014						
		Stainless steel, strength class 80,	Stainless steel, strength class 80,						
4	Hexagon nut	acc. to EN ISO 3506-2:2020,	acc. to EN ISO 3506-2:2020,						
		according to EN 10088-1:2014	according to EN 10088-1:2014						

Figures not to scale

Rebar connection with injection system FIS V Plus

Product description

Properties and materials of fischer rebar anchors FRA

Annex A 6

Appendix 7 / 21

Specifications of intended use part 1 Table B1.1: Overview use and performance categories Anchorages subject to FIS V Plus with ... Reinforcing bar fischer rebar anchor FRA ADDDDDDDDDDDDDDDDDD Hammer drilling or compressed air all sizes drilling with standard drill bit Hammer drilling with hollow drill bit (fischer "FHD", Heller "Duster Nominal drill bit diameter (d₀) Expert". Bosch 12 mm to 35 mm "Speed Clean". Hilti "TE-CD. TE-YD") dry or wet Use category all sizes 11 concrete Tables: uncracked C1.1 Characteristic Tables: concrete C12 resistance under C1.1 C1.3 all sizes all sizes C1.2 static and quasi C2.1 static loading, in cracked C1.3 C2.2 concrete Characteristic ___1) ___1) resistance under seismic loading Installation direction D3 (downward and horizontal and upwards (e.g. overhead)) $T_{i.min} = 0$ °C to $T_{i.max} = +40$ °C Installation temperature (max. short term temperature +80 °C; Service Temperature -40 °C to +80 °C max long term temperature +50 °C) temperature range Table C2.3 Resistance to fire all sizes Annex C 3 all sizes 1) No performance assessed

Intended use
Specifications part 1

Annex B 1
Appendix 8 / 21

Rebar connection with injection system FIS V Plus

Specifications of intended use part 2

Anchorages subject to:

- Static and quasi-static loading: reinforcing bar (rebar) size 8 mm to 28 mm; FRA M12 to M24
- Resistance to fire: reinforcing bar (rebar) size 8 mm to 28 mm; FRA M12 to M24

Base materials:

- Compacted reinforced or unreinforced normal weight concrete without fibres according to FN 206·2013+A1·2016
- Concrete strength classes C12/15 to C50/60 according to EN 206:2013+A1:2016
- Maximum chloride content of 0,40 % (CL 0.40) related to the cement content according to EN 206:2013+A1:2016
- Non-carbonated concrete

Note: In case of a carbonated surface of the existing concrete structure the carbonated layer shall be removed in the area of the post-installed rebar connection with a diameter of ϕ + 60 mm prior to the installation of the new rebar. The depth of concrete to be removed shall correspond to at least the minimum concrete cover in accordance with EN 1992-1-1:2004+AC:2010. The foregoing may be neglected if building components are new and not carbonated and if building components are in dry conditions.

Use conditions (Environmental conditions) for fischer rebar anchors FRA

• For all conditions according to EN1993-1-4:2006+A1:2015 corresponding to corrosion resistance classes to **Annex A 6 Table A6.2**

Design:

- Fastenings are designed under the responsibility of an engineer experienced in fastenings and concrete work.
- Verifiable calculation notes and drawings are prepared taking account of the forces to be transmitted.
- Design according to EN 1992-1-1:2011; EN 1992-1-2:2011 and Annex B 3 and B 4.
- The actual position of the reinforcement in the existing structure shall be determined on the basis of the construction documentation and taken into account when designing.


Installation:

- The installation of post-installed rebar respectively fischer rebar anchor FRA shall be done only by suitable trained installer and under Supervision on site; the conditions under which an installer may be considered as suitable trained and the conditions for Supervision on site are up to the Member States in which the installation is done.
- Check the position of the existing rebars (if the position of existing rebars is not known, it shall be determined using a rebar detector suitable for this purpose as well as on the basis of the construction documentation and then marked on the building component for the overlap joint).

General construction rules for post-installed rebars

Figure B3.1:

- Only tension forces in the axis of the rebar may be transmitted.
- The transfer of shear forces between new concrete and existing structure shall be designed additionally according to EN 1992-1-1:2011.
- The joints for concreting must be roughened to at least such an extent that aggregate protrude.



- $^{1)}$ If the clear distance between lapped bars exceeds 4 ϕ then the lap length shall be increased by the difference between the clear bar distance and 4 ϕ
 - c concrete cover of post-installed rebar
 - c₁ concrete cover at end-face of existing rebar
 - c_{min} minimum concrete cover according to **Table B5.1** and to EN 1992-1-1:2011,

Section 4.4.1.2


- φ nominal diameter of reinforcing bar
- lo lap length, according to EN 1992-1-1:2011
- I_v effective embedment depth, $\ge I_0 + c_1$
- do nominal drill bit diameter, see Annex B 6

Rebar connection with injection system FIS V Plus	
Intended use	Annex B 3
General construction rules for post-installed rebars	Appendix 10 / 21

General construction rules for post-installed fischer rebar anchors FRA

Figure B4.1:

- · Only tension forces in the axis of the fischer rebar anchor FRA may be transmitted.
- The tension force must be transferred via an overlap joint to the reinforcement in the building part.
- The transmission of the shear load shall be ensured by appropriate additional measures, e.g. by shear lugs or by anchors with a European Technical Assessment (ETA).
- In the anchor plate, the holes for the tension anchor shall be executed as slotted holes with the axis in the direction of the shear force



 $^{1)}$ If the clear distance between lapped bars exceeds 4 ϕ then the lap length shall be increased by the difference between the clear bar distance and 4 ϕ .

c concrete cover of post-installed fischer rebar anchor FRA

concrete cover at end-face of existing rebar

c_{min} minimum concrete cover according to **Table B5.1** and to EN 1992-1-1:2011,

Section 4.4.1.2

φ nominal diameter of reinforcing bar

lo lap length, according to EN 1992-1-1:2011, Section 8.7.3

 $I_{e,ges}$ overall embedment depth, $\geq I_0 + I_e$

d₀ nominal drill bit diameter, see Annex B 6

le length of the bonded in threaded part

thickness of the fixture

I_v effective embedment depth

Rebar connection with injection system FIS V Plus	
Intended use	Annex B 4
General construction rules for post-installed fischer rebar anchors FRA	Appendix 11 / 21

Table B5.1: Minimum concrete cover c_{min}¹⁾ depending of the drilling method and the drilling tolerance

	nominal diameter	Minimum concrete cover c _{min}					
Drilling method	of reinforcing bar φ [mm]	Without drilling aid [mm]	lling aid [mm]				
Hammer drilling with standard drill	< 25	30 mm + 0,06 l _ν ≥ 2 φ	30 mm + 0,02 l _v ≥ 2 ф				
bit or hollow drill bit	≥ 25	40 mm + 0,06 l _ν ≥ 2 φ	40 mm + 0,02 l _ν ≥ 2 φ				
Compressed air	< 25	50 mm + 0,08 l _v	50 mm + 0,02 l _v	Drilling aid			
drilling	≥ 25	60 mm + 0,08 l _ν ≥ 2 φ	60 mm + 0,02 l _v ≥ 2 ф	₩ Drilling aid			

¹⁾ See Annex B 3, figure B3.1 and Annex B 4, figure B4.1 Note: The minimum concrete cover as specified in EN 1992-1-1:2011 must be observed.

Table B5.2: Dispensers and cartridge sizes corresponding to maximum embedment depth l_{v,max}

	acptir iv,ii	ia A				
reinforcing bars (rebar)	fischer rebar	Manual dispenser	Accu and pneumatic dispenser (small)	Accu and pneumatic dispenser (large)		
	anchor FRA		Cartridge size			
		< 50	00 ml	> 500 ml		
φ [mm]	thread [-]	I _{v,max} / I _{e,ç}	_{ges,max} [mm]	I _{v,max} / I _{e,ges,max} [mm]		
8			1000			
10			1000			
12	FRA M12 FRA HCR M12	1000	1200	1800		
14						
16	FRA M16 FRA HCR M16		1500			
20	FRA M20 FRA HCR M20	700	1300			
25	FRA M24 FRA HCR M24	700	1000	2000		
28		700	700]		

Table B5.3: Conditions for use static mixer without an extension tube

Nominal drill hole diameter	d_0		10	12	14	16	18	20	25	30	35
Drill hole depth h₀ by using	FIS MR Plus	[mm]	≤ 90		≤ 120	≤ 140	≤ 150	≤ 160	≤ 210		
	FIS JMR		-	-	≤ 90	≤ 160	≤ 180	≤ 190	≤ 220	≤ 2	:50

Rebar connection with injection system FIS V Plus	
Intended use	Annex B 5
Minimum concrete cover; dispenser and cartridge sizes corresponding to maximum embedment depth	Appendix 12 / 21

Table Do. 1. W	TOIKING LIMES LWORK O	and curing times to	ure	
Temperature in the		orking time ¹⁾		uring time ²⁾
anchorage base [°C]	FIS V Plus	FIS VS Plus Low Speed	FIS V Plus	FIS VS Plus Low Speed
0 to 5 3)	13 min		3 h	6 h
> 5 to 10 ³⁾	9 min	20 min	90 min	3 h
> 10 to 20	5 min	10 min	60 min	2 h

6 min

4 min

45 min

35 min

Working times to and curing times to

4 min

2 min

Table D6 1.

> 20 to

> 30 to

30

40 4)

Table B6.2: Installation tools for drilling and cleaning the bore hole and injection of the mortar

reinforcing			Injection					
bars (rebar)	fischer rebar anchor FRA	Nominal drill bit diameter	Diameter of cutting edge	Steel brush diameter	Diameter of fischer compressed-air nozzle	Diameter of extension tube	Injection adapter	
φ [mm]	Designation	d₀ [mm]	d _{cut} [mm]	d₀ [mm]	[mm]	[mm]	[colour]	
8 ¹⁾		10	≤ 10,50	11,0				
°′′		12	≤ 12,50	12,5				nature
10 ¹⁾		12	≤ 12,50	12,5	11	9	Hature	
10 /		14	≤ 14,50	15			blue	
12 ¹⁾	FRA M12 ¹⁾	14	≤ 14,50	15			blue	
12 ′	FRA HCR M12 ¹⁾	16	≤ 16,50	17	15		red	
14		18	≤ 18,50	19			yellow	
16	FRA M16 FRA HCR M16	20	≤ 20,55	21,5	19	9 or 15	green	
20	FRA M20 FRA HCR M20	25	≤ 25,55	26,5	19		black	
25 ¹⁾	FRA M24 ¹⁾	30	≤ 30,55	32			grey	
25"	FRA HCR M24 ¹⁾	35	≤ 35,70	37	28		brown	
28		35	≤ 35,70	37			brown	

¹⁾ Both drill bit diameters can be used.

Rebar connection with injection system FIS V Plus

Working times and curing times;

Installation tools for drilling and cleaning the bore hole and injection of the mortar

Annex B 6

60 min

60 min

Appendix 13 / 21

¹⁾ Maximum time from the beginning of the injection to rebar / fischer rebar anchor FRA setting and positioning.

²⁾ For wet concrete the curing time must be doubled.

³⁾ If the temperature in the concrete falls below 10 °C the cartridge must be warmed up to +15 °C.

⁴⁾ If the temperature in the concrete exceeds 30 °C the cartridge must be cooled down to +15 °C up to 20 °C.

Safety regulations



Review the Safety Data Sheet (SDS) before use for proper and safe handling! Wear well-fitting protective goggles and protective gloves when working with mortar FIS V Plus / FIS VS Plus Low Speed.

Important: Observe the instructions for use provided with each cartridge.


Installation instruction part 1; Installation with FIS V Plus / FIS VS Plus Low Speed

Hole drilling

Note: Before drilling, remove carbonized concrete; clean contact areas (see **Annex B 2**) In case of aborted drill holes the drill hole shall be filled with mortar

Hammer drilling or compressed air drilling

1a




Drill the hole to the required embedment depth using a hammer drill with carbide drill bit set in rotation hammer mode or a pneumatic drill.

Drill bit sizes see Table B6.2.

Hammer drilling with hollow drill bit

1b



Drill the hole to the required embedment depth using a hammer drill with hollow drill bit in rotation hammer mode. Dust extraction conditions see drill hole cleaning

Annex B 8

Drill bit sizes see Table B6.2

C_{drill}


Measure and control concrete cover c

 $(c_{drill} = c + \emptyset / 2)$

Drill parallel to surface edge and to existing rebar.

Where applicable use drilling aid.

2



For holes $I_V > 20$ cm use drilling aid. Three different options can be considered:

- A) drilling aid
- B) Slat or spirit level
- C) Visual check

Minimum concrete cover cmin see Table B5.1.

Rebar connection with injection system FIS V Plus

Intended use

Safety regulations; Installation instruction part 1, hole drilling

Annex B 7


Appendix 14 / 21

Installation instruction part 2; Installation with FIS V Plus / FIS VS Plus Low Speed


Drill hole cleaning

Hammer or compressed air drilling






Clean the drill hole: For $d_0 < 18$ mm and depths I_v resp. $I_{e,ges} \le 12 \cdot \phi$ blow out the hole three times by hand.




For $d_0 > 18$ mm and depths I_v resp. $I_{e,ges} > 12 \cdot \varphi$ blow out the hole three times with oil-free compressed air (p \geq 6 bar). Use suitable compressed-air nozzle (see Table B6.2).


3a



Brush drill hole three times; for drill hole diameters $d_0 \ge 30$ mm attach brush to a power tool and brush hole with a speed of max. 550 revolutions per minute. For deep holes a brush extension is mandatory. Use suitable brushes (see **Table B6.2**).



Clean the drill hole: For $d_0 < 18$ mm and depths I_v resp. $I_{e,ges} \le 12 \cdot \phi$ blow out the hole three times by hand.




For $d_0 > 18$ mm and depths I_v resp. $I_{e,ges} > 12 \cdot \varphi$ blow out the hole three times with oil-free compressed air $(p \ge 6 \text{ bar})$ Use suitable compressed-air nozzle (see **Table B6.2**).

Hammer drilling with hollow drill bit



3b



Use a suitable dust extraction system, e. g.

fischer FVC 35 M or a comparable dust extraction system with equivalent performance data.

Drill the hole with hollow drill bit. The dust extraction system has to extract the drill dust nonstop during the drilling process and must be adjusted to maximum power.

No further drill hole cleaning necessary.

Rebar connection with injection system FIS V Plus

Intended use

Installation instruction part 2, drill hole cleaning

Annex B 8

Appendix 15 / 21

Installation instruction part 3: Installation with FIS V Plus / FIS VS Plus Low Speed reinforcing bars (rebar) / fischer rebar anchor FRA and cartridge preparation Before use, make asure that the rebar or the fischer rebar anchor FRA is dry and free of oil or other residue. Mark the embedment depth I_V (e.g. with tape) <u>eterekterekteketeinektektektek</u> 4 Insert rebar in borehole, to verify drill hole depth and setting depth I_v resp. I_{e,ges.} Twist off the sealing cap 5 Twist on the static mixer (the spiral in the static mixer must be clearly visible). Place the cartridge into a suitable dispenser. 6 Press out approximately 10 cm of mortar until the resin is permanently grey in colour. Mortar which is not grey in colour 7 will not cure and must be disposed.

Rebar	connectio	n with	injection	system	FIS	V	Plus

Intended use

Installation instruction part 3, reinforcing bars (rebar) / fischer rebar anchor FRA and cartridge preparation

Annex B 9

Appendix 16 / 21

Installation instruction part 4; Installation with FIS V Plus / FIS VS Plus Low Speed

Injection of the mortar without extension tube

Inject the mortar from the back of the hole towards the front and slowly withdraw the static mixer step by step with each trigger pull.

Avoid bubbles


Fill holes approximately 2/3 full, to ensure that the annular gap between the rebar and the concrete will be completely filled with adhesive over the entire embedment length.

The conditions for mortar injection without extension tube can be found in **Table B5.3**




After injecting, release the dispenser. This will prevent further mortar discharge from the static mixer.

Injection of the mortar with extension tube



Assemble mixing nozzle FIS MR Plus or FIS JMR, extension tube and appropriate injection adapter (see **Table B6.2**).

Mortar level mark



Mark the required mortar level I_m and embedment depth I_v resp. $I_{e,ges}$ with tape or marker on the injection extension tube.

a) Estimation:


$$l_m = \frac{1}{3} \cdot l_v resp. l_m = \frac{1}{3} \cdot l_{e,ges}$$
 [mm]

b) Precise equation for optimum mortar volume:

$$l_m = l_v \, resp. \, l_{e,ges} \, \left((1,2 \cdot \frac{d_s^2}{d_0^2} - 0,2) \right)$$
 [mm]

8b

8a



Insert injection adapter to back of the hole. Begin injection allowing the pressure of the injected adhesive mortar to push the injection adapter towards the front of the hole. Do not actively pull out!

Fill holes approximately 2/3 full, to ensure that the annular gap between the rebar and the concrete will be completely filled with adhesive over the embedment length.

When using an injection adapter continue injection until the mortar level mark I_m becomes visible.

Maximum embedment depth see Table B5.2.



After injecting, release the dispenser. This will prevent further mortar discharge from static mixer.

Rebar connection with injection system FIS V Plus

Intended use

Installation instruction part 4, mortar injection

Annex B 10

Appendix 17 / 21

Installation instruction part 5: Installation with FIS V Plus / FIS VS Plus Low Speed Insert rebar / fischer rebar anchor FRA Insert the rebar / fischer rebar anchor FRA slowly twisted into the borehole until the embedment mark is reached 9 Recommendation: Rotation back and forth of the reinforcement bar or the fischer rebar anchor FRA makes pushing easy. For overhead installation, support the rebar / fischer rebar anchor FRA and 10 secure it from falling till mortar started to harden, e.g. using wedges. After installing the rebar or fischer rebar anchor FRA the annular gap must be completely filled with mortar. Proper installation 11 Desired embedment depth is reached ly, resp. le.ges. embedment mark at concrete surface Excess mortar flows out of the borehole after the rebar has been fully inserted up to the embedment mark. Observe the working time "twork" (see Table B6.1), which varies according to temperature of base material. Minor adjustments to the rebar / fischer rebar anchor FRA position may be performed during the working time 12 Full load may be applied only after the curing time "tcure" has elapsed (see Table B 6.1). Mounting the fixture for fischer rebar anchor FRA, 13 max Tinst see Table A6.1. max T_{inst} Rebar connection with injection system FIS V Plus Annex B 11 Intended use

Appendix 18 / 21

Installation instruction part 5, insert rebar / fischer rebar anchor FRA

Minimum anchorage length and minimum lap length

The minimum anchorage length $I_{b,min}$ and the minimum lap length $I_{0,min}$ according to EN 1992-1-1:2011 shall be multiplied by the relevant amplification factor α_{lb} according to **Table C1.1**.

Table C1.1: Amplification factor α_{lb} related to concrete strength class and drilling method

1					
111		1 11		l compressed	
ınammer	ariiina	naliaw	ariiina anc	I COMNTACEAN	air ariiiina
II IAIIIIIICI	MIIIIIIM.		ariiiiia anc	, combicaca	an annini

Rebar / fischer		Amplification factor α _{lb}									
rebar anchor FRA		Concrete strength class									
φ [mm]	C12/15	C16/20	C20/25	C25/30	C30/37	C35/45	C40/50	C45/55	C50/60		
8 to 25		1,0					1,1		1,2		
28					1,0						

Table C1.2: Bond efficiency factor k_b related to concrete strength class and drilling method

Hammer drilling, hollow drilling and compressed air drilling

Rebar / fischer				Bond e	fficiency f	actor k _b			
rebar anchor FRA		Concrete strength class							
φ [mm]	C12/15	C16/20	C20/25	C25/30	C30/37	C35/45	C40/50	C45/55	C50/60
8 to 25		1,00							
28	1,00 0,91 0,84 0,84						0,84		

Table C1.3: Design values of the bond strength f_{bd,PIR} in N/mm² related to concrete strength class and drilling method for good bond conditions

 $f_{bd,PIR} = k_b \cdot f_{bd}$

fbd: Design value of the bond strength in N/mm² considering the concrete strength classes and

the rebar diameter for good bond condition (for all other bond conditions multiply the values

by $\eta_1 = 0.7$)

and recommended partial factor γ_c = 1,5 according to EN 1992-1-1:2011

k_b: Bond efficiency factor according to **Table C1.2**

Hammer drilling, hollow drilling and compressed air drilling

			•						
Rebar / fischer				Bond stre	ength f _{bd,Pl}	R [N/mm²]			
rebar anchor FRA	chor FRA Concrete strength class								
φ [mm]	C12/15	C16/20	C20/25	C25/30	C30/37	C35/45	C40/50	C45/55	C50/60
8 to 25	1,6	2,0	2,3	2,7	3,0	3,4	3,7	4,0	4,3
28	1,6	2,0	2,3	2,7	3,0	3,4	3,4	3,4	3,7

Rebar connection with injection system FIS V Plus

Performance

Amplification factor α_{lb} , bond efficiency factor k_b , design values of the bond strength $f_{bd,PIR}$

Annex C 1

Table C2.1: Characteristic tensile yield strength for rebar part of fischer rebar anchors FRA

fischer rebar anchor FRA /		M12	M16	M20	M24		
Characteristic tensile yield strength for rebar part							
Rebar diameter	ф	[mm]	12	16	20	25	
Characteristic tensile yield strength for rebar	f yk	[N/mm ²]	500	500	500	500	
Partial factor for rebar part	γ _{Ms,N} 1)	[-]	1,15				

¹⁾ In absence of national regulations

Table C2.2: Characteristic resistance to steel failure under tension loading of fischer rebar anchors FRA

fischer rebar anchor FRA / F	RA HCR		M12	M16	M20	M24	
Characteristic resistance to steel failure under tension loading							
Characteristic resistance	N _{Rk,s}	[kN]	62	111	173	263	
Partial factor							
Partial factor	γMs,N ¹⁾	[-]	1,4				

¹⁾ In absence of national regulations

Table C2.3: Characteristics resistance to steel failure for fischer rebar anchors FRA under tension loading and fire exposure R30 to R120

fischer rebar anchor FRA / FRA HCR			M12	M16	M20	M24	
Characteristic	R30			2,5	4,7	7,4	10,6
resistance to steel failure under tension loading and fire exposure	R60	NI NI	[kN]	2,1	3,9	6,1	8,8
	R90	N _{Rk,s,fi}		1,7	3,1	4,9	7,1
	R120			1,3	2,5	3,9	5,6

Rebar connection	with injection	system FIS	V Plus
------------------	----------------	------------	--------

Performance

Characteristic tensile yield strength for rebar part of FRA; Design value of the steel bearing capacity N_{Rk,s,fi} under fire exposure for fischer rebar anchor FRA

Annex C 2

Design value of the ultimate bond strength f_{bd,fi} at increased temperature for concrete strength classes C12/15 to C50/60 (all drilling methods)

The design value of the bond strength $f_{bd,fi}$ at increased temperature has to be calculated by the following equation:

$$f_{bd,fi} = k_{fi}(\theta) \cdot f_{bd,PIR} \cdot \frac{\gamma_c}{\gamma_{mfi}}$$

If:
$$\theta > 74$$
 °C

$$k_{fi}(\theta) = \frac{24,308 \cdot e^{-0,012 \cdot \theta}}{f_{hd,PIR} \cdot 4,3} \le 1,0$$

If:
$$\theta > \theta_{max}$$
 (317 °C)

$$k_{fi}(\theta)$$

fbd fi

= Design value of the ultimate bond strength at increased temperature in N/mm²

θ

= Temperature in °C in the mortar layer

 $k_{fi}(\theta)$

= Reduction factor at increased temperature

fbd.PIR

= Design value of the bond strength in N/mm² in cold condition according to **Table C1.3** considering the concrete strength classes, the rebar diameter, the drilling method and the bond conditions according to EN 1992-1-1:2011

γс


= 1.5 recommended partial factor according to EN 1992-1-1:2011

 $\gamma_{m,fi}$

= 1.0 recommended partial factor

For evidence at increased temperature the anchorage length shall be calculated according to EN 1992-1-1:2011 Equation 8.3 using the temperature-dependent ultimate design value of bond strength f_{bd,fi}.

Figure C3.1: Example graph of reduction factor k_{fi} (θ) for concrete class C20/25 for good bond conditions



Rebar connection with injection system FIS V Plus

Performance

Design value of bond strength fbd,fi at increased temperature

Annex C 3