

SUORITUSTASOILMOITUS

DoP 0362

fischer fischer RM II injektointi järjestelmälle (injektioankureiden kiinnitys betoniin)

FI

- Tuotetyypin yksilöllinen tunnistus: DoP 0362
- Aiottu käyttötarkoitus (aiotut käyttötarkoitukset): Jälkikäteen tehtäviin kiinnityksiin halkeilevassa tai halkeilemattomassa betonissa, katso lisäys, erityisesti liitteet B1 - B7.
- Valmistaja: fischerwerke GmbH & Co. KG, Otto-Hahn-Straße 15, 79211 Denzlingen, Saksa
- Valtuutettu edustaja: -
- Suoritustason pysyvyyden arvioinnissa ja varmentamisessa käytetty järjestelmä/käytetyt järjestelmät: 1
- Eurooppalainen arviointiasiakirja: EAD 330499-01-0601, Edition 04/2020
Eurooppalainen tekninen arviointi: ETA-16/0340; 2024-04-16
Teknisestä arvioinnista vastaava laitos: DIBt- Deutsches Institut für Bautechnik
Ilmoitettu laitos/ilmoitetut laitokset: 2873 TU Darmstadt
- Ilmoitettu suoritusaste/ilmoitetut suoritusastot:
Mekaaninen kestävyys ja vakaus (BWR 1)
Tyypillinen kestävyys kuormitukselle (staattinen ja lähes staattinen kuormitus):
Teräksen murtokuorma: Liitteet C1, C2
Ulosvetoarvon ja betonikuorman varmuuskerroin: Liitteet C4, C5
Betonimassan murtokuorma: Liite C3
Reunaetäisyys halkeamien estämiseksi kuormituksessa: Liite C3
Kestävyys: Liitteet C3 - C5
Maximi asennusmomentti: Liitteet B3, B4
Pienin reuna- ja keskinäis etäisyys: Liitteet B3, B4
Tyypillinen kestävyys leikkauskuormalle (staattinen ja näennäisstaattinen kuormitus):
Teräksen murtokuorma: Liitteet C1, C2
Taivutusvoiman murtokuorma: Liite C3
Betonireunan murtokuorma: Liite C3
Siirtymät lyhyt-kestoisessa ja pitkä-kestoisessa kuormituksessa:
Siirtymät lyhyt-kestoisessa ja pitkä-kestoisessa kuormituksessa: Liite C6
Ominainen kestävyys ja siirtymät seismisille suoritusluokille C1 ja C2:
Kestävyys kuormitukselle, siirtymät, luokka C1: NPD
Kestävyys kuormitukselle, siirtymät, luokka C2: NPD
Leikkauskuorman kestävyys, siirtymät, luokka C1: NPD
Leikkauskuorman kestävyys, siirtymät, luokka C2: NPD
Rengasmaisen aukon kerroin: NPD
Hygienia, terveys ja ympäristö (BWR 3)
Vaarallisten aineiden pitoisuus, päästöt ja / tai vapautuminen: NPD
- Asianmukainen tekninen asiakirja ja/tai tekninen erityisasiakirja: -

Edellä yksilöidyn tuotteen suoritusaste on ilmoitettujen suoritusasteiden joukon mukainen. Tämä suoritusasteilmoitus on asetuksen (EU) N:o 305/2011 mukaisesti annettu edellä ilmoitetun valmistajan yksinomaisella vastuulla.

Valmistajan puolesta allekirjoittanut:



Dr.-Ing. Oliver Geibig, Toimitusjohtaja Liiketoimintayksikkö & Suunnittelu
Tumlingen, 2024-05-06



Jürgen Grün, Toimitusjohtaja Kemia & Laatu

Tämä suoritusasteilmoitus on laadittu useilla kielillä. Jos tulkinnasta syntyy erimielisyyttä, englanninkielinen versio on aina katsottava ensisijaiseksi.

Lisäys sisältää vapaaehtoisesti ilmoitettua ja täydentävää englanninkielistä tietoa, joka ylittää (kielestä riippumatta määritellyt) lakisääteiset vaatimukset.

Translation guidance Essential Characteristics and Performance Parameters for Annexes

Käännösopas oleellisten piirteiden ja suorituskäytävien parametrien liitteille

Mechanical resistance and stability (BWR 1)		
Mekaaninen kestävyys ja vakaus (BWR 1)		
Characteristic resistance to tension load (static and quasi-static loading):		
Tyypillinen kestävyys kuormitukselle (staattinen ja lähes staattinen kuormitus):		
1	Resistance to steel failure: Teräksen murtokuorma:	$N_{Rk,s}$ [kN]
2	Resistance to combined pull- out and concrete cone failure: Ulosvetoarvon ja betonikuorman varmuuskerroin:	T_{Rk} and/or $T_{Rk,100}$ [N/mm ²], ψ_{sus}^0 [-] (BF) $N_{Rk,p}$ and/or $N_{Rk,p,100}$ [kN] (BEF)
3	Resistance to concrete cone failure: Betonimassan murtokuorma:	$c_{cr,N}$ [mm], $k_{cr,N}$, $k_{ucr,N}$ [-]
4	Edge distance to prevent splitting under load: Reunaetäisyys halkeamien estämiseksi kuormituksessa:	$c_{cr,sp}$ [mm]
5	Robustness: Kestävyys:	V_{inst} [-]
6	Maximum installation torque: Maximi asennusmomentti:	$\max T_{inst}$ [Nm] (BF)
	Installation torque: Asennusmomentti:	T_{inst} [Nm] (BEF)
7	Minimum edge distance and spacing: Pienin reuna- ja keskinäis etäisyys:	c_{min} , s_{min} , h_{min} [mm]
Characteristic resistance to shear load (static and quasi-static loading):		
Tyypillinen kestävyys leikkauskuormalle (staattinen ja näennäisstaattinen kuormitus):		
8	Resistance to steel failure: Teräksen murtokuorma:	$V_{Rk,s}^0$ [kN], $M_{Rk,s}^0$ [Nm], k_7 [-]
9	Resistance to pry-out failure: Taivutusvoiman murtokuorma:	k_8 [-]
10	Resistance to concrete edge failure: Betonireunan murtokuorma:	d_{nom} , l_f [mm]
Displacements under short-term and long-term loading:		
Siirtymät lyhyt-kestoisessa ja pitkä-kestoisessa kuormituksessa:		
11	Displacements under short-term and long-term loading: Siirtymät lyhyt-kestoisessa ja pitkä-kestoisessa kuormituksessa:	δ_0 , δ_{∞} [mm or mm/(N/mm ²)]
Characteristic resistance and displacements for seismic performance categories C1 and C2:		
Ominainen kestävyys ja siirtymät seismisille suoritusluokille C1 ja C2:		
12	Resistance to tension load, displacements:	
	Kestävyys kuormitukselle, siirtymät, luokka C1:	C1 $N_{Rk,s,C1}$ [kN] (all) $T_{Rk,C1}$ [N/mm ²] (BF) $N_{Rk,p,C1}$ [kN] (BEF)
	Kestävyys kuormitukselle, siirtymät, luokka C2:	C2 $N_{Rk,s,C2}$ [kN] (all) $T_{Rk,C2}$ [N/mm ²] (BF) $N_{Rk,p,C2}$ [kN] (BEF) $\delta_{N,C2}$ [mm] (all)
13	Resistance to shear load, displacements:	
	Leikkauskuorman kestävyys, siirtymät, luokka C1:	C1 $V_{Rk,s,C1}$ [kN] (all)
	Leikkauskuorman kestävyys, siirtymät, luokka C2:	C2 $V_{Rk,s,C2}$ [kN] (all) $\delta_{V,C2}$ [mm] (all)
14	Factor annular gap: Rengasmaisen aukon kerroin:	α_{gap} [-]
Hygiene, health and the environment (BWR 3)		
Hygieniä, terveys ja ympäristö (BWR 3)		
15	Content, emission and/or release of dangerous substances: Vaarallisten aineiden pitoisuus, päästöt ja / tai vapautuminen:	-

Specific Part

1 Technical description of the product

The fischer capsule system RM II is a bonded anchor for use in concrete consisting of a capsule RM II and a steel element according to Annex A2.

The capsule RM II is placed in the hole and the steel element is driven by machine with simultaneous hammering and turning.

The anchor rod is anchored via the bond between steel element, chemical mortar and concrete.

The product description is given in Annex A.

2 Specification of the intended use in accordance with the applicable European Assessment Document

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the anchor of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment

3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Characteristic resistance to tension load (static and quasi-static loading)	See Annex B 3 and B 4, C 1 to C 5
Characteristic resistance to shear load (static and quasi-static loading)	See Annex C 1 to C 4
Displacements under short-term and long-term loading	See Annex C 6
Characteristic resistance and displacements for seismic performance categories C1 and C2	No performance assessed

3.2 Hygiene, health and the environment (BWR 3)

Essential characteristic	Performance
Content, emission and/or release of dangerous substances	No performance assessed

4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base


In accordance with the European Assessment Document EAD 330499-01-0601 the applicable European legal act is: [96/582/EC].

The system to be applied is: 1


Installation conditions

fischer anchor rod RG M; installation in concrete

Pre-positioned installation:




Pre-positioned installation with subsequently injected fischer filling disc:




fischer internal threaded anchor RG M I; installation in concrete

Pre-positioned installation:



Pre-positioned installation with subsequently injected fischer filling disc:



Pictures not to scale

h_0 = drill hole depth

h_{ef} = effective anchorage depth

t_{fix} = thickness of fixture

fischer RM II

Product description
Installation conditions

Annex A 1

Appendix 3 / 18

Overview product components


Capsule RM II

Size: 8, 10, 12, 16, 16E, 20/22, 24



fischer anchor rod RG M

Size: M8, M10, M12, M16, M20, M24




fischer internal threaded anchor RG M I


Size: M8, M10, M12, M16, M20




Screw / threaded rod / washer / hexagon nut



fischer filling disc with injection adapter



fischer RM II – RG M Connector



Size: M8, M10, M12, M16, M20, M24

Pictures not to scale

fischer RM II

Product description
Overview product components


Annex A 2

Appendix 4 / 18

Table A3.1: Materials				
Part	Designation	Material		
1	Capsule RM II	Mortar, hardener, filler		
	Steel grade	Steel	Stainless steel R	High corrosion resistant steel HCR
		zinc plated	acc. to EN 10088-1:2014 Corrosion resistance class CRC III acc. to EN 1993-1-4:2006+A1:2015	acc. to EN 10088-1:2014 Corrosion resistance class CRC V acc. to EN 1993-1-4:2006+A1:2015
2	Anchor rod	Property class 4.8, 5.8 or 8.8; EN ISO 898-1:2013 zinc plated $\geq 5 \mu\text{m}$, ISO 4042:2022 or hot dip galvanised $\geq 40 \mu\text{m}$ EN ISO 10684:2004 $f_{uk} \leq 1000 \text{ N/mm}^2$	Property class 50, 70 or 80 EN ISO 3506-1:2020 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; 1.4062, 1.4662, 1.4462 EN 10088-1:2014 $f_{uk} \leq 1000 \text{ N/mm}^2$	Property class 50 or 80 EN ISO 3506-1:2009 or property class 70 with $f_{yk} = 560 \text{ N/mm}^2$ 1.4565; 1.4529 EN 10088-1:2014 $f_{uk} \leq 1000 \text{ N/mm}^2$
		Fracture elongation $A_5 > 8 \%$,		
3	Washer ISO 7089:2000	zinc plated $\geq 5 \mu\text{m}$, ISO 4042:2022 or hot dip galvanised $\geq 40 \mu\text{m}$ EN ISO 10684:2004	1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362 EN 10088-1:2014	1.4565; 1.4529 EN 10088-1:2014
4	Hexagon nut	Property class 4, 5 or 8; EN ISO 898-2:2012 zinc plated $\geq 5 \mu\text{m}$, ISO 4042:2022 or hot dip galvanised $\geq 40 \mu\text{m}$ EN ISO 10684:2004	Property class 50, 70 or 80 EN ISO 3506-2:2020 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362 EN 10088-1:2014	Property class 50, 70 or 80 EN ISO 3506-2:2020 1.4565; 1.4529 EN 10088-1:2014
5	fischer internal threaded anchor RG M I	Property class 5.8 ISO 898-1:2013 zinc plated $\geq 5 \mu\text{m}$, ISO 4042:2022	Property class 70 EN ISO 3506-1:2020 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362 EN 10088-1:2014	Property class 70 EN ISO 3506-1:2020 1.4565; 1.4529 EN 10088-1:2014
6	Commercial standard screw or threaded rod for fischer internal threaded anchor RG M I	Property class 5.8 or 8.8; EN ISO 898-1:2013 zinc plated $\geq 5 \mu\text{m}$, ISO 4042:2022 fracture elongation $A_5 > 8 \%$	Property class 70 EN ISO 3506-1:2020 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362 EN 10088-1:2014 fracture elongation $A_5 > 8 \%$	Property class 70 EN ISO 3506-1:2020 1.4565; 1.4529 EN 10088-1:2014 fracture elongation $A_5 > 8 \%$
7	fischer filling disc similar to DIN 6319-G	zinc plated $\geq 5 \mu\text{m}$, ISO 4042:2022 or hot dip galvanised $\geq 40 \mu\text{m}$ EN ISO 10684:2004	1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362 EN 10088-1:2014	1.4565; 1.4529 EN 10088-1:2014
fischer RM II				Annex A 3 Appendix 5 / 18
Product description Materials				

Specifications of intended use part 1

Table B1.1: Overview use and performance categories

Anchorages subject to		RM II with ...					
		fischer anchor rod RG M 		fischer internal threaded anchor RG M I 			
Hammer drilling with standard drill bit 		Manual or robotic-assisted by fischer BauBot all sizes		Manual all sizes			
Hammer drilling with hollow drill bit (fischer „FHD“, Heller "Duster Expert"; Bosch „Speed Clean“; Hilti "TE-CD, TE-YD", DreBo „D-Plus“, DreBo „D-Max“) 		Nominal drill bit diameter (d ₀) 12 mm to 28 mm		all sizes			
Static and quasi static load, in	uncracked concrete	all sizes	Tables: C1.1, C3.1, C4.1, C6.1	all sizes	Tables: C2.1, C3.1, C5.1, C6.2		
	cracked concrete	M10, M12, M16, M20, M24					
	I1 dry or wet concrete	all sizes		all sizes			
	I2 flooded hole	M12, M16, M20, M24		M8, M10, M16			
Installation direction		D3 (downward and horizontal and upwards (e.g. overhead) installation)					
Installation temperature		T _{i,min} = -15 °C to T _{i,max} = +40 °C					
In-service temperature	Temperature range I	-40 °C to +40 °C	(max. short term temperature +40 °C max. long term temperature +24 °C)				
	Temperature range II	-40 °C to +80 °C	(max. short term temperature +80 °C max. long term temperature +50 °C)				
	Temperature range III	-40 °C to +120 °C	(max. short term temperature +120 °C max. long term temperature +72 °C)				
fischer RM II					Annex B 1 Appendix 6 / 18		
Intended Use Specifications part 1							

Specifications of intended use part 2

Base materials:

- Compacted reinforced or unreinforced normal weight concrete without fibres strength classes C20/25 to C50/60 according to EN 206:2013+A2:2021

Use conditions (Environmental conditions):

- Structures subject to dry internal conditions
(zinc coated steel, stainless steel or high corrosion resistant steel)
- For all other conditions according to EN1993-1-4:2006 + A1:2015 corresponding to corrosion resistance classes to Annex A 3 table A3.1.

Design:

- Anchorages have to be designed by a responsible engineer with experience of concrete anchor design.
- Verifiable calculation notes and drawings are to be prepared taking account of the loads to be anchored. The position of the anchor is indicated on the design drawings (e.g. position of the anchor relative to reinforcement or to supports, etc.).
- Anchorages are designed in accordance with:
EN 1992-4:2018 and EOTA Technical Report TR 055, Edition February 2018.

Installation:

- Anchor installation has to be carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters of the site.
- For manual installation the anchorage depth should be marked and adhered to on installation.
- For robot-assisted installation using fischer BauBot, maintain the effective anchoring depth by selecting the appropriate installation program.
- Overhead installation is allowed.

fischer RM II

Intended Use
Specifications part 2


Annex B 2

Appendix 7 / 18

Table B3.1: Installation parameters for fischer anchor rods RG M

Anchor rods RG M		thread	M8	M10	M12	M16	M20	M24
Nominal drill bit diameter	d_0	[mm]	10	12	14	18	25	28
Drill hole depth	h_0		$h_0 = h_{ef}$					
Effective embedment depth	h_{ef}		80	90	110	125	170	210
Minimum spacing and minimum edge distance	$s_{min} = c_{min}$		40	45	55	65	85	105
Diameter of clearance hole in the pre-positioned anchorage fixture	d_f		9	12	14	18	22	26
Minimum thickness of concrete member	h_{min}		$h_{ef} + 30$ (≥ 100)			$h_{ef} + 2d_0$		
Maximum installation torque	$\max T_{inst}$	[Nm]	10	20	40	60	120	150

fischer anchor rod RG M




Marking (on random place) fischer anchor rod RG M

Steel zinc plated PC ¹⁾ 8.8	• or +	Steel hot-dip PC ¹⁾ 8.8	•
High corrosion resistant steel HCR PC ¹⁾ 50	•	High corrosion resistant steel HCR PC ¹⁾ 70	-
High corrosion resistant steel HCR PC ¹⁾ 80	(	Stainless steel R property class 50	~
Stainless steel R property class 80	*		

Alternatively: Colour coding according to DIN 976-1:2016

¹⁾ PC = property class

Installation conditions:



Pictures not to scale

fischer RM II

Intended Use



Installation parameters anchor rods RG M

Annex B 3

Appendix 8 / 18


Table B4.1: Installation parameters for fischer internal threaded anchors RG M I

Internal threaded anchors RG M I		thread	M8	M10	M12	M16	M20
Diameter of anchor	$d = d_H$	[mm]	12	16	18	22	28
Nominal drill bit diameter	d_0		14	18	20	24	32
Drill hole depth	h_0		$h_0 = h_{ef} = L_H$				
Effective embedment depth ($h_{ef} = L_H$)	h_{ef}		90	90	125	160	200
Minimum spacing and minimum edge distance	s_{min} = c_{min}		55	65	75	95	125
Diameter of clearance hole in the fixture	d_f		9	12	14	18	22
Minimum thickness of concrete member	h_{min}		120	125	165	205	260
Maximum screw-in depth	$l_{E,max}$		18	23	26	35	45
Minimum screw-in depth	$l_{E,min}$		8	10	12	16	20
Maximum installation torque	$\max T_{inst}$	[Nm]	10	20	40	80	120

fischer internal threaded anchor RG M I

Marking: Anchor size e. g.: **M10**
 Stainless steel → additional **R**; e.g.: **M10 R**
 High corrosion resistant steel → additional **HCR**; e.g.: **M10 HCR**

Retaining bolt or threaded rods (including nut and washer) must comply with the appropriate material and strength class of Annex A 3, Table A3.1.

Installation conditions:

Pictures not to scale

fischer RM II

Intended Use


Installation parameters fischer internal threaded anchors RG M I

Annex B 4

Appendix 9 / 18

Table B5.1: Dimensions of resin capsule RM II

Capsule RM II		8	10	12	16	16 E	20/22	24
Capsule diameter	d _P	[mm]	9,0	10,5	12,5	16,5	23,0	
Capsule length	L _P		85	90	97	95	123	190

**Table B5.2: Assignment of resin capsule RM II to fischer anchor rod RG M**

Anchor rod RG M			M8	M10	M12	M16	M20	M24
Effective anchorage depth	h _{ef}	[mm]	80	90	110	125	170	210
Related capsule RM II		[-]	8	10	12	16	20/22	24

Table B5.3: Assignment of resin capsule RM II to the fischer internal threaded anchor RG M I

Internal threaded anchor RG M I			M8	M10	M12	M16	M20
Effective anchorage depth	h _{ef}	[mm]	90	90	125	160	200
Related capsule RM II		[-]	10	12	16	16E	24

Table B5.4: Minimum curing time

(During the curing time of the mortar the concrete temperature may not fall below the listed minimum temperature; minimal capsule temperature -15 °C)

Temperature in the anchoring base [°C]	Minimum curing time t _{cure}
-15 to -10	30 h
> -10 to -5	16 h
> -5 to 0	10 h
> 0 to +5	45 min
> +5 to +10	30 min
> +10 to +20	20 min
> +20 to +30	5 min
> +30 to +40	3 min

fischer RM II

Intended Use



Dimensions of the capsules, Assignment of the capsule to the anchor rod and internal threaded anchor, Minimum curing time

Annex B 5

Appendix 10 / 18


Installation instructions part 1

Manual or robotic-assisted, (by fischer BauBot), drilling and cleaning the hole (hammer drilling with standard drill bit)

1		Specified drill hole depth h_0 should be adhered to (manual e.g. mark on the drill bit, with BauBot by selecting the appropriate drilling program). Drill the hole. Drill hole diameter d_0 and drill hole depth h_0 see Tables B3.1, B4.1.
2		When reaching the drill hole depth h_0 pull out the drill bit whilst power drill is switched on. To reduce the drill dust in the drill hole repeat this step minimum three times, beginning from the drill hole bottom (discharging the bore hole). Trickling of the bore dust into the drill hole has to be avoided. (e.g. with exhausting the drill dust) Blowing out or brushing the drill hole is not necessary.

Go to step 3

Manual drilling and cleaning the hole (hammer drilling with hollow drill bit)

1		Check a suitable hollow drill (see Table B1.1) for correct operation of the dust extraction.
2		Use a suitable dust extraction system, e.g. fischer FVC 35 M or a comparable dust extraction system with equivalent performance data. Drill the hole with hollow drill bit. The dust extraction system has to extract the drill dust nonstop during the drilling process and must be adjusted to maximum power. Diameter of drill hole d_0 and drill hole depth h_0 see Tables B3.1, B4.1.

Go to step 3

fischer RM II










Intended use
Installation instructions part 1

Annex B 6

Appendix 11 / 18

Installation instructions part 2

Installation of capsule RM II with fischer anchor rods RG M or fischer internal threaded anchors RG M I

3		Push the capsule RM II into the drill hole.		Depending on the anchor being installed, use a suitable setting tool (e.g. RA-SDS).
4			Only use clean and oil-free metal parts. Using a suitable adapter, drive the RG M or fischer internal threaded anchor RG M I into the capsule using a hammer drill set on rotary hammer action. Stop when the metal part reaches the bottom of the hole and is set to the correct embedment depth.	
Option 3+4		Combined setting method with fischer BauBot, capsule RM II and fischer anchor rod RG M.		
5			When reaching the correct embedment depth, excess mortar must be emerged from the mouth of the drill hole.	
6			Wait for the specified curing time, t_{cure} see Table B5.4 . Mounting the fixture $max T_{inst}$ see Table B3.1, B4.1 .	
Option		After the minimum curing time is reached, the gap between metal part and fixture (annular clearance) may be filled with mortar via the fischer filling disc. compressive strength $\geq 50 \text{ N/mm}^2$ (e.g. fischer injection mortars FIS HB, FIS SB, FIS V Plus, FIS EM Plus).		

fischer RM II

Intended use

Installation instructions part 2

Annex B 7

Appendix 12 / 18

Table C1.1: Characteristic values for steel failure under tension / shear load of fischer anchor rods RG M

Anchor rod RG M			M8	M10	M12	M16	M20	M24		
Bearing capacity under tension load, steel failure ³⁾										
Characteristic resistance $N_{Rk,s}$	Steel zinc plated	Property class	4.8	[kN]	15(13)	23(21)	33	63	98	141
			5.8		19(17)	29(27)	43	79	123	177
			8.8		29(27)	47(43)	68	126	196	282
	Stainless steel R and high corrosion resistant steel HCR		50		19	29	43	79	123	177
			70		26	41	59	110	172	247
			80		30	47	68	126	196	282
Partial factors ¹⁾										
Partial factor $\gamma_{Ms,N}$	Steel zinc plated	Property class	4.8	[-]	1,50					
			5.8		1,50					
			8.8		1,50					
	Stainless steel R and high corrosion resistant steel HCR		50		2,86					
			70		1,50 ²⁾ / 1,87					
			80		1,60					
Bearing capacity under shear load, steel failure ³⁾										
without lever arm										
Characteristic resistance $V_{Rk,s}$	Steel zinc plated	Property class	4.8	[kN]	9(8)	14(13)	20	38	59	85
			5.8		11(10)	17(16)	25	47	74	106
			8.8		15(13)	23(21)	34	63	98	141
	Stainless steel R and high corrosion resistant steel HCR		50		9	15	21	39	61	89
			70		13	20	30	55	86	124
			80		15	23	34	63	98	141
Ductility factor		k_7	[-]	1,0						
with lever arm										
Charact. resistance $M_{Rk,s}^0$	Steel zinc plated	Property class	4.8	[Nm]	15(13)	30(27)	52	133	259	448
			5.8		19(16)	37(33)	65	166	324	560
			8.8		30(26)	60(53)	105	266	519	896
	Stainless steel R and high corrosion resistant steel HCR		50		19	37	65	166	324	560
			70		26	52	92	232	454	784
			80		30	60	105	266	519	896
Partial factors ¹⁾										
Partial factor $\gamma_{Ms,V}$	Steel zinc plated	Property class	4.8	[-]	1,25					
			5.8		1,25					
			8.8		1,25					
	Stainless steel R and high corrosion resistant steel HCR		50		2,38					
			70		1,25 ²⁾ / 1,56					
			80		1,33					
¹⁾ In absence of other national regulations										
²⁾ Only for fischer RG M made of high corrosion-resistant steel HCR										
³⁾ Values in brackets are valid for undersized fischer anchor rods RG M with smaller stress area A_s for hot dip galvanised standard threaded rods according to EN ISO 10684:2004+AC:2009										

¹⁾ In absence of other national regulations
²⁾ Only for fischer RG M made of high corrosion-resistant steel HCR
³⁾ Values in brackets are valid for undersized fischer anchor rods RG M with smaller stress area A_s for hot dip galvanised standard threaded rods according to EN ISO 10684:2004+AC:2009

Table C2.1: Characteristic values for **steel failure** under tension / shear load of **fischer internal threaded anchors RG M I**

Internal threaded anchor RG M I				M8	M10	M12	M16	M20	
Bearing capacity under tension load, steel failure									
Characteristic bearing capacity with screw	$N_{Rk,s}$	Property class	5.8	[kN]	19	29	43	79	123
			8.8		29	47	68	108	179
		Property class 70	R		26	41	59	110	172
			HCR		26	41	59	110	172
Partial safety factors ¹⁾									
Partial safety factor	$\gamma_{Ms,N}$	Property class	5.8	[-]	1,50				
			8.8		1,50				
		Property class 70	R		1,87				
			HCR		1,87				
Bearing capacity under shear load, steel failure									
without lever arm									
Characteristic bearing capacity with screw	$V^0_{Rk,s}$	Property class	5.8	[kN]	9,2	14,5	21,1	39,2	62,0
			8.8		14,6	23,2	33,7	54,0	90,0
		Property class 70	R		12,8	20,3	29,5	54,8	86,0
			HCR		12,8	20,3	29,5	54,8	86,0
Ductility factor			k_7	[-]	1,0				
with lever arm									
Characteristic bending moment with screw	$M^0_{Rk,s}$	Property class	5.8	[Nm]	20	39	68	173	337
			8.8		30	60	105	266	519
		Property class 70	R		26	52	92	232	454
			HCR		26	52	92	232	454
Partial safety factors ¹⁾									
Partial safety factor	$\gamma_{Ms,V}$	Property class	5.8	[-]	1,25				
			8.8		1,25				
		Property class 70	R		1,56				
			HCR		1,56				

¹⁾ In absence of other national regulations

fischer RM II

Performances

Characteristic values for steel failure under tension / shear load of fischer internal threaded anchor RG M I

Annex C 2

Appendix 14 / 18

Table C4.1: Characteristic values for **combined pull-out** and concrete failure for **fischer anchor rods RG M** in hammer drilled holes; **uncracked or cracked concrete**

Anchor rod RG M			M8	M10	M12	M16	M20	M24	
Combined pullout and concrete cone failure									
Calculation diameter		d	[mm]	8	10	12	16	20	24
Uncracked concrete									
Characteristic bond resistance in uncracked concrete C20/25									
Hammer-drilling with standard drill bit or hollow drill bit (dry and wet concrete)									
Temperature range	I: 24 °C / 40 °C		$\tau_{Rk,ucr}$ [N/mm ²]	12,5	12,5	12,5	12,5	12,5	12,5
	II: 50 °C / 80 °C			12,0	12,0	12,0	12,0	12,0	12,0
	III: 72 °C / 120 °C			10,5	10,5	10,5	10,5	10,5	10,5
Hammer-drilling with standard drill bit or hollow drill bit (flooded hole)									
Temperature range	I: 24 °C / 40 °C		$\tau_{Rk,ucr}$ [N/mm ²]	- ¹⁾	- ¹⁾	12,5	12,5	12,5	12,5
	II: 50 °C / 80 °C			- ¹⁾	- ¹⁾	12,0	12,0	12,0	12,0
	III: 72 °C / 120 °C			- ¹⁾	- ¹⁾	10,5	10,5	10,5	10,5
Installation factors									
Dry and wet concrete		γ_{inst}	[-]	1,2					
Flooded hole				- ¹⁾	- ¹⁾	1,4			
Cracked concrete									
Characteristic bond resistance in cracked concrete C20/25									
Hammer-drilling with standard drill bit or hollow drill bit (dry and wet concrete)									
Temperature range	I: 24 °C / 40 °C		$\tau_{Rk,cr}$ [N/mm ²]	- ¹⁾	4,5	4,5	4,5	4,5	4,5
	II: 50 °C / 80 °C			- ¹⁾	4,0	4,0	4,0	4,0	4,0
	III: 72 °C / 120 °C			- ¹⁾	3,5	3,5	3,5	3,5	3,5
Hammer-drilling with standard drill bit or hollow drill bit (flooded hole)									
Temperature range	I: 24 °C / 40 °C		$\tau_{Rk,cr}$ [N/mm ²]	- ¹⁾	- ¹⁾	4,5	4,5	4,5	4,5
	II: 50 °C / 80 °C			- ¹⁾	- ¹⁾	4,0	4,0	4,0	4,0
	III: 72 °C / 120 °C			- ¹⁾	- ¹⁾	3,5	3,5	3,5	3,5
Installation factors									
Dry and wet concrete		γ_{inst}	[-]	- ¹⁾	1,2				
Flooded hole				- ¹⁾	- ¹⁾	1,4			

¹⁾ No performance assessed

fischer RM II

Performances

Characteristic values for combined pull-out and concrete failure for fischer anchor rod RG M

Annex C 4

Appendix 16 / 18

Table C5.1: Characteristic values for **combined pull-out** and concrete failure for **fischer internal threaded anchors RG M I** in hammer drilled holes; **uncracked or cracked concrete**

Internal threaded anchors RG M I			M8	M10	M12	M16	M20	
Combined pullout and concrete cone failure								
Calculation diameter		d	[mm]	12	16	18	22	28
Uncracked concrete								
Characteristic bond resistance in uncracked concrete C20/25								
Hammer-drilling with standard drill bit or hollow drill bit (dry and wet concrete)								
Temperature range	I: 24 °C / 40 °C	$\tau_{Rk,ucr}$	[N/mm ²]	11	11	11	11	11
	II: 50 °C / 80 °C			10,5	10,5	10,5	10,5	10,5
	III: 72 °C / 120 °C			9,5	9,5	9,5	9,5	9,5
Hammer-drilling with standard drill bit or hollow drill bit (flooded hole)								
Temperature range	I: 24 °C / 40 °C	$\tau_{Rk,ucr}$	[N/mm ²]	11	11	- ¹⁾	11	- ¹⁾
	II: 50 °C / 80 °C			10,5	10,5	- ¹⁾	10,5	- ¹⁾
	III: 72 °C / 120 °C			9,5	9,5	- ¹⁾	9,5	- ¹⁾
Installation factors								
Dry and wet concrete		γ_{inst}	[-]	1,2				
Flooded hole				1,4	- ¹⁾	1,4	- ¹⁾	
Cracked concrete								
Characteristic bond resistance in cracked concrete C20/25								
Hammer-drilling with standard drill bit or hollow drill bit (dry and wet concrete)								
Temperature range	I: 24 °C / 40 °C	$\tau_{Rk,cr}$	[N/mm ²]	4,5	4,5	4,5	4,5	4,5
	II: 50 °C / 80 °C			4,0	4,0	4,0	4,0	4,0
	III: 72 °C / 120 °C			3,5	3,5	3,5	3,5	3,5
Hammer-drilling with standard drill bit or hollow drill bit (flooded hole)								
Temperature range	I: 24 °C / 40 °C	$\tau_{Rk,cr}$	[N/mm ²]	4,5	4,5	- ¹⁾	4,5	- ¹⁾
	II: 50 °C / 80 °C			4,0	4,0	- ¹⁾	4,0	- ¹⁾
	III: 72 °C / 120 °C			3,5	3,5	- ¹⁾	3,5	- ¹⁾
Installation factors								
Dry and wet concrete		γ_{inst}	[-]	1,2				
Flooded hole				1,4	- ¹⁾	1,4	- ¹⁾	

¹⁾ No performance assessed

Table C6.1: Displacements for fischer anchor rods RG M

Anchor rod RG M		M8	M10	M12	M16	M20	M24
Displacement-Factors for tension load ¹⁾							
Uncracked or cracked concrete; Temperature range I, II, III							
δ _{N0} -Factor	[mm/(N/mm ²)]	0,07	0,08	0,09	0,10	0,11	0,12
δ _{N∞} -Factor		0,13	0,14	0,15	0,17	0,17	0,18
Displacement-Factors for shear load ²⁾							
Uncracked or cracked concrete; Temperature range I, II, III							
δ _{V0} -Factor	[mm/kN]	0,18	0,15	0,12	0,09	0,07	0,06
δ _{V∞} -Factor		0,27	0,22	0,18	0,14	0,11	0,09
1) Calculation of effective displacement: δ _{N0} = δ _{N0} -Factor · τ δ _{N∞} = δ _{N∞} -Factor · τ (τ: acting bond strength under tension load)				2) Calculation of effective displacement: δ _{V0} = δ _{V0} -Factor · V δ _{V∞} = δ _{V∞} -Factor · V (V: acting shear load)			

Table C6.2: Displacements for fischer internal threaded anchors RG M I

Internal threaded anchor RG M I		M8	M10	M12	M16	M20
Displacement-Factors for tension load ¹⁾						
Uncracked or cracked concrete; Temperature range I, II, III						
δ _{N0} -Factor	[mm/(N/mm ²)]	0,09	0,10	0,10	0,11	0,19
δ _{N∞} -Factor		0,13	0,15	0,15	0,17	0,19
Displacement-Factors for shear load ²⁾						
Uncracked or cracked concrete; Temperature range I, II, III						
δ _{V0} -Factor	[mm/kN]	0,12	0,09	0,08	0,07	0,05
δ _{V∞} -Factor		0,18	0,14	0,12	0,10	0,08
1) Calculation of effective displacement: δ _{N0} = δ _{N0} -Factor · τ δ _{N∞} = δ _{N∞} -Factor · τ (τ: acting bond strength under tension load)				2) Calculation of effective displacement: δ _{V0} = δ _{V0} -Factor · V δ _{V∞} = δ _{V∞} -Factor · V (V: acting shear load)		

fischer RM II

Performances

Displacements for anchor rods RGM and fischer internal threaded anchors RG M I

Annex C 6

Appendix 18 / 18