



DÉCLARATION DES PERFORMANCES

DoP 0281

pour fischer Highbond-Anchor FHB II Inject (cheville à scellement à expansion pour utilisation dans le béton)

FR

1. Code d'identification unique du type de produit:

DoP 0281

2. Usage(s) prévu(s):

Fixation dans du béton fissuré ou non fissuré voir annexes, en particulier les annexes B1 - B7.

3. Fabricant:

fischerwerke GmbH & Co. KG, Otto-Hahn-Straße 15, 79211 Denzlingen, Allemagne

4. Mandataire:

-

5. Système(s) d'évaluation et de vérification de la constance des performances:

1

6. Document d'évaluation européen:

ETAG 001, Part 5, April 2013, utilisé en tant que DEE

ETA-16/0637; 2017-12-14

Organisme d'évaluation technique:

DIBt- Deutsches Institut für Bautechnik

Organisme(s) notifié(s):

2873 TU Darmstadt

7. Performance(s) déclarée(s):

Résistance mécanique et stabilité (BWR 1)

Résistance caractéristique à la charge de traction (charge statique et quasi-statique):

Résistance à la rupture de l'acier (charge de traction): Annexes C1, C2

Résistance à la rupture par extraction glissement: et rupture du cône béton: Annexes C1, C2

Résistance à la rupture du cône béton: Annexes C1, C2

Distance au bord pour éviter la rupture par fendage sous charge: Annexes C1, C2

Robustesse : Annexes C1, C2

$\gamma_2 = \gamma_{inst}$

Couple de serrage: Annexes B3, B4

Distance au bord et entraxe mini.: Annexes B3, B4

Résistance caractéristique à la charge de cisaillement (charge statique et quasi-statique):

Résistance à la rupture de l'acier: Annexes C3, C4

($k_1 = k_2$)

Résistance à la rupture par effet de levier: Annexes C3, C4

($k_0 = k_3$)

Résistance à la rupture du béton en bord de dalle: Annexes C3, C4

Déplacements sous charge à court et long terme :

Déplacements sous charge à court et long terme : Annexes C5, C6

Résistance caractéristique et déplacements pour les catégories de performance sismique C1 et C2:

Résistance à la charge de traction, catégorie C1: NPD

Résistance à la charge de traction, catégorie C2: NPD

Résistance à la charge de cisaillement, catégorie C1: NPD

Résistance à la charge de cisaillement, catégorie C2: NPD

Facteur espace annulaire: NPD

Hygiène, santé et environnement (BWR 3)

Contenu, émission et/ou rejet de substances dangereuses: NPD

8. Documentation technique appropriée et/ou documentation technique spécifique:

-

Les performances du produit identifié ci-dessus sont conformes aux performances déclarées. Conformément au règlement (UE) no 305/2011, la présente déclaration des performances est établie sous la seule responsabilité du fabricant mentionné ci-dessus.

Signé pour le fabricant et en son nom par:

Dr.-Ing. Oliver Geibig, Directeur Général Business Units & Ingénierie
Tumlingen, 2021-01-19

Jürgen Grün, Directeur Général Chimie & Qualité

Cette DoP a été préparée en plusieurs langues. En cas de différend relatif à l'interprétation, la version anglaise prévaudra.

L'annexe comprend des informations volontaires et complémentaires en langue anglaise dépassant les exigences légales (spécifiées de manière neutre).

Specific Part

1 Technical description of the product

The fischer Highbond-Anchor FHB II is a torque controlled bonded anchor consisting of a mortar cartridge with mortar fischer FIS HB and an anchor rod FHB II - A L or FHB II - A S with hexagon nut and washer.

The anchor rod is placed into a drilled hole filled with injection mortar. The load transfer is realised by mechanical interlock of several cones in the bonding mortar and then via a combination of bonding and friction forces in the anchorage ground (concrete).

The product description is given in Annex A.

2 Specification of the intended use in accordance with the applicable European Assessment Document

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the anchor of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment

3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Characteristic values under tension and shear load	See Annex C 1 to C 4
Displacements under tension and shear loads	See Annex C 5 and C 6

3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire	Anchorages satisfy requirements for Class A1
Resistance to fire	No performance assessed

3.3 Hygiene, health and the environment (BWR 3)

Regarding dangerous substances there may be requirements (e.g. transposed European legislation and national laws, regulations and administrative provisions) applicable to the products falling within the scope of this European Technical Assessment. In order to meet the provisions of Regulation (EU) No 305/2011, these requirements need also to be complied with, when and where they apply.

3.4 Safety in use (BWR 4)

The essential characteristics regarding Safety in use are included under the Basic Works Requirement Mechanical resistance and stability.

4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

In accordance with guideline for European technical approval ETAG 001, April 2013, used as European Assessment Document (EAD) according to Article 66 Paragraph 3 of Regulation (EU) No 305/2011, the applicable European legal act is: [96/582/EC].

The system to be applied is: 1

5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable European Assessment Document

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited at Deutsches Institut für Bautechnik.

Issued in Berlin on 14 December 2017 by Deutsches Institut für Bautechnik


BD Dipl.-Ing. Andreas Kummerow
Head of Department

beglaubigt:
Lange


Installation conditions part 1

fischer Highbond - Anchor FHB II Inject - A L


Pre-positioned installation



Push through installation not with mortar capsule (annular gap filled with mortar)



Pre-positioned or push through installation with subsequently pressed filling disk (annular gap filled with mortar)



Pictures not to scale

h_{ef} = effective anchorage depth

t_{fix} = thickness of fixture

fischer Highbond-Anchor FHB II Inject

Product description

Installation conditions part 1; FHB II Inject – A L


Annex A 1

Appendix 3 / 20


Installation conditions part 2

fischer Highbond - Anchor FHB II Inject - A S


Pre-positioned installation



Push through installation



Pre-positioned or push through installation with subsequently pressed filling disk (annular gap filled with mortar)



Pictures not to scale

h_{ef} = effective anchorage depth

t_{fix} = thickness of fixture

fischer Highbond-Anchor FHB II Inject

Product description



Installation conditions part 2; FHB II Inject – A S

Annex A 2

Appendix 4 / 20

Overview system components part 1



Mortar cartridge (shuttle cartridge) with sealing cap; Size: 360 ml, 950 ml



Imprint: fischer FIS HB, processing notes, shelf-life, piston travel scale (optional), curing times and processing times (depending on temperature), hazard code, size, volume




Mortar cartridge (coaxial cartridge) with sealing cap; Size: 150 ml, 300 ml



Imprint: fischer FIS HB, processing notes, shelf-life, piston travel scale (optional), curing times and processing times (depending on temperature), hazard code, size, volume



Static mixer MR or UMR




Extension tube for static mixer



Cleaning brush BS



Blow-out pump ABG or ABP with cleaning nozzle



Pictures not to scale

fischer Highbond-Anchor FHB II Inject

System description

Overview system components part 1;
cartridges / mortar capsule / accessories

Annex A 3



Appendix 5 / 20

Overview system components part 2

fischer Highbond - Anchor rod; pre-assembled condition


fischer Highbond - Anchor rod FHB II Inject - A L

fischer Highbond - Anchor rod FHB II Inject - A S




Anchor rod FHB II Inject - A L

Size: M8, M10, M12, M16, M20




Anchor rod FHB II Inject - A L

Size: M24




Anchor rod FHB II Inject - A S


Size: M10, M12, M16, M20, M24




Washer



Hexagon nut



fischer filling disk FFD



Pictures not to scale

fischer Highbond-Anchor FHB II Inject

System description

Overview system components part 2;

Anchor rod / washer / hexagon nut / fischer filling disk FFD

Annex A 4

Appendix 6 / 20

Table A5.1: Materials

Part	Designation	Material		
1	Mortar cartridge	Mortar, hardener, filler		
	Steel grade	Steel, zinc plated	Stainless steel A4	High corrosion resistant steel C
2	Fischer Highbond-Anchor rod FHB II - A L or FHB II - A S	Property class 8.8; EN ISO 898-1:2013 zinc plated $\geq 5 \mu\text{m}$, EN ISO 4042:1999 A2K $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 12 \%$ fracture elongation	Property class 80 EN ISO 3506-1:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; 1.4062, 1.4662, 1.4462 EN 10088-1:2014 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 12 \%$ fracture elongation	Property class 80 EN ISO 3506-1:2009 1.4565; 1.4529 EN 10088-1:2014 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 12 \%$ fracture elongation
3	Washer ISO 7089:2000	zinc plated $\geq 5 \mu\text{m}$ EN ISO 4042:1999 A2K	1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2014	1.4565; 1.4529 EN 10088-1:2014
4	Hexagon nut	Property class 8; EN ISO 898-2:2012 zinc plated $\geq 5 \mu\text{m}$, ISO 4042:1999 A2K	Property class 70 EN ISO 3506-1:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2014	Property class 70 EN ISO 3506-1:2009 1.4565; 1.4529 EN 10088-1:2014
5	fischer filling disk FFD similar to DIN 6319-G	zinc plated $\geq 5 \mu\text{m}$, EN ISO 4042:1999 A2K	1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2014	1.4565; 1.4529 EN 10088-1:2014

fischer Highbond-Anchor FHB II Inject

System description
Materials
Annex A 5

Appendix 7 / 20

Specifications of intended use (part 1)

Table B1.1: Overview use and performance categories

Anchors subject to		fischer injection mortar FIS HB with ...															
		FHB II Inject – A L		FHB II Inject – A S													
Hammer drilling with standard drill bit		all sizes															
Hammer drilling with hollow drill bit (Heller "Duster Expert" or Hilti "TE-CD, TE-YD")		Nominal drill bit diameter (d_0) ≥ 12 mm															
Static or quasi static load, in	uncracked concrete	all sizes	Tables: C1.1, C3.1, C5.1	all Sizes	Tables: C2.1, C4.1, C6.1												
	cracked concrete																
Use category	dry or wet concrete	all sizes															
Kind of installation	Pre-positioned anchor	all sizes															
	Push through anchor	all sizes															
Installation temperature	-5 °C to +40 °C																
In-service temperature	-40 °C to +80 °C (max. short term temperature +80 °C and max. long term temperature +50 °C)																
fischer Highbond-Anchor FHB II Inject																	
Intended use Specifications (part 1)																	
Annex B 1																	
Appendix 8 / 20																	

Specifications of intended use (part 2)

Base materials:

- Reinforced or unreinforced normal weight concrete Strength classes C20/25 to C50/60 according to EN 206-1:2000

Use conditions (Environmental conditions):

- Structures subject to dry internal conditions (zinc coated steel, stainless steel or high corrosion resistant steel)
- Structures subject to external atmospheric exposure (including industrial and marine environment) and to permanently damp internal condition, if no particular aggressive conditions exist (stainless steel or high corrosion resistant steel)
- Structures subject to external atmospheric exposure, to permanently damp internal conditions or in other particular aggressive conditions (high corrosion resistant steel)

Note: Particular aggressive conditions are e.g. permanent, alternating immersion in seawater or the splash zone of seawater, chloride atmosphere of indoor swimming pools or atmosphere with extreme chemical pollution (e.g. in desulphurization plants or road tunnels where de-icing materials are used)

Design:

- Anchorages have to be designed by a responsible engineer with experience of concrete anchor design
- Verifiable calculation notes and drawings are to be prepared taking account of the loads to be anchored. The position of the anchor is indicated on the design drawings (e.g. position of the anchor relative to reinforcement or to supports, etc.)
- Anchorages under static or quasi-static actions are designed in accordance with:
EOTA ETAG 001 Annex C, 08/2010 or CEN/TS 1992-4:2009

Installation:

- Anchor installation is to be carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters of the site
- In case of aborted hole: The hole shall be filled with mortar
- Observe the effective anchorage depth
- Overhead installation is allowed

fischer Highbond-Anchor FHB II Inject

Intended Use
Specifications (part 2)

Annex B 2

Appendix 9 / 20


Table B3.1: Installation parameters for fischer Highbond – Anchor rods FHB II Inject – A L

Anchor rod FHB II Inject– A L	Thread	M8x	M10x	M12x		M16x			M20x	M24x
		60	95	100	120	125	145	160	210	210
Cone diameter	[mm]	9,4	10,7	12,5		16,8			23,0	
Width across flats		13	17	19		24			30	36
Nominal drill hole diameter		10	12	14		18			25	
Drill hole depth		66	101	106	126	131	151	166	216	
Effective anchorage depth		60	95	100	120	125	145	160	210	
Minimum spacing and minimum edge distance		$s_{\min} = c_{\min}$		40		55	60	70	90	
Diameter of clearance hole in the fixture ¹⁾		pre-positioned anchorage	$d_f \leq$	9	12	14			22	26
		push through anchorage	$d_f \leq$	11	14	16			26	
Min. thickness of concrete member		h_{\min}		100	140	170	190	220	280	
Installation torque	T_{inst}	[Nm]	15	20	40	60			100	
Thickness of fixture	$t_{\text{fix}} \leq$	[mm]	1500							
fischer filling disk FFD ²⁾	$\geq d_a$		-	26	30	38			46	54
	t_s		-	6	6	7			8	10

¹⁾ For larger clearance holes in the fixture see EOTA ETAG 001 Annex C, 08/2010 or CEN/TS 1992-4-:2009

²⁾ Using fischer filling disk FFD reduces t_{fix} (usable length of the anchor)

fischer Highbond – Anchor rod FHB II Inject – A L




Marking: work symbol, size of anchor, setting depth. e.g.: M10x95

For stainless steel additional **A4**. For high corrosion resistant steel additional **C**.

For high corrosion resistant steel additional marking **C** also on the face side

Installation conditions:



Pictures not to scale

fischer Highbond-Anchor FHB II Inject

Intended Use

Installation parameters fischer Highbond-Anchor rod FHB II Inject – A L

Annex B 3

Appendix 10 / 20


Tabelle B4.1: Installation parameters for fischer Highbond – Anchor rods FHB II Inject – A S

Anchor rod FHB II Inject – A S	Thread	M10x		M12x	M16x	M20x	M24x	
		60	75	75	95	170	170	
Cone diameter	[mm]	d _k	9,4	11,3	14,5	23,0		
Width across flats		SW	17	19	24	30	36	
Nominal drill hole diameter		d ₀	10	12	16	25		
Drill hole depth		h ₀	66	81	81	101	176	
Effective anchorage depth		h _{ef}	60	75	75	95	170	
Minimum spacing and minimum edge distance		s _{min} = c _{min}		40	50	80		
Diameter of clearance hole in the fixture ¹⁾		pre-positioned anchorage	d _f ≤	12	14	18	22	26
		push through anchorage	d _f ≤	12	14	18	26	
Min. thickness of concrete member		h _{min}	100	120	150	240		
Installation torque	T _{inst}	[Nm]	15	30	50	100		
Thickness of fixture	t _{fix} ≤	[mm]	1500					
fischer filling disk FFD ²⁾	≥ d _a		26	30	38	46	54	
	t _s		6	6	7	8	10	

¹⁾ For larger clearance holes in the fixture see EOTA ETAG 001 Annex C, 08/2010 or CEN/TS 1992-4-:2009

²⁾ Using fischer filling disk FFD reduces t_{fix} (usable length of the anchor)

fischer Highbond – Anchor rod FHB II Inject – A S




Marking: work symbol, size of anchor, setting depth. e.g.: M10x75

For stainless steel additional **A4**. For high corrosion resistant steel additional **C**.

For high corrosion resistant steel additional marking **C** also on the face side

Installation conditions:



Pictures not to scale

fischer Highbond-Anchor FHB II Inject

Intended Use


Installation parameters fischer Highbond-Anchor rod FHB II Inject– A S

Annex B 4

Table B5.1: Parameters of the cleaning brush BS (steel brush)

The size of the steel brush refers to the nominal drill hole diameter

Drill hole diameter	d_0	[mm]	10	12	14	16	18	25
Brush diameter	d_b		11	13	16	20		27

**Table B5.2:** Maximum processing time of the mortar **FIS HB** and minimum curing time
(During the curing time of the mortar the concrete temperature may not fall below the listed minimum temperature)

System temperature [°C]	Maximum processing time t_{work}	Minimum curing time ¹⁾ t_{cure}
-5 to -1	---	6 h
0 to +4	---	3 h
> +5 to +9	15 min	90 min
> +10 to +19	6 min	35 min
> +20 to +29	4 min	20 min
> +30 to +40	2 min	12 min

¹⁾ In wet concrete the curing times must be doubled

Pictures not to scale

fischer Highbond-Anchor FHB II Inject

Intended Use



Parameters of the cleaning brush; Processing times and curing times

Annex B 5

Appendix 12 / 20

Installation instructions part 1; Installation with injection mortar FIS HB

Bohrlocherstellung und Bohrlochreinigung (Hammerbohren mit Standardbohrer)

1		Drill the hole with hammer drill. Drill hole diameter d_0 and drill hole depth h_0 see Tables B3.1, B4.1
2	 min. 2x	Blow out the drill hole twice. If necessary, remove standing water out of the bore hole
		For drill hole diameter $d_0 < 25$ mm with hand-blowout or oil-free compressed air
		For drill hole diameter $d_0 = 25$ mm with oil-free compressed air ($p \geq 6$ bar) Use a cleaning nozzle.
3	 min. 2x	Brush the bore hole twice. Corresponding brushes see Table B5.1
4	 min. 2x	Blow out the drill hole twice
		For drill hole diameter $d_0 < 25$ mm with hand-blowout or oil-free compressed air
		For drill hole diameter $d_0 = 25$ mm with oil-free compressed air ($p \geq 6$ bar) Use a cleaning nozzle.
Go to step 5		
Drilling and cleaning the hole (hammer drilling with hollow drill bit)		
1		Check a suitable hollow drill (see Table B1.1) for correct operation of the dust extraction
2		Use a suitable dust extraction system, e. g. Bosch GAS 35 M AFC or a comparable dust extraction system with equivalent performance data Drill the hole with hollow drill bit. The dust extraction system has to extract the drill dust nonstop during the drilling process and must be adjusted to maximum power. Diameter of drill hole d_0 and drill hole depth h_0 see Tables B3.1, B4.1
Go to step 5		
fischer Highbond-Anchor FHB II Inject		
Intended use Installation instructions part 1; Installation with injection mortar		Annex B 6 Appendix 13 / 20

Installation instructions part 2; Installation with injection mortar FIS HB

Preparing the cartridge

5		Remove the sealing cap
		Screw on the static mixer (the spiral in the static mixer must be clearly visible)
6		Place the cartridge into the dispenser
7		Extrude approximately 10 cm of material until the resin is evenly grey in colour. Do not use mortar that is not uniformly grey

Injection of the mortar

8		Fill approximately 2/3 of the drill hole with mortar. Exact quantity of mortar (travel scale on the cartridge) see instruction sheet. Fill the drill hole with mortar, always begin from the bottom of the hole to avoid bubbles
		Push-through installation: By using Highbond-Anchor rods FHB II Inject - AL the drill hole in the fixture must be also filled with mortar. By using Highbond-Anchor rods FHB II Inject - AS is this not necessary.
		For drill hole depth ≥ 170 mm use an extension tube

Installation Highbond-Anchor rod FHB II Inject- A L and FHB II Inject – A S

9		Only use clean and oil-free anchor rods. Push the anchor rod down to the bottom of the hole, turning it slightly while doing so.
10		After inserting the anchor rod FHB II Inject - AL , surplus mortar must be escaped from the fixture. After inserting the anchor rod FHB II Inject - AS , surplus mortar must be escaped from the bore hole or must be visible in the fixture.
		For overhead installations support the anchor rod with wedges. (e.g. fischer centering wedges)
11		Wait for the specified curing time t_{cure} see Table B5.2
12		Mounting the fixture T_{inst} see Tables B3.1, B4.1
Option		After the minimum curing time is reached, the gap between anchor and fixture (annular clearance) may be filled with mortar via the fischer filling disc FFD. compressive strength ≥ 50 N/mm ² (e.g. FIS HB). ATTENTION: Using fischer filling disk FFD reduces t_{fix} (usable length of the anchor)

fischer Highbond-Anchor FHB II Inject

Intended use
Installation instructions part 2; Installation with injection mortar

Annex B 7

Appendix 14 / 20

Table C1.1: Characteristic values under static and quasi-static **tension load** for **fischer Highbond-Anchors FHB II Inject - A L**

Anchor rod FHB II Inject – A L	M8x 60	M10x 95	M12x 100 120	M16x 125 145 160	M20x 210	M24x 210				
Bearing capacity under tensile load, steel failure										
Characteristic resistance $N_{Rk,s}$	Steel, zinc plated	[kN]	25,1	34,4	49,8	96,6	137,6			
	Stainless steel A4		25,1	34,4	49,8	96,6	137,6			
	High corrosion resistant steel C									
Partial safety factors¹⁾										
Partial safety factor $\gamma_{Ms,N}$	Steel, zinc plated	[-]			1,5 ¹⁾					
	Stainless steel A4				1,5 ¹⁾					
	High corrosion resistant steel C				1,5 ¹⁾					
Pullout failure in cracked concrete C20/25										
Characteristic resistance	$N_{Rk,p}$	[kN]			-- ²⁾					
Pullout and splitting failure in uncracked concrete C20/25										
Characteristic resistance	$N_{Rk,p}$	[kN]			-- ²⁾					
Edge distance	$c_{cr,sp}$	[mm]	300	476	380	600	375	500	580	630
Spacing	$s_{cr,sp}$		150	238	190	300	188	250	290	315
Pullout and splitting failure in uncracked concrete C20/25										
Characteristic resistance	$N_{Rk,p}$	[kN]	20	35	40	50	-- ²⁾	75	95	-- ²⁾
Edge distance	$c_{cr,sp}$	[mm]					1,5 h_{ef}			
Spacing	$s_{cr,sp}$						3,0 h_{ef}			
Factors for the compressive strength of concrete > C20/25										
Increasing factor for $N_{Rk,p}$	C25/30	[-] Ψ_c			1,10					
	C30/37				1,22					
	C35/45				1,34					
	C40/50				1,41					
	C45/55				1,48					
	C50/60				1,55					
Factors acc. to CEN/TS 1992-4:2009 Section 6.2.2.3										
Uncracked concrete	k_{ucr}	[-]			10,1					
Cracked concrete	k_{cr}				7,2					
Concrete cone failure										
Effective anchorage depth	h_{ef}	[mm]	60	95	100	120	125	145	160	210
Partial safety factor ^{1) 4)}	γ_{Mc}	[-]	1,5				1,5			
¹⁾ In absence of other national regulations										
²⁾ Not decisive (proof of splitting failure acc. ETAG 001, Annex C)										
³⁾ Proof of splitting failure acc. ETAG 001, Annex C, (Section 5.3). Instead of $N_{Rk,c}^0$ use $N_{Rk,p}$.										
⁴⁾ $\gamma_2 = 1,0$ is included										
fischer Highbond-Anchor FHB II Inject							Annex C 1			
Performances										
Characteristic values under static and quasi-static tension load for fischer Highbond-Anchor FHB II Inject – A L							Appendix 15 / 20			

Table C2.1: Characteristic values under static and quasi-static **tension load** for
fischer Highbond-Anchor FHB II Inject – A S

Anchor rod FHB II Inject – A S	M10x	M12x	M16x	M20x	M24x
	60	75	75	95	170
Bearing capacity under tensile load, steel failure					
Characteristic resistance $N_{Rk,s}$	Steel, zinc plated	[kN]	25,1	34,4	61,6
	Stainless steel A4		25,1	34,4	61,6
	High corrosion resistant steel C				128,5
Partial safety factors¹⁾					
Partial safety factor $\gamma_{Ms,N}$	Steel, zinc plated	[-]	1,5 ¹⁾		
	Stainless steel A4		1,5 ¹⁾		
	High corrosion resistant steel C		1,5 ¹⁾		
Pullout failure in cracked concrete C20/25					
Characteristic resistance	$N_{Rk,p}$	[kN]		---	²⁾
Pullout and splitting failure in uncracked concrete C20/25					
Characteristic resistance	$N_{Rk,p}$	[kN]		---	²⁾
Edge distance	$c_{cr,sp}$	[mm]	300	340	510
Spacing	$s_{cr,sp}$		150	170	255
Pullout and splitting failure in uncracked concrete C20/25					
Characteristic resistance	$N_{Rk,p}$ ³⁾	[kN]	20	25	40
Edge distance	$c_{cr,sp}$	[mm]		1,5 h_{ef}	
Spacing	$s_{cr,sp}$			3,0 h_{ef}	
Factors for the compressive strength of concrete > C20/25					
Increasing factor for $N_{Rk,p}$	C25/30	Ψ _c		1,10	
	C30/37			1,22	
	C35/45			1,34	
	C40/50			1,41	
	C45/55			1,48	
	C50/60			1,55	
Factors acc. to CEN/TS 1992-4:2009 Section 6.2.2.3					
Uncracked concrete	k_{ucr}	[-]		10,1	
Cracked concrete	k_{cr}			7,2	
Concrete cone failure					
Effective anchorage depth	h_{ef}	[mm]	60	75	95
Partial safety factor ^{1) 4)}	γ_{Mc}	[-]	1,5		1,5
¹⁾ In absence of other national regulations					
²⁾ Not decisive (proof of splitting failure acc. ETAG 001, Annex C)					
³⁾ Proof of splitting failure acc. ETAG 001, Annex C, (Section 5.3). Instead of $N_{Rk,c}^0$ use $N_{Rk,p}$.					
⁴⁾ $\gamma_2 = 1,0$ is included					
fischer Highbond-Anchor FHB II Inject					
Performances					
Characteristic values under static and quasi-static tension load for fischer Highbond-Anchor FHB II Inject – A S					
Annex C 2					
Appendix 16 / 20					

Table C3.1: Characteristic values under static and quasi-static **shear load** for **fischer Highbond-Anchor FHB II Inject – A L**

Anchor rod FHB II Inject – A L M8x M10x M12x M16x M20x M24x

Bearing capacity under shear load, steel failure

without lever arm

	Steel, zinc plated	V _{Rk,s} [kN]	13,7	20,8	30,3	56,3	87,9	126,9
Characteristic resistance	Stainless steel A4 and High corrosion resistant steel C		15,2	23,2	33,7	62,7	97,9	141

with lever arm

Characteristic bending moment	Steel, zinc plated	$M^0_{Rk,s}$ [Nm]	31	62	105	266	519	896
	Stainless steel A4 and High corrosion resistant steel C		31	62	105	266	519	896

Partial safety factors

Partial safety factor ¹⁾	$\gamma_{Ms,V}$	[-]	1,25
Ductility factor acc. to CEN/TS 1992-4-5:2009 Section 6.3.2.1	k_2	[-]	1,0

Concrete pry-out failure

Factor k acc. TR029 Section 5.2.3.3 or k_3 acc.CEN/TS 1992-4-5:2009 Section 6.3.3	$k_{(3)}$ [-]	2,0
		1,5
Partial safety factors ¹⁾	γ_{Mcp}	1,5
		1,5

Concrete edge failure

Effective length of anchor	l_f	[mm]	60	95	100	112	125	144	200
Calculation diameter	d		10	12	14		18		25
Partial safety factor ¹⁾	γ_{M_0}	[-]				1.5			

¹⁾ In absence of other national regulations

fischer Highbond-Anchor EHB II Inject

Performances

Characteristics values under static and quasi-static shear load for fischer Highbond-Anchor FHB II Inject – A L

Annex C 3

Appendix 17 / 20

Table C4.1: Characteristic values under static and quasi-static **shear load** for
fischer Highbond-Anchor FHB II Inject – A S

Anchor rod FHB II Inject – A S		M10x	M12x	M16x	M20x	M24x	
		60	75	75	95	170	170
Bearing capacity under shear load, steel failure							
without lever arm							
Characteristic resistance	Steel, zinc plated	V _{Rk,s} [kN]	19,7	27,3	50,8	80,3	114,2
	Stainless steel A4		24,1	33,7	62,7	97,9	124,5
	High corrosion resistant steel C		24,1	33,7	62,7	97,9	141
with lever arm							
Characteristic bending moment	Steel, zinc plated	M ⁰ _{Rk,s} [Nm]	62	105	266	519	896
	Stainless steel A4 and		62	105	266	519	896
	High corrosion resistant steel C						
Partial safety factors							
Partial safety factor ¹⁾	γ _{Ms,V}	[-]		1,25			
Ductility factor acc. to CEN/TS 1992-4-5:2009 Section 6.3.2.1	k ₂	[-]		1,0			
Concrete pry-out failure							
Factor k acc. TR029 Section 5.2.3.3 or k ₃ acc.CEN/TS 1992-4-5:2009 Section 6.3.3	k ₍₃₎	[-]		2,0			
Partial safety factors ¹⁾	γ _{Mcp}	[-]		1,5			
Concrete edge failure							
Effective length of anchor	l _f	[mm]	60	75	95	170	
Calculation diameter	d		10	12	16	25	
Partial safety factor ¹⁾	γ _{Mc}	[-]		1,5			
¹⁾ In absence of other national regulations							
fischer Highbond-Anchor FHB II Inject							Annex C 4
Performances Characteristic values under static and quasi-static shear load for fischer Highbond-Anchor FHB II Inject – A S							
							Appendix 18 / 20

Table C5.1: Displacement for fischer Highbond-Anchor FHB II Inject – A L

Table C6.1: Displacement for fischer Highbond-Anchor FHB II Inject – A S

Anchor rod FHB II Inject – A S	M10x 60	M12x 75	M16x 95	M20x 170	M24x 170
Displacement under tension load					
Cracked concrete					
Tension load [kN]	6,6	11,1	15,9	38,0	
δ_{N0} [mm]	0,8	0,3	0,4	0,6	
$\delta_{N\infty}$			1,7		
Uncracked concrete					
Tension load [kN]	9,3	15,6	22,3	53,3	
δ_{N0} [mm]		0,2		0,5	
$\delta_{N\infty}$			1,7		
Displacement under shear load					
Cracked or uncracked concrete					
Steel zinc plated					
Shear load [kN]	11,3	12,7	29,0	45,9	65,3
δ_{V0} [mm]	1,2	1,5		2,8	
$\delta_{V\infty}$	1,8	2,3		4,2	
Stainless steel A4					
Shear load [kN]	13,8	19,3	35,8	55,9	71,1
δ_{V0} [mm]	1,0	1,1	2,2		3,5
$\delta_{V\infty}$	1,5	1,7	3,3		5,3
High corrosion resistant steel C					
Shear load [kN]	13,8	19,3	35,8	55,9	80,6
δ_{V0} [mm]	1,2	1,3	2,4	3,7	5,0
$\delta_{V\infty}$	1,8	2,0	3,6	5,6	7,5
fischer Highbond-Anchor FHB II Inject					
Performances Displacement for fischer Highbond-Anchor FHB II Inject - A S					
Annex C 6					
Appendix 20 / 20					