



DÉCLARATION DES PERFORMANCES

DoP 0196

pour fischer RM II (fixation à scellement pour utilisation dans le béton)

FR

1. <u>Code d'identification unique du type de produit:</u>	DoP 0196	
2. <u>Usage(s) prévu(s):</u>	Fixation dans du béton fissuré ou non fissuré.	
3. <u>Fabricant:</u>	Voir annexes, en particulier les annexes fischerwerke GmbH & Co. KG, Otto-Hahn-Straße 15, 79211 Denzlingen, Allemagne	B1- B7
4. <u>Mandataire:</u>	-	
5. <u>Système(s) d'évaluation et de vérification de la constance des performances:</u>	1	
6. <u>Document d'évaluation européen:</u> Evaluation Technique Européenne: Organisme d'évaluation technique: Organisme(s) notifié(s):	EAD 330499-01-0601 ETA-16/0340; 2020-06-17 DIBt- Deutsches Institut für Bautechnik 1343 MPA Darmstadt / 2873 TU Darmstadt	
7. <u>Performance(s) déclarée(s):</u> Résistance mécanique et stabilité (BWR 1) Résistance caractéristique à la charge de traction (charge statique et quasi-statique):	Résistance à la rupture de l'acier (charge de Résistance à la rupture par extraction glissement: et rupture du cône béton): Résistance à la rupture du cône béton: Distance au bord pour éviter la rupture par fendage sous charge: Robustesse : Couple de serrage maxi.: Distance au bord et entraxe mini.:	Annexes C1, C2 Annexes C4, C5 Annexes C3 Annexes C3 Annexe C3- C5 Annexes B3, B4 Annexes B3, B4
		$\tau_{Rk,100}^0 = \text{NPD}$ $\psi_{sus}^0 = \text{NPD}$
Résistance caractéristique à la charge de cisaillement (charge statique et quasi-statique):	Résistance à la rupture de l'acier: Résistance à la rupture par effet de levier: Résistance à la rupture du béton en bord de dalle:	Annexes C1, C2 Annexe C3 Annexe C3
Résistance caractéristique et déplacements pour les catégories de performance sismique C1 et C2:	Résistance à la charge de traction, catégorie C1: Résistance à la charge de traction, catégorie C2: Résistance à la charge de cisaillement, catégorie C1: Résistance à la charge de cisaillement, catégorie C2: Facteur espace annulaire:	NPD NPD NPD NPD NPD
Déplacements sous charge à court et long terme :	Déplacements sous charge à court et long terme :	Annexe C6
Hygiène, santé et environnement (BWR 3) Contenu, émission et/ou rejet de substances dangereuses:	NPA	



8. Documentation technique appropriée et/ou
documentation technique spécifique:

Les performances du produit identifié ci-dessus sont conformes aux performances déclarées. Conformément au règlement (UE) no 305/2011, la présente déclaration des performances est établie sous la seule responsabilité du fabricant mentionné ci-dessus.

Signé pour le fabricant et en son nom par:

ppn. Thilo Pregartner

Thilo Pregartner, Dr.-Ing.
Tumlingen, 2020-07-01

i.V. P. Schillinger

Peter Schillinger, Dipl.-Ing.

Cette DoP a été préparée en plusieurs langues. En cas de différend relatif à l'interprétation, la version anglaise prévaudra.

L'annexe comprend des informations volontaires et complémentaires en langue anglaise dépassant les exigences légales (spécifiées de manière neutre).

Specific Part

1 Technical description of the product

The fischer capsule system RM II is a bonded anchor for use in concrete consisting of a capsule RM II and a steel element according to Annex A2.

The capsule RM II is placed in the hole and the steel element is driven by machine with simultaneous hammering and turning.

The anchor rod is anchored via the bond between steel element, chemical mortar and concrete.

The product description is given in Annex A.

2 Specification of the intended use in accordance with the applicable European Assessment Document

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the anchor of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment

3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Characteristic resistance to tension load (static and quasi-static loading)	See Annex B 3 and B 4, C 1 to C 5
Characteristic resistance to shear load (static and quasi-static loading)	See Annex C 1 to C 4
Displacements under short-term and long-term loading	See Annex C 6
Characteristic resistance and displacements for seismic performance categories C1 and C2	No performance assessed

3.2 Hygiene, health and the environment (BWR 3)

Essential characteristic	Performance
Content, emission and/or release of dangerous substances	No performance assessed

4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base


In accordance with the European Assessment Document EAD 330499-01-0601 the applicable European legal act is: [96/582/EC].

The system to be applied is: 1


Installation conditions

fischer anchor rod RG M; installation in concrete

Pre-positioned installation:




Pre-positioned installation with subsequently injected fischer filling disc:




fischer internal threaded anchor RG M I; installation in concrete

Pre-positioned installation:



Pre-positioned installation with subsequently injected fischer filling disc:



Pictures not to scale

h_0 = drill hole depth

h_{ef} = effective anchorage depth

t_{fix} = thickness of fixture

fischer RM II

Product description

Installation conditions

Annex A 1

Appendix 3/ 18

Overview product components


Capsule RM II

Size: 8, 10, 12, 16, 16E, 20/22, 24



fischer anchor rod RG M

Size: M8, M10, M12, M16, M20, M24




fischer internal threaded anchor RG M I


Size: M8, M10, M12, M16, M20



Screw / threaded rod / washer / hexagon nut



fischer filling disc with injection adapter



Pictures not to scale

fischer RM II

Product description

Overview product components

Annex A 2

Appendix 4/ 18

Table A3.1: Materials


Part	Designation	Material		
1	Capsule RM II	Mortar, hardener, filler		
Steel grade	Steel	Stainless steel R	High corrosion resistant steel HCR	
	zinc plated	acc. to EN 10088-1:2014 Corrosion resistance class CRC III acc. to EN 1993-1-4:2015	acc. to EN 10088-1:2014 Corrosion resistance class CRC V acc. to EN 1993-1-4:2015	
2	Anchor rod	Property class 4.8, 5.8 or 8.8; EN ISO 898-1:2013 zinc plated $\geq 5 \mu\text{m}$, ISO 4042:2018/Zn5/An(A2K) or hot dip galvanised $\geq 40 \mu\text{m}$ EN ISO 10684:2004 $f_{uk} \leq 1000 \text{ N/mm}^2$	Property class 50, 70 or 80 EN ISO 3506-1:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; 1.4062, 1.4662, 1.4462 EN 10088-1:2014 $f_{uk} \leq 1000 \text{ N/mm}^2$	Property class 50 or 80 EN ISO 3506-1:2009 or property class 70 with $f_{yk} = 560 \text{ N/mm}^2$ 1.4565; 1.4529 EN 10088-1:2014 $f_{uk} \leq 1000 \text{ N/mm}^2$
		Fracture elongation $A_5 > 8 \%$,		
3	Washer ISO 7089:2000	zinc plated $\geq 5 \mu\text{m}$, ISO 4042:2018/Zn5/An(A2K) or hot dip galvanised $\geq 40 \mu\text{m}$ EN ISO 10684:2004	1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362 EN 10088-1:2014	1.4565; 1.4529 EN 10088-1:2014
4	Hexagon nut	Property class 4, 5 or 8; EN ISO 898-2:2012 zinc plated $\geq 5 \mu\text{m}$, ISO 4042:2018/Zn5/An(A2K) or hot dip galvanised $\geq 40 \mu\text{m}$ EN ISO 10684:2004	Property class 50, 70 or 80 EN ISO 3506-1:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362 EN 10088-1:2014	Property class 50, 70 or 80 EN ISO 3506-1:2009 1.4565; 1.4529 EN 10088-1:2014
5	fischer internal threaded anchor RG M I	Property class 5.8 ISO 898-1:2013 zinc plated $\geq 5 \mu\text{m}$, ISO 4042:2018/Zn5/An(A2K)	Property class 70 EN ISO 3506-1:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362 EN 10088-1:2014	Property class 70 EN ISO 3506-1:2009 1.4565; 1.4529 EN 10088-1:2014
6	Commercial standard screw or threaded rod for fischer internal threaded anchor RG M I	Property class 5.8 or 8.8; EN ISO 898-1:2013 zinc plated $\geq 5 \mu\text{m}$, ISO 4042:2018/Zn5/An(A2K) fracture elongation $A_5 > 8 \%$	Property class 70 EN ISO 3506-1:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362 EN 10088-1:2014 fracture elongation $A_5 > 8 \%$	Property class 70 EN ISO 3506-1:2009 1.4565; 1.4529 EN 10088-1:2014 fracture elongation $A_5 > 8 \%$
7	fischer filling disc similar to DIN 6319-G	zinc plated $\geq 5 \mu\text{m}$, ISO 4042:2018/Zn5/An(A2K) or hot dip galvanised $\geq 40 \mu\text{m}$ EN ISO 10684:2004	1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362 EN 10088-1:2014	1.4565; 1.4529 EN 10088-1:2014

fischer RM II

Product description
Materials
Annex A 3

Specifications of intended use (part 1)

Table B1.1: Overview use and performance categories

Anchorage subject to		RM II with ...			
		fischer anchor rod RG M		fischer internal threaded anchor RG M I	
Hammer drilling with standard drill bit		all sizes		all sizes	
Hammer drilling with hollow drill bit (fischer „FHD“, Heller "Duster Expert"; Bosch „Speed Clean“; Hilti "TE-CD, TE-YD", DreBo „D-Plus“, DreBo „D-Max“)		Nominal drill bit diameter (d_0) 12 mm to 28 mm		all sizes	
Static and quasi static load, in	uncracked concrete	all sizes	Tables: C1.1, C3.1, C4.1, C6.1	all sizes	Tables: C2.1, C3.1, C5.1, C6.2
	cracked concrete	M10, M12, M16, M20, M24		all sizes	
Use category	I1 dry or wet concrete	all sizes		M8, M10, M16	
I2 flooded hole	M12, M16, M20, M24				
Installation direction	D3 (downward and horizontal and upwards (e.g. overhead installation))				
Installation temperature	$T_{i,min} = -15^\circ\text{C}$ to $T_{i,max} = +40^\circ\text{C}$				
In-service temperature	Temperature range I	-40 °C to +40 °C	(max. short term temperature +40 °C and max. long term temperature +24 °C)		
	Temperature range II	-40 °C to +80 °C	(max. short term temperature +80 °C and max. long term temperature +50 °C)		
	Temperature range III	-40 °C to +120 °C	(max. short term temperature +120 °C and max. long term temperature +72 °C)		
fischer RM II					
Intended Use Specifications (part 1)				Annex B 1 Appendix 6/ 18	

Specifications of intended use (part 2)

Base materials:

- Compacted reinforced or unreinforced normal weight concrete without fibres strength classes C20/25 to C50/60 according to EN 206:2013+A1:2016

Use conditions (Environmental conditions):

- Structures subject to dry internal conditions (zinc coated steel, stainless steel or high corrosion resistant steel)
- For all other conditions according to EN1993-1-4:2015 corresponding to corrosion resistance classes to Annex A 3 table A3.1.

Design:

- Anchorages have to be designed by a responsible engineer with experience of concrete anchor design.
- Verifiable calculation notes and drawings are to be prepared taking account of the loads to be anchored. The position of the anchor is indicated on the design drawings (e.g. position of the anchor relative to reinforcement or to supports, etc.)
- Anchorages are designed in accordance with:
EN 1992-4:2018 and EOTA Technical Report TR 055, Edition February 2018.

Installation:

- Anchor installation has to be carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters of the site
- In case of aborted hole: The hole shall be filled with mortar
- Anchorage depth should be marked and adhered to on installation
- Overhead installation is allowed

fischer RM II

Intended Use
Specifications (part 2)


Annex B 2

Appendix 7 / 18

Table B3.1: Installation parameters for fischer anchor rods RG M

Anchor rods RG M		thread	M8	M10	M12	M16	M20	M24
Width across flats	SW	[mm]	13	17	19	24	30	36
Nominal drill bit diameter	d_0		10	12	14	18	25	28
Drill hole depth	h_0		$h_0 = h_{\text{ef}}$					
Effective embedment depth	h_{ef}		80	90	110	125	170	210
Minimum spacing and minimum edge distance	$s_{\text{min}} = c_{\text{min}}$		40	45	55	65	85	105
Diameter of pre-clearance hole in the fixture ¹⁾	d_f		9	12	14	18	22	26
Minimum thickness of concrete member	h_{min}	$h_{\text{ef}} + 30$ (≥ 100)			$h_{\text{ef}} + 2d_0$			
Maximum installation torque	max T_{inst}	[Nm]	10	20	40	60	120	150

fischer anchor rod RG M




Marking (on random place) fischer anchor rod RG M

Steel zinc plated PC ¹⁾ 8.8	• or +	Steel hot-dip PC ¹⁾ 8.8	•
High corrosion resistant steel HCR PC ¹⁾ 50	•	High corrosion resistant steel HCR PC ¹⁾ 70	-
High corrosion resistant steel HCR PC ¹⁾ 80	(Stainless steel R property class 50	~
Stainless steel R property class 80	*		

Alternatively: Colour coding according to DIN 976-1:2016

¹⁾ PC = property class

Installation conditions:



Pictures not to scale

fischer RM II

Intended Use
Installation parameters anchor rods RG M


Annex B 3

Appendix 8/ 18

Table B4.1: Installation parameters for fischer internal threaded anchors RG M I

Internal threaded anchors RG M I	thread	M8	M10	M12	M16	M20
Diameter of anchor	d = d _H [mm]	12	16	18	22	28
Nominal drill bit diameter		14	18	20	24	32
Drill hole depth		$h_0 = h_{\text{ef}} = L_H$				
Effective embedment depth ($h_{\text{ef}} = L_H$)		90	90	125	160	200
Minimum spacing and minimum edge distance		55	65	75	95	125
Diameter of clearance hole in the fixture ¹⁾		9	12	14	18	22
Minimum thickness of concrete member		120	125	165	205	260
Maximum screw-in depth		18	23	26	35	45
Minimum screw-in depth		8	10	12	16	20
Maximum installation torque	max T _{inst} [Nm]	10	20	40	80	120

fischer internal threaded anchor RG M I




Marking: Anchor size e. g.: **M10**

Stainless steel → additional **R**; e.g.: **M10 R**

High corrosion resistant steel → additional **HCR**; e.g.: **M10 HCR**

Retaining bolt or threaded rods (including nut and washer) must comply with the appropriate material and strength class of Annex A 3, Table A3.1.

Installation conditions:



Pictures not to scale

fischer RM II


Intended Use

Installation parameters fischer internal threaded anchors RG M I

Annex B 4

Table B5.1: Dimensions of **resin capsule RM II**

Capsule RM II		8	10	12	16	16 E	20/22	24
Capsule diameter	d _P	9,0	10,5	12,5	16,5		23,0	
Capsule length	L _P	85	90	97	95	123	160	190

**Table B5.2:** Assignment of **resin capsule RM II** to **fischer anchor rod RG M**

Anchor rod RG M			M8	M10	M12	M16	M20	M24
Effective anchorage depth	h _{ef}	[mm]	80	90	110	125	170	210
Related capsule RM II		[-]	8	10	12	16	20/22	24

Table B5.3: Assignment of **resin capsule RM II** to the **fischer internal threaded anchor RG MI**

Internal threaded anchor RG MI			M8	M10	M12	M16	M20
Effective anchorage depth	h _{ef}	[mm]	90	90	125	160	200
Related capsule RM II		[-]	10	12	16	16E	24

Table B5.4: Minimum curing time

(During the curing time of the mortar the concrete temperature may not fall below the listed minimum temperature; minimal capsule temperature -15 °C)

Concrete temperature [°C]	Minimum curing time t_{cure}
-15 to -10	30 h
> -10 to -5	16 h
> -5 to 0	10 h
> 0 to 5	45 min
> 5 to 10	30 min
> 10 to 20	20 min
> 20 to 30	5 min
> 30 to 40	3 min

fischer RM II



Intended Use

Dimensions of the capsules, Assignment of the capsule to the anchor rod and internal threaded anchor, Minimum curing time

Annex B 5


Installation instructions part 1

Drilling and cleaning the hole (hammer drilling with standard drill bit)

1		<p>Specified drill hole depth h_0 should be adhered to (e.g. mark on the drill bit). Drill the hole. Drill hole diameter d_0 and drill hole depth h_0 see Tables B3.1, B4.1</p>
2	 	<p>When reaching the drill hole depth h_0 pull out the drill bit whilst power drill is switched on. To reduce the drill dust in the drill hole repeat this step minimum three times, beginning from the drill hole bottom (discharging the bore hole)</p> <p>Trickling of the bore dust into the drill hole has to be avoided. (e.g. with exhausting the drill dust) Blowing out or brushing the drill hole is not necessary</p>

Go to step 3

Drilling and cleaning the hole (hammer drilling with hollow drill bit)

1		<p>Check a suitable hollow drill (see Table B1.1) for correct operation of the dust extraction</p>
2		<p>Use a suitable dust extraction system, e.g. fischer FVC 35 M or a comparable dust extraction system with equivalent performance data</p> <p>Drill the hole with hollow drill bit. The dust extraction system has to extract the drill dust nonstop during the drilling process and must be adjusted to maximum power. Diameter of drill hole d_0 and drill hole depth h_0 see Tables B3.1, B4.1</p>

Go to step 3

fischer RM II








Intended use
Installation instructions part 1

Annex B 6

Appendix 11/ 18

Installation instructions part 2

Installation of capsule RM II with fischer anchor rods RG M or fischer internal threaded anchors RG M I

3		<p>Push the capsule RM II into the drill hole</p>		<p>Depending on the anchor being installed, use a suitable setting tool (e.g. RA-SDS)</p>
4				<p>Only use clean and oil-free metal parts. Using a suitable adapter, drive the RG M or fischer internal threaded anchor RG M I into the capsule using a hammer drill set on rotary hammer action. Stop when the metal part reaches the bottom of the hole and is set to the correct embedment depth</p>
5				<p>When reaching the correct embedment depth, excess mortar must be emerged from the mouth of the drill hole</p>
6				<p>Wait for the specified curing time, t_{cure} see Table B5.4 Mounting the fixture max T_{inst} see Table B3.1, B4.1</p>
Option				<p>After the minimum curing time is reached, the gap between metal part and fixture (annular clearance) may be filled with mortar via the fischer filling disc. compressive strength $\geq 50 \text{ N/mm}^2$ (e.g. fischer injection mortars FIS HB, FIS SB, FIS V, FIS EM Plus)</p>

fischer RM II

Intended use
Installation instructions part 2

Annex B 7

Appendix 12/ 18

Table C1.1: Characteristic values for **steel failure** under tension / shear load of **fischer anchor rods RG M**

Anchor rod RG M			M8	M10	M12	M16	M20	M24	
Bearing capacity under tension load, steel failure³⁾									
Characteristic resistance $N_{Rk,s}$	Property class	4.8	15(13)	23(21)	33	63	98	141	
		5.8	19(17)	29(27)	43	79	123	177	
		8.8	29(27)	47(43)	68	126	196	282	
		50	19	29	43	79	123	177	
		70	26	41	59	110	172	247	
		80	30	47	68	126	196	282	
		[kN]							
Partial factors¹⁾									
Partial factor $\gamma_{Ms,N}$	Property class	4.8			1,50				
		5.8			1,50				
		8.8			1,50				
		50			2,86				
		70			1,50 ²⁾ / 1,87				
		80			1,60				
		[-]							
Bearing capacity under shear load, steel failure³⁾									
without lever arm									
Characteristic resistance $V_{Rk,s}^0$	Property class	4.8	9(8)	14(13)	20	38	59	85	
		5.8	11(10)	17(16)	25	47	74	106	
		8.8	15(13)	23(21)	34	63	98	141	
		50	9	15	21	39	61	89	
		70	13	20	30	55	86	124	
		80	15	23	34	63	98	141	
		[kN]							
Ductility factor	k ₇	[-]			1,0				
with lever arm									
Characteristic resistance $M_{Rk,s}^0$	Property class	4.8	15(13)	30(27)	52	133	259	448	
		5.8	19(16)	37(33)	65	166	324	560	
		8.8	30(26)	60(53)	105	266	519	896	
		50	19	37	65	166	324	560	
		70	26	52	92	232	454	784	
		80	30	60	105	266	519	896	
		[Nm]							
Partial factors¹⁾									
Partial factor $\gamma_{Ms,V}$	Property class	4.8			1,25				
		5.8			1,25				
		8.8			1,25				
		50			2,38				
		70			1,25 ²⁾ / 1,56				
		80			1,33				
		[-]							
1) In absence of other national regulations									
2) Only for fischer RG M made of high corrosion-resistant steel HCR									
3) Values in brackets are valid for undersized fischer anchor rods RG M with smaller stress area A _s for hot dip galvanised standard threaded rods according to EN ISO 10684:2004+AC:2009									
fischer RM II									
Performances Characteristic values for steel failure under tension / shear load of fischer anchor rods RG M								Annex C 1	
								Appendix 13/ 18	

Table C2.1: Characteristic values for **steel failure** under tension / shear load of **fischer internal threaded anchors RG M I**

Internal threaded anchor RG M I			M8	M10	M12	M16	M20								
Bearing capacity under tension load, steel failure															
Characteristic bearing capacity with screw N _{Rk,s}	Property class 5.8	[kN]	19	29	43	79	123								
			29	47	68	108	179								
	Property class R		26	41	59	110	172								
			26	41	59	110	172								
Partial factors¹⁾															
Partial factor $\gamma_{Ms,N}$	Property class 5.8	[-]	1,50												
			1,50												
	Property class R		1,87												
			1,87												
Bearing capacity under shear load, steel failure															
without lever arm															
Characteristic bearing capacity with screw V ⁰ _{Rk,s}	Property class 5.8	[kN]	9,2	14,5	21,1	39,2	62,0								
			14,6	23,2	33,7	54,0	90,0								
	Property class R		12,8	20,3	29,5	54,8	86,0								
			12,8	20,3	29,5	54,8	86,0								
Ductility factor	K ₇	[-]	1,0												
with lever arm															
Characteristic bending moment with screw M ⁰ _{Rk,s}	Property class 5.8	[Nm]	20	39	68	173	337								
			30	60	105	266	519								
	Property class R		26	52	92	232	454								
			26	52	92	232	454								
Partial factors¹⁾															
Partial factor $\gamma_{Ms,V}$	Property class 5.8	[-]	1,25												
			1,25												
	Property class R		1,56												
			1,56												
fischer RM II															
Performances Characteristic values for steel failure under tension / shear load of fischer internal threaded anchor RG MI						Annex C 2									
						Appendix 14/ 18									

¹⁾ In absence of other national regulations

Table C3.1: Characteristic values for concrete failure under tension / shear load

Size		All sizes							
Tension load									
Installation factor	γ_{inst}	[$-$]	See annex C 4 to C 5						
Factors for the compressive strength of concrete > C20/25									
Increasing factor for τ_{Rk}	C25/30	Ψ_c	[-]	1,02					
	C30/37			1,04					
	C35/45			1,07					
	C40/50			1,08					
	C45/55			1,09					
	C50/60			1,10					
Splitting failure									
Edge distance	$h / h_{\text{ref}} \geq 2,0$	$C_{\text{cr,sp}}$	[mm]	1,0 h_{ref}					
	$2,0 > h / h_{\text{ref}} > 1,3$			4,6 h_{ref} - 1,8 h					
	$h / h_{\text{ref}} \leq 1,3$			2,26 h_{ref}					
Spacing	$S_{\text{cr,sp}}$			2 $C_{\text{cr,sp}}$					
Concrete cone failure									
Uncracked concrete	$k_{\text{ucr,N}}$	[-]		11,0					
Cracked concrete	$k_{\text{cr,N}}$			7,7					
Edge distance	$C_{\text{cr,N}}$	[mm]		1,5 h_{ref}					
Spacing	$S_{\text{cr,N}}$			2 $C_{\text{cr,N}}$					
Factors for sustained tension load									
Factor	Ψ_{sus}^0	[$-$]		- ¹⁾					
Shear load									
Installation factor	γ_{inst}	[$-$]		1,0					
Concrete pry-out failure									
Factor for pry-out failure	k_8	[$-$]		2,0					
Concrete edge failure									
Effective length of fastener in shear loading	l_f	[mm]		for $d_{\text{nom}} \leq 24$ mm: min (h_{ref} ; 12 d_{nom})					
Calculation diameters									
Size				M8	M10	M12	M16		
fischer anchor rods	d	[mm]		8	10	12	16		
fischer internal threaded anchors RG M I	d_{nom}			12	16	18	22		
fischer RM II									
Performances									
Characteristic values for concrete failure under tensile / shear load									
Annex C 3									
Appendix 15/ 18									

¹⁾ No performance assessed

²⁾ Anchor type not part of the assessment

Table C4.1: Characteristic values for **combined pull-out** and concrete failure for **fischer anchor rods RG M** in hammer drilled holes; **uncracked or cracked concrete**

Table C5.1: Characteristic values for **combined pull-out** and concrete failure for **fischer internal threaded anchors RG M 1** in hammer drilled holes; **uncracked or cracked concrete**

Table C6.1: Displacements for fischer anchor rods RG M

Anchor rod RG M	M8	M10	M12	M16	M20	M24
Displacement-Factors for tension load¹⁾						
Uncracked or cracked concrete; Temperature range I, II, III						
δ_{N0} -Factor	[mm/(N/mm ²)]	0,07	0,08	0,09	0,10	0,11
$\delta_{N\infty}$ -Factor		0,13	0,14	0,15	0,17	0,18
Displacement-Factors for shear load²⁾						
Uncracked or cracked concrete; Temperature range I, II, III						
δ_{V0} -Factor	[mm/kN]	0,18	0,15	0,12	0,09	0,07
$\delta_{V\infty}$ -Factor		0,27	0,22	0,18	0,14	0,11

1) Calculation of effective displacement:

$$\delta_{N0} = \delta_{N0}\text{-Factor} \cdot \tau_{Ed}$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-Factor} \cdot \tau_{Ed}$$

(τ_{Ed} : Design value of the applied tensile stress)

2) Calculation of effective displacement:

$$\delta_{V0} = \delta_{V0}\text{-Factor} \cdot V_{Ed}$$

$$\delta_{V\infty} = \delta_{V\infty}\text{-Factor} \cdot V_{Ed}$$

(V_{Ed} : Design value of the applied shear force)

Table C6.2: Displacements for fischer internal threaded anchors RG M I

Internal threaded anchor RG M I	M8	M10	M12	M16	M20
Displacement-Factors for tension load¹⁾					
Uncracked or cracked concrete; Temperature range I, II, III					
δ_{N0} -Factor	[mm/(N/mm ²)]	0,09	0,10	0,10	0,11
$\delta_{N\infty}$ -Factor		0,13	0,15	0,15	0,17
Displacement-Factors for shear load²⁾					
Uncracked or cracked concrete; Temperature range I, II, III					
δ_{V0} -Factor	[mm/kN]	0,12	0,09	0,08	0,07
$\delta_{V\infty}$ -Factor		0,18	0,14	0,12	0,10

1) Calculation of effective displacement:

$$\delta_{N0} = \delta_{N0}\text{-Factor} \cdot \tau_{Ed}$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-Factor} \cdot \tau_{Ed}$$

(τ_{Ed} : Design value of the applied tensile stress)

2) Calculation of effective displacement:

$$\delta_{V0} = \delta_{V0}\text{-Factor} \cdot V_{Ed}$$

$$\delta_{V\infty} = \delta_{V\infty}\text{-Factor} \cdot V_{Ed}$$

(V_{Ed} : Design value of the applied shear force)

fischer RM II

Performances

Displacements for anchor rods RGM and fischer internal threaded anchors RG M I

Annex C 6