IZJAVA O SVOJSTVIMA

DoP 0414

za fischer Strong Undercut Anchor FSU (Mehaničko sidro za uporabu u betonu)

HR

1. Jedinstveni identifikator tipa proizvoda: **DoP 0414**

2. Namjena korištenja: **Naknadno učvršćivanje u napuknutom i ne-napuknutom betonu, vidi dodatak, posebno priloge B1 - B6.**

3. Proizvođač: **fischerwerke GmbH & Co. KG, Klaus-Fischer-Str. 1, 72178 Waldachtal, Njemačka**

4. Ovlašteni zastupnik: **–**

5. Sistem/i od AVCP: **1**

6. Europski dokument za ocjenjivanje: **EAD 330232-02-0601**
   Europska tehnička ocjena: **ETA-22/0674; 2026-03-25**
   Tijelo za tehničko ocjenjivanje: **DIBt- Deutsches Institut für Bautechnik**
   Prijavljeno tijelo/prijavljena tijela: **2873 TU Darmstadt**

7. Objavljena svojstva:

Mehanička otpornost i stabilnost (BWR 1)

Karakteristični otpor na opterećenje (statičko i kvazi-statičko opterećenje) Metoda A:

1 Otpornost na lom čelika: vidi dodatak, posebno prilog C1
2 Otpornost na čupanje: vidi dodatak, posebno prilog C1
3 Otpornost na lom betona: vidi dodatak, posebno prilog C1
4 Robusnost: vidi dodatak, posebno prilog C1
5 Minimalna udaljenost od ruba i razmak: vidi dodatak, posebno prilog C4
6 Udaljenost ruba kako bi se spriječilo cijepanje pod opterećenjem: vidi dodatak, posebno prilog C1

Karakteristični otpor na smicanje (statičko i kvazi-statičko opterećenje), Metoda A:

7 Otpornost na lom čelika (posmično opterećenje): vidi dodatak, posebno priloge C2, C3
8 Otpornost na otkazivanje: vidi dodatak, posebno priloge C2, C3

Karakteristična otpornost za pojednostavljeni návrh:

9 Metoda B: NPD
10 Metoda C: NPD

Istisnine:

11 Pomaci pri statičkom i kvazi-statičkom opterećenju: vidi dodatak, posebno prilog C9

Krutost:

12 Krutost u elastičnom području pod vlačnim opterećenjem: vidi dodatak, posebno prilog C11
13 Karakteristike krutosti za opterećenje napetosti za nelinearne modele opruga: vidi dodatak, posebno prilog C11

Karakteristična otpornost za seizmičku kategoriju performansi C1:

14 Otpornost na vlačno opterećenje (napetost): vidi dodatak, posebno prilog C7
15 Otpornost na posmično opterećenje:, Faktor prstenaste pukotine: vidi dodatak, posebno prilog C7

Karakteristični otpor i pomaci za kategorije seizmičke učinkovitosti C2:

16 Otpornost na vlačno opterećenje (napetost), pomaci: vidi dodatak, posebno priloge C8, C10
17 Otpornost na posmično opterećenje, pomaci, Faktor prstenaste pukotine: vidi dodatak, posebno priloge C8, C10

Sigurnost u slučaju požara (BWR 2)

18 Reakcija na vatru: Klasa (A1)

Otpornost na vatru:

19 Vatrootpornost na lom čelika (vlačna sila): vidi dodatak, posebno prilog C5
20 Vatrootpornost na čupanje (vlačna sila): vidi dodatak, posebno prilog C5
21 Vatrootpornost na lom čelika (posmik): vidi dodatak, posebno priloge C5, C6

Trajnost:

22 Trajnost: vidi dodatak, posebno priloge A3, B1

8. Odgovarajuća tehnička dokumentacija i/ili specifična tehnička dokumentacija: **–**

Svojstva gore navedenog proizvoda su u skladu sa skupom izjava o svojstvima.Ova izjava o svojstvima se izdaje, u skladu sa Europskom regulativom (EU) Br. 305/2011, pod punom odgovornošću gore navedenog proizvođača.

Za proizvođača i u njegovo ime potpisao:

i.V.

Dr. Christian Weber, Voditelj razvoja

Dieter Pfaff, Voditelj Međunarodne federacije za proizvodnju i upravljanje kvalitetom

Tumlingen, 2026-07-01

Ovaj DoP je pripremljen u različitim jezicima. U slučaju da postoji spor u tumačenju, engleska verzija će uvijek prevladati.
U aneksu se nalaze dodatni podaci na engleskom jeziku, koji ne podliježu zakonskoj regulativi.

Translation guidance Essential Characteristics and Performance Parameters for Annexes

Smjernice za prijevod. Bitne karakteristike i parametri izvedbe za dodatke

Mechanical resistance and stability (BWR 1) **Mehanička otpornost i stabilnost (BWR 1)**		
Characteristic resistance under static and quasi-static loading, Method A **Karakteristični otpor na opterećenje (statičko i kvazi-statičko opterećenje) Metoda A:**		
1	Resistance to steel failure: **Otpornost na lom čelika:**	$N_{Rk,s}$ [kN], E_s [N/mm^2]
2	Resistance to pull- out failure: **Otpornost na čupanje:**	$N_{Rk,p}$ [kN], ψ_c
3	Resistance to concrete cone failure: **Otpornost na lom betona:**	$k_{cr,N}$, $k_{ucr,N}$ [-], h_{ef}, $c_{cr,N}$ [mm]
4	Robustness: **Robusnost:**	γ_{inst} [-]
5	Minimum edge distance and spacing: **Minimalna udaljenost od ruba i razmak:**	c_{min}, s_{min}, h_{min} [mm]
6	Edge distance to prevent splitting under load: **Udaljenost ruba kako bi se spriječilo cijepanje pod opterećenjem:**	$N^0_{Rk,sp}$ [kN], $c_{cr,sp}$ [mm]
Characteristic resistance to shear load (static and quasi-static loading), Method A **Karakteristični otpor na smicanje (statičko i kvazi-statičko opterećenje), Metoda A:**		
7	Resistance to steel failure under shear load: **Otpornost na lom čelika (posmično opterećenje):**	$V^0_{Rk,s}$ [kN], $M^0_{Rk,s}$ [Nm], k_7 [-]
8	Resistance to pry-out failure: **Otpornost na otkazivanje:**	k_8 [-]
Characteristic Resistance for simplified design: **Karakteristična otpornost za pojednostavljeni návrh:**		
9	Method B: **Metoda B:**	F^0_{Rk} [kN], $M^0_{Rk,s}$ [Nm] ψ_c [-], c_{cr}, s_{cr}, c_{min}, s_{min}, h_{min} [mm]
10	Method C: **Metoda C:**	F_{Rk} [kN], $M^0_{Rk,s}$ [Nm], c_{cr}, s_{cr}, h_{min} [mm]
Displacements **Istisnine:**		
11	Displacements under static and quasi-static loading: **Pomaci pri statičkom i kvazi-statičkom opterećenju:**	δ_{N0}, $\delta N_{50years}$, $\delta N_{100years}$, δ_{V0}, $\delta_{V\infty}$ [mm]
12	Stiffness characteristics for tension loading for non-linear spring models: **Krutost:**	$k_{1,ucr}$, $k_{2,ucr}$, $k_{3,ucr}$, $k_{4,ucr}$,
12	Stiffness in the elastic range under tension loading **Krutost u elastičnom području pod vlačnim opterećenjem:**	$k_{A,ucr}$, $k_{A,cr}$ [N/mm]
13	Stiffness characteristics for tension loading for non-linear spring models **Karakteristike krutosti za opterećenje napetosti za nelinearne modele opruga:**	$k_{A,ucr}$, $k_{B,ucr}$, $k_{C,ucr}$, $k_{D,ucr}$ [N/mm] $k_{A,cr}$, $k_{B,cr}$, $k_{C,cr}$, $k_{D,cr}$ [N/mm]
Characteristic resistance for seismic performance category C1: **Karakteristična otpornost za seizmičku kategoriju performansi C1:**		
14	Resistance to tension load: **Otpornost na vlačno opterećenje (napetost):**	$N_{Rk,s,C1}$ [kN], $N_{Rk,p,C1}$ [kN]
15	Resistance to shear load:, Factor annular gap: **Otpornost na posmično opterećenje:, Faktor prstenaste pukotine:**	$V_{Rk,s,C1}$ [kN]
Characteristic resistance and displacements for seismic performance categorie C2: **Karakteristični otpor i pomaci za kategorije seizmičke učinkovitosti C2:**		
16	Resistance to tension load, displacements: **Otpornost na vlačno opterećenje (napetost), pomaci:**	$N_{Rk,s,C2}$ [kN], $N_{Rk,p,C2}$ [kN] $\delta_{N,C2(0,5)}$, $\delta_{N,C2(0,8)}$ [mm]
17	Resistance to shear load and displacements, factor annular gap: **Otpornost na posmično opterećenje, pomaci, Faktor prstenaste pukotine:**	$V_{Rk,s,C2}$ [kN], $\delta_{V,C2(0,5)}$, $\delta_{V,C2(0,8)}$ [mm]
Safety in case of fire (BWR 2) **Sigurnost u slučaju požara (BWR 2)**		
18	Reaction to fire: **Reakcija na vatru:**	Class
Resistance to fire: **Otpornost na vatru:**		
19	Fire resistance to steel failure (tension load): **Vatrootpornost na lom čelika (vlačna sila):**	$N_{Rk,s,fi}$ [kN]
20	Fire resistance to pull-out failure (tension load): **Vatrootpornost na čupanje (vlačna sila):**	$N_{Rk,p,fi}$ [kN]
21	Fire resistance to steel failure (shear load): **Vatrootpornost na lom čelika (posmik):**	$V_{Rk,s,fi}$ [kN], $M^0_{Rk,s,fi}$ [Nm]
Aspects of durability **Trajnost:**		
22	Durability: **Trajnost:**	Class

Specific part

1 Technical description of the product

The fischer Strong Undercut Anchor is an anchor made of galvanised steel or of stainless steel which is placed in a cylindrical hole and anchored by displacement-controlled, self-undercutted mechanical interlock.

The product description is given in Annex A.

2 Specification of the intended use in accordance with the applicable European Assessment Document

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the anchor of at least 50 years and 100 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment

3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Characteristic resistance to tension load (static and quasi-static loading), Method A	See Annex C1 and C4
Characteristic resistance to shear load (static and quasi-static loading)	See Annex C2 and C3
Displacements	See Annex C9
Stiffness	See Annex C11
Characteristic resistance and displacements for seismic performance categories C1 and C2	See Annex C7, C8 and C10

3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire	Class A1
Resistance to fire	See Annex C5 and C6

3.3 Aspects of Durability


Essential characteristic	Performance
Durability	See Annex B1

4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base


In accordance with the European Assessment Document EAD 330232-02-0601 the applicable European legal act is: [96/582/EC].

The system to be applied is: 1

Pre-setting anchor FSU / FSU R



Push-through anchor FSU-P / FSU-P R




Legend


d_0	=	Nominal drill hole diameter
d_f	=	Diameter of clearance hole in the fixture
h_{ef}	=	Effective embedment depth
h_1	=	Depth of drill hole to deepest point
h	=	Thickness of member
t_{fix}	=	Thickness of fixture
U	=	Gap after setting

(Figures not to scale)

Pre-setting anchor FSU / FSU R



Push-through anchor FSU-P / FSU-P R



Product marking, example: FSU-P M10x100/20 R optional: Brand

Type of fastener — Identification R (stainless steel version)

Thread size x effective embedment depth (h_{ef}) / Maximum thickness of the fixture (t_{fix})

Table A6.1: Dimensions [mm]

Type of anchor	t_{fix}	d_K	d_{S1}	d_{S2}	d_{S3}	M	l_S	l_B	l_F	SW
FSU M10x100/20 (R)	≤ 20	19,3	19,0	17,5	18,5	10	100	148	-	17
FSU M12x125/30 (R)	≤ 30	21,5	21,0	19,3	20,5	12	125	188	-	19
FSU M12x125/50 (R)	≤ 50	21,5	21,0	19,3	20,5	12	125	208	-	19
FSU M16x190/40 (R)	≤ 40	29,0	29,0	26,5	28,5	16	191	273	-	24
FSU M16x190/60 (R)	≤ 60	29,0	29,0	26,5	28,5	16	191	293	-	24
FSU-P M10x100/20 (R)	≥ 10 ≤ 20	19,3	19,0	17,5	18,5	10	120	148	20	17
FSU-P M12x125/30 (R)	≥ 12 ≤ 30	21,5	21,0	19,3	20,5	12	155	188	30	19
FSU-P M12x125/50 (R)	≥ 12 ≤ 50	21,5	21,0	19,3	20,5	12	175	208	50	19
FSU-P M16x190/40 (R)	≥ 15 ≤ 40	29,0	29,0	26,5	28,5	16	231	273	40	24
FSU-P M16x190/60 (R)	≥ 15 ≤ 60	29,0	29,0	26,5	28,5	16	251	293	60	24

(Figures not to scale)

Table A3.1: Materials FSU

Part	Designation	Material	
		FSU, FSU-P	FSU R, FSU-P R
1	Cone bolt	Steel, zinc plated ≥ 5 µm, EN ISO 4042:2022	Stainless steel according to EN 10088:2023
2	Plastic sleeve	Plastic	
3	Sleeve	Steel, zinc plated ≥ 5 µm, EN ISO 4042:2022	Stainless steel according to EN 10088:2023
4	Protective cap	Plastic	
5	Washer	Steel, zinc plated ≥ 5 µm, EN ISO 4042:2022	Stainless steel according to EN 10088:2023
6	Hexagon nut	Steel, zinc plated ≥ 5 µm, EN ISO 4042:2022	Stainless steel A4-80

Stop drill bit FSU-SD




Table A3.2: Required stop drill bits for FSU

Type of anchor	Type of stop drill bit	d_0 [mm]	L [mm]
FSU M10x100/20 (R)	FSU-SD 20x100	20	107
FSU M12x125/30 (R)	FSU-SD 22x125	22	132
FSU M12x125/50 (R)			
FSU M16x190/40 (R)	FSU-SD 30x190	30	200
FSU M16x190/60 (R)			
FSU-P M10x100/20 (R)	FSU-SD 20x120	20	127
FSU-P M12x125/30 (R)	FSU-SD 22x155	22	162
FSU-P M12x125/50 (R)	FSU-SD 22x175	22	182
FSU-P M16x190/40 (R)	FSU-SD 30x230	30	240
FSU-P M16x190/60 (R)	FSU-SD 30x250	30	260

(Figure not to scale)

Machine setting tool FSU-ST




Table A4.1: Required machine setting tools for FSU

Type of anchor	Type of machine setting tool
FSU M10x100/20 (R)	FSU-ST M10
FSU M12x125/30 (R)	FSU-ST M12
FSU M12x125/50 (R)	
FSU M16x190/40 (R)	FSU-ST M16
FSU M16x190/60 (R)	
FSU-P M10x100/20 (R)	FSU-ST M10
FSU-P M12x125/30 (R)	FSU-ST M12
FSU-P M12x125/50 (R)	
FSU-P M16x190/40 (R)	FSU-ST M16
FSU-P M16x190/60 (R)	

Table A4.2: Recommendations for hammer drills used with FSU-ST

Technical feature		Recommendation FSU, FSU-P, FSU R, FSU-P R		
		M10x100	M12x125	M16x190
Drill chuck	[-]	SDS plus		SDS Max
Hammer drilling RPM	[U/min]	600 - 1800		200 - 700
Hammer impact energy	[J]	2,5 - 6		8 - 13

(Figure not to scale)

Specifications of intended use with working life 50 and 100 years

Fastenings subject to:

Size		FSU, FSU R, FSU-P, FSU-P R				
		M10x100/20	M12x125/30	M12x125/50	M16x190/40	M16x190/60
Static and quasi-static loads		✓				
Cracked and uncracked concrete						
Seismic loads performance category	C1					
	C2					
Fire exposure						

Base materials:

- Compacted reinforced and unreinforced normal weight concrete without fibres (cracked and uncracked) according to EN 206:2013+A2:2021.
- Strength classes C20/25 to C50/60 according to EN 206:2013+A2:2021.

Use conditions (Environmental conditions):


- Structures subject to dry internal conditions (FSU, FSU-P, FSU R, FSU-P R).
- For all other conditions according to EN 1993-1-4:2006 + A1:2015 corresponding to corrosion resistance class CRC III: FSU R, FSU-P R.

Design:


- Anchorages are designed under the responsibility of an engineer experienced in anchorages and concrete work.
- Verifiable calculation notes and drawings are prepared taking account of the loads to be anchored. The position of the anchor is indicated on the design drawings (e.g. position of the anchor relative to reinforcement or to supports, etc.).
- Anchorages are designed in accordance with EN 1992-4:2018.
- For requirements to resistance to fire local spalling of the concrete cover must be avoided.
- The stiffness characteristics k_A-k_D (Annex C11) are intended to be used in finite element calculations, such as linear- and non-linear spring models, for the design of the fastener as a function of fastener displacements and the anchor plate stiffness.

Table B2.1: Installation parameters

Size			FSU, FSU R			FSU-P, FSU-P R		
			M10x100 /20	M12x125 /30	M12x125 /50	M10x100 /20	M12x125 /30	M12x125 /50
Nominal drill hole diameter	d_0	[mm]	20	22	22	20	22	22
Cutting diameter of drill bits	$d_{cut} \leq$		20,5	22,5	22,5	20,5	22,5	22,5
Depth of drill hole to deepest point	$h_1 \geq$		107	132	132	127-t_{fix}	162-t_{fix}	182-t_{fix}
Effective embedment depth	$h_{ef} \geq$		100	125	125	100	125	125
Diameter of clearance hole in the fixture	$d_f \leq$		12	14	14	21	23	23
Thickness of the fixture	t_{fix}		≤ 20	≤ 30	≤ 50	≥ 10 ≤ 20	≥ 12 ≤ 30	≥ 12 ≤ 50
Gap after setting	U		2 - 5	3 - 6	3 - 6	2 - 5	3 - 6	3 - 6
Required setting torque	T_{inst}	[Nm]	40	80	80	40	80	80



FSU (R)




FSU-P (R)


(Figures not to scale)

Table B3.1: Installation parameters

Size			FSU, FSU R		FSU-P, FSU-P R	
			M16x190 /40	M16x190 /60	M16x190 /40	M16x190 /60
Nominal drill hole diameter	d_0	[mm]	30	30	30	30
Cutting diameter of drill bits	$d_{cut} \leq$		30,55	30,55	30,55	30,55
Depth of drill hole to deepest point	$h_1 \geq$		200	200	240-t_{fix}	260-t_{fix}
Effective embedment depth	$h_{ef} \geq$		190	190	190	190
Diameter of clearance hole in the fixture	$d_f \leq$		18	18	32	32
Thickness of the fixture	t_{fix}		≤ 40	≤ 60	≥ 15 ≤ 40	≥ 15 ≤ 60
Gap after setting	U		3 - 8	3 - 8	3 - 8	3 - 8
Required setting torque	T_{inst}	[Nm]	120	120	120	120



FSU (R)




FSU-P (R)


(Figures not to scale)

Installation instructions


- Fastener installation carried out by appropriately qualified personnel according to the design drawings and under the supervision of the person responsible for technical matters on the site.
- Use of the fastener only as supplied by the manufacturer without exchanging the components of the fastener.
- Fastener installation in accordance with the manufacturer's specifications and drawings and using the appropriate tools (machine setting tool FSU-ST, stop drill bit FSU-SD).
- Drill hole created perpendicular (tolerance +/- 5°) to concrete surface.
- Cleaning the hole of drilling dust.
- Fastener installation ensuring complete expansion of the sleeve with checking that the coloured ring marking on the bolt is visible above the top edge of the anchor sleeve, therefore it is required using the setting tool FSU-ST, that is the appropriate depth ring marking of the setting tool at least flush with the concrete surface (pre-setting) respecting with the fixture surface (Push-through-setting).
- Fastener installation ensuring complete shear load capacity, after setting the gap between the top edge of the sleeve and the concrete surface (pre-setting) or with surface of the fixture (Push-through-setting) has to be in the specified range according to Annex B2 Table B2.1 or Annex B3 Table B3.1, respectively.
- Positioning of the drill holes and the undercut without damaging the reinforcement.
- In case of aborted hole: new drilling at a minimum distance twice the depth of the aborted drill hole or smaller distance, if the aborted drill hole is filled with high strength mortar and, if under shear or oblique tension load, it is not in the direction of load application.
- Application of the torque moment given in Annex B2 Table B2.1 or Annex B3 Table B3.1, respectively, using a calibrated torque wrench.


Installation instructions for pre-setting anchor FSU, FSU R

1) 


2) 


1) Drill the hole with the designated stop drill bit FSU-SD (see Table A3.2).
2) Clean the hole.

3) 


4) 


3) Place the anchor in the hole by hand. Do not use any hammering tools.
4) Use the designated setting tool FSU-ST (see Table A4.1) and follow the recommendations for the hammer drill (see Table A4.2).

5) 


6) 

5) Place the setting tool in the grooves provided on the anchor. Carry out the setting process with the rotary-impact mode of the hammer drill. The setting process is completed when the marking ring of the setting tool is flush with the concrete surface.
6) After removing the setting tool, the red coloured ring marking on the bolt must be visible above the top edge of the anchor sleeve. The gap U between the top edge of the sleeve and the concrete surface must be in the specified range according to Table B2.1 or B3.1, respectively.

7) 


8) 

7) Place the fixture.
8) Remove the protective cap. Place the spring washer and the hexagon nut on the bolt. Take care of the right orientation of the spring washer, in the way, that the outer diameter of the washer in uncompressed condition is in touch with the fixture, only. Apply the installation torque.


9) 

9) Correctly installed fastener.


Installation instructions for push-though anchor FSU-P, FSU-P R




1) Drill the hole with the designated stop drill bit FSU-SD (see table A3.2) in compliance with the specified range of fixture thicknesses (see Table B2.1 or B3.1, respectively).
2) Clean the hole.




3) Place the anchor in the hole by hand. Do not use any hammering tools.
4) Use the designated setting tool FSU-ST (see Table A4.1) and follow the recommendations for the hammer drill (see Table A4.2).



5) Place the setting tool in the grooves provided on the anchor. Carry out the setting process with the rotary-impact mode of the hammer drill. The setting process is completed when the marking ring of the setting tool is flush with the fixture surface.
6) After removing the setting tool, the red coloured ring marking on the bolt must be visible above the top edge of the anchor sleeve. The gap U between the top edge of the sleeve and the fixture surface must be in the specified range according to Table B2.1 or Table B3.1, respectively.



7) Remove the protective cap. Place the spring washer and the hexagon nut on the bolt. Take care of the right orientation of the spring washer, in the way, that the outer diameter of the washer in uncompressed condition is in touch with the fixture, only. Apply the installation torque.



8) Correctly installed fastener.

Table C1.1: Characteristic tension resistance under static and quasi-static action for a working life of 50 and 100 years

Size				FSU, FSU-P, FSU R, FSU-P R		
				M10x100	M12x125	M16x190
Steel failure						
Characteristic resistance		$N_{Rk,s}$	[kN]	46,4	67,4	125,6
Partial factor for steel failure		γ_{Ms}	[-]	1,5		
Pullout failure						
Characteristic resistance in C20/25	cracked concrete	$N_{Rk,p,cr} = N_{Rk,p,cr,50}$	[kN]	46,4	67,4	125,6
	cracked concrete	$N_{Rk,p,cr} = N_{Rk,p,cr,100}$	[kN]		63,4	
	uncracked concrete	$N_{Rk,p,ucr} = N_{Rk,p,ucr,100}$	[kN]		67,4	
Increasing factor for $N_{Rk,p}$; $N_{Rk,p,100}$ $N_{Rk,p} = \psi_c * N_{Rk,p}$ (C20/25) $N_{Rk,p,100} = \psi_c * N_{Rk,p,100}$ (C20/25)		$\psi_c = \psi_{c,cr} = \psi_{c,ucr}$	[-]	C25/30	1,12	
				C30/37	1,22	
				C35/45	1,32	
				C40/50	1,41	
				C45/55	1,50	
				C50/60	1,58	
Installation sensitivity factor		γ_{inst}	[-]	1,0		
Concrete cone and splitting failure						
Effective embedment depth		h_{ef}	[mm]	100	125	190
Factor for cracked concrete		$k_{cr,N}$	[-]	8,9		
Factor for uncracked concrete		$k_{ucr,N}$	[-]	12,7		
Characteristic spacing		$s_{cr,N}$	[mm]	$3 \times h_{ef}$		
Characteristic edge distance		$c_{cr,N}$	[mm]	$1,5 \times h_{ef}$		
Characteristic spacing for splitting failure		$s_{cr,sp}$	[mm]	$3 \times h_{ef}$		
Characteristic edge distance for splitting failure		$c_{cr,sp}$	[mm]	$1,5 \times h_{ef}$		
Characteristic resistance for splitting failure		$N^0_{Rk,sp}$	[kN]	$\min \{N^0_{Rk,c}; N_{Rk,p}\}$ [1)]		

1) $N^0_{Rk,c}$ according to EN 1992-4:2018.

Table C2.1: Characteristic shear resistance under static and quasi-static action for a working life of 50 and 100 years

Size			FSU, FSU R	
			M10x100	M12x125
Steel failure without lever arm				
Characteristic resistance	$V^0_{Rk,s}$ FSU	[kN]	26,8	38,2
	$V^0_{Rk,s}$ FSU R		32,9	49,9
Partial factor for steel failure	γ_{Ms}	[-]	1,25	
Factor for ductility	k_7		1,0	
Steel failure with lever arm				
Characteristic bending resistance	$M^0_{Rk,s}$	[Nm]	59,8	104,8
Partial factor for steel failure	γ_{Ms}	[-]	1,25	
Concrete pryout failure				
Factor for pryout failure	k_8	[-]	2,5	
Concrete edge failure				
Effective length in concrete	l_f	[mm]	100	125
Effective diameter of fastener	d_{nom}		19	21

Table C2.2: Characteristic shear resistance under static and quasi-static action for a working life of 50 and 100 years

Size			FSU, FSU R
			M16x190
Steel failure without lever arm			
Characteristic resistance	$V^0_{Rk,s}$ FSU	[kN]	69,1
	$V^0_{Rk,s}$ FSU R		87,9
Partial factor for steel failure	γ_{Ms}	[-]	1,25
Factor for ductility	k_7		1,0
Steel failure with lever arm			
Characteristic bending resistance	$M^0_{Rk,s}$	[Nm]	266,4
Partial factor for steel failure	γ_{Ms}	[-]	1,25
Concrete pryout failure			
Factor for pryout failure	k_8	[-]	2,5
Concrete edge failure			
Effective length in concrete	l_f	[mm]	190
Effective diameter of fastener	d_{nom}		29

Table C3.1: Characteristic shear resistance under static and quasi-static action for a working life of 50 and 100 years

Size			FSU-P, FSU-P R			
			M10x100		M12x125	
Steel failure without lever arm						
Characteristic resistance	for t_{fix}	[mm]	$10 \le t_{fix} < 15$	$15 \le t_{fix} \le 20$	$12 \le t_{fix} < 20$	$20 \le t_{fix} \le 50$
	$V^0_{Rk,s}$ FSU-P	[kN]	66,1	69,6	86,4	96,7
	$V^0_{Rk,s}$ FSU-P R		74,6	80,6	102,9	103,6
Partial factor for steel failure	γ_{Ms}	[-]	1,25			
Factor for ductility	k_7		1,0			
Steel failure with lever arm						
Characteristic bending resistance	$M^0_{Rk,s}$	[Nm]	59,8		104,8	
Partial factor for steel failure	γ_{Ms}	[-]	1,25			
Concrete pryout failure						
Factor for pryout failure	k_8	[-]	2,5			
Concrete edge failure						
Effective length in concrete	l_f	[mm]	100		125	
Effective diameter of fastener	d_{nom}		19		21	

Table C3.2: Characteristic shear resistance under static and quasi-static action for a working life of 50 and 100 years

Size			FSU-P, FSU-P R M16x190	
Steel failure without lever arm				
Characteristic resistance	for t_{fix}	[mm]	$15 \le t_{fix} < 40$	$40 \le t_{fix} \le 60$
	$V^0_{Rk,s}$ FSU-P	[kN]	178,8	226,7
	$V^0_{Rk,s}$ FSU-P R		214,7	286,7
Partial factor for steel failure	γ_{Ms}	[-]	1,25	
Factor for ductility	k_7		1,0	
Steel failure with lever arm				
Characteristic bending resistance	$M^0_{Rk,s}$	[Nm]	266,4	
Partial factor for steel failure	γ_{Ms}	[-]	1,25	
Concrete pryout failure				
Factor for pryout failure	k_8	[-]	2,5	
Concrete edge failure				
Effective length in concrete	l_f	[mm]	190	
Effective diameter of fastener	d_{nom}		29	

Table C4.1: Minimum thickness of concrete members

Size			FSU, FSU R				
			M10x100/20	M12x125/30	M12x125/50	M16x190/40	M16x190/60
Minimum thickness of concrete member	h_{min}	[mm]	170	215		270	

Table C4.2: Minimum thickness of concrete members

Size			FSU-P, FSU-P R				
			M10x100/20	M12x125/30	M12x125/50	M16x190/40	M16x190/60
Maximum thickness of the fixture	$t_{fix,max}$	[mm]	20	30	50	40	60
Minimum thickness of concrete member	h_{min}		$190\text{-}t_{fix}$ [1)]	$245\text{-}t_{fix}$ [1)]	$265\text{-}t_{fix}$ [1)]	$310\text{-}t_{fix}$ [1)]	$330\text{-}t_{fix}$ [1)]

[1)] t_{fix} = actual thickness of the fixture.

Table C4.3: Minimum spacings and edge distances

Size			FSU, FSU-P, FSU R, FSU-P R				
			M10x100/20	M12x125/30	M12x125/50	M16x190/40	M16x190/60
Minimum spacing	s_{min}	[mm]	80	90		100	
Minimum edge distance	c_{min}		80	90		100	

Table C5.1: Characteristic tension resistance under fire exposure for a working life of 50 and 100 years

Size				FSU, FSU-P		FSU R, FSU-P R	
				M10x100	M12x125	M10x100	M12x125
Characteristic resistance **steel failure**	$N_{Rk,s,fi}$	R30	[kN]	3,7	4,5	7,2	10,4
		R60		2,2	3,2	5,3	7,7
		R90		1,7	2,8	4,7	6,9
		R120		1,5	2,6	4,4	6,4
Characteristic resistance **Concrete cone failure**	$N_{Rk,c,fi}$	R30-R90		19,9	34,8	19,9	34,8
		R120		15,9	27,8	15,9	27,8
Characteristic resistance **pullout failure**	$N_{Rk,p,fi,50}$	R30-R90		11,6	16,9	11,6	16,9
		R120		9,3	13,5	9,3	13,5
	$N_{Rk,p,fi,100}$	R30-R90		11,6	15,9	11,6	15,9
		R120		9,3	12,7	9,3	12,7

Table C5.2: Characteristic tension resistance under fire exposure for a working life of 50 and 100 years

Size				FSU, FSU-P M16x190	FSU R, FSU-P R M16x190
Characteristic resistance **steel failure**	$N_{Rk,s,fi}$	R30	[kN]	7,9	19,4
		R60		5,6	14,4
		R90		4,9	12,8
		R120		4,5	11,9
Characteristic resistance **Concrete cone failure**	$N_{Rk,c,fi}$	R30-R90		99,0	99,0
		R120		79,2	79,2
Characteristic resistance **pullout failure**	$N_{Rk,p,fi}$	R30-R90		31,4	31,4
		R120		25,1	25,1

Table C5.3: Characteristic shear resistance under fire exposure for a working life of 50 and 100 years

Size				FSU, FSU-P		FSU R, FSU-P R	
				M10x100	M12x125	M10x100	M12x125
Characteristic resistance **steel failure without lever arm**	$V_{Rk,s,fi}$	R30	[kN]	3,7	4,5	7,2	10,4
		R60		2,2	3,2	5,3	7,7
		R90		1,7	2,8	4,7	6,9
		R120		1,5	2,6	4,4	6,4
Characteristic bending resistance **steel failure with lever arm**	$M^0_{Rk,s,fi}$	R30	[Nm]	4,8	6,9	9,2	16,2
		R60		2,9	5,0	6,9	12,0
		R90		2,2	4,4	6,1	10,6
		R120		1,9	4,0	5,7	10,0
Concrete failure $V^0_{Rk,c,fi}$ and $V_{Rk,cp,fi}$				According to EN 1992-4:2018			

Table C6.1: Characteristic shear resistance under fire exposure for a working life of 50 and 100 years

Size				FSU, FSU-P M16x190	FSU R, FSU-P R M16x190
Characteristic resistance **steel failure without lever arm**	$V_{Rk,s,fi}$	R30	[kN]	7,9	19,4
		R60		5,6	14,4
		R90		4,9	12,8
		R120		4,5	11,9
Characteristic bending resistance **steel failure with lever arm**	$M^0_{Rk,s,fi}$	R30		16,7	41,2
		R60		11,9	30,6
		R90		10,3	27,1
		R120		9,5	25,3
Concrete failure $V^0_{Rk,c,fi}$ and $V_{Rk,cp,fi}$				According to EN 1992-4:2018	

Table C6.2: Minimum spacings and minimum edge distances under fire exposure for tension and shear load

Size			FSU, FSU-P, FSU R, FSU-P R All sizes
Minimum spacing	$s_{min,fi}$	[mm]	$4 \cdot h_{ef}$
Minimum edge distance	$c_{min,fi}$		$2 \cdot h_{ef}$, for fire exposure from more than one side $c_{min,fi} \geq 300$ mm

Table C7.1: Characteristic values of tension and shear resistance under seismic performance category C1 for a working life of 50 and 100 years

Size				FSU, FSU-P, FSU R, FSU-P R	
				M10x100	M12x125
Factor for annular gap	without filling of annular gap	α_{gap}	[-]	0,5	
Steel failure					
Characteristic resistance tension load seismic performance category C1		$N_{Rk,s,C1}$	[kN]	46,4	67,4
Pullout failure					
Characteristic resistance tension load in cracked concrete seismic performance category C1		$N_{Rk,p,C1} = N_{Rk,p,C1,50}$	[kN]	46,4	67,4
		$N_{Rk,p,C1} = N_{Rk,p,C1,100}$			63,4

Steel failure without lever arm							
Characteristic resistance shear load seismic performance category C1	for t_{fix}	[mm]	$10 \le t_{fix} < 15$	$15 \le t_{fix} \le 20$	$12 \le t_{fix} < 20$	$20 \le t_{fix} \le 50$
	$V_{Rk,s,C1}$ FSU	[kN]	18,8		26,8	
	$V_{Rk,s,C1}$ FSU R		23,0		34,9	
	$V_{Rk,s,C1}$ FSU-P		46,3	48,7	60,5	67,7
	$V_{Rk,s,C1}$ FSU-P R		52,2	56,4	72,0	72,5

Table C7.2: Characteristic values of tension and shear resistance under seismic performance category C1 for a working life of 50 and 100 years

Size				FSU, FSU-P, FSU R, FSU-P R M16x190
Factor for annular gap	without filling of annular gap	α_{gap}	[-]	0,5
Steel failure				
Characteristic resistance tension load seismic performance category C1		$N_{Rk,s,C1}$	[kN]	125,6
Pullout failure				
Characteristic resistance tension load in cracked concrete seismic performance category C1		$N_{Rk,p,C1}$	[kN]	125,6

Steel failure without lever arm				
Characteristic resistance shear load seismic performance category C1	for t_{fix}	[mm]	$15 \le t_{fix} < 40$	$40 \le t_{fix} \le 60$
	$V_{Rk,s,C1}$ FSU	[kN]	62,2	
	$V_{Rk,s,C1}$ FSU R		70,3	
	$V_{Rk,s,C1}$ FSU-P		89,4	120,2
	$V_{Rk,s,C1}$ FSU-P R		107,4	152,0

Table C8.1: Characteristic values of tension and shear resistance under seismic performance category C2 for a working life of 50 and 100 years

Size				FSU, FSU-P, FSU R, FSU-P R	
				M10x100	M12x125
Factor for annular gap	without filling of annular gap	α_{gap}	[-]	0,5	
Steel failure					
Characteristic resistance tension load seismic performance category C2		$N_{Rk,s,C2}$	[kN]	46,4	67,4
Pullout failure					
Characteristic resistance tension load in cracked concrete seismic performance category C2		$N_{Rk,p,C2} = N_{Rk,p,C2,50}$	[kN]	46,4	67,4
		$N_{Rk,p,C2} = N_{Rk,p,C2,100}$			63,4
Steel failure without lever arm					
Characteristic resistance shear load seismic performance category C2		for t_{fix}	[mm]	$10 \le t_{fix} < 15$	$15 \le t_{fix} \le 20$ / $12 \le t_{fix} < 20$ / $20 \le t_{fix} \le 50$
		$V_{Rk,s,C2}$ FSU	[kN]	20,1	24,5
		$V_{Rk,s,C2}$ FSU R		22,8	31,9
		$V_{Rk,s,C2}$ FSU-P		39,6 / 41,8	51,8 / 62,9
		$V_{Rk,s,C2}$ FSU-P R		37,2	56,6 / 67,3

Table C8.2: Characteristic values of tension and shear resistance under seismic performance category C2 for a working life of 50 and 100 years

Size				FSU, FSU-P, FSU R, FSU-P R
				M16x190
Factor for annular gap	without filling of annular gap	α_{gap}	[-]	0,5
Steel failure				
Characteristic resistance tension load seismic performance category C2		$N_{Rk,s,C2}$	[kN]	125,6
Pullout failure				
Characteristic resistance tension load in cracked concrete seismic performance category C2		$N_{Rk,p,C2}$	[kN]	125,6
Steel failure without lever arm				
Characteristic resistance shear load seismic performance category C2		for t_{fix}	[mm]	$15 \le t_{fix} < 40$ / $40 \le t_{fix} \le 60$
		$V_{Rk,s,C2}$ FSU	[kN]	62,2
		$V_{Rk,s,C2}$ FSU R		70,3
		$V_{Rk,s,C2}$ FSU-P		89,4 / 120,2
		$V_{Rk,s,C2}$ FSU-P R		107,4 / 152,0

Table C9.1: Displacements under static and quasi-static tension loads for a working life of 50 and 100 years

Size			FSU, FSU-P, FSU R, FSU-P R		
			M10x100	M12x125	M16x190
Tension load in cracked concrete C20/25	N	[kN]	21,8	33,1	59,8
Displacements	δ_{N0}	[mm]	1,1	1,3	1,8
	$\delta_{N,50years} = \delta_{N,100years}$		1,3	1,3	1,5
Tension load in uncracked concrete C20/25	N	[kN]	21,8	33,1	59,8
Displacements	δ_{N0}	[mm]	1,1	1,7	1,8
	$\delta_{N,50years}$		2,8	2,8	2,4
	$\delta_{N,100years}$				2,5

Table C9.2: Displacements under static and quasi-static shear loads for a working life of 50 and 100 years

Size			FSU, FSU-P, FSU R, FSU-P R		
			M10x100	M12x125	M16x190
Shear load in cracked and uncracked concrete C20/25	V	[kN]	13,8	21,3	32,9
Displacements FSU	δ_{V0}	[mm]	5,4	6,7	2,1
	$\delta_{V\infty}$		8,0	10,0	3,2
Shear load in cracked and uncracked concrete C20/25	V	[kN]	16,9	25,6	41,9
Displacements FSU R	δ_{V0}	[mm]	2,4	3,8	4,0
	$\delta_{V\infty}$		3,6	5,8	6,0
Shear load in cracked and uncracked concrete C20/25	V	[kN]	36,3	52,2	108,0
Displacements FSU-P	δ_{V0}	[mm]	5,9	7,2	8,5
	$\delta_{V\infty}$		8,8	10,7	12,8
Shear load in cracked and uncracked concrete C20/25	V	[kN]	39,6	55,4	134,9
Displacements FSU-P R	δ_{V0}	[mm]	8,91	8,7	11,0
	$\delta_{V\infty}$		13,4	13,1	16,5

Table C10.1: Displacements under tension loads for seismic performance category C2 for a working life of 50 and 100 years

Size			FSU, FSU-P, FSU R, FSU-P R		
			M10x100	M12x125	M16x190
Displacements	$\delta_{N,C2(0,5)}$	[mm]	4,6	4,6	2,6
	$\delta_{N,C2(0,8)}$		11,4	10,4	5,1

Table C10.2: Displacements under shear loads for seismic performance category C2 for a working life of 50 and 100 years

Size			FSU, FSU-P, FSU R, FSU-P R			
			M10x100		M12x125	
for t_{fix}			$10 \le t_{fix} < 15$	$15 \le t_{fix} \le 20$	$12 \le t_{fix} < 20$	$20 \le t_{fix} \le 50$
Displacements FSU	$\delta_{V,C2(0,5)}$	[mm]	5,2		5,0	
	$\delta_{V,C2(0,8)}$		7,3		6,7	
Displacements FSU R	$\delta_{V,C2(0,5)}$		4,7		4,1	
	$\delta_{V,C2(0,8)}$		6,8		5,9	
Displacements FSU-P	$\delta_{V,C2(0,5)}$		4,8		5,0	
	$\delta_{V,C2(0,8)}$		10,7		18,5	
Displacements FSU-P R	$\delta_{V,C2(0,5)}$		3,7		4,2	
	$\delta_{V,C2(0,8)}$		7,8		13,2	

Table C10.3: Displacements under shear loads for seismic performance category C2 for a working life of 50 and 100 years

Size			FSU, FSU-P, FSU R, FSU-P R M16x190	
for t_{fix}			$15 \le t_{fix} < 40$	$40 \le t_{fix} \le 60$
Displacements FSU	$\delta_{V,C2(0,5)}$	[mm]	6,1	
	$\delta_{V,C2(0,8)}$		8,9	
Displacements FSU R	$\delta_{V,C2(0,5)}$		5,8	
	$\delta_{V,C2(0,8)}$		9,7	
Displacements FSU-P	$\delta_{V,C2(0,5)}$		4,5	5,6
	$\delta_{V,C2(0,8)}$		7,0	13,0
Displacements FSU-P R	$\delta_{V,C2(0,5)}$		3,6	4,9
	$\delta_{V,C2(0,8)}$		5,3	16,7

Table C11.1: Stiffness characteristics (mean values) under static and quasi-static tension loads for a working life of 50 and 100 years

Size			FSU, FSU-P, FSU-R, FSU-P R		
			M10x100	M12x125	M16x190
Stiffness characteristics in cracked concrete	$k_{A,cr}$	[kN/mm]	20,1	22,6	21,8
	$k_{B,cr}$		13,8	16,0	15,4
	$k_{C,cr}$		10,4	12,2	10,9
	$k_{D,cr}$		1,8	2,0	1,9
Stiffness characteristics in uncracked concrete	$k_{A,ucr}$		33,1	35,0	28,6
	$k_{B,ucr}$		25,2	24,5	23,5
	$k_{C,ucr}$		20,6	17,3	18,3
	$k_{D,ucr}$		3,7	3,4	3,3

- The stiffness characteristics k_A-k_D are intended to be used in finite element calculations, such as linear- and non-linear spring models (k_A for linear spring model and k_A-k_D for non-linear spring model), for the design of the fastener group as a function of fastener displacements and the anchor plate stiffness.
- For linear spring model: mean displacement for any load N: $\delta_{mean} = N / k_A$.

