



## TELJESÍTMÉNYNYILATKOZAT

### DoP 0369

fischer injektált FIS V Zero rendszerhez (Injektált fém rögzítőelem falazatba történő alkalmazáshoz)

HU

1. A terméktípus egyedi azonosító kódja:

**DoP 0369**

2. Felhasználás célja(i):

**Falazatokba utólag beszerelhető rögzítés, Id. a Mellékletet, különösen ezt a mellékletet B1 - B14.**

3. Gyártó:

**fischerwerke GmbH & Co. KG, Otto-Hahn-Straße 15, 79211 Denzlingen, Németország**

4. A meghatalmazott képviselő:

**-**

5. Az AVCP-rendszer(ek):

**1**

6. Az európai értékelési dokumentum:

**EAD 330076-01-0604, Edition 10/2022**

**ETA-21/0267; 2024-11-14**

Európai műszaki értékelés:

A műszaki értékelést végző szerv:

Bejelentett szerv(ek):

**DIBt- Deutsches Institut für Bautechnik**

**2873 TU Darmstadt**

7. A nyilatkozatban szereplő teljesítmény(ek):

#### Mechanikus szilárdság és stabilitás (BWR 1)

Karakterisztikus ellenállás értéke statikus és kvázi-statikus terhelésre:

1 Karakterisztikus ellenállás értéke egy önálló dübel acél tönkremenettelével szemben húzóterhelés hatására: Id. a Mellékletet, különösen ezt a mellékletet C1, C3

2 Karakterisztikus ellenállás értéke egy önálló dübel acél tönkremenettelével szemben erőkarral illetve erőkar nélküli nyíróterhelés hatására: Id. a Mellékletet, különösen ezt a mellékletet C2, C3

3 Karakterisztikus ellenállás értéke egy önálló dübel kihúzdással vagy téglá kitörésével szemben húzóterhelés hatására, Csökkentő tényező: Id. a Mellékletet, különösen ezt a mellékletet C5, C7, C10, C13, C15, C18

4 Karakterisztikus ellenállás értéke egy önálló dübel helyi téglá tönkremenettel- vagy téglá kitörésével szemben nyíróterhelés hatására: Id. a Mellékletet, különösen ezt a mellékletet C5, C7, C11, C13, C15, C19

5 Karakterisztikus ellenállás értéke egy dübelcsoport téglá kitörésével szemben húzóterhelés hatására: Id. a Mellékletet, különösen ezt a mellékletet B13, B14, C4, C6, C8, C9, C12, C14, C17

6 Karakterisztikus ellenállás értéke egy dübelcsoport helyi téglá tönkremenettel-vagy kitörésével szemben nyíróterhelés hatására: Id. a Mellékletet, különösen ezt a mellékletet B13 ,B14, C4, C5, C6, C7, C8, C9, C11, C12, C13, C14, C15, C17, C19

7 Peremtávolságok, tengelytávolság, rögzítési alap vastagság: Id. a Mellékletet, különösen ezt a mellékletet B13, B14, C4, C6, C8, C9, C12, C14, C16

8 Elmozdulások húzás és nyírás hatására: Id. a Mellékletet, különösen ezt a mellékletet C21

9 Maximális meghúzási nyomaték: Id. a Mellékletet, különösen ezt a mellékletet B4-B7

Karakterisztikus ellenállás és elmozdulások értéke szeizmikus terhelésre:

10 Ellenállás húzó terhelés esetén, elmozdulások: NPD

11 Ellenállás nyíró terhelés esetén, elmozdulások: NPD

12 Faktor Annuláris rés: NPD

#### Tűzvédelem (BWR 2)

13 Viselkedése tűz esetén: Osztály (A1)

14 Ellenállás értéke tűznek kitett húzás és nyírás hatására erőkarral és erőkar nélküli esetnél, minimális perem- és tengelytávolságok értékei:  
NPD

#### Higiénia, egészség- és környezetvédelem (BWR 3)

15 Veszélyes anyagok tartalma, kibocsátása és / vagy kibocsátása: NPD

8. Megfelelő műszaki dokumentáció és/vagy egyedi műszaki dokumentáció:

**-**

A fent azonosított termék teljesítménye megfelel a bejelentett teljesítmény(ek)nek. A 305/2011/EU rendeletnek megfelelően e teljesítménynyilatkozat kiadásáért kizárolag a fent meghatározott gyártó a felelős.

A gyártó nevében és részéről aláíró személy:

Dr. Ronald Mihala, Fejlesztési és termelési igazgatóság vezetője  
Tumlingen, 2024-12-12

Jürgen Grün Vegyi és Minőségért felelős vezérigazgató

Ez a Teljesítmény nyilatkozat különböző nyelveken elkészült. Vitás értelmezés esetén az angol verzió az irányadó.

A melléklet a (nyelvsemleges formában megadott) törvényi előírásokon túl önkéntesen megadott, kiegészítő információkat is tartalmaz angolul.

Translation guidance Essential Characteristics and Performance Parameters for Annexes  
**Mellékletek Alapvető jellemzői és Teljesítményparaméterei fordítási útmutató**

Mechanical resistance and stability (BWR 1)	
<b>Mechanikus szilárdság és stabilitás (BWR 1)</b>	
Characteristic resistance for static and quasi-static loading:	
<b>Karakterisztikus ellenállás értéke statikus és kvázi-statikus terhelésre:</b>	
1	Characteristic resistance to steel failure of a single anchor under tension loading: <b>Karakterisztikus ellenállás értéke egy önálló dübel acél tönkremenetelével szemben húzóterhelés hatására:</b>
2	Characteristic resistance to steel failure of a single anchor under shear loading with and without level arm: <b>Karakterisztikus ellenállás értéke egy önálló dübel acél tönkremenetelével szemben erőkarral illetve erőkar nélküli nyíróterhelés hatására:</b>
3	Characteristic resistance to pull-out failure or brick breakout failure of a single anchor under tension loading, Reduction factor: <b>Karakterisztikus ellenállás értéke egy önálló dübel kihúzódással vagy téglá kitörésével szemben húzóterhelés hatására, Csökkentő tényező:</b>
4	Characteristic resistance to local brick failure or brick breakout failure of a single anchor under shear loading: <b>Karakterisztikus ellenállás értéke egy önálló dübel helyi téglá tönkremenetellel- vagy téglá kitörésével szemben nyíróterhelés hatására:</b>
5	Characteristic resistance to brick breakout failure of an anchor group under tension loading: <b>Karakterisztikus ellenállás értéke egy dübelcsoport téglá kitörésével szemben húzóterhelés hatására:</b>
6	Characteristic resistance to local brick failure or brick breakout failure of an anchor group under shear loading: <b>Karakterisztikus ellenállás értéke egy dübelcsoport helyi téglá tönkremenetellel-vagy kitörésével szemben nyíróterhelés hatására:</b>
7	Edge distances, spacing, member thickness: <b>Peremtávolságok, tengelytávolság, rögzítési alap vastagság:</b>
8	Displacements under tension and shear loading: <b>Elmozdulások húzás és nyírás hatására:</b>
9	Maximum installation torque: <b>Maximális meghúzási nyomaték:</b>
Characteristic resistance and displacements for seismic loading:	
<b>Karakterisztikus ellenállás és elmozdulások értéke szeizmikus terhelésre:</b>	
10	Resistance to tension load, displacements: <b>Ellenállás húzó terhelés esetén, elmozdulások:</b>
11	Resistance to shear load, displacements: <b>Ellenállás nyíró terhelés esetén, elmozdulások:</b>
12	Factor annular gap: <b>Faktor Annuláris rés:</b>
Safety in case of fire (BWR 2)	
<b>Tűzvédelem (BWR 2)</b>	
13	Reaction to fire: <b>Viselkedése tűz esetén:</b>
14	Resistance to fire under tension and shear loading with and without level arm, minimum edge distances and spacing: <b>Ellenállás értéke tűznek kitett húzás és nyírás hatására erőkarral és erőkar nélküli esetnél, minimális perem- és tengelytávolságok értékei:</b>
Hygiene, health and the environment (BWR 3)	
<b>Higiénia, egészség- és környezetvédelem (BWR 3)</b>	
15	Content, emission and/or release of dangerous substances: <b>Veszélyes anyagok tartalma, kibocsátása és / vagy kibocsátása:</b>

## **Specific Part**

### **1 Technical description of the product**

The fischer injection system FIS V Zero for masonry is a bonded anchor (injection type) consisting of a mortar cartridge with injection mortar fischer FIS V Zero, a perforated sleeve and an anchor rod with hexagon nut and washer or an internal threaded rod. The steel elements are made of zinc coated steel, stainless steel or high corrosion resistant steel.

The anchor rod is placed into a drilled hole filled with injection mortar and is anchored via the bond between steel element, injection mortar and masonry and mechanical interlock.

The product description is given in Annex A.

### **2 Specification of the intended use in accordance with the applicable European Assessment Document**

The performances given in Section 3 are only valid if the fastener is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the fastener of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

### **3 Performance of the product and references to the methods used for its assessment**

#### **3.1 Mechanical resistance and stability (BWR 1)**

<b>Essential characteristic</b>	<b>Performance</b>
Characteristic resistance for static and quasi-static loading	See Annexes B 4 to B 7, B 14 C 1 to C 21
Characteristic resistance and displacements for seismic loading	No performance assessed

#### **3.2 Safety in case of fire (BWR 2)**

<b>Essential characteristic</b>	<b>Performance</b>
Reaction to fire	Class A1
Resistance to fire under tension and shear loading with and without lever arm. Minimum edge distances and spacing	No performance assessed

#### **3.3 Hygiene, health and the environment (BWR 3)**

<b>Essential characteristic</b>	<b>Performance</b>
Content, emission and/or release of dangerous substances	No performance assessed

4

**Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base**


In accordance with the European Assessment Document EAD 330076-01-0604 the applicable European legal act is: [97/177/EC].

The system to be applied is: 1


# Installation conditions part 1

## Anchor rods with perforated sleeve FIS H K; Installation in perforated and solid brick masonry

### Pre-positioned installation:



### Installation with render bridge



### Size of the perforated sleeve:

FIS H 12x50 K

FIS H 16x85 K


FIS H 20x85 K

FIS H 12x85 K


FIS H 16x130 K

FIS H 20x130 K

### Push through installation:



### Installation with render bridge



### Size of the perforated sleeve:


FIS H 18x130/200 K

FIS H 22x130/200 K


## Internal threaded anchor FIS E with perforated sleeve FIS H K;

### Installation in perforated and solid brick masonry

### Pre-positioned installation:



### Installation with render bridge



Figures not to scale

$h_{ef}$  = effective anchorage depth

$t_{tol}$  = thickness of unbearing layer (e.g. plaster)

$t_{fix}$  = thickness of fixture

## fischer injection system FIS V Zero for masonry

### Product description

Installation conditions part 1,


Anchor rods and internal threaded anchor with perforated sleeve FIS H K

### Annex A1



## Installation conditions part 2

**Anchor rods without perforated sleeve FIS H K; installation in solid brick masonry and autoclaved aerated concrete (AAC)**

**Pre-positioned installation:**




**Push through installation: Annular gap filled with mortar**




Installation with render bridge

**Internal threaded anchors FIS E without perforated sleeve FIS H K; installation in solid brick masonry**

**Pre-positioned installation:**



**Installation with render bridge**



Figures not to scale

$h_0$  = depth of drill hole

$t_{tol}$  = thickness of unbearing layer (e.g. plaster)

$h_{ef}$  = effective anchorage depth

$t_{fix}$  = thickness of fixture

fischer injection system FIS V Zero for masonry

**Product description**

Installation conditions part 2,



Anchor rods and internal threaded anchor without perforated sleeve

**Annex A2**


## Overview system components part 1

### Injection cartridge (shuttle cartridge) with sealing cap

Size: 360 ml, 825 ml





**Imprint:** fischer FIS V Zero, processing notes, shelf-life, piston travel scale (optional), curing time and processing time (depending on temperature), size, volume



### Injection cartridge (coaxial cartridge) with sealing cap

Size: 100 ml, 150 ml, 300 ml, 380 ml, 400 ml, 410 ml




**Imprint:** fischer FIS V Zero, processing notes, shelf-life, piston travel scale (optional), curing time and processing time (depending on temperature), size, volume




### Static mixer MR Plus or FIS JMR (only 825ml) and extension tube


Static mixer FIS MR Plus




Static mixer FIS JMR



Extension tube



### Cleaning brush BS



### Blow-out pump ABG or ABP



Figures not to scale

### fischer injection system FIS V Zero for masonry


#### Product description

Overview system components part 1: cartridge / static mixer / cleaning tools

#### Annex A3

## Overview system components part 2

### fischer anchor rod




Size: M8, M10, M12, M16

### Internal threaded anchor FIS E



Size: 11x85 M8  
15x85 M10 / M12

### Perforated sleeve FIS H K




Size: FIS H 12x50 K  
FIS H 12x85 K  
FIS H 16x85 K  
FIS H 20x85 K



Size: FIS H 16x130 K  
FIS H 20x130 K

### Perforated sleeve FIS H K (push through installation)



Size:  
FIS H 18x130/200 K  
FIS H 22x130/200 K

### Washer



### Hexagon nut



Figures not to scale

### fischer injection system FIS V Zero for masonry

#### Product description

Overview system components part 2: Metal parts / perforated sleeves FIS H K

#### Annex A4

**Table A5.1: Materials**


Part	Designation	Material		
1	Injection cartridge	Mortar, hardener; filler		
	Steel grade	Steel	Stainless steel R	High corrosion-resistant steel HCR
		zinc plated	acc. to EN 10088-1:2023 Corrosion resistance class CRC III acc. to EN 1993-1-4:2020	acc. to EN 10088-1:2023 Corrosion resistance class CRC V acc. to EN 1993-1-4:2020
2	Anchor rod	Property class 4.6; 4.8; 5.8 or 8.8; EN ISO 898-1: 2013 zinc plated $\geq 5\mu\text{m}$ , EN ISO 4042:2022 Zn5/An(A2K) or hot-dip galvanised EN ISO 10684:2004+AC:2009 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 8\%$ fracture elongation	Property class 50, 70 or 80 EN ISO 3506-1:2020 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; 1.4062; 1.4662; 1.4462; EN 10088-1:2023 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 8\%$ fracture elongation	Property class 50 or 80 EN ISO 3506-1:2020 or property class 70 with $f_{yk} = 560 \text{ N/mm}^2$ 1.4565; 1.4529 EN 10088-1:2023 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 8\%$ fracture elongation
3	Washer ISO 7089:2000	zinc plated $\geq 5\mu\text{m}$ , ISO 4042:2022 Zn5/An(A2K) or hot-dip galvanised EN ISO 10684:2004	1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2023	1.4565; 1.4529 EN 10088-1:2023
4	Hexagon nut	Property class 5 or 8; EN ISO 898-2:2012 zinc plated $\geq 5\mu\text{m}$ , ISO 4042:2022 Zn5/An(A2K) or hot-dip galvanised ISO 10684:2004	Property class 50, 70 or 80 EN ISO 3506-1:2020 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2023	Property class 50, 70 or 80 EN ISO 3506-1:2020 1.4565; 1.4529 EN 10088-1:2023
5	Internal threaded anchor FIS E	Property class 5.8; EN 10277-1:2018 zinc plated $\geq 5\mu\text{m}$ , ISO 4042:2022 Zn5/An(A2K)	Property class 70 EN ISO 3506-1:2020 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2023	Property class 70 EN ISO 3506-1:2020 1.4565; 1.4529 EN 10088-1:2023
6	Commercial standard screw or threaded rod for internal threaded anchor FIS E	Property class 5.8 or 8.8; EN ISO 898-1:2013 zinc plated $\geq 5\mu\text{m}$ , ISO 4042:2022 Zn5/An(A2K)	Property class 70 EN ISO 3506-1:2020 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2023	Property class 70 EN ISO 3506-1:2020 1.4565; 1.4529 EN 10088-1:2023
7	Perforated sleeve FIS H K	PP / PE		

fischer injection system FIS V Zero for masonry

**Product description**  
Materials
**Annex A5**

# Specifications of intended use (part 1)

**Table B1.1:** Overview installation and use

		fischer injection system FIS V Zero for masonry	
Hole drilling with hammer drill mode 		all bricks	
Hole drilling with rotary drill mode 		all bricks	
Static and quasi-static load		all bricks	
Use conditions	dry masonry	all bricks	
Installation	Pre-positioned	Anchor rod or internal threaded anchor (in solid brick masonry and autoclaved aerated concrete)	Perforated sleeve with anchor rod or internal threaded anchor (in perforated and solid brick masonry)  Size: FIS H 12x50 K FIS H 12x85 K FIS H 16x85 K FIS H 16x130 K FIS H 20x85 K FIS H 20x130 K
	Push through	Anchor rod (in solid brick masonry and autoclaved aerated concrete)	Perforated sleeve with anchor rod (in perforated and solid brick masonry)  Size: FIS H 18x130/200 K FIS H 22x130/200 K
Installation and use conditions	condition d/d (dry/dry)	all bricks	
Installation temperature		$T_{i,min} = -10 \text{ }^{\circ}\text{C}$ to $T_{i,max} = +40 \text{ }^{\circ}\text{C}$	
Service temperature	Temperature range Ta	-40 °C to +40 °C	(max. short term temperature +40 °C max. long term temperature +24 °C)
	Temperature range Tb	-40 °C to +80 °C	(max. short term temperature +80 °C max. long term temperature +50 °C)
	Temperature range Tc	-40 °C to +120 °C	(max. short term temperature +120 °C; max. long term temperature +72 °C)
fischer injection system FIS V Zero for masonry			<b>Annex B1</b>
Intended use Specifications (part 1)			

## Specifications of intended use (part 2)

### Anchorages subject to:

- Static and quasi-static loads

### Base materials:

- Solid brick masonry (base material group b) and AAC masonry (base material group d), acc. to Annex B 12
- Hollow brick masonry (base material group c), according to Annex B12
- Minimum thickness of masonry member is  $h_{ef}+30\text{mm}$
- Mortar strength class of the masonry M2,5 at minimum according to EN 998-2:2016
- For other bricks in solid masonry, hollow, perforated masonry or AAC masonry the characteristic resistance of the anchor may be determined by job site tests according to EOTA Technical Report TR 053:2016-04 under consideration of the  $\beta$ -factor according to Annex C20, Table C20.1

Note (only applies to solid bricks and AAC):

The characteristic resistance is also valid for larger brick sizes, higher mean compressive strength and higher mean gross dry density of the masonry unit.

### Temperature Range:

- **T<sub>a</sub>**: from -40°C to +40°C (max. short term temperature +40°C and max. long term temperature +24°C)
- **T<sub>b</sub>**: from -40°C to +80°C (max. short term temperature +80°C and max. long term temperature +50°C)
- **T<sub>c</sub>**: from -40°C to +120°C (max. short term temperature +120°C and max. long term temperature +72°C)

### Use conditions (Environmental conditions):

- Structures subject to dry internal conditions (zinc plated steel, stainless steel or high corrosion resistant steel)
- For all other conditions according to EN 1993-1-4:2006+A2:2020 corresponding to corrosion resistance classes to Annex A5, Table A5.1.

fischer injection system FIS V Zero for masonry

Intended use  
Specifications (part 2)

Annex B2

## Specifications of intended use (part 2 continued)

### Design:

- The anchorages have to be designed in accordance with EOTA Technical Report TR 054:2022-07, Design method A under the responsibility of an experienced in anchorages and masonry work.
- Applies to all bricks, if no other values are specified:

$$N_{Rk} = N_{Rk,b} = N_{Rk,p} = N_{Rk,b,c} = N_{Rk,p,c}$$

$$V_{Rk} = V_{Rk,b} = V_{Rk,c,II} = V_{Rk,c,\perp}$$

For the Calculation of pulling out a brick under tension load  $N_{Rk,pb}$  or pushing out a brick under shear load  $V_{Rk,pb}$  see EOTA Technical Report TR 054:2022-07.

$N_{Rk,s}$ ,  $V_{Rk,s}$  and  $M^0_{Rk,s}$  see annex C1-C3

Factors for job site tests see Annex C20 and displacements see Annex C21

- Verifiable calculation notes and drawings have to be prepared taking account the relevant masonry in the region of the anchorage, the loads to be transmitted and their transmission to the supports of the structure. The position of the anchor is indicated on the design drawings.

### Installation:

- Condition d/d: Installation and use in structures subject to dry, internal conditions
- Hole drilling see Annex B1.1
- In case of aborted hole: The hole shall be filled with mortar
- Bridging of unbearing layer (e.g. plaster) at perforated brick masonry see Annex B6, Table B6.1
- Anchor installation carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters of the site
- Fastening screws or anchor rods (including nut and washer) must comply with the appropriate material and property class of the fischer internal threaded anchor FIS E.
- Minimum curing time see Annex B8, Table B8.2
- Commercial standard threaded rods, washers and hexagon nuts may also be used if the following requirements are fulfilled:

Material dimensions and mechanical properties of the metal parts according to the specifications are given in Annex A5, Table 5.1

Conformation of material and mechanical properties of the metal parts by inspection certificate 3.1 according to EN 10204:2004, the documents shall be stored

Marking of the anchor rod with the effective anchorage depth. This may be done by the manufacturer of the rod or by a person on job site

fischer injection system FIS V Zero for masonry

Intended use  
Specifications (part 2 continued)


Annex B3

**Table B4.1:** Installation parameters for anchor rods in solid bricks and AAC without perforated sleeves FIS H K

Anchor rod	Thread	M8	M10	M12	M16
Nominal drill hole diameter	$d_0$ [mm]	10	12	14	18
Effective anchorage depth $h_{ef}^{(1)}$ in solid brick (cycl. drill hole)	$h_{0,min}=h_{ef,min}$ [mm]			100	
Effective anchorage depth $h_{ef}^{(1)}$ in solid brick (depth of drill hole $h_0 = h_{ef}$ )	$h_{ef,max}$ [mm]			50	
Diameter of clearance hole in the fixture	pre-positioned installation $d_f \leq$ [mm]  push through installation $d_f \leq$ [mm]	9	12	14	18
Diameter of cleaning brush	$d_b \geq$ [mm]			see Table B8.1	
Maximum installation torque	max $T_{inst}$ [Nm]			see parameters of brick Annex C	

<sup>1)</sup>  $h_{ef,min} \leq h_{ef} \leq h_{ef,max}$  is possible.

#### fischer anchor rods M8, M10, M12, M16



#### Marking (on random place) fischer anchor rod:


Steel zinc plated PC <sup>1)</sup> 8.8	• or +	Steel hot-dip galvanised PC <sup>1)</sup> 8.8	•
High corrosion resistant steel HCR PC <sup>1)</sup> 50	•	High corrosion resistant steel HCR PC <sup>1)</sup> 70	-
High corrosion resistant steel HCR PC <sup>1)</sup> 80	(	Stainless steel R property class 50	~
Stainless steel R property class 80	*		

Alternatively: Colour coding according to DIN 976-1: 2016;  
property class 4.6 marking according to EN ISO 898-1:2013

<sup>1)</sup> PC = property class

#### Installation conditions:

##### Anchor rod



Figures not to scale

#### fischer injection system FIS V Zero for masonry

##### Intended use


Installation parameters for anchor rods without perforated sleeve

#### Annex B4

**Table B5.1:** Installation parameters for internal threaded anchors FIS E in solid bricks without perforated sleeves

Internal threaded anchor FIS E	11x85 M8	15x85 M10	15x85 M12
Diameter of anchor $d_H$ [mm]	11	15	
Nominal drill hole diameter $d_0$ [mm]	14	18	
Length of anchor $L_H$ [mm]		85	
Effective anchorage depth $h_0 = h_{ef}$ [mm]		85	
Diameter of cleaning brush $d_b \geq$ [mm]		see Table B8.1	
Maximum installation torque $\max T_{inst}$ [Nm]		see parameters of brick Annex C4-C16	
Diameter of clearance hole in the fixture $d_f$ [mm]	9	12	14
Screw-in depth $l_E, \text{min}$ [mm]	8	10	12
$l_E, \text{max}$ [mm]		60	

### fischer Internal threaded anchor FIS E




#### Marking:

Size, e.g. **M8**, Stainless steel: R, e.g. **M8 R**, High corrosion-resistant steel: HCR, e.g. **M8 HCR**

#### Installation conditions:

##### Internal threaded anchor



Figures not to scale

#### fischer injection system FIS V Zero for masonry

##### Intended use

Installation parameters for internal threaded rods FIS E without perforated sleeve

#### Annex B5

**Table B6.1:** Installation parameters for anchor rods and internal threaded anchors FIS E with perforated sleeves FIS H K (pre-positioned installation)

perforated sleeve FIS H K	12x50	12x85 <sup>2)</sup>	16x85	16x130 <sup>2)</sup>	20x85	20x130 <sup>2)</sup>
Nominal drill hole diameter $d_0 = D_{\text{sleeve,nom}}$		12		16		20
Depth of drill hole	$h_0$ [mm]	55	90	90	135	90
Effective anchorage depth	$h_{\text{ef,min}}$ [mm]	50	65	85	110	85
	$h_{\text{ef,max}}$ [mm]	50	85	85	130	85
Size of threaded rod	[ - ]	M8		M8 and M10		M12 and M16
Size of internal threaded anchor FIS E	-	-	11x85	-	15x85	-
Diameter of cleaning brush <sup>1)</sup>	$d_b \geq$ [mm]			see Table B8.1		
Maximum installation torque	max $T_{\text{inst}}$ [Nm]			see parameters of brick Annex C		

<sup>1)</sup> Only for solid areas in hollow bricks and solid bricks.


<sup>2)</sup> Bridging of unbearing layer (e.g. plaster) is possible. When reducing the effective anchorage depth  $h_{\text{ef,min}}$ , the values of the next shorter perforated sleeve of the same diameter must be used. The smaller value of characteristic resistance must be taken.

#### Perforated sleeve

FIS H 12x50 K; FIS H 12x85 K; FIS H 16x85 K; FIS H 16x130 K;  
FIS H 20x85 K; FIS H 20x130 K


#### Marking:

Size  $D_{\text{sleeve,nom}} \times L_{\text{sleeve}}$   
(e.g.: 16x85)




#### fischer Internal threaded anchor FIS E

FIS E 11x85 M8




FIS E 15x85 M10, FIS E 15x85 M12




#### Installation conditions:

##### Anchor rod with perforated sleeve



##### Internal threaded anchor with perforated sleeve



Figures not to scale

#### fischer injection system FIS V Zero for masonry

##### Intended use

Installation parameters for anchor rods and internal threaded anchors FIS E with perforated sleeve FIS H K (pre-positioned installation)

##### Annex B6


**Table B7.1:** Installation parameters for anchor rods with perforated push through sleeves (push through installation)

Perforated sleeve FIS H K	18x130/200	22x130/200	
Nominal sleeve diameter $D_{\text{ sleeve,nom }}$ [mm]	16	20	
Nominal drill hole diameter $d_0$ [mm]	18	22	
Depth of drill hole $h_0$ [mm]	135		
Effective anchorage depth $h_{\text{ef}}$ [mm]		$\geq 130$	
Diameter of cleaning brush <sup>1)</sup> $d_b \geq$ [mm]		see Table B8.1	
Size of threaded rod [-]	M10	M12	M16
Maximum installation torque max $T_{\text{inst}}$ [Nm]		see parameters of brick Annex C	
Thickness of fixture $t_{\text{fix,max}}$ [mm]		200	

<sup>1)</sup> Only for solid areas in hollow bricks and solid bricks.


#### Perforated push through sleeve

FIS H 18x130/200 K; FIS H 22x130/200 K



#### Installation conditions:

##### Anchor rod with perforated sleeve



Figures not to scale

fischer injection system FIS V Zero for masonry

Intended use


Installation parameters for anchor rods with perforated push through sleeves (push through installation)

**Annex B7**

**Table B8.1:** Parameters of the cleaning brush BS (steel brush with steel bristles)

The size of the cleaning brush refers to the drill hole diameter

Nominal drill hole diameter	$d_0$ [mm]	10	12	14	16	18	20	22
Steel brush diameter	$d_b$ [mm]	11	14	16	20	20	25	25



Only for solid areas in hollow bricks or solid bricks and autoclaved aerated concrete

**Table B8.2:** Maximum processing times and minimum curing times

(During the curing time of the mortar the temperature of the anchoring base may not fall below the listed minimum temperature)

Temperature at anchoring base [°C]	Maximum processing time $t_{work}$	Minimum curing time $t_{cure}$
	FIS V Zero	FIS V Zero
-10 to -5 <sup>1)</sup>	6 h	72 h
> -5 to 0 <sup>1)</sup>	2 h	24 h
> 0 to 5 <sup>1)</sup>	45 min	12 h
> 5 to 10	20 min	6 h
> 10 to 15	8 min	3 h
> 15 to 20	5 min	2 h
> 20 to 25	3 min	1 h
> 25 to 30	2 min	45 min
> 30 to 40	1 min	30 min

<sup>1)</sup> Minimum cartridge temperature +5°C

Figures not to scale

fischer injection system FIS V Zero for masonry

**Intended use**











Parameters of the cleaning brush (steel brush)

Processing time and curing time

**Annex B8**

# Installation instruction part 1

## Installation in solid brick and autoclaved aerated concrete without perforated sleeve

1		Drill the hole (drilling method see Annex C of the respective brick) depth of drill hole $h_0$ and nominal drill hole diameter $d_0$ see <b>Table B4.1; B5.1</b>		
2				Blow out the drill hole twice. Brush twice and blow out twice again.
3		Remove the sealing cap. Screw on the static mixer. (the spiral in the static mixer must be clearly visible)		
4		Place the cartridge into a suitable dispenser		Extrude approximately 10 cm of material out until the resin is evenly grey in colour. Do not use mortar that is not uniformly grey.
5		Fill approximately 2/3 of the drill hole with mortar beginning from the bottom of the hole. <sup>1)</sup> Avoid bubbles.		For push through installation fill the annular gap with mortar.
6		Only use clean and oil-free metal parts. Mark the setting depth. Insert the anchor rod or internal threaded anchor FIS E by hand.  Recommendation: Rotation back and forth of the anchor rod or internal threaded anchor FIS E makes pushing easy.  When reaching the setting depth mark, excess mortar must emerge from the mouth of the drill hole.		
7		Do not touch. Minimum curing time see <b>Table B8.2</b>		Mounting the fixture. max $T_{inst}$ see parameter of brick.

<sup>1)</sup> Exact volume of mortar see manufacturer's specifications

fischer injection system FIS V Zero for masonry

Intended use







Installation instruction part 1

Installation in solid brick without perforated sleeve

Annex B9

## Installation instruction part 2

### Installation in perforated or solid brick with perforated sleeve (pre-positioned installation)

1		Drill the hole (drilling method see Annex C of the respective brick). depth of drill hole $h_0$ and nominal drill hole diameter $d_0$ see <b>Table B6.1</b>	When install perforated sleeves in solid bricks or solid areas of hollow bricks, also clean the hole by blowing out and brushing.
2		Remove the sealing cap. Screw on the static mixer. (the spiral in the static mixer must be clearly visible)	
3		Place the cartridge into a suitable dispenser.	 Extrude approximately 10 cm of material out until the resin is evenly grey in colour. Do not use mortar that is not uniformly grey.
4		Insert the perforated sleeve flush with the surface of the masonry or plaster.	 Fill the perforated sleeve completely with mortar beginning from the bottom of the hole. <sup>1)</sup>
5		Only use clean and oil-free metal parts. Mark the setting depth. Insert the anchor rod or the internal threaded anchor FIS E by hand. Recommendation: Rotation back and forth of the anchor rod or internal threaded anchor FIS E makes pushing easy until reaching the setting depth mark (anchor rod) or flush with the surface (internal threaded anchor).	
6		Do not touch. Minimum curing time see <b>Table B8.2</b>	 max $T_{inst}$ Mounting the fixture. max $T_{inst}$ see parameter of brick.

<sup>1)</sup> Exact volume of mortar see manufacturer's specification.

fischer injection system FIS V Zero for masonry

Intended use











Installation instruction part 2

Installation in perforated or solid brick with perforated sleeve (pre-positioned installation)

Annex B10

# Installation instruction part 3

## Installation in perforated or solid brick with perforated sleeve (push through installation)

1		Push the movable stop up to the correct thickness of fixture and cut the overlap.		Drill the hole through the fixture. Depth of drill hole ( $h_0 + t_{fix}$ ) and nominal drill hole diameter $d_0$ see Table B7.1
2		Remove the sealing cap. Screw on the static mixer. (the spiral in the static mixer must be clearly visible)		
3		Place the cartridge into a suitable dispenser.		Extrude approximately 10 cm of material out until the resin is evenly grey in colour. Do not use mortar that is not uniformly grey.
4		Insert the perforated sleeve flush with the surface of the fixture into the drill hole.		Fill the sleeve with mortar beginning from the bottom of the hole. <sup>1)</sup> For deep drill holes use an extension tube.
5		Only use clean and oil-free metal parts. Mark the setting depth. Insert the anchor rod by hand.  Recommendation: Rotation back and forth of the anchor rod makes pushing easy until reaching the setting depth mark (anchor rod).		
6		Do not touch. Minimum curing time see Table B8.2		Mounting the fixture. max $T_{inst}$ see parameter of brick.

<sup>1)</sup> Exact volume of mortar see manufacturer's specification.

fischer injection system FIS V Zero for masonry

Intended use

Installation instruction part 3

Installation in perforated or solid brick with perforated sleeve (push through installation)

Annex B11


Appendix 18 / 42

**Table B12.1:** Overview of assessed bricks


Kind of masonry	Brick format [mm]	Mean compressive strength [N/mm <sup>2</sup> ]	Main country of origin	Mean gross dry density ρ [kg/dm <sup>3</sup> ]	Annex
<b>Solid brick Mz</b>					
<b>Solid brick Mz</b>	≥ 230x108x55	36 - 48	Denmark	≥2,0	C4/C5
<b>Solid calcium silicate (sand - lime) brick KS / perforated calcium silicate (sand - lime) brick KSL</b>					
<b>Solid calcium silicate brick KS</b>	NF	≥240x115x71	8- 20	Germany	≥2,0
<b>Perforated calcium silicate brick KSL</b>	3DF	240x175x113	8 - 16	Germany	≥1,6
<b>Vertical perforated brick HLz</b>					
<b>Vertical perforated brick HLz</b>	230x108x55	6 - 16	Denmark	≥1,6	C12/C13
<b>Lightweight aggregate concrete hollow block Hbl</b>					
<b>Lightweight aggregate concrete hollow block Hbl</b>	500x200x200	2 - 4	France	≥1,0	C14/C15
<b>Autoclaved aerated concrete</b>					
AAC	PP2 / AAC	2		≥0,35	
	PP4 / AAC	4	Germany	≥0,5	
	PP6 / AAC	6		≥0,65	C16-C19

**Table B12.2:** Overview dimensions of perforated and hollow bricks


Perforated calcium silicate (sand-lime) brick KSL, 3DF, EN 771-2:2011+A1:2015; e.g. KS Wemding according to Annex C8



Lightweight aggregate concrete hollow block Hbl, EN 771-3: 2011+A1:2015; e.g. Sepa according to Annex C 14



Vertical perforated brick HLz, EN 771-1: 2011+A1:2015; e.g. Wienerberger according to Annex C 12



Measures in [mm]

Figures not to scale

fischer injection system FIS V Zero for masonry

Intended use


Overview of assessed bricks

Overview dimensions of perforated and hollow bricks

**Annex B12**

Appendix 19 / 42

## Spacing and edge distance



\* Only, if vertical joints are not completely filled with mortar

- $s_{min} \parallel$  = Minimum spacing parallel to horizontal joint
- $s_{min} \perp$  = Minimum spacing perpendicular to horizontal joint
- $s_{cr} \parallel$  = Characteristic spacing parallel to horizontal joint
- $s_{cr} \perp$  = Characteristic spacing perpendicular to horizontal joint
- $c_{cr} = c_{min}$  = Edge distance
- $\alpha_{g,N}(s_{min} \parallel)$  = Group factor for tension load, anchor group parallel to horizontal joint
- $\alpha_{g,V}(s_{min} \parallel)$  = Group factor for shear load, anchor group parallel to horizontal joint
- $\alpha_{g,N}(s_{min} \perp)$  = Group factor for tension load, anchor group vertical to horizontal joint
- $\alpha_{g,V}(s_{min} \perp)$  = Group factor for shear load, anchor group vertical to horizontal joint

## Spacing and edge distance (continuation)

For  $s \geq s_{cr}$   $\alpha_g = 2$

For  $s_{min} \leq s < s_{cr}$   $\alpha_g$  according to installation parameters of brick Annex C

Group of 2 anchors

$$N^g_{Rk} = \alpha_{g,N} \cdot N_{Rk}; \quad V^g_{Rk,b} = V^g_{Rk,c,II} = V^g_{Rk,c,\perp} = \alpha_{g,V} \cdot V_{Rk}$$

Group of 4 anchors

$$N^g_{Rk} = \alpha_{g,N} (s_{min,II}) \cdot \alpha_{g,N} (s_{min,\perp}) \cdot N_{Rk};$$

$$V^g_{Rk,b} = V^g_{Rk,c,II} = V^g_{Rk,c,\perp} = \alpha_{g,V} (s_{min,II}) \cdot \alpha_{g,V} (s_{min,\perp}) \cdot V_{Rk}$$

with  $N_{Rk}$  and  $\alpha_{g,N}$  depending on  $s_{min,II}$  or  $s_{min,\perp}$  acc. to Annex C

with  $V_{Rk}$  and  $\alpha_{g,V}$  depending on  $s_{min,II}$  or  $s_{min,\perp}$  acc. to Annex C

fischer injection system FIS V Zero for masonry

Intended use  
Spacing and edge distance (continuation)

Annex B14

**Table C1.1: Characteristic resistance to steel failure of a single anchor under tension loading of fischer anchor rods and standard threaded rods**

Anchor rod / standard threaded rod		M8 <sup>3)</sup>	M10 <sup>3)</sup>	M12	M16
<b>Characteristic resistance to steel failure under tension loading</b>					
Characteristic resistance $N_{Rk,s}$	Steel zinc plated Stainless steel R and High corrosion resistant steel HCR	Property class 4.6 4.8 5.8 8.8 50 70 80	[kN] 15(13) 15(13) 19(17) 29(27) 19 26 30	15(13)	23(21)
				23(21)	33
				33	63
				43	79
				68	126
				43	79
				59	110
				68	126
<b>Partial factors<sup>1)</sup></b>					
$\gamma_{Ms,N}$	Steel zinc plated Stainless steel R and High corrosion resistant steel HCR	Property class 4.6 4.8 5.8 8.8 50 70 80	[-] 2,00 1,50 1,50 1,50 2,86 1,50 <sup>2)</sup> / 1,87 1,60	2,00	
				1,50	
				1,50	
				1,50	
				2,86	
				1,50 <sup>2)</sup> / 1,87	
				1,60	

<sup>1)</sup> In absence of other national regulations

<sup>2)</sup> Only for fischer anchor rod FIS A made of high corrosion-resistant steel HCR

<sup>3)</sup> Values in brackets are valid for undersized threaded rods with smaller stress area  $A_s$  for hot dip galvanised standard threaded rods according to EN ISO 10684:2004+AC:2009

fischer injection system FIS V Zero for masonry

#### Performances

Characteristic resistance to steel failure of a single anchor under tension loading of fischer anchor rods and standard threaded rods

#### Annex C1

**Table C2.1:** Characteristic resistance to **steel failure** of a single anchor under shear loading with and without lever arm of **fischer anchor rods** and **standard threaded rods**

Anchor rod / standard threaded rod		M8 <sup>3)</sup>	M10 <sup>3)</sup>	M12	M16		
<b>Characteristic resistance to steel failure under shear loading</b>							
<b>without lever arm</b>							
Characteristic resistance $V_{Rk,s}$	Property class	4.6	[kN]	9(8)	14(13)		
		4.8		9(8)	14(13)		
		5.8		11(10)	17(16)		
		8.8		15(13)	23(21)		
		50	[Nm]	9	15		
		70		13	20		
		80		15	23		
					34		
<b>with lever arm</b>							
Characteristic resistance $M_{Rk,s}$	Property class	4.6	[Nm]	15(13)	30(27)		
		4.8		15(13)	30(27)		
		5.8		19(16)	37(33)		
		8.8		30(26)	60(53)		
		50	[-]	19	37		
		70		26	52		
		80		30	60		
					105		
<b>Partial factors<sup>1)</sup></b>							
Partial factors $\gamma_{Ms,V}$	Property class	4.6	[-]	1,67			
		4.8		1,25			
		5.8		1,25			
		8.8		1,25			
		50	[-]	2,38			
		70		1,25 <sup>2)</sup> / 1,56			
		80		1,33			
1) In absence of other national regulations							
2) Only for fischer anchor rod FIS A made of high corrosion-resistant steel HCR							
3) Values in brackets are valid for undersized threaded rods with smaller stress area $A_s$ for hot dip galvanised standard threaded rods (M8 resp. M10) according to EN ISO 10684:2004+AC:2009.							
fischer injection system FIS V Zero for masonry							
<b>Performances</b>							
Characteristic resistance to steel failure of a single anchor under shear loading with and without lever arm of fischer anchor rods and standard threaded rods							
<b>Annex C2</b>							
Appendix 23 / 42							

**Table C3.1: Characteristic resistance to steel failure of a single anchor under tension / shear loading of internal threaded anchors FIS E**

fischer internal threaded anchor FIS E			M8	M10	M12	
<b>Characteristic resistance to steel failure under tension loading</b>						
Characteristic resistance with screw N <sub>Rk,s</sub>	Property class	5.8	[kN]	18	29	
	Property class 70	R		26	41	
		HCR		26	41	
<b>Partial factors <sup>1)</sup></b>						
Partial factors γ <sub>Ms,N</sub>	Property class	5.8	[-]	1,50		
	Property class 70	R		1,87		
		HCR		1,87		
<b>Characteristic resistance to steel failure under shear loading</b>						
<b>without lever arm</b>						
Characteristic resistance with screw V <sub>Rk,s</sub>	Property class	5.8	[kN]	9	15	
	Property class 70	R		13	20	
		HCR		13	20	
<b>with lever arm</b>						
Characteristic resistance M <sup>0</sup> <sub>Rk,s</sub>	Property class	5.8	[Nm]	19	37	
	Property class 70	R		26	52	
		HCR		26	52	
<b>Partial factors <sup>1)</sup></b>						
Partial factors γ <sub>Ms,V</sub>	Property class	5.8	[-]	1,25		
	Property class 70	R		1,56		
		HCR		1,56		

<sup>1)</sup> In absence of other national regulations


#### fischer injection system FIS V Zero for masonry

##### Performances

Characteristic resistance to steel failure of a single anchor under tension / shear loading of internal threaded anchors FIS E

##### Annex C3

# Solid brick Mz, EN 771-1: 2011+A1:2015



Solid brick Mz, EN 771-1: 2011+A1:2015		
Producer	e.g. Wienerberger	
Nominal dimensions [mm]	length L	width W
≥ 230	≥ 108	≥ 55
Mean gross dry density $\rho$ [kg/dm <sup>3</sup> ]	≥ 2,0	
Normalised mean compressive strength [N/mm <sup>2</sup> ]	36 / 48	
Standard	EN 771-1: 2011+A1:2015	

Table C4.1: Installation parameters

Anchor rod	M8	M10	M12	M16	-	-
Internal threaded anchor FIS E	-	-	-	-	M8	M10   M12
					11x85	15x85
<b>Anchor rod and internal threaded anchor FIS E without perforated sleeve</b>						
Effective anchorage depth $h_{\text{ef}}$ [mm]	50	80	50	80	50	85
Max. installation torque $\text{max } T_{\text{inst}}$ [Nm]			10			10
<b>General installation parameters</b>						
Edge distance $c_{\min} = c_{\text{cr}}$				100		
Spacing	$s_{\min \parallel}$			100		
	$s_{\text{cr} \parallel}$	[mm]		3 x $h_{\text{ef}}$		
	$s_{\min \perp}$			100		
	$s_{\text{cr} \perp}$			3 x $h_{\text{ef}}$		
<b>Drilling method</b>						
Hole drilling with rotary drill mode or hammer drilling with hard metal hammer drill						

Table C4.2: Group factors

Anchor rods	M8	M10	M12	M16	-	-
Internal threaded anchor FIS E	-	-	-	-	M8	M10   M12
					11x85	15x85
Group factors	$\alpha_{g,N} (s_{\min \parallel})$			1,81		
	$\alpha_{g,V} (s_{\min \parallel})$			1,49		
	$\alpha_{g,N} (s_{\min \perp})$			1,74		
	$\alpha_{g,V} (s_{\min \perp})$			1,49		

fischer injection system FIS V Zero for masonry

**Performances**  
Solid brick Mz, dimensions, installation parameters

**Annex C4**

**Table C5.1:** Characteristic resistance to pull-out failure or brick breakout failure of a single anchor under tension loading

Anchor rod	M8	M10	M12	M16	-	-
Internal threaded anchor FIS E	-	-	-	-	M8	M10 M12
					11x85	15x85

Tension resistance  $N_{Rk} = N_{Rk,p} = N_{Rk,b} = N_{Rk,p,c} = N_{Rk,b,c}$  [kN] depending on the normalised mean compressive strength  $f_b$ ; (temperature range 24/40°C)

Normalised mean compressive strength $f_b$	Effective anchorage depth $h_{ef}$ [mm]								
	50	80	50	80	50	80	50	80	85
36 N/mm <sup>2</sup>	2,5	3,0	3,0	3,0	3,0	3,0	3,0	4,5	2,5
48 N/mm <sup>2</sup>	3,0	3,5	3,5	3,5	3,5	3,5	3,5	5,0	3,0

Tension resistance  $N_{Rk} = N_{Rk,p} = N_{Rk,b} = N_{Rk,p,c} = N_{Rk,b,c}$  [kN] depending on the normalised mean compressive strength  $f_b$  (temperature range 50/80°C and 72/120°C)

Normalised mean compressive strength $f_b$	Effective anchorage depth $h_{ef}$ [mm]								
	50	80	50	80	50	80	50	80	85
36 N/mm <sup>2</sup>	1,5	2,0	2,0	2,0	2,0	2,0	2,0	3,5	1,5
48 N/mm <sup>2</sup>	1,5	2,5	2,5	2,5	2,5	2,5	2,5	4,0	1,5

**Table C5.2:** Characteristic resistance to local brick failure or brick edge failure of a single anchor under shear loading

Anchor rod	M8	M10	M12	M16	-	-
Internal threaded anchor FIS E	-	-	-	-	M8	M10 M12
					11x85	15x85

Shear resistance  $V_{Rk} = V_{Rk,b} = V_{Rk,c,II} = V_{Rk,c,\perp}$  [kN] depending on the normalised mean compressive strength  $f_b$ ; (temperature range 24/40°C, 50/80°C and 72/120°C)

Normalised mean compressive strength $f_b$	Effective anchorage depth $h_{ef}$ [mm]								
	50	80	50	80	50	80	50	80	85
36 N/mm <sup>2</sup>	2,5	4,5	2,5	4,5	2,5	4,5	2,5	4,5	2,5
48 N/mm <sup>2</sup>	3,0	5,0	3,0	5,0	3,0	5,0	3,0	5,0	3,0


Factor for job site tests see annex C20 and displacements see annex C21

fischer injection system FIS V Zero for masonry

**Performances**  
Solid brick Mz, Characteristic resistance under tension and shear loading

**Annex C5**

# Solid calcium silicate (sand-lime) brick KS, NF, EN 771-2: 2011+A1:2015



Solid calcium silicate (sand-lime) brick KS, NF, EN 771-2: 2011+A1:2015			
Producer	---		
Nominal dimensions [mm]	length L	width W	height H
≥ 240	≥ 115	≥ 71	---
Mean gross dry density [kg/dm <sup>3</sup> ]	≥ 2,0		
Normalised mean compressive strength [N/mm <sup>2</sup> ]	12 / 16 / 20		
Standard	EN 771-2: 2011+A1:2015		

Table C6.1: Installation parameters

Anchor rod	M8	M10	M12	M16	-	-						
Internal threaded anchor FIS E	-	-	-	-	M8	M10 M12						
<b>Anchor rod and internal threaded anchor FIS E without perforated sleeve</b>												
Effective anchorage depth $h_{\text{ef}}$ [mm]	50	80	50	80	50	85						
Max. installation torque $\max T_{\text{inst}}$ [Nm]	8		10		8	10						
<b>General installation parameters</b>												
Edge distance $C_{\min} = C_{\text{cr}}$	[mm]	100										
$s_{\min \parallel}$		100										
$s_{\text{cr} \parallel}$		3 × $h_{\text{ef}}$										
$s_{\min \perp}$		100										
$s_{\text{cr} \perp}$		3 × $h_{\text{ef}}$										
<b>Drilling method</b>												
Hole drilling with rotary drill mode or hammer drilling with hard metal hammer drill												

Table C6.2: Group factors

Anchor rod	M8	M10	M12	M16	-	-
Internal threaded anchor FIS E	-	-	-	-	M8	M10 M12
					11x85	15x85
Group factors	$\alpha_{g,N}(s_{\min \parallel})$	[-]	1,67			
	$\alpha_{g,V}(s_{\min \parallel})$		1,26			
	$\alpha_{g,N}(s_{\min \perp})$		1,67			
	$\alpha_{g,V}(s_{\min \perp})$		2,0			

fischer injection system FIS V Zero for masonry

## Performances

Solid calcium silicate (sand-lime) brick KS, NF, dimensions, installation parameters

## Annex C6

# Solid calcium silicate (sand-lime) brick KS, NF, EN 771-2: 2011+A1:2015

**Table C7.1:** Characteristic resistance to pull-out failure or brick breakout failure of a single anchor under tension loading

Anchor rod	M8	M10	M12	M16	-	-
Internal threaded anchor FIS E	-	-	-	-	M8	M10 M12
					11x85	15x85

Tension resistance  $N_{Rk} = N_{Rk,p} = N_{Rk,b} = N_{Rk,p,c} = N_{Rk,b,c}$  [kN] depending on the normalised mean compressive strength  $f_b$ ; (temperature range 24/40°C)

Normalised mean compressive strength $f_b$	Effective anchorage depth $h_{ef}$ [mm]									
	50	80	50	80	50	80	50	80	85	85
12 N/mm <sup>2</sup>	2,0	2,0	2,5	4,5	2,0	4,5	2,0	2,0		2,0
16 N/mm <sup>2</sup>	2,5	2,5	2,5	5,0	2,5	5,0	2,5	2,5		2,5
20 N/mm <sup>2</sup>	2,5	3,0	3,0	6,0	2,5	6,0	2,5	3,0		2,5

Tension resistance  $N_{Rk} = N_{Rk,p} = N_{Rk,b} = N_{Rk,p,c} = N_{Rk,b,c}$  [kN] depending on the normalised mean compressive strength  $f_b$ ; (temperature range 50/80°C and 72/120°C)

Normalised mean compressive strength $f_b$	Effective anchorage depth $h_{ef}$ [mm]									
	50	80	50	80	50	80	50	80	85	85
12 N/mm <sup>2</sup>	1,5	1,5	1,5	3,0	1,5	3,0	1,5	1,5		1,5
16 N/mm <sup>2</sup>	1,5	1,5	2,0	3,5	1,5	3,5	1,5	1,5		1,5
20 N/mm <sup>2</sup>	2,0	2,0	2,0	4,0	2,0	4,0	2,0	2,0		2,0

**Table C7.2:** Characteristic resistance to local brick failure or brick edge failure of a single anchor under shear loading

Anchor rod	M8	M10	M12	M16	-	-
Internal threaded anchor FIS E	-	-	-	-	M8	M10 M12
					11x85	15x85

Shear resistance  $V_{Rk} = V_{Rk,b} = V_{Rk,c,II} = V_{Rk,c,\perp}$  [kN] depending on the normalised mean compressive strength  $f_b$ ; (temperature range 24/40°C, 50/80°C and 72/120°C)

Normalised mean compressive strength $f_b$	Effective anchorage depth $h_{ef}$ [mm]									
	50	80	50	80	50	80	50	80	85	85
12 N/mm <sup>2</sup>	3,5	3,5	4,5	4,5	3,5	4,0	3,5	4,0	3,5	3,5
16 N/mm <sup>2</sup>	4,0	4,0	5,0	5,0	4,0	4,5	4,0	4,5	4,0	4,0
20 N/mm <sup>2</sup>	4,5	4,5	6,0	6,0	4,5	5,0	4,5	5,0	4,5	4,5

Factor for job site tests see annex C20 and displacements see annex C21


fischer injection system FIS V Zero for masonry

## Performances


Solid calcium silicate (sand-lime) brick KS, NF, Characteristic resistance under tension and shear loading

## Annex C7

# Perforated calcium silicate (sand-lime) brick KSL, 3DF, EN 771-2: 2011+A1:2015



Perforated calcium silicate (sand-lime) brick KSL, 3DF, EN 771-2: 2011+A1:2015		
Producer	e.g. KS Wemding	
Nominal dimensions [mm]	length L	width W
	240	175
Mean gross dry density $\rho$ [kg/dm <sup>3</sup> ]	$\geq 1,6$	
Normalised mean compressive strength [N/mm <sup>2</sup> ]	6 / 8 / 10 / 12 / 16	
Standard	EN 771-2: 2011+A1:2015	



Dimensions see  
also Annex B12

**Table C8.1:** Installation parameters  
(Pre-positioned installation with perforated sleeve FIS H K)

Anchor rod	M8	M8	-	M8	M10	M8	M10	-	M12	M16	M12	M16
Internal threaded anchor FIS E	-	-	M8					M10	M12			
			11x85					15x85				

## Perforated sleeve FIS H K

Perforated sleeve FIS H K	12x50	12x85	16x85	16x130	20x85	20x130
---------------------------	-------	-------	-------	--------	-------	--------

## Anchor rod and internal threaded anchor FIS E with perforated sleeve FIS H K

Max. installation torque	max T <sub>inst</sub> [Nm]	8	8	8	8	10	8	10	10
--------------------------	----------------------------	---	---	---	---	----	---	----	----

## General installation parameters

Edge distance	$c_{min} = c_{cr}$		100
	$s_{min \parallel}$		100
Spacing	$s_{cr \parallel}$	[mm]	240
	$s_{min \perp}$		100
	$s_{cr \perp}$		115

## Drilling method

Hole drilling with rotary drill mode or hammer drilling with hard metal hammer drill

**Table C8.2:** Group factors

Anchor rod	M8	M8	-	M8	M10	M8	M10	-	M12	M16	M12	M16
Internal threaded anchor FIS E	-	-	M8					M10	M12			
			11x85					15x85				
Perforated sleeve FIS H K	12x50	12x85	16x85	16x130		20x85		20x130				
Group factors	$\alpha_{g,N} (s_{min \parallel})$	[-]										
	$\alpha_{g,V} (s_{min \parallel})$											
	$\alpha_{g,N} (s_{min \perp})$											
	$\alpha_{g,V} (s_{min \perp})$											

fischer injection system FIS V Zero for masonry

## Performances

Perforated calcium silicate (sand-lime) brick KSL, 3DF, dimensions, installation parameters

## Annex C8

# Perforated calcium silicate (sand-lime) brick KSL, 3DF, EN 771-2: 2011+A1:2015

**Table C9.1:** Installation parameters  
(Push through installation with perforated sleeve FIS H K)

Anchor rod	M10	M12	M16
Perforated sleeve FIS H K	18x130/200		22x130/200
<b>Anchor rod with perforated sleeve FIS H K</b>			
Max. installation torque	max $T_{inst}$ [Nm]		10
<b>General installation parameters</b>			
Edge distance $c_{min} = c_{cr}$		100	
$s_{min \parallel}$		100	
Spacing	$s_{cr \parallel}$ [mm]	240	
$s_{min \perp}$		100	
$s_{cr \perp}$		115	

## Drilling method

Hole drilling with rotary drill mode or hammer drilling with hard metal hammer drill

**Table C9.2:** Group factors

Anchor rod	M10	M12	M16
Perforated sleeve FIS H K	18x130/200		22x130/200
Group factors	$\alpha_{g,N} (s_{min \parallel})$	1,14	
	$\alpha_{g,V} (s_{min \parallel})$	1,51	
	$\alpha_{g,N} (s_{min \perp})$	1,14	
	$\alpha_{g,V} (s_{min \perp})$	1,54	

fischer injection system FIS V Zero for masonry

## Performances

Perforated calcium silicate (sand-lime) brick KSL, 3DF, dimensions, installation parameters

## Annex C9

**Perforated calcium silicate (sand-lime) brick KSL, 3DF, EN 771-2: 2011+A1:2015**
**Table C10.1:** Characteristic resistance to pull-out failure or brick breakout failure of a single anchor under tension loading (Pre-positioned installation)

<b>Anchor rod</b>	<b>M8</b>	<b>M8</b>	<b>-</b>	<b>M8</b>	<b>M10</b>	<b>M8</b>	<b>M10</b>	<b>-</b>	<b>M12</b>	<b>M16</b>	<b>M12</b>	<b>M16</b>
<b>Internal threaded anchor FIS E</b>	<b>-</b>	<b>-</b>	<b>M8</b>	<b>11x85</b>	<b>-</b>	<b>-</b>	<b>M10</b>	<b>M12</b>	<b>-</b>	<b>15x85</b>	<b>-</b>	<b>-</b>
<b>Perforated sleeve FIS H K</b>	<b>12x50</b>	<b>12x85</b>		<b>16x85</b>		<b>16x130</b>		<b>20x85</b>		<b>20x130</b>		

**Tension resistance  $N_{Rk} = N_{Rk,p} = N_{Rk,b} = N_{Rk,p,c} = N_{Rk,b,c}$  [kN] depending on the normalised mean compressive strength  $f_b$ ; (temperature range 24/40°C)**

Norm. mean compressive strength $f_b$						
<b>6 N/mm<sup>2</sup></b>	1,2	0,9	2,0	0,9	2,0	
<b>8 N/mm<sup>2</sup></b>	1,5	1,2	2,5	1,2	2,5	
<b>10 N/mm<sup>2</sup></b>	1,5	1,5	3,0	1,5	3,0	
<b>12 N/mm<sup>2</sup></b>	2,0	1,5	3,5	1,5	3,5	
<b>16 N/mm<sup>2</sup></b>	2,5	2,0	4,5	2,0	4,5	

**Tension resistance  $N_{Rk} = N_{Rk,p} = N_{Rk,b} = N_{Rk,p,c} = N_{Rk,b,c}$  [kN] depending on the normalised mean compressive strength  $f_b$ ; (temperature range 50/80°C and 72/120°C)**

Norm. mean compressive strength $f_b$						
<b>6 N/mm<sup>2</sup></b>	0,6	0,75	1,5	0,75	1,5	
<b>8 N/mm<sup>2</sup></b>	0,75	0,9	2,0	0,9	2,0	
<b>10 N/mm<sup>2</sup></b>	0,9	0,9	2,5	0,9	2,5	
<b>12 N/mm<sup>2</sup></b>	0,9	1,2	2,5	1,2	2,5	
<b>16 N/mm<sup>2</sup></b>	1,2	1,5	3,5	1,5	3,5	

**Table C10.2:** Characteristic resistance to pull-out failure or brick breakout failure of a single anchor under tension loading (Push through installation)

<b>Anchor rod</b>	<b>M10</b>	<b>M12</b>	<b>M16</b>
<b>Perforated sleeve FIS H K</b>		<b>18x130/200</b>	<b>22x130/200</b>

**Tension resistance  $N_{Rk} = N_{Rk,p} = N_{Rk,b} = N_{Rk,p,c} = N_{Rk,b,c}$  [kN] depending on the normalised mean compressive strength  $f_b$ ; (temperature range 24/40°C)**

Norm. mean compressive strength $f_b$						
<b>6 N/mm<sup>2</sup></b>		2,0				
<b>8 N/mm<sup>2</sup></b>		2,5				
<b>10 N/mm<sup>2</sup></b>		3,0				
<b>12 N/mm<sup>2</sup></b>		3,5				
<b>16 N/mm<sup>2</sup></b>		4,5				

**Tension resistance  $N_{Rk} = N_{Rk,p} = N_{Rk,b} = N_{Rk,p,c} = N_{Rk,b,c}$  [kN] depending on the normalised mean compressive strength  $f_b$ ; (temperature range 50/80°C and 72/120°C)**

Norm. mean compressive strength $f_b$						
<b>6 N/mm<sup>2</sup></b>		1,5				
<b>8 N/mm<sup>2</sup></b>		2,0				
<b>10 N/mm<sup>2</sup></b>		2,5				
<b>12 N/mm<sup>2</sup></b>		2,5				
<b>16 N/mm<sup>2</sup></b>		3,5				

Factor for job site tests see annex C20 and displacements see annex C21

fischer injection system FIS V Zero for masonry	<b>Annex C10</b>
<b>Performances</b> Perforated calcium silicate (sand-lime) brick KSL, 3DF, Characteristic resistance under tension loading	

**Perforated calcium silicate (sand-lime) brick KSL, 3DF, EN 771-2: 2011+A1:2015**
**Table C11.1:** Characteristic resistance to local brick failure or brick edge failure of a single anchor under shear loading (Pre-positioned installation)

Anchor rod	M8	M8	-	M8	M10	M8	M10	-	M12	M16	M12	M16
Internal threaded anchor FIS E	-	-	M8	11x85	-	-	-	M10	M12	-	-	-
								15x85				
Perforated sleeve FIS H K	12x50	12x85		16x85		16x130		20x85		20x130		
<b>Shear resistance <math>V_{Rk} = V_{Rk,b} = V_{Rk,c,II} = V_{Rk,c,\perp}</math> [kN] depending on the normalised mean compressive strength <math>f_b</math>; (temperature range 24/40°C, 50/80°C and 72/120°C)</b>												
Normalised mean compressive strength $f_b$												
6 N/mm <sup>2</sup>		1,5			2,0				3,0			
8 N/mm <sup>2</sup>			2,0			2,5			3,5			
10 N/mm <sup>2</sup>			2,5			3,0			4,5			
12 N/mm <sup>2</sup>			2,5			3,5			5,0			
16 N/mm <sup>2</sup>			3,5			4,0			6,5			

**Table C11.2:** Characteristic resistance to local brick failure or brick edge failure of a single anchor under shear loading (Push through installation)

Anchor rod	M10	M12	M16
Perforated sleeve FIS H K	18x130/200		22x130/200
<b>Shear resistance <math>V_{Rk} = V_{Rk,b} = V_{Rk,c,II} = V_{Rk,c,\perp}</math> [kN] depending on the normalised mean compressive strength <math>f_b</math>; (temperature range 24/40°C, 50/80°C and 72/120°C)</b>			
Normalised mean compressive strength $f_b$			
6 N/mm <sup>2</sup>		2,0	
8 N/mm <sup>2</sup>		2,5	
10 N/mm <sup>2</sup>		3,0	
12 N/mm <sup>2</sup>		3,5	
16 N/mm <sup>2</sup>		4,0	

Factor for job site tests see annex C20 and displacements see annex C21


fischer injection system FIS V Zero for masonry

**Performances**


Perforated calcium silicate (sand-lime) brick KSL, 3DF, Characteristic resistance under shear loading

**Annex C11**

# Vertical perforated brick HLz, EN 771-1: 2011+A1:2015



Vertical perforated brick HLz, EN 771-1: 2011+A1:2015		
Producer	e.g. Wienerberger.	
Nominal dimensions [mm]	length L	width W
230	108	55
Mean gross dry density $\rho$ [kg/dm <sup>3</sup> ]		$\geq 1,6$
Normalised mean compressive strength [N/mm <sup>2</sup> ]		8 / 10 / 12 / 16
Standard	EN 771-1: 2011+A1:2015	



Dimensions see also Annex B12

Table C12.1: Installation parameters

Anchor rod	M8	M8	-	M8	M10	M8	M10	-	M12	M16	M12	M16
Internal threaded anchor FIS E	-	-		M8				M10	M12			
				11x85				15x85				
Perforated sleeve FIS H K	12x50	12x85		16x85		16x130		20x85		20x130		

## Anchor rod and internal threaded anchor FIS E with perforated sleeve FIS H K

Max. installation torque	max T <sub>inst</sub> [Nm]	5
--------------------------	----------------------------	---

## General installation parameters

Edge distance	C <sub>min</sub> = C <sub>cr</sub>	[mm]	100
	s <sub>min II</sub>		100
Spacing	s <sub>cr II</sub>		230
	s <sub>min ⊥</sub>		60
Group factors	s <sub>cr ⊥</sub>		60

## Drilling method

Hole drilling with rotary drill mode or hammer drilling with hard metal hammer drill

Table C12.2: Group factors

Anchor rod	M8	M8	-	M8	M10	M8	M10	-	M12	M16	M12	M16
Internal threaded anchor FIS E	-	-		M8				M10	M12			
				11x85				15x85				
Perforated sleeve FIS H K	12x50	12x85		16x85		16x130		20x85		20x130		
Group factors	$\alpha_{g,N}$ (s <sub>min II</sub> )	[-]						1,65				
	$\alpha_{g,V}$ (s <sub>min II</sub> )							1,64				
	$\alpha_{g,N}$ (s <sub>min ⊥</sub> )							1,65				
	$\alpha_{g,V}$ (s <sub>min ⊥</sub> )							2,00				

fischer injection system FIS V Zero for masonry

## Performances

Vertical perforated brick HLz, dimensions, installation parameters

## Annex C12

**Table C13.1:** Characteristic resistance to pull-out failure or brick breakout failure of a single anchor under tension loading

Anchor rod	M8	M8	-	M8	M10	M8	M10	-	M12	M16	M12	M16
Internal threaded anchor FIS E	-	-	M8 11x85	-	-	-	-	M10 15x85	M12	-	-	-
Perforated sleeve FIS H K	12x50	12x85		16x85		16x130		20x85		20x130		

Tension resistance  $N_{Rk} = N_{Rk,p} = N_{Rk,b} = N_{Rk,p,c} = N_{Rk,b,c}$  [kN] depending on the normalised mean compressive strength  $f_b$ ; (temperature range 24/40°C)

Normalised mean compressive strength $f_b$						
8 N/mm <sup>2</sup>	1,2	1,5	1,5	2,5	1,5	2,5
10 N/mm <sup>2</sup>	1,2	2,0	2,0	2,5	2,0	2,5
12 N/mm <sup>2</sup>	1,5	2,0	2,0	3,0	2,0	3,0
16 N/mm <sup>2</sup>	1,5	2,5	2,5	3,5	2,5	3,5

Tension resistance  $N_{Rk} = N_{Rk,p} = N_{Rk,b} = N_{Rk,p,c} = N_{Rk,b,c}$  [kN] depending on the normalised mean compressive strength  $f_b$ ; (temperature range 50/80°C and 72/120°C)

Normalised mean compressive strength $f_b$						
8 N/mm <sup>2</sup>	0,6	1,2	1,2	1,5	1,2	1,5
10 N/mm <sup>2</sup>	0,75	1,2	1,2	2,0	1,2	2,0
12 N/mm <sup>2</sup>	0,75	1,5	1,5	2,0	1,5	2,0
16 N/mm <sup>2</sup>	0,9	1,5	1,5	2,5	1,5	2,5

**Table C13.2:** Characteristic resistance to local brick failure or brick edge failure of a single anchor under shear loading

Anchor rod	M8	M8	-	M8	M10	M8	M10	-	M12	M16	M12	M16
Internal threaded anchor FIS E	-	-	M8 11x85	-	-	-	-	M10 15x85	M12	-	-	-
Perforated sleeve FIS H K	12x50	12x85		16x85		16x130		20x85		20x130		


Shear resistance  $V_{Rk} = V_{Rk,b} = V_{Rk,c,II} = V_{Rk,c,\perp}$  [kN] depending on the normalised mean compressive strength  $f_b$ ; (temperature range 24/40°C, 50/80°C and 72/120°C)

Normalised mean compressive strength $f_b$						
8 N/mm <sup>2</sup>	2,0	3,5	2,5	3,5	2,5	3,5
10 N/mm <sup>2</sup>	2,0	4,0	3,0	4,0	3,0	4,0
12 N/mm <sup>2</sup>	2,0	4,0	3,0	4,5	3,0	4,5
16 N/mm <sup>2</sup>	2,5	5,0	3,5	5,0	3,5	5,0


Factor for job site tests see annex C20 and displacements see annex C21

fischer injection system FIS V Zero for masonry	Annex C13
Performances Vertical perforated brick HLz, Characteristic resistance under tension and shear loading	

# Lightweight aggregate concrete hollow block Hbl , EN 771-3: 2011+A1:2015



Lightweight aggregate concrete hollow block Hbl, EN 771-3: 2011+A1:2015		
Producer	e.g. Sepa	
Nominal dimensions [mm]	length L	width W
	500	200
Mean gross dry density $\rho$ [kg/dm <sup>3</sup> ]	$\geq 1,0$	
Normalised mean compressive strength [N/mm <sup>2</sup> ]	2 / 4	
Standard	EN 771-1: 2011+A1:2015	



Dimensions see also Annex B12

Table C14.1: Installation parameters

Anchor rod	-	M8	M10	M8	M10	M10	M12	-	M12	M16	M12	M16
Internal threaded anchor FIS E	M8	-	-	-	-	-	-	M10	M12	-	-	-
	11x85							15x85	15x85			
Perforated sleeve FIS H K	16x85		16x130		18x130/200		20x85		20x130			

## Anchor rod and internal threaded anchor FIS E with perforated sleeve FIS H K

Max. installation torque	max T <sub>inst</sub> [Nm]	2
--------------------------	----------------------------	---

## General installation parameters

Edge distance	C <sub>min</sub> = C <sub>cr</sub>	[mm]	100
	s <sub>min</sub> II		100
Spacing	s <sub>cr</sub> II		500
	s <sub>min</sub> $\perp$		100
	s <sub>cr</sub> $\perp$		200

## Drilling method

Hole drilling with rotary drill mode or hammer drilling with hard metal hammer drill

Table C14.2: Group factors

Anchor rod	-	M8	M10	M8	M10	M10	M12	-	M12	M16	M12	M16												
Internal threaded anchor FIS E	M8	-	-	-	-	-	-	M10	M12	-	-	-												
	11x85							15x85	15x85															
Perforated sleeve FIS H K	16x85		16x130		18x130/200		20x85		20x130															
Group factors	$\alpha_{g,N}$ (s <sub>min</sub> II)	[-]	2,00																					
	$\alpha_{g,V}$ (s <sub>min</sub> II)		1,28																					
	$\alpha_{g,N}$ (s <sub>min</sub> $\perp$ )		1,40																					
	$\alpha_{g,V}$ (s <sub>min</sub> $\perp$ )		2,00																					

fischer injection system FIS V Zero for masonry

## Performances

Lightweight aggregate concrete hollow block Hbl, dimensions, installation parameters

## Annex C14

# Lightweight aggregate concrete hollow block Hbl, EN 771-3: 2011+A1:2015

**Table C15.1:** Characteristic resistance to pull-out failure or brick breakout failure of a single anchor under tension loading

Anchor rod	-	M8	M10	M8	M10	M10	M12	-	M12	M16	M12	M16
Internal threaded anchor FIS E	M8	-	-	-	-	-	-	M10	M12	-	-	-
	11x85							15x85				
Perforated sleeve FIS H K		16x85		16x130	18x130/200			20x85		20x130		

Tension resistance  $N_{Rk} = N_{Rk,p} = N_{Rk,b} = N_{Rk,p,c} = N_{Rk,b,c}$  [kN] depending on the normalised mean compressive strength  $f_b$ ; (temperature range 24/40°C)

Normalised mean compressive strength $f_b$			
2 N/mm <sup>2</sup>	0,4		0,6
4 N/mm <sup>2</sup>	0,5		0,75

Tension resistance  $N_{Rk} = N_{Rk,p} = N_{Rk,b} = N_{Rk,p,c} = N_{Rk,b,c}$  [kN] depending on the normalised mean compressive strength  $f_b$ ; (temperature range 50/80°C and 72/120°C)

Normalised mean compressive strength $f_b$			
2 N/mm <sup>2</sup>	0,3		0,5
4 N/mm <sup>2</sup>	0,4		0,6

**Table C15.2:** Characteristic resistance to local brick failure or brick edge failure of a single anchor under shear loading

Anchor rod	-	M8	M10	M8	M10	M10	M12	-	M12	M16	M12	M16
Internal threaded anchor FIS E	M8	-	-	-	-	-	-	M10	M12	-	-	-
	11x85							15x85				
Perforated sleeve FIS H K		16x85		16x130	18x130/200			20x85		20x130		

Shear resistance  $V_{Rk} = V_{Rk,b} = V_{Rk,c,II} = V_{Rk,c,\perp}$  [kN] depending on the normalised mean compressive strength  $f_b$ ; (temperature range 24/40°C, 50/80°C and 72/120°C)

Normalised mean compressive strength $f_b$			
2 N/mm <sup>2</sup>	1,5		
4 N/mm <sup>2</sup>	2,0		

Factor for job site tests see annex C20 and displacements see annex C21

fischer injection system FIS V Zero for masonry

## Performances

Lightweight aggregate concrete hollow block Hbl  
Characteristic resistance under tension and shear loading

## Annex C15

# Autoclaved aerated concrete (cylindrical drill hole), EN 771-4:2011+A1:2015



Producer	e.g. Ytong		
Mean gross dry density $\rho$	[kg/dm <sup>3</sup> ]	0,35	0,5
Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	[N/mm <sup>2</sup> ]	2,5 / 2	5 / 4
Standard or annex	EN 771-4:2011+A1:2015		

Table C16.1: Installation parameters

Anchor rod	M8	M10	M12	M16
Internal threaded anchor FIS E	-	-	-	-
<b>Anchor rod and internal threaded anchor FIS E without perforated sleeve</b>				
Effective anchorage depth $h_{\text{ef}}$ [mm]	100	100	100	100
Max. installation torque $\max T_{\text{inst}}$ [Nm]	2	2	2	2
<b>General installation parameters</b>				
Edge distance $c_{\min}$		100		
	$c_{\text{cr}}$	250		
Spacing $s_{\text{cr II}}$		250		
	$s_{\min \text{ II}}$	100		
	$s_{\text{cr} \perp}$	250		
	$s_{\min \perp}$	100		

## Drilling method

Hammer drilling with hard metal hammer drill

- <sup>1)</sup> The compressive strength of the single brick must not be less than 80% of the mean compressive strength.

fischer injection system FIS V Zero for masonry

## Performance

Autoclaved aerated concrete (cylindrical drill hole), dimensions, installation parameters

## Annex C16

**Table C17.1:** Group factors for autoclaved aerated concrete  
(Min. compressive strength single brick 2 N/mm<sup>2</sup>)

Anchor rod		M8	M10	M12	M16
Group factors	$\alpha_{g,N} \parallel, (s_{min} \parallel)$	[-]	1,13		
	$\alpha_{g,N} \perp, (s_{min} \perp)$		1,20		
	$\alpha_{g,V}, (s_{min} \parallel)$		1,39		
	$\alpha_{g,V}, (s_{min} \perp)$		1,17		

**Table C17.2:** Group factors for autoclaved aerated concrete  
(Min. compressive strength single brick 4 N/mm<sup>2</sup>)

Anchor rod		M8	M10	M12	M16
Group factors	$\alpha_{g,N} \parallel, (s_{min} \parallel)$	[-]	1,13		
	$\alpha_{g,N} \perp, (s_{min} \perp)$		1,20		
	$\alpha_{g,V}, (s_{min} \parallel)$		1,39		
	$\alpha_{g,V}, (s_{min} \perp)$		1,17		

**Table C17.3:** Group factors for autoclaved aerated concrete  
(Min. compressive strength single brick 6 N/mm<sup>2</sup>)

Anchor rod		M8	M10	M12	M16
Group factors	$\alpha_{g,N} \parallel, (s_{min} \parallel)$	[-]	1,13		
	$\alpha_{g,N} \perp, (s_{min} \perp)$		1,20		
	$\alpha_{g,V}, (s_{min} \parallel)$		1,39		
	$\alpha_{g,V}, (s_{min} \perp)$		1,17		

fischer injection system FIS V Zero for masonry

**Performance**  
Autoclaved aerated concrete (cylindrical drill hole), Group factors

**Annex C17**

# Autoclaved aerated concrete (cylindrical drill hole), EN 771-4:2011+A1:2015

**Table C18.1:** Characteristic resistance to pull-out failure or brick breakout failure of a single anchor under tension loading

Anchor rod		M8	M10	M12	M16
<b>Tension resistance <math>N_{Rk} = N_{Rk,p} = N_{Rk,b} = N_{Rk,p,c} = N_{Rk,b,c}</math> [kN] depending on the mean compressive strength / Min. compressive strength single brick; (temperature range 24/40°)</b>					
Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	Use conditions		Effective anchorage depth $h_{ef}$ [mm]		
		100	100	100	100
2,5 / 2 N/mm <sup>2</sup>	d/d	1,2	1,2	1,2	1,5
5 / 4 N/mm <sup>2</sup>	d/d	1,2	1,2	1,2	1,5
8 / 6 N/mm <sup>2</sup>	d/d	1,2	1,2	1,2	1,5

Anchor rod		M8	M10	M12	M16
<b>Tension resistance <math>N_{Rk} = N_{Rk,p} = N_{Rk,b} = N_{Rk,p,c} = N_{Rk,b,c}</math> [kN] depending on the mean compressive strength / Min. compressive strength single brick; (temperature range 50/80°C)</b>					
Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	Use conditions		Effective anchorage depth $h_{ef}$ [mm]		
		100	100	100	100
2,5 / 2 N/mm <sup>2</sup>	d/d	0,9	0,9	1,2	1,5
5 / 4 N/mm <sup>2</sup>	d/d	0,9	0,9	1,2	1,5
8 / 6 N/mm <sup>2</sup>	d/d	0,9	0,9	1,2	1,5

<sup>1)</sup> The compressive strength of the single brick must not be less than 80% of the mean compressive strength.

fischer injection system FIS V Zero for masonry

**Performance**

Autoclaved aerated concrete (cylindrical drill hole),  
Characteristic resistance under tension loading

**Annex C18**

Appendix 39 / 42

**Table C19.1:** Characteristic resistance to local brick failure or brick edge failure of a single anchor under shear loading

Anchor rod		M8	M10	M12	M16
Internal threaded anchor FIS E		-	-	-	-
<b>Shear resistance <math>V_{Rk} = V_{Rk,b} = V_{Rk,c,II} = V_{Rk,c,\perp}</math> [kN] depending on the mean compressive strength / Min. compressive strength single brick; (temperature range 24/40°C and 50/80°C) <math>c_{min} \geq 100\text{mm}</math></b>					
Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	Use conditions		Effective anchorage depth $h_{ef}$ [mm]		
2,5 / 2 N/mm <sup>2</sup>	d/d	100	100	100	100
5 / 4 N/mm <sup>2</sup>	d/d	1,2	1,2	1,2	1,2
8 / 6 N/mm <sup>2</sup>	d/d	1,2	1,2	1,2	1,2

Anchor rod		M8	M10	M12	M16
Internal threaded anchor FIS E		-	-	-	-
<b>Shear resistance <math>V_{Rk} = V_{Rk,b} = V_{Rk,c,II} = V_{Rk,c,\perp}</math> [kN] depending on the mean compressive strength / Min. compressive strength single brick; (temperature range 24/40°C and 50/80°C) <math>c_{cr} &gt; 250\text{mm}</math></b>					

Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	Use conditions		Effective anchorage depth $h_{ef}$ [mm]		
2,5 / 2 N/mm <sup>2</sup>	d/d	100	100	100	100
5 / 4 N/mm <sup>2</sup>	d/d	2,5	2,5	2,5	2,5
8 / 6 N/mm <sup>2</sup>	d/d	2,5	2,5	2,5	2,5

<sup>1)</sup> The compressive strength of the single brick must not be less than 80% of the mean compressive strength.

Factor for job site tests see annex C20, table C20.2 and displacements see annex C 21

fischer injection system FIS V Zero for masonry

**Performance**

Autoclaved aerated concrete (cylindrical drill hole),  
Characteristic resistance under shear loading

**Annex C19**

Appendix 40 / 42

## **β-factors for job site tests**

**Table C20.1:** β-factors for job site tests

Installation and use conditions	d/d		
temperature range [°C]	24/40	50/80	72/120
M8	0,81	0,47	0,45
M10	0,62	0,49	0,45
M12 / FIS E 11x85	0,62	0,49	0,52
M16 / FIS E 15x85	0,56	0,45	0,57

**Table C20.2:** β-factors for job site tests for AAC

Installation and use conditions	d/d	
temperature range [°C]	24/40	50/80
All sizes	0,58	0,49

fischer injection system FIS V Zero for masonry

**Performances**  
β-factors for job site tests

**Annex C20**

Appendix 41 / 42

**Table C21.1: Displacements**

Material	Size	Effective anchorage depth [mm]	N [kN]	$\delta N_0$ [mm]	$\delta N_\infty$ [mm]	V [kN]	$\delta V_0$ [mm]	$\delta V_\infty$ [mm]
Solid brick acc. to C4-C5	M8	50	0,57	0,00	0,00	0,71	0,08	0,12
		80	1,00	0,00	0,00	1,71	0,32	0,48
	M10	50	0,57	0,00	0,00	0,71	0,18	0,27
		80	1,00	0,01	0,02	1,71	0,50	0,75
	M12	50	1,29	0,03	0,06	0,71	0,05	0,08
		80	1,00	0,01	0,02	1,71	0,75	1,13
	M16	50	1,29	0,03	0,06	0,71	0,35	0,53
		80	1,71	0,04	0,08	1,71	0,20	0,30
Solid calcium silicate (sand-lime) brick acc. to C6-C7	M8	50	0,86	0,03	0,06	1,43	0,32	0,48
		80	0,86	0,00	0,00	1,43		
	M10	50	0,86	0,00	0,00	1,43	0,34	0,51
		80	1,71	0,02	0,04	1,43		
	M12	50	0,86	0,03	0,06	1,43	0,12	0,18
		80	1,71	0,04	0,08	1,43	0,32	0,48
	M16	50	0,86	0,03	0,06	1,43	0,57	0,86
		80	1,14	0,02	0,04	1,43	0,20	0,03
Perforated calcium silicate (sand-lime) brick acc. to C8-C11	M8	12x50	0,71	0,01	0,02	1,00	0,16	0,24
		12x85				1,14	0,57	0,86
	M8	16x85	0,57	0,02	0,04	1,14	1,03	1,55
	M10	16x130	1,29	0,06	0,12	1,86	1,15	1,73
	M12	20x85	0,57	0,03	0,06	1,86	1,24	1,86
	M16	20x130	1,29	0,04	0,08			
Perforated brick Hz acc. to C12-C13	M8	12x50	0,43	0,00	0,00	0,71	0,25	0,38
		12x85	0,71	0,00	0,00	1,43	0,61	0,92
	M8	16x85	0,71	0,03	0,06	1,00	0,36	0,54
		16x130	1,00	0,02	0,04	1,43	0,30	0,45
	M12	20x85	0,71	0,00	0,00	1,00	0,22	0,33
	M16	20x130	1,00	0,04	0,08	1,43	0,17	0,26
Lightweight aggregate concrete hollow block Hbl acc. to C14-C15	M8	16x85	0,14	0,03	0,06	0,57	1,54	2,31
		16x130	0,14	0,02	0,04	0,57	1,01	1,52
	M12	20x85	0,14	0,06	0,12	0,57	1,31	1,97
		20x130	0,21	0,04	0,08	0,57	0,82	1,23
Autoclaved aerated concrete acc. to C16-C19	M8x100 M10x100		0,48	0,08	0,16	0,89	1,49	2,24
	M12x100		0,49	0,09	0,18	0,89	1,49	2,24
	M16x100		0,65	0,12	0,24	0,89	1,49	2,24

fischer injection system FIS V Zero for masonry

**Performances**  
displacements

**Annex C21**