

DICHIARAZIONE DI PRESTAZIONE

DoP 0376

per profilo di ancoraggio fischer FES con bullone testa a martello per profilo di ancoraggio fischer FBC (profilo di ancoraggio per utilizzo in calcestruzzo)

IT

1. Codice di identificazione unico del prodotto-tipo: **DoP 0376**
2. Usi previsti: **Profilo di ancoraggio per utilizzo in calcestruzzo fessurato e non fessurato, vedi appendice, in particolare gli allegati da B1- B8.**
3. Fabbricante: **fischerwerke GmbH & Co. KG, Klaus-Fischer-Str. 1, 72178 Waldachtal, Germany**
4. Mandatario: **–**
5. Sistemi di VVCP: **1**
6. Documento per la valutazione europea:
Valutazione tecnica europea: **EAD 330008-04-0601, Edition 07/2024**
Organismo di valutazione tecnica: **ETA-18/0862; 2025-05-19**
Organismi notificati: **DIBt- Deutsches Institut für Bautechnik**
2873 TU Darmstadt
7. Prestazioni dichiarate:
Resistenza meccanica e stabilità (BWR 1)
Resistenza caratteristica al carico di tensione (carico statico e quasi-statico):
 - 1) Resistenza alla rottura dell'acciaio dell'ancoraggio: Allegato C1
 - 2) Resistenza alla rottura dell'acciaio della connessione tra ancoraggio e canale: Allegato C1
 - 3) Resistenza alla rottura dell'acciaio per flessione locale dell'orlo del canale e conseguente estrazione del bullone testa a martello: Allegato C1
 - 4) Resistenza a rottura dell'acciaio del bullone testa a martello: Allegato C10
 - 5) Resistenza a rottura dell'acciaio per flessione del canale: Allegati A5, C2
 - 6) Massima coppia di serraggio per evitare danni durante l'installazione: Allegato B4
 - 7) Resistenza alla rottura per sfilamento: Allegati C3,C4
 - 8) Resistenza alla rottura del cono di calcestruzzo: Allegati B3, C3, C4
 - 9) Distanza dal bordo, interasse, spessore elemento minimo per evitare la rottura per splitting del calcestruzzo durante l'installazione: Allegati A5, B3
 - 10) Distanza dal bordo e interasse caratteristici per evitare la rottura per splitting del calcestruzzo dovuta ai carichi: Allegati C3, C4
 - 11) Resistenza alla rottura per blow-out del calcestruzzo: Allegato A4**Resistenza caratteristica al carico di taglio (carico statico e quasi statico):**
 - 12) Resistenza alla rottura dell'acciaio del bullone testa a martello sotto azione di taglio senza braccio di leva: Allegato C10
 - 13) Resistenza alla rottura dell'acciaio del bullone testa a martello per flessione sotto azione di taglio con braccio di leva: Allegato C11
 - 14) Resistenza alla rottura dell'acciaio per flessione locale dell'orlo del canale, rottura dell'acciaio della connessione tra ancoraggio e canale o rottura dell'acciaio del profilo di ancoraggio (azione di taglio in direzione trasversale): Allegati C6, C7
 - 15) Resistenza alla rottura dell'acciaio della connessione tra gli orli del canale e il bullone testa a martello (azione di taglio in direzione longitudinale dell'asse del profilo di ancoraggio): Allegato C8
 - 16) Fattore di sensibilità all'installazione (Scorrimento longitudinale): Allegato C8
 - 17) Resistenza alla rottura dell'acciaio dell'ancoraggio (Scorrimento longitudinale): Allegati C6, C7
 - 18) Resistenza alla rottura dell'acciaio della connessione tra ancoraggio e canale (azione di taglio in direzione longitudinale dell'asse del profilo di ancoraggio): Allegati C6, C7
 - 19) Resistenza alla rottura per pry-out: Allegato C8
 - 20) Resistenza alla rottura del bordo di calcestruzzo: Allegato C8**Resistenza caratteristica sotto azioni statiche e quasi statiche di trazione e taglio**
 - 21) Resistenza alla rottura del profilo di ancoraggio: Allegato C9**Resistenza caratteristica sotto azioni di trazione di fatica:**
 - 22) Resistenza a fatica per rottura dell'acciaio dell'intero sistema (funzione continua o tri-lineare, Metodo di valutazione A1, A2): NPD
 - 23) Resistenza limite a fatica per rottura dell'acciaio dell'intero sistema (Metodo di valutazione B): NPD
 - 24) Resistenza a fatica per rottura dell'acciaio dell'intero sistema (Funzione linearizzata, Metodo di valutazione C): NPD
 - 25) Resistenza a fatica per rottura relativa al calcestruzzo (funzione esponenziale, Metodo di valutazione A1, A2): NPD
 - 26) Resistenza limite a fatica per rottura relativa al calcestruzzo (Metodo di valutazione B): NPD
 - 27) Resistenza a fatica per rottura relativa al calcestruzzo (Funzione linearizzata, Metodo di valutazione C): NPD**Resistenza caratteristica sotto carico sismico (categoria di prestazione sismica C1)**
 - 28) Resistenza al cedimento dell'acciaio sotto carico sismico di trazione (categoria di prestazione sismica C1): Allegati C12, C14
 - 29) Resistenza al cedimento dell'acciaio sotto carico sismico di taglio per carico di taglio in direzione trasversale (categoria di prestazione sismica C1): Allegati C13, C14
 - 30) Resistenza al cedimento dell'acciaio sotto carico sismico di taglio per carico di taglio lungo l'asse longitudinale del canale (categoria di prestazione sismica C1): Allegato C13

Resistenza caratteristica sotto carico di trazione e/o taglio statico e quasi-statico

31) Spostamenti: Allegati C5, C9

Sicurezza in caso di incendio (BWR 2)

32) Reazione al fuoco: Classe (A1)

33) Resistenza al fuoco: Allegati C15, C16

Durabilità:

34) Durabilità: Allegati A7, B1


8. Documentazione tecnica appropriata e/o --
documentazione tecnica specifica:

La prestazione del prodotto sopra identificato è conforme all'insieme delle prestazioni dichiarate. La presente dichiarazione di prestazione è emessa, in conformità al regolamento (UE) n. 305/2011, sotto la sola responsabilità del fabbricante sopra identificato.

Firmato a nome e per conto del fabbricante da:



Dr. Ronald Mihala, Direttore generale Ricerca e Sviluppo
Tumlingen, 2025-06-02



Dieter Pfaff, Capo della Federazione Internazionale della Produzione e Gestione della Qualità

Questa Dichiarazione di Prestazione (DoP) è stata preparata in varie lingue. In caso di contestazioni sull'interpretazione, prevarrà sempre la versione inglese.

L'Appendice include informazioni volontarie e complementari in lingua inglese che superano i requisiti di legge (lingua specificata in modo neutrale).

Translation guidance Essential Characteristics and Performance Parameters for Annexes

Guida alla traduzione delle Caratteristiche Essenziali e dei Parametri di Prestazione per gli Annessi

Mechanical resistance and stability (BWR 1)		
Resistenza meccanica e stabilità (BWR 1)		
Characteristic resistance to tension load (static and quasi-static loading):		
Resistenza caratteristica al carico di tensione (carico statico e quasi-statico):		
1	Resistance to steel failure of anchors: Resistenza alla rottura dell'acciaio dell'ancoraggio:	$N_{Rk,s,a}$
2	Resistance to steel failure of the connection between anchors and channel: Resistenza alla rottura dell'acciaio della connessione tra ancoraggio e canale:	$N_{Rk,s,c}$
3	Resistance to steel failure of channel lips and sunsequently pullout of channel bolt: Resistenza alla rottura dell'acciaio per flessione locale dell'orlo del canale e conseguente estrazione del bullone testa a martello:	$N_{Rk,s,l}^0 ; S_{l,N}$
4	Resistance to steel failure of channel bolt: Resistenza a rottura dell'acciaio del bullone testa a martello:	$N_{Rk,s}$
5	Resistance to steel failure by exceeding the bending strength of the channel: Resistenza a rottura dell'acciaio per flessione del canale:	$M_{Rk,s,flex} ; S_{max}$
6	Maximum installation torque moment to avoid damage during installation: Massima coppia di serraggio per evitare danni durante l'installazione:	$T_{inst,g} ; (T_{inst,s})$
7	Resistance to pull-out failure of the anchor: Resistenza alla rottura per sfilamento:	$N_{Rk,p}$
8	Resistance to concrete cone failure: Resistenza alla rottura del cono di calcestruzzo:	$k_{cr,N} ; k_{ucr,N} ; h_{ef}$
9	Minimum edge distance, spacing, member thickness to prevent concrete splitting during installation: Distanza dal bordo, interasse, spessore elemento minimo per evitare la rottura per splitting del calcestruzzo durante l'installazione:	$s_{min} ; c_{min} ; h_{min}$
10	Characteristic edge distance and spacing to avoid splitting of concrete under load: Distanza dal bordo e interasse caratteristici per evitare la rottura per splitting del calcestruzzo dovuta ai carichi:	$s_{cr,sp} ; c_{cr,sp}$
11	Resistance to blowout failure- bearing area of head: Resistenza alla rottura per blow-out del calcestruzzo:	A_h
Characteristic resistance to shear load (static and quasi-static loading):		
Resistenza caratteristica al carico di taglio (carico statico e quasi statico):		
12	Resistance to steel failure of channel bolt under shear loading without lever arm: Resistenza alla rottura dell'acciaio del bullone testa a martello sotto azione di taglio senza braccio di leva:	$V_{Rk,s}$
13	Resistance to steel failure by bending of the channel bolt under shear load with lever arm: Resistenza alla rottura dell'acciaio del bullone testa a martello per flessione sotto azione di taglio con braccio di leva:	$M_{Rk,s}^0$
14	Resistance to steel failure of channel lips, steel failure of connection between anchor and channel or steel failure of anchor (shear load in transverse direction): Resistenza alla rottura dell'acciaio per flessione locale dell'orlo del canale, rottura dell'acciaio della connessione tra ancoraggio e canale o rottura dell'acciaio del profilo di ancoraggio (azione di taglio in direzione trasversale):	$V_{Rk,s,l,y}^0 ; S_{l,v} ; V_{Rk,s,c,y} ; V_{Rk,s,a,y}$
15	Resistance to steel failure of connection between channel lips and channel bolt (shear load in longitudinal channel axis): Resistenza alla rottura dell'acciaio della connessione tra gli orli del canale e il bullone testa a martello (azione di taglio in direzione longitudinale dell'asse del profilo di ancoraggio):	$V_{Rk,s,l,x}$
16	Factor for sensistivity to installation: Fattore di sensibilità all'installazione (Scorrimento longitudinale):	γ_{inst}
17	Resistance to steel failure of the anchor: Resistenza alla rottura dell'acciaio dell'ancoraggio (Scorrimento longitudinale):	$V_{Rk,s,a,x}$
18	Resistance to steel failure of connection between anchor and channel (shear load in longitudinal channel axis): Resistenza alla rottura dell'acciaio della connessione tra ancoraggio e canale (azione di taglio in direzione longitudinale dell'asse del profilo di ancoraggio):	$V_{Rk,s,c,x}$
19	Resistance to concrete pry-out failure: Resistenza alla rottura per pry-out:	k_g
20	Resistance to concrete edge failure: Resistenza alla rottura del bordo di calcestruzzo:	$k_{cr,v} ; k_{ucr,v}$
Characteristic resistance under combined static and quasi-static tension and shear loading		
Resistenza caratteristica sotto azioni statiche e quasi statiche di trazione e taglio		
21	Resistance to steel failure of the anchor channel: Resistenza alla rottura del profilo di ancoraggio:	k_{13}, k_{14}
Characteristic resistance under fatigue tension loading:		
Resistenza caratteristica sotto azioni di trazione di fatica:		
22	Fatigue resistance to steel failure of the whole system (continuous or tri-linear function): Resistenza a fatica per rottura dell'acciaio dell'intero sistema (funzione continua o tri-lineare, Metodo di valutazione A1, A2):	$\Delta N_{Rk,s,0,n}$ ($n=1$ to $n=\infty$)
23	Fatigue limit resistance to steel failure of the whole system: Resistenza limite a fatica per rottura dell'acciaio dell'intero sistema (Metodo di valutazione B):	$\Delta N_{Rk,s,0,\infty}$
24	Fatigue resistance to steel failure of the whole system (linearized function, assessment method C): Resistenza a fatica per rottura dell'acciaio dell'intero sistema (Funzione linearizzata, Metodo di valutazione C):	$\Delta N_{Rk,s,l0,n} ; N_{lok,s,n}$ ($n=10^4$ to $n=\infty$)
25	Fatigue resistance to concrete related failure (exponential function): Resistenza a fatica per rottura relativa al calcestruzzo (funzione esponenziale, Metodo di valutazione A1, A2):	$\Delta N_{Rk,c,0,n} ; \Delta N_{Rk,p,0,n}$ ($n=1$ to $n=\infty$)
26	Fatigue limit resistance to concrete related failure: Resistenza limite a fatica per rottura relativa al calcestruzzo (Metodo di valutazione B):	$\Delta N_{Rk,c,0,\infty} ; \Delta N_{Rk,p,0,\infty}$
27	Fatigue resistance to concrete related failure (linearized function, assessment method C): Resistenza a fatica per rottura relativa al calcestruzzo (Funzione linearizzata, Metodo di valutazione C):	$\Delta N_{Rk,c,E,n} ; N_{Rk,p,E,n}$ ($n=10^4$ to $n=\infty$)

Characteristic resistance under seismic loading (seismic performance category C1)		
Resistenza caratteristica sotto carico sismico (categoria di prestazione sismica C1)		
28	Resistance to steel failure under seismic tension loading (seismic performance category C1): Resistenza al cedimento dell'acciaio sotto carico sismico di trazione (categoria di prestazione sismica C1):	$N_{Rk,s,a,eq}$; $N_{Rk,s,c,eq}$; $N^0_{Rk,s,l,eq}$; $N_{Rk,s,eq}$; $M_{Rk,s,flex,eq}$
29	Resistance to steel failure under seismic shear loading for shear load in transverse direction (seismic performance category C1): Resistenza al cedimento dell'acciaio sotto carico sismico di taglio per carico di taglio in direzione trasversale (categoria di prestazione sismica C1):	$V_{Rk,s,eq}$; $V^0_{Rk,s,l,y,eq}$; $V_{Rk,s,c,y,eq}$; $V_{Rk,s,a,y,eq}$
30	Resistance to steel failure under seismic shear loading for shear load in longitudinal channel axis (seismic performance category C1): Resistenza al cedimento dell'acciaio sotto carico sismico di taglio per carico di taglio lungo l'asse longitudinale del canale (categoria di prestazione sismica C1):	$V_{Rk,s,l,x,eq}$; $V_{Rk,s,a,x,eq}$; $V_{Rk,s,c,x,eq}$
Characteristic resistance under static and quasi-static tension and / or shear loading:		
Resistenza caratteristica sotto carico di trazione e/o taglio statico e quasi-statico		
31	Displacements: Spostamenti:	δ_{N0} ; $\delta_{N\infty}$; $\delta_{V,y,0}$; $\delta_{V,y,\infty}$; $\delta_{V,x,0}$; $\delta_{V,x,\infty}$
Safety in case of fire (BWR 2)		
Sicurezza in caso di incendio (BWR 2)		
32	Reaction to fire: Reazione al fuoco:	Class
33	Resistance to fire: Resistenza al fuoco:	$N_{Rk,s,fi}$; $V_{Rk,y,s,fi}$; $C_{min,fi}$; $S_{min,fi}$
Durability:		
Durabilità:		
34	Durability: Durabilità:	Description

Specific Part

1 Technical description of the product

The fischer Anchor Channel FES with fischer Channel Bolts FBC is a system consisting of a C-shaped channel profile of steel and at least two metal anchors non-detachably fixed on the channel back and fischer Channel Bolts.

The anchor channel is embedded surface-flush in the concrete. fischer Channel Bolts with appropriate hexagonal nuts and washers are fixed to the channel.

The product description is given in Annex A.

2 Specification of the intended use in accordance with the applicable European Assessment Document

The performances given in Section 3 are only valid if the anchor channel is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the anchor channel of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment

3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Characteristic resistance under tension load (static and quasi-static loading)	
- Resistance to steel failure of anchors	$N_{Rk,s,a}$ see Annex C1
- Resistance to steel failure of the connection between anchors and channel	$N_{Rk,s,c}$ see Annex C1
- Resistance to steel failure of channel lips and subsequently pull-out of channel bolt	$N_{Rk,s,l}^0$; $s_{l,N}$ see Annex C1
- Resistance to steel failure of channel bolt	$N_{Rk,s}$ see Annex C10
- Resistance to steel failure by exceeding the bending strength of the channel	s_{max} see Annex A5 $M_{Rk,s,flex}$ see Annex C2
- Maximum installation torque to avoid damage during installation	$T_{inst,g}$; $T_{inst,s}$ see Annex B4
- Resistance to pull-out failure of the anchor	$N_{Rk,p}$ see Annex C3 and C4
- Resistance to concrete cone failure	h_{ef} see Annex B3 $k_{cr,N}$; $k_{ucr,N}$ see Annex C3 and C4
- Minimum edge distances, spacing and member thickness to avoid concrete splitting during installation	s_{min} see Annex A5 c_{min} ; h_{min} see Annex B3
- Characteristic edge distance and spacing to avoid splitting of concrete under load	$s_{cr,sp}$; $c_{cr,sp}$ see Annex C3 and C4
- Resistance to blowout failure - bearing area of anchor head	A_h see Annex A4

Essential characteristic	Performance
Characteristic resistance under shear load (static and quasi-static loading) - Resistance to steel failure of channel bolt under shear loading without lever arm - Resistance to steel failure by bending of the channel bolt under shear load with lever arm - Resistance to steel failure of channel lips, steel failure of connection between anchor and channel and steel failure of anchor (shear load in transverse direction) - Resistance to steel failure of connection between channel lips and channel bolt (longitudinal shear) - Factor for sensitivity to installation (longitudinal shear) - Resistance to steel failure of the anchor (longitudinal shear) - Resistance to steel failure of connection between anchor and channel (longitudinal shear) - Resistance to concrete pry-out failure - Resistance to concrete edge failure	$V_{Rk,s}$ see Annex C10 $M_{Rk,s}^0$ see Annex C11 $V_{Rk,s,l,y}^0$; $S_{l,V}$; $V_{Rk,s,c,y}$; $V_{Rk,s,a,y}$ see Annex C6 and C7 $V_{Rk,s,l,x}$ see Annex C8 γ_{inst} see Annex C8 $V_{Rk,s,a,x}$ see Annex C6 and C7 $V_{Rk,s,c,x}$ see Annex C6 and C7 k_8 see Annex C8 $k_{cr,V}$; $k_{ucr,V}$ see Annex C8
Characteristic resistance under combined tension and shear load (static and quasi-static load) - Resistance to steel failure of the anchor channel	k_{13} ; k_{14} see Annex C9
Characteristic resistance under fatigue tension loading - Fatigue resistance to steel failure of the whole system (continuous or tri-linear function, assessment method A1, A2) - Fatigue limit resistance to steel failure of the whole system (assessment method B) - Fatigue resistance to steel failure of the whole system (linearized function, assessment method C) - Fatigue resistance to concrete related failure (exponential function, assessment method A1, A2) - Fatigue limit resistance to concrete related failure (assessment method B) - Fatigue resistance to concrete related failure (linearized function, assessment method C)	No Performance assessed No Performance assessed No performance assessed No Performance assessed No Performance assessed No performance assessed

Essential characteristic	Performance
Characteristic resistance under seismic loading (seismic performance category C1)	
Resistance to steel failure under seismic tension loading (seismic performance category C1)	$N_{Rk,s,a.eq}$; $N_{Rk,s,c.eq}$; $N^0_{Rk,s,l.eq}$; $M_{Rk,s,flex.eq}$ see Annex C12 $N_{Rk,s.eq}$ see Annex C14
Resistance to steel failure under seismic shear loading for shear load in transverse direction (seismic performance category C1)	$V_{Rk,s.eq}$ see Annex C14 $V^0_{Rk,s,l,y.eq}$; $V_{Rk,s,c,y.eq}$; $V_{Rk,s,a,y.eq}$ see Annex C13
Resistance to steel failure under seismic shear loading for shear load in longitudinal channel axis (seismic performance category C1)	$V_{Rk,s,l,x.eq}$; $V_{Rk,s,a,x.eq}$; $V_{Rk,s,c,x.eq}$ see Annex C13
Characteristic resistance under static and quasi-static tension and/or shear loading	
Displacements	δ_{N0} ; $\delta_{N\infty}$ see Annex C5 $\delta_{V,y,0}$; $\delta_{V,y,\infty}$; $\delta_{V,x,0}$; $\delta_{V,x,\infty}$ see Annex C9

3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire	Class A1
Characteristic resistance to fire	$N_{Rk,s,fi}$; $V_{Rk,s,y,fi}$ see Annex C15



3.3 Aspects of durability linked with the Basic Works Requirements

Essential characteristic	Performance
Durability	See Annex B1

4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

In accordance with EAD No. 330008-04-0601, the applicable European legal act is: [2000/273/EC].

The system to be applied is: 1




fischer Anchor Channel FES with fischer Channel Bolts FBC


Product Description
 Installed condition

Annex A1

Appendix 4 / 34



Round Anchor



I-Anchor

- Fischer Anchor channel FES
with fischer Channel Bolt FBC:
- 1 Channel profile
 - 2 Anchor
 - 3 Channel bolt
 - 4 Hexagonal nut
 - 5 Washer
 - 6 Fixture

Marking of the fischer anchor channel FES:

e.g.:  I-50/30

 = Identifying mark of the manufacturer

I = Additional marking for I-anchors
No marking for round anchors

50/30(-P) = Anchor channel size
(29/20; 38/23; 40/22; 50/30; 52/34;
28/15; 38/17; 40/25; 49/30; 54/33)

P = Additional marking for P-version



Stamped into back of channel

Optional: printed on channel web or channel lips

H = Hot rolled channel, C = Cold formed channel

No marking for material acc. Annex A7 Table A7.1
(Channel profile)

Marking of the fischer channel bolt FBC:

e.g.:  5030 8.8 N

 = Identifying mark of the manufacturer

5030 = Size of channel bolt


8.8 = Steel grade

A4-70 = Stainless steel

N = Notching channel bolt (if applicable)

• = Electroplated

No marking for hot-dip galvanised




Additional marking of channel bolt (smooth, serrated,
notching channel bolt head) according to Annex A6 at
the top of thread.

fischer Anchor Channel FES with fischer Channel Bolts FBC


Product Description
Marking and materials

Annex A2


Appendix 5 / 34




FES-H(I)-40/22(-P), -50/30(-P), -52/34



FES-H-S-29/20, -38/23 (serrated)



FES-C-40/25, -49/30, -54/33



FES-C-28/15, -38/17

Table A3.1: Dimensions of hot-rolled and cold-formed channel profile (steel and stainless steel)

Anchor Channel FES-	Material	b _{ch} [mm]	h _{ch} [mm]	t _{ch} [mm]	d _{ch} [mm]	f [mm]	f ₁ [mm]	I _y [mm ⁴]
C-28/15	Steel	28,0	15,5	2,3	12,0	2,3	- ¹⁾	4.280
C-38/17	Steel	38,0	17,3	3,0	18,0	3,0	- ¹⁾	8.240
C-40/25	Steel	40,0	25,0	2,8	18,0	6,0	- ¹⁾	20.340
C-49/30	Steel	50,0	30,0	3,3	22,0	7,0	- ¹⁾	43.080
C-54/33	Steel	54,0	33,0	5,0	22,0	8,5	- ¹⁾	74.090
H-S-29/20	Steel	30,0	20,0	3,0	14,0	5,2	- ¹⁾	11.150
H-S-38/23	Steel/ Stainless steel	38,0	23,0	3,3	18,0	6,0	- ¹⁾	21.070
H-(I)-40/22(-P)	Steel	40,0	23,5	2,6	18,0	6,2	3,6	21.660
H-(I)-50/30(-P)	Steel	50,0	30,0	3,0	22,5	8,1	5,5	54.960
H-(I)-52/34	Steel	52,5	34,0	4,0	22,5	11,5	8,3	96.330

¹⁾ This dimension is not available for this product.

fischer Anchor Channel FES with fischer Channel Bolts FBC

Product Description
Dimensions of channels

Annex A3
Appendix 6 / 34




Table A.4.1: Dimensions of anchor (welded I-anchor or forged round anchor)

Anchor Channel FES -	I-anchor						Round anchor				
	$l_{a,min}$ [mm]	$t_{w,min}$ [mm]	$b_{h,min}$ [mm]	t_h [mm]	w_A [mm]	$A_{h,min}$ [mm ²]	$l_{a,min}$ [mm]	d_a [mm]	d_h [mm]	t_h [mm]	A_h [mm ²]
C-28/15	- ²⁾						31,0	6	12,0	1,3	85
C-38/17	- ²⁾						60,8	8	16,0	2,0	151
C-40/25	- ²⁾						56,0	8	16,0	2,0	151
C-49/30	- ²⁾						66,0	10	20,0	2,2	236
C-54/33	- ²⁾						124,5	11	24,3	2,5	369
H-S-29/20 ¹⁾	- ²⁾						59,5	8	18,0	2,0	204
H-S-38/23	- ²⁾						76,2	10	20,0	2,2	236
H-(I)-40/22	62	5	20	5	20	300	68,5	8	16,0	2,0	151
H-40/22-P	- ²⁾						69,7	10	20,0	2,2	236
H-(I)-50/30	69	5	20	5	25	375	66,2	10	20,0	2,2	236
H-50/30-P	- ²⁾						78,5	11	24,3	2,5	369
H-(I)-52/34 ³⁾	126	5	20	5	40	600	123,5	11	24,3	2,5	369


¹⁾ Alternative round anchor: $d_a = 10$ mm, $d_h = 20$ mm, $t_h = 2,5$ mm, $A_h = 236$ mm², $l_{a,min} = 59,5$ mm.

²⁾ Product not available.

³⁾ Alternative I-anchor: $t_w = 6$ mm, $b_h = 25$ mm, $t_h = 5$ mm, $w_A = 40$ mm, $l_{a,min} = 126$ mm.

Table A5.1: Dimensions of Anchor Channels FES

Anchor channel FES-	Anchor type	S _{min} [mm]	S _{max} [mm]	X _{min} [mm]	X _{max} [mm]	l _{min} [mm]	l _{max} [mm]
C-28/15	round	50	200	25	35	100	6.070
C-38/17			250				
C-40/25		100				200	
C-49/30			100				
C-54/33		100				250	
H-S-29/20			100				
H-S-38/23	100	250		150			
H-(I-)40/22(-P)			round or I		100	250	35
H-(I-)50/30	round or I						
H-I-52/34	I						
H-50/30-P H-52/34	round						



fischer Anchor Channel FES with fischer Channel Bolts FBC

Product Description

Anchor position and channel length

Annex A5

Appendix 8 / 34

Table A6.1: Steel grade and coating

Channel Bolt	Carbon steel ¹⁾	Stainless steel ¹⁾
Steel grade	8.8	A4-70
f_{uk} [N/mm ²]	800 / 830	700
f_{yk} [N/mm ²]	640 / 660 ²⁾	450
Coating	G ³⁾ F ⁴⁾	-

¹⁾ Material properties according to Annex A7.





²⁾ Material properties according to EN ISO 898-1:2013+AC:2013.

³⁾ Electroplated.

⁴⁾ Hot-dip galvanised.

Table A6.2: Dimensions of fischer Channel Bolts FBC

Anchor Channel FES-	Channel Bolt FBC-	Steel grade	Dimensions			
			d [mm]	b _{cbo,1} [mm]	b _{cbo,2} [mm]	t _{cbo} [mm]
C-28/15	28/15	8.8	8	11,0	22,2	5,0
			10			5,0
			12			7,0
C-38/17	38/17	8.8	10	16,0	30,0	6,0
			12			7,0
			16			8,0
H-S-29/20	S-29/20	8.8	12	13,0	22,0	6,5
H-S-38/23	S-38/23	8.8	12	16,7	29,1	5,8
C-38/17		A4-70	16			
H(-I)-40/22(-P) C-40/25	40/22	8.8	10	14,0	32,5	8,0
		8.8	12	14,0		
		A4-70	16	17,0		
H(-I)-40/22(-P)	N-40/22	8.8	16	17,0	33,0	7,8
C-49/30 H(-I)-50/30 C-54/33 H(-I)-52/34	50/30	8.8	10	17,1	40,5	9,0
		8.8	12	17,1		10,0
		A4-70	16	17,1		11,0
	N-50/30	8.8	20	20,5	42,2	12,0
			16	17,5		12,0
H(-I)-50/30(-P) H(-I)-52/34			20	21,0		12,0



fischer Anchor Channel FES with fischer Channel Bolts FBC

Product Description
Channel bolts

Annex A6

Appendix 9 / 34

Table A7.1: Materials and properties

Component	Carbon steel			Stainless steel
	Mechanical properties	Coating	Coating	Mechanical properties
1	2	2a	2b	3
Channel profile	1.0038, 1.0044 acc. to EN 10025:2004 1.0976, 1.0979 acc. to EN 10149:2013	Hot-dip galvanised ≥ 50 µm acc. to EN ISO 1461:2022		1.4401, 1.4404, 1.4571, 1.4578 according to EN 10088: 2023
Anchor	1.0038, 1.0213, 1.0214 acc. to EN 10025:2004 1.5525, 1.5535 acc. to EN 10263:2017 1.5523 acc. to EN 10269:2014-02	Hot-dip galvanised ≥ 50 µm acc. to EN ISO 1461:2022		1.4401, 1.4404, 1.4571, 1.4578 according to EN 10088: 2023
Channel bolt	Steel grade 8.8 acc. to EN ISO 898-1:2013 +AC:2013	Electroplated acc. to EN ISO 4042:2022	Hot-dip galvanised ≥ 50 µm acc. to EN ISO 10684:2004 + AC:2009	Steel grade 70 according to EN ISO 3506-1: 2020
Plain washer ¹⁾ acc. to EN ISO 7089:2000 and EN ISO 7093-1:2000	Hardness class A ≥ 200 HV	Electroplated acc. to EN ISO 4042:2022	Hot-dip galvanised ≥ 50 µm acc. to EN ISO 10684:2004 + AC:2009	1.4401, 1.4404, 1.4571; 1.4578 according to EN 10088: 2023
Hexagonal nut acc. to EN ISO 4032:2023	Property class 5 or 8 acc. to EN ISO 898-2:2022	Electroplated acc. to EN ISO 4042:2022	Hot-dip galvanised ≥ 50 µm acc. to EN ISO 10684:2004 + AC:2009	Property class 70 or 80 according to EN ISO 3506-2: 2020

¹⁾ Not in the scope of delivery.

fischer Anchor Channel FES with fischer Channel Bolts FBC

Product Description
Materials

Annex A7
Appendix 10 / 34

Specification of intended use

Anchor channels and channel bolts subject to:

- Static and quasi-static tension, shear perpendicular to the longitudinal axis of the channel
- Static and quasi-static shear in the direction of the longitudinal axis of the channel.
(anchor channels FES-H(-I)-40/22(-P) with notching channel bolts FBC-N-40/22, anchor channels FES-H(-I)-50/30(-P) or FES-H(-I)-52/34 with notching channel bolts FBC-N-50/30 and serrated anchor channels FES-H-S in combination with serrated channel bolts FBC-S).
- Seismic tension, seismic shear perpendicular to the longitudinal axis of the channel and seismic shear in the direction of the longitudinal axis of the channel (seismic performance category C1)
(anchor channels and channel bolts according to Annex C12).
- Fire exposure for concrete strength class C20/25 to C50/60 for tension and shear perpendicular to the longitudinal axis of the channel
(anchor channels and channel bolts according to Annex C15).

Base materials:

- Reinforced or unreinforced compacted normal weight concrete without fibres according to EN 206:2013+A2:2021.
- Strength classes C12/15 to C90/105 according to EN 206:2013+A2:2021.
- Cracked or uncracked concrete.

Use conditions (Environmental conditions):

- Structures subject to dry internal conditions
(anchor channels and channel bolts according to Annex A7, Table A7.1, column 2a and 2b, 3).
- Structures subject to internal conditions with usual humidity (e.g. kitchens, bathrooms and laundries in residential buildings, exceptional permanent damp conditions and application under water)
(anchor channels and channel bolts according to Annex A7, Table A7.1, column 2b, 3).
- According to EN 1993-1-4:2006 +A1:2015+A2:2020 relating to corrosion resistance class CRC III
(anchor channels, channel bolts, washers and nuts made of stainless steel according to Annex A7, Table A7.1, column 3).

Design:

- Anchor channels are designed under the responsibility of an engineer experienced in anchorages and concrete work.
- Verifiable calculation notes and drawings are prepared taking account of the loads to be anchored. The position of the anchor channel and channel bolts are indicated on the design drawings (e.g. position of the anchor channel relative to the reinforcement or to supports).
- For static and quasi-static loading as well as seismic loading (performance category C1) and fire exposure the anchor channels are designed in accordance with EN 1992-4:2018 and EOTA TR 047 "Design of Anchor Channels", May 2021.
- The characteristic resistances are calculated with the minimum effective embedment depth.

fischer Anchor Channel FES with fischer Channel Bolts FBC

Intended Use
Specifications

Annex B1
Appendix 11 / 34

Installation:

- The installation of anchor channels is carried out by appropriately qualified personnel under the supervision of the person responsible for the technical matters on site.
- Use of the anchor channels only as supplied by the manufacturer - without any manipulations, repositioning or exchanging of channel components.
- Cutting of anchor channels is allowed only if pieces according to Annex A5, Table A5.1 are generated including end spacing x and minimum channel length l_{min} and only to be used in dry internal conditions. For anchor channels made of stainless steel there are no restrictions regarding corrosion resistance when using channel pieces, if cutting is done professionally and contamination of cutting edges with corroding material is avoided.
- Installation in accordance with the installation instruction given in Annexes B5, B6, B7 or B8.
- The anchor channels are fixed on the formwork, reinforcement or auxiliary construction such that no movement of the channels will occur during the time of laying the reinforcement and of placing and compacting the concrete.
- The concrete around the head of the anchors is properly compacted. The channels are protected from penetration of concrete into the internal space of the channels.
- Washers may be chosen according to Annex A7 and provided separately by the user.
- Orientating the channel bolt (groove according to Annex B6, B7 and B8) rectangular to the channel axis.
- The required installation torque given in Annex B4 must be applied and must not be exceeded.
- Notching channel bolts FBC-N may be used only once after applying the installation torque $T_{inst,s}$.

fischer Anchor Channel FES with fischer Channel Bolts FBC

Intended Use
Specifications

Annex B2

Appendix 12 / 34

Table B3.1: Installation parameters

Anchor Channel FES-			C-28/15	C-38/17	H-S-29/20	H-S-38/23	C-40/25 H-40/22 H-40/22-P H-I-40/22	C-49/30 H-50/30 H-50/30-P H-I-50/30	C-54/33 H-52/34 H-I-52/34
Minimum effective embedment depth	$h_{ef,min}$	[mm]	45	76	77	97	79 90 91 79	94 94 106 94	155 155 155
Minimum edge distance	c_{min}		40	50	50	75	50 50 50 50	75 75 75 75	100 100 100
Minimum thickness of concrete member	$h_{min}^{1)}$		55	87 ²⁾	120 ³⁾	100	90 100 100 100	100 100 109 100	160 160 170

1) For corrosion protection: $h_{min} = h_{ef} + t_h + C_{nom}$; C_{nom} acc. to EN 1992-1-1:2004 + AC:2010.

2) $h_{min} = 100$ mm for FES-C-38/17 in combination with FBC-S-38/23.

3) $h_{min} = 100$ mm if $c_{min} = 100$ mm and $s_{min} = 100$ mm.




Table B3.2: Minimum spacing for channel bolts

Channel bolt			M8	M10	M12	M16	M20
Minimum spacing between channel bolts	$s_{cbo,min}$	[mm]	40	50	60	80	100

fischer Anchor Channel FES with fischer Channel Bolts FBC

Intended Use

Installation parameters for fischer Anchor Channels FES

Annex B3


Appendix 13 / 34

Table B4.1: Required installation torque T_{inst}

fischer Anchor channel FES-	fischer Channel Bolt FBC	Thread diameter	$T_{inst}^{1)}$ [Nm]			
			General		Steel - steel contact	
			$T_{inst,g}$		$T_{inst,s}$	
			8.8	A4-70	8.8	A4-70
C-28/15	28/15	M8	7	-2)	15	-2)
		M10	10	-2)	30	-2)
		M12	13	-2)	45	-2)
C-38/17	38/17	M10	15	-2)	30	-2)
		M12	20	-2)	45	-2)
		M16	30	-2)	100	-2)
H-S-29/20	S-29/20	M12	80	-2)	80	-2)
H-S-38/23	S-38/23	M12	80	80	80	80
		M16	100	100	100	100
C-38/17		M12	40	-2)	80	-2)
		M16	50	-2)	100	-2)
H(-I)-40/22(-P) C-40/25	40/22	M10	15	-2)	30	-2)
		M12	24	24	45	45
		M16	32	32	100	100
	N-40/22	M16	-2)	-2)	200	-2)
C-49/30	50/30	M10	15	-2)	30	-2)
H(-I)-50/30(-P)		M12	25	25	45	45
C-54/33		M16	60	60	100	100
H(-I)-52/34		M20	75	75	230	230
H(-I)-50/30(-P), H(-I)-52/34	N-50/30	M16	-2)	-2)	200	-2)
		M20	-2)	-2)	400	-2)

1) T_{inst} must not be exceeded.

2) No performance assessed.



fischer Anchor Channel FES with fischer Channel Bolts FBC



Intended Use

Installation parameters for fischer Channel Bolts FBC








Annex B4

Appendix 14 / 34

Anchor channel FES



X		
25 - 35 mm	FES-H-	FES-C-
	S - 29/20	28/15
	S - 38/23	38/17
	(I-)40/22(-P)	40/25
	(I-)50/30	49/30
35 mm	I-52/34	54/33
	50/30-P	
	52/34	




fischer Anchor Channel FES with fischer Channel Bolts FBC












Intended Use
Installation instruction for fischer Anchor Channels FES

Annex B5
Appendix 15 / 34

Channel bolt FBC



	FBC	FES-H(I)	FESC
2815	-	-	28/15
3817	-	-	38/17
4022	40/22	40/22	40/25
5030	50/30	52/34	49/30
		54/33	



FBC	T _{inst} [Nm]	M8	M10	M12	M16	M20
2815	A	7	10	13	-	-
	B	15	30	45	-	-
3817	A	-	15	20	30	-
	B	-	30	45	100	-
4022 ¹⁾	A	-	15	24	32	-
	B	-	30	45	100	-
5030 ²⁾	A	-	15	25	60	75
	B	-	30	45	100	230

¹⁾T_{inst} must not be exceeded.

²⁾applies to all materials (8.8 and A4-70).

fischer Ankerschiene FES mit fischer Spezialschrauben FBC

Verwendungszweck
Montageanleitung für fischer Zahnschrauben FBC-S

Anhang B7

Appendix 16 / 34

Serrated channel bolt FBC-S

1

	FBC-S	FES-H-S	FES-C
2920	29/20	29/20	-
3823	38/23	38/23	38/17

2

3

4

5

6

7

8

9

10

11

12

FBC-S	FES	T _{inst} ¹⁾ [Nm]	M12	M16
2920	HS-29/20	A	80	-
		B	80	-
3823 ²⁾	HS-38/23	A	80	100
		B	80	100
	C-38/17	A	40	50
		B	80	100

¹⁾T_{inst} must not be exceeded.

²⁾ Applies to all materials (8.8 and A4-70).

fischer Anchor Channel FES with fischer Channel Bolts FBC

Intended Use

Installation instruction for Serrated fischer Channel Bolts FBC-S

Annex B7

Appendix 17 / 34

Notching channel bolt FBC-N

1

FBC-N-4022	40/22	
FBC-N-5030		50/30 52/34

2

3

4

5

6

7

8

12

FBC-N-	FES-	T _{inst} ¹ [Nm]		
		M12	M16	M20
4022	H-(I)-4022-(P)	-	200	-
5030	H-(I)-5030-(P)	-	200	400
	H-(I)-52/34	-	200	400

¹⁾T_{inst} must not be exceeded.

fischer Anchor Channel FES with fischer Channel Bolts FBC

Intended Use

Installation instruction for Notching fischer Channel Bolts FBC-N

Annex B8

Appendix 18 / 34

Table C1.1: Characteristic resistances under tension load – steel failure of hot-rolled anchor channels

Anchor Channel FES-H-			S-29/20	S-38/23 S-38/23-A4	40/22 40/22-P I-40/22	50/30 50/30-P I-50/30	52/34 I-52/34
Steel failure: Anchor							
Characteristic resistance	N _{Rk,s,a}	[kN]	25,0	31,0 40,0	20,0 42,0 35,0	31,0 44,0 44,0	55,0 70,4
Partial factor	γ _{Ms} ¹⁾	[-]	1,8				
Steel failure: Connection between anchor and channel							
Characteristic resistance	N _{Rk,s,c}	[kN]	25,0	30,3 40,0	20,0 40,1 38,0	31,0 44,0 40,0	55,0 70,4
Partial factor	γ _{Ms} ¹⁾	[-]	1,8				
Steel failure: Local flexure of channel lips							
Characteristic spacing of channel bolts for N _{Rk,s,l}	s _{l,N}	[mm]	60	76	80 80 80	100 100 100	105 105
Characteristic resistance	N ⁰ _{Rk,s,l}	[kN]	25,0	30,3 45,0	38,0 42,0 38,0	43,0 52,0 43,0	72,0 72,0
Partial factor	γ _{Ms} ¹⁾	[-]	1,8				

¹⁾ In absence of other national regulations.

Table C1.2: Characteristic resistances under tension load – steel failure of cold-formed anchor channels

Anchor Channel FES-C-			28/15	38/17	40/25	49/30	54/33
Steel failure: Anchor							
Characteristic resistance	$N_{Rk,s,a}$	[kN]	9,0	20,0	20,0	31,0	55,0
Partial factor	$\gamma_{Ms}^{1)}$	[-]	1,8				
Steel failure: Connection between anchor and channel							
Characteristic resistance	$N_{Rk,s,c}$	[kN]	9,0	18,0	20,0	31,0	55,0
Partial factor	$\gamma_{Ms}^{1)}$	[-]	1,8				
Steel failure: Local flexure of channel lips							
Characteristic spacing of channel bolts for $N_{Rk,s,l}$	$s_{l,N}$	[mm]	56	76	80	100	108
Characteristic resistance	$N^0_{Rk,s,l}$	[kN]	9,0	18,0	20,0	31,0	55,0
Partial factor	$\gamma_{Ms}^{1)}$	[-]	1,8				

¹⁾ In absence of other national regulations.

fischer Anchor Channel FES with fischer Channel Bolts FBC

Performance

Characteristic resistances under tension load – Steel failure of anchor channel

Annex C1

Appendix 19 / 34

Table C2.1: Characteristic flexural resistance of hot rolled channels under tension load

Anchor Channel FES-H-			S-29/20	S-38/23 S-38/23-A4	40/22 40/22-P I-40/22	50/30 50/30-P I-50/30	52/34 I-52/34
Steel failure: Flexure of channel							
Characteristic flexural resistance of channel	$M_{Rk,s,flex}$	[Nm]	704	1.240 1.305	1.118 1.118 1.118	2.185 2.185 2.185	3.163 3.670
Partial factor	$\gamma_{Ms,flex}^{1)}$	[-]	1,15				

¹⁾ In absence of other national regulations.

Table C2.2: Characteristic flexural resistance of cold-formed channels under tension load

Anchor Channel FES-C-			28/15	38/17	40/25	49/30	54/33
Steel failure: Flexure of channel							
Characteristic flexural resistance of channel	$M_{Rk,s,flex}$	[Nm]	310	567	915	1.554	2.350
Partial factor	$\gamma_{Ms,flex}^{1)}$	[-]	1,15				

¹⁾ In absence of other national regulations.

fischer Anchor Channel FES with fischer Channel Bolts FBC

Performance

Characteristic resistances under tension load – Steel failure of anchor channel

Annex C2

Appendix 20 / 34

Table C3.1: Characteristic resistances under tension load – concrete failure of hot rolled anchor channels

Anchor Channel FES-H-			S-29/20	S-38/23	40/22 40/22-P I-40/22	50/30 50/30-P I-50/30	52/34 I-52/34
Concrete failure: Pull-out failure							
Characteristic resistance in cracked concrete C12/15	N _{Rk,p}	[kN]	18,4	21,2	13,6 21,2 27,0	21,2 33,2 33,8	33,2 54,0
Characteristic resistance in uncracked concrete C12/15			25,7	29,7	19,0 29,7 37,8	29,7 46,5 47,3	46,5 75,6
Increasing factor of N _{Rk,p} = N _{Rk,p} (C12/15)*ψ _c	C16/20	ψ _c [-]	1,33				
	C20/25		1,67				
	C25/30		2,08				
	C30/37		2,50				
	C35/45		2,92				
	C40/50		3,33				
	C45/55		3,75				
	C50/60		4,17				
	C55/67		4,58				
	≥C60/75		5,00				
Partial factor	γ _{Mp} =γ _{Mc} ¹⁾	[-]	1,5				
Concrete failure: Concrete cone failure							
Product factor k ₁	k _{cr,N}	[-]	7,8	8,1	8,0 8,0 7,9	8,1 8,2 8,1	8,7 8,7
	k _{ucr,N}	[-]	11,2	11,6	11,4 11,5 11,2	11,5 11,7 11,5	12,4 12,4
Partial factor	γ _{Mc} ¹⁾	[-]	1,5				
Concrete failure: Splitting							
Characteristic edge distance	C _{cr,sp}	[mm]	231	291	270 273 237	282 318 282	465 465
Characteristic spacing	S _{cr,sp}	[mm]	462	582	540 546 474	564 636 564	930 930
Partial factor	γ _{Msp} =γ _{Mc} ¹⁾	[-]	1,5				

¹⁾ In absence of other national regulations.

fischer Anchor Channel FES with fischer Channel Bolts FBC

Performance

Characteristic resistances under tension load – concrete failure of hot rolled anchor channels

Annex C3

Appendix 21 / 34

Table C4.1: Characteristic resistances under tension load – concrete failure of cold-formed anchor channels

Anchor Channel FES-C-			28/15	38/17	40/25	49/30	54/33
Concrete failure: Pull-out failure							
Characteristic resistance in cracked concrete C12/15	N _{Rk,p}	[kN]	7,6	13,6	13,6	21,2	33,2
Characteristic resistance in uncracked concrete C12/15			10,7	19,0	19,0	29,7	46,5
Increasing factor of N _{Rk,p} = N _{Rk,p} (C12/15)*ψ _c	C16/20	ψ _c [-]	1,33				
	C20/25		1,67				
	C25/30		2,08				
	C30/37		2,50				
	C35/45		2,92				
	C40/50		3,33				
	C45/55		3,75				
	C50/60		4,17				
	C55/67		4,58				
	≥C60/75		5,00				
Partial factor	γ _{Mp} =γ _{Mc} ¹⁾	[-]	1,5				
Concrete failure: Concrete cone failure							
Product factor k ₁	k _{Cr,N}	[-]	7,2	7,8	7,9	8,1	8,7
	k _{ucr,N}	[-]	10,3	11,2	11,2	11,5	12,4
Partial factor	γ _{Mc} ¹⁾	[-]	1,5				
Concrete failure: Splitting failure							
Characteristic edge distance	C _{cr,sp}	[mm]	135	228	237	282	465
Characteristic spacing	S _{cr,sp}	[mm]	270	456	474	564	930
Partial factor	γ _{Msp} =γ _{Mc} ¹⁾	[-]	1,5				

¹⁾ In absence of other national regulations.

fischer Anchor Channel FES with fischer Channel Bolts FBC

Performance

Characteristic resistances under tension load – concrete failure of cold formed anchor channels

Annex C4

Appendix 22 / 34

Table C5.1: Displacements of hot-rolled anchor channels under tension load

Anchor Channel FES-H-			S-29/20	S-38/23 S-38/23-A4	40/22 40/22-P I-40/22	50/30 50/30-P I-50/30	52/34 I-52/34
Tension load	N	[kN]	14,6	19,4 19,2	15,1 16,7 15,1	17,1 20,6 17,1	28,6 28,6
Short-term displacement ¹⁾	δ_{N0}	[mm]	2,3	1,4 1,3	2,2 2,5 2,2	1,5 1,8 1,5	1,9 1,9
Long-term displacement ¹⁾	$\delta_{N\infty}$	[mm]	4,6	2,8 2,6	4,4 5,0 4,4	3,0 3,6 3,0	3,8 3,8

¹⁾ Displacements in midspan of the anchor channel, including slip of channel bolt, deformation of channel lips, bending of the channel and slip of the anchor channel in concrete.

Table C5.2: Displacements of cold-formed anchor channels under tension load

Anchor Channel FES-C-			28/15	38/17	40/25	49/30	54/33
Tension load	N	[kN]	3,6	7,1	7,9	12,3	21,8
Short-term displacement ¹⁾	δ_{N0}	[mm]	0,7	1,3	1,5	1,4	1,2
Long-term displacement ¹⁾	$\delta_{N\infty}$	[mm]	1,4	2,6	3,0	2,8	2,4

¹⁾ Displacements in midspan of the anchor channel, including slip of channel bolt, deformation of channel lips, bending of the channel and slip of the anchor channel in concrete.

fischer Anchor Channel FES with fischer Channel Bolts FBC

Performance

Characteristic resistance under tension load - displacements

Annex C5

Appendix 23 / 34

Table C6.1: Characteristic resistances under shear load – steel failure of hot-rolled anchor channels

Anchor Channel FES-H-			S-29/20	S-38/23 S-38/23-A4	40/22 40/22-P I-40/22	50/30 50/30-P I-50/30	52/34 I-52/34
Steel failure: Anchor							
Characteristic resistance	$V_{Rk,s,a,y}$	[kN]	25,0	30,3 40,0	40,0 50,8 40,0	60,0 87,9 60,0	100 100
	$V_{Rk,s,a,x}$	[kN]	15,1	18,8 24,0	12,0 25,4 22,8	18,6 26,8 24,0	33,0 42,2
Partial factor	$\gamma_{Ms}^{1)}$	[-]	1,8				
Steel failure: Connection between anchor and channel							
Characteristic resistance	$V_{Rk,s,c,y}$	[kN]	25,0	30,3 40,0	40,0 50,8 40,0	60,0 87,9 60,0	100 100
	$V_{Rk,s,c,x}$	[kN]	15,0	18,2 24,0	12,0 25,2 22,8	18,6 26,4 24,0	33,0 42,2
Partial factor	$\gamma_{Ms}^{1)}$	[-]	1,8				
Steel failure: Local flexure of channel lips							
Characteristic spacing of channel bolts for $V_{Rk,s,l}$	$s_{l,v}$	[mm]	60	76	80 80 80	100 100 100	108 108
Characteristic resistance	$V^0_{Rk,s,l,y}$	[kN]	25,0	30,3 40,0	40,0 50,8 40,0	60,0 87,9 60,0	100 100
Partial factor	$\gamma_{Ms}^{1)}$	[-]	1,8				

¹⁾ In absence of other national regulations.

fischer Anchor Channel FES with fischer Channel Bolts FBC

Performance

Characteristic resistance under shear load - Steel failure of hot-rolled anchor channels

Annex C6

Appendix 24 / 34

Table C7.1: Characteristic resistances under shear load – steel failure of cold-formed anchor channels

Anchor Channel FES-C-			28/15	38/17	40/25	49/30	54/33
Steel failure: Anchor							
Characteristic resistance	$V_{Rk,s,a,y}$	[kN]	9	18	20	31	55
	$V_{Rk,s,a,x}$	[kN]	–2)	–2)	–2)	–2)	–2)
Partial factor	γ_{Ms} 1)	[-]	1,8				
Steel failure: Connection between anchor and channel							
Characteristic resistance	$V_{Rk,s,c,y}$	[kN]	9	18	20	31	55
	$V_{Rk,s,c,x}$	[kN]	–2)	–2)	–2)	–2)	–2)
Partial factor	γ_{Ms} 1)	[-]	1,8				
Steel failure: Local flexure of channel lips							
Characteristic spacing of channel bolts for $V_{Rk,s,l}$	$s_{l,V}$	[mm]	56	76	80	100	108
Characteristic resistance	$V^0_{Rk,s,l,y}$	[kN]	9	18	20	31	55
Partial factor	γ_{Ms} 1)	[-]	1,8				

¹⁾ In absence of other national regulations.

²⁾ No performance assessed.

fischer Anchor Channel FES with fischer Channel Bolts FBC

Performance

Characteristic resistance under shear load - Steel failure of cold-formed anchor channels

Annex C7

Appendix 25 / 34

Table C8.1: Characteristic resistance for shear load in direction of the longitudinal axis of the channel – steel failure

Anchor Channel FES-H-			S-29/20	S-38/23	40/22 40/22-P I-40/22	50/30 50/30-P I-50/30	52/34 I-52/34
Steel failure: Connection between channel lips and channel bolt							
Characteristic resistance	$V_{Rk,s,l,x}$	[kN]	FBC-S-29/20-M12-8.8	22,5	– ²⁾	– ²⁾	– ²⁾
			FBC-S-38/23-M12-8.8	– ²⁾	23,2	– ²⁾	– ²⁾
			FBC-S-38/23-M12-A4-70	– ²⁾	29,0	– ²⁾	– ²⁾
			FBC-S-38/23-M16-8.8	– ²⁾	30,3	– ²⁾	– ²⁾
			FBC-S-38/23-M16-A4-70	– ²⁾	29,0	– ²⁾	– ²⁾
			FBC-N-40/22-M16-8.8	– ²⁾	– ²⁾	14,0	– ²⁾
			FBC-N-50/30-M16-8.8	– ²⁾	– ²⁾	10,7	10,7
			FBC-N-50/30-M20-8.8	– ²⁾	– ²⁾	21,0	21,0
Installation factor	$\gamma_{inst}^{1)}$	[-]		1,2	8.8: 1,0 A4-70: 1,2	1,2	M16: 1,2 M20: 1,4

¹⁾ In absence of other national regulations.

²⁾ No performance assessed.

Table C8.2: Characteristic resistances of the hot-rolled anchor channel under shear load – concrete failure

Anchor Channel FES-H-			S-29/20	S-38/23	40/22 40/22-P I-40/22	50/30 50/30-P I-50/30	52/34 I-52/34
Concrete failure: Pry-out failure							
Product factor	k ₈	[-]	2,0	2,0	2,0	2,0	2,0
Partial factor	γ _{Mc} ¹⁾	[-]	1,5				
Concrete failure: Concrete edge failure							
Product factor k ₁₂	k _{cr,V}	[-]	7,5	7,5	7,5	7,5	7,5
	k _{ucr,V}	[-]	10,5	10,5	10,5	10,5	10,5
Partial factor	γ _{Mc} ¹⁾	[-]	1,5				

¹⁾ In absence of other national regulations.

Table C8.3: Characteristic resistances of the cold-formed anchor channel under shear load – concrete failure

Anchor Channel FES-C			28/15	38/17	40/25	49/30	54/33
Concrete failure: Pry-out failure							
Product factor	k ₈	[-]	1	2	2	2	2
Partial factor	γ _{Mc} ¹⁾	[-]	1,5				
Concrete failure: Concrete edge failure							
Product factor k ₁₂	k _{Cr,V}	[-]	5,8	7,5	7,5	7,5	7,5
	k _{uCr,V}	[-]	8,1	10,5	10,5	10,5	10,5
Partial factor	γ _{Mc} ¹⁾	[-]	1,5				

¹⁾ In absence of other national regulations.

fischer Anchor Channel FES with fischer Channel Bolts FBC

Performance
Characteristic resistance under shear load

Annex C8
Appendix 26 / 34

Table C9.1: Displacements under shear load

Anchor Channel FES-			C-28/15	C-38/17	H-S-29/20	H-S-38/23 H-S-38/23-A4	C-40/25 H-40/22 H-40/22-P H-I-40/22	C-49/30 H-50/30 H-50/30-P H-I-50/30	C-54/33 H-52/34 H-I-52/34
Shear load perpendicular to the longitudinal axis of the channel	V_y	[kN]	3,6	7,1	14,6	23,0 23,0	7,9 15,9 20,2 15,9	12,3 23,8 34,9 23,8	21,8 39,7 39,7
Short-term displacement ¹⁾	$\delta_{V,y,0}$	[mm]	0,7	1,3	2,3	3,8 2,8	1,5 2,1 2,2 2,1	1,4 3,7 2,1 3,7	1,2 4,0 4,0
Long-term displacement ¹⁾	$\delta_{V,y,\infty}$	[mm]	1,1	2,0	3,5	5,7 4,2	2,3 3,2 3,3 3,2	2,1 5,5 3,2 5,5	1,8 5,9 5,9
Shear load in direction of the longitudinal axis of the channel	V_x	[kN]	- ³⁾	- ³⁾	16,6	15,4 21,2	- ³⁾ 4,6 4,6 4,6	- ³⁾ 4) 4) 4)	- ³⁾ 4) 4)
Short-term displacement ²⁾	$\delta_{V,x,0}$	[mm]	- ³⁾	- ³⁾	1,9	0,8 2,0	- ³⁾ 0,9 0,9 0,9	- ³⁾ 5) 5) 5)	- ³⁾ 5) 5)
Long-term displacement ²⁾	$\delta_{V,x,\infty}$	[mm]	- ³⁾	- ³⁾	2,9	1,2 3,0	- ³⁾ 1,4 1,4 1,4	- ³⁾ 6) 6) 6)	- ³⁾ 6) 6)

¹⁾ Displacements in midspan of the anchor channel, including slip of channel bolt, deformation of channel lips and slip of the anchor channel in concrete.

²⁾ Displacements of the anchor channel, including slip of channel bolt, deformation of channel lips and slip of the anchor channel in concrete.

³⁾ No performance assessed.

⁴⁾ For FBC-N-5030-M16 $V_x = 3,5$ kN, for FBC-N-5030-M20 $V_x = 6,7$ kN.

⁵⁾ For FBC-N-5030-M16 $\delta_{V,x,0} = 0,4$ mm, for FBC-N-5030-M20 $\delta_{V,x,0} = 0,1$ mm.

⁶⁾ For FBC-N-5030-M16 $\delta_{V,x,\infty} = 0,6$ mm, for FBC-N-5030-M20 $\delta_{V,x,\infty} = 0,2$ mm.

Table C9.2: Characteristic resistances under combined tension and shear load

Anchor Channel FES-			C-28/15	C-38/17	H-S-29/20	H-S-38/23	C-40/25 H-40/22 H-40/22-P H-I-40/22	C-49/30 H-50/30 H-50/30-P H-I-50/30	C-54/33 H-52/34 H-I-52/34
Steel failure: Local flexure of channel lips and flexure of channel									
Product factor	k ₁₃	[-]	according to EN 1992-4:2018, 7.4.3.1						
Steel failure: Anchor and connection between anchor and channel									
Product factor	k ₁₄	[-]	according to EN 1992-4:2018, 7.4.3.1						

fischer Anchor Channel FES with fischer Channel Bolts FBC
Performance

Displacement under shear load, characteristic resistance under combined tension and shear load

Annex C9

Appendix 27 / 34

Table C10.1: Characteristic resistances under tension and shear load – steel failure of channel bolts

Channel bolt thread diameter				M8	M10	M12	M16	M20	
Steel failure: Special screw 8.8									
Characteristic tensile resistance	FBC-28/15	N _{Rk,s}	[kN]	29,2	33,0	45,1	-2)	-2)	
	FBC-38/17			-2)	46,4	67,4	89,9	-2)	
	FBC-S-29/20			-2)	-2)	48,5	-2)	-2)	
	FBC-S-38/23			-2)	-2)	67,4	71,5	-2)	
	FBC-40/22			-2)	46,4	55,1	82,2	-2)	
	FBC-N-40/22			-2)	-2)	-2)	100,9	-2)	
	FBC-50/30			-2)	46,4	67,4	96,5	127,2	
	FBC-N-50/30			-2)	-2)	-2)	113,5	134,0	
Partial factor		γ _{Ms} ¹⁾	[-]	1,5					
Steel failure: Special screw A4-70									
Characteristic tensile resistance	FBC-S-38/23	N _{Rk,s}	[kN]	-2)	-2)	59,0	71,5	-2)	
	FBC-40/22			-2)	-2)	54,9	102,8	-2)	
	FBC-50/30			-2)	-2)	59,0	82,8	163,1	
Partial factor		γ _{Ms} ¹⁾	[-]	1,87					
Characteristic shear resistance 8.8			V _{Rk,s}	[kN]	14,6	23,2	33,7	62,8	98,0
Characteristic shear resistance A4-70					-2)	-2)	35,4	65,9	102,9
Partial factor (shear loads 8.8)			γ _{Ms} ¹⁾	[-]	1,25				
Partial factor (shear loads A4-70)			γ _{Ms} ¹⁾	[-]	1,56				

¹⁾ In absence of other national regulations.

²⁾ No performance assessed.

fischer Anchor Channel FES with fischer Channel Bolts FBC

Performance

Characteristic resistances under tension and shear load of channel bolts

Annex C10

Appendix 28 / 34

Table C11.1: Characteristic resistances under shear load with lever arm – steel failure of channel bolts

Channel bolt ²⁾ thread diameter					M8	M10	M12	M16	M20
Steel failure									
Characteristic flexural resistance	M ⁰ _{Rk,s}	[Nm]	FBC-(S-) (N-)	8.8	30,0	59,8	104,8	266,4	519,3
				A4-70	- ³⁾	- ³⁾	91,7	233,1	454,4
Partial factor	γ _{Ms} ¹⁾	[-]	FBC-(S-) (N-)	8.8	1,25				
				A4-70	1,56				
Internal lever arm	a	[mm]	FBC-28/15	8.8	16,7	18,1	19,4	- ³⁾	- ³⁾
			FBC-38/17	8.8	- ³⁾	22,7	24,0	26,0	- ³⁾
			FBC-S-29/20	8.8	- ³⁾	- ³⁾	20,0	- ³⁾	- ³⁾
			FBC-S-38/23	8.8 A4-70	- ³⁾	- ³⁾	22,4	25,7	- ³⁾
			FBC-40/22	8.8	- ³⁾	23,5	24,8	26,8	- ³⁾
			FBC-N-40/22	8.8	- ³⁾	- ³⁾	- ³⁾	26,9	- ³⁾
			FBC-50/30	8.8	- ³⁾	27,7	29,0	31,0	33,3
			FBC-N-50/30	8.8	- ³⁾	- ³⁾	- ³⁾	31,5	33,9
			FBC-40/22	A4-70	- ³⁾	- ³⁾	24,7	26,7	- ³⁾
			FBC-50/30	A4-70	- ³⁾	- ³⁾	28,8	30,9	33,1

¹⁾ In absence of other national regulations.

²⁾ Materials according to Annex A7, Table A7.1.

³⁾ No performance assessed.

The characteristic flexure resistance according to Table C11.1 is limited as follows:


$$M_{Rk,s}^0 \leq 0,5 \cdot N_{Rk,s,l}^0 \cdot a \quad (N_{Rk,s,l}^0 \text{ according to Annex C1, Table C1.1 and Table C1.2})$$

$$M_{Rk,s}^0 \leq 0,5 \cdot N_{Rk,s} \cdot a \quad (N_{Rk,s} \text{ according to Annex C10, Table 10.1})$$

a = Internal lever arm according to Table C11.1

T_s = Tension force acting on the channel lips

C_s = Compression force acting on the channel lips



fischer Anchor Channel FES with fischer Channel Bolts FBC

Performance

Characteristic resistances under shear load of channel bolts

Annex C11

Appendix 29 / 34

**Table 12.1: Combination of anchor channels and channel bolts under seismic load
(performance category C1)**

Anchor channel FES-	Channel Bolt FBC-	Thread diameter	Steel grade	Corrosion protection
H-S-38/23	S-38/23	M12 M16	8.8	G ¹⁾ F ²⁾
H-50/30 H-52/34	N-50/30	M20		

¹⁾ Electroplated.

²⁾ Hot-dip galvanised.

**Table C12.2: Characteristic resistance under seismic tension load- steel failure of anchor channels
(performance category C1)**

Anchor Channel FES-H-			S-38/23	H50/30	H52/34
Steel failure: Anchor					
Characteristic resistance	N _{Rk,s,a,eq}	[kN]	31,0	31,0	31,0
Partial factor	γ _{Ms,eq} ¹⁾	[-]	1,8		
Steel failure: Connection between anchor and channel					
Characteristic resistance	N _{Rk,s,c,eq}	[kN]	30,3	31,0	31,0
Partial factor	γ _{Ms,eq} ¹⁾	[-]	1,8		
Steel failure: Local flexure of channel lips					
Characteristic resistance	N ⁰ _{Rk,s,l,eq}	[kN]	30,3	43,0	43,0
Partial factor	γ _{Ms,eq} ¹⁾	[-]	1,8		

¹⁾ In absence of other national regulations.

**Table 12.3: Characteristic flexural resistance of the channel under seismic tension load
(performance category C1)**

Anchor Channel FES-			H-S-38/23	H-50/30	H-52/43
Steel failure: Flexure of channel					
Characteristic flexural resistance of channel	$M_{Rk,s,flex,eq}$	[Nm]	1.240	2.185	2.185
Partial factor	$\gamma_{Ms,flex,eq}$ ¹⁾	[-]	1,15		

¹⁾ In absence of other national regulations.

fischer Anchor Channel FES with fischer Channel Bolts FBC

Performance

Characteristic resistance under seismic tension load (performance category C1)

Annex C12

Appendix 30 / 34

**Table C13.1: Characteristic resistance under seismic shear load- steel failure of anchor channels
(performance category C1)**

Anchor Channel FES-			H-S-38/23	H-50/30	H-52/34
Steel failure: Anchor					
Characteristic resistance	$V_{Rk,s,a,y,eq}$	[kN]	30,3	60,0	60,0
	$V_{Rk,s,a,x,eq}$	[kN]	18,8	18,6	18,6
Partial factor	$\gamma_{Ms,eq}^{1)}$	[-]	1,8		
Steel failure: Connection between anchor and channel					
Characteristic resistance	$V_{Rk,s,c,y,eq}$	[kN]	30,3	60,0	60,0
	$V_{Rk,s,c,x,eq}$	[kN]	18,2	18,6	18,6
Partial factor	$\gamma_{Ms,eq}^{1)}$	[-]	1,8		
Steel failure: Local flexure of channel lips					
Characteristic resistance	$V_{Rk,s,l,y,eq}^0$	[kN]	30,3	60,0	60,0
Partial factor	$\gamma_{Ms,eq}^{1)}$	[-]	1,8		

¹⁾ In absence of other national regulations.

Table C13.2: Characteristic resistance for seismic shear load in direction of the longitudinal axis of the channel - steel failure (performance category C1)

Anchor Channel FES-				H-S-38/23	H-50/30	H-52/34
Steel failure: Connection between channel lips and channel bolt						
Characteristic resistance	$V_{Rk,s,l,x,eq}$	[kN]	FBC-S-38/23-M12-8.8	23,2	- ²⁾	- ²⁾
			FBC-S-38/23-M16-8.8	23,2	- ²⁾	- ²⁾
			FBC-N-50/30-M20-8.8	- ²⁾	21,0	21,0
Installation factor	$\gamma_{inst}^{1)}$	[-]		1,0	1,4	1,4

¹⁾ In absence of other national regulations.

²⁾ No performance assessed.

fischer Anchor Channel FES with fischer Channel Bolts FBC

Performance

Characteristic resistance under seismic shear load perpendicular to the channel and in direction of the longitudinal axis of the channel (performance category C1)

Annex C13

Appendix 31 / 34

**Table C14.1: Characteristic resistance under seismic tension and seismic shear load
– steel failure of channel bolt (performance category C1)**

Channel bolt thread diameter				M12	M16	M20
Steel failure: Special screw						
Characteristic tensile resistance	FBC-S-38/23	$N_{Rk,s,eq}$	[kN]	67,4	67,4	– ²⁾
	FBC-N-50/30			– ²⁾	– ²⁾	134,0
Partial factor		γ_{Ms} ¹⁾	[-]	1,5		
Characteristic shear resistance 8.8		$V_{Rk,s,eq}$	[kN]	33,7	33,7	98,0
Partial factor (shear loads 8.8)		γ_{Ms} ¹⁾	[-]	1,25		

¹⁾ In absence of other national regulations.

²⁾ No performance assessed.

fischer Anchor Channel FES with fischer Channel Bolts FBC

Performance

Characteristic resistance of the channel bolt under seismic tension and seismic shear load (performance category C1)

Annex C14

Appendix 32 / 34

Table C15.1: Characteristic resistance under fire exposure – steel failure

Channel bolt thread diameter						M8	M10	M12	M16	M20
Steel failure:		Anchor, connection between anchor and channel, local flexure of channel lips, channel bolts								
Characteristic resistance under fire exposure ³⁾	FES-H-S-29/2	FBC-S-29/20	R30 R60 R90 R120	$N_{Rk,s,fi}$ = $V_{Rk,s,y,fi}$	[kN]	- 2)	- 2)	2,5 2,4 1,7 1,4	- 2)	- 2)
	FES-H-S-38/23	FBC-S-38/23	R30 R60 R90 R120			- 2)	- 2)	4,6 4,1 2,8 2,1	4,6 4,1 2,8 2,1	- 2)
	FES-H(-I)-40/22(-P)	FBC-40/22	R30 R60 R90 R120			- 2)	1,3 1,0 0,7 0,6	2,0 1,7 1,4 1,3	4,5 3,4 2,3 1,7	- 2)
	FES-H(-I)-50/30(-P)	FBC(-N)-50/30	R30 R60 R90 R120			- 2)	1,3 1,0 0,7 0,6	2,0 1,7 1,4 1,3	5,2 4,2 3,2 2,7	5,2 4,2 3,2 2,7
	FES-H(-I)-52/34	FBC(-N)-50/30	R30 R60 R90 R120			- 2)	1,3 1,0 0,7 0,6	4,6 4,1 2,8 2,1	5,2 4,2 3,2 2,7	8,0 6,5 5,0 4,2
	FES-C-28/15	FBC-28/15	R30 R60 R90 R120			0,6 0,6 0,5 0,4	1,3 1,0 0,7 0,6	1,3 1,0 0,7 0,6	- 2)	- 2)
	FES-C-38/17	FBC-38/17 FBC-S-38/23-M16	R30 R60 R90 R120			- 2)	1,3 1,0 0,7 0,6	1,3 1,0 0,7 0,6	3,5 2,8 1,8 1,3	- 2)
	FES-C-40/25	FBC-40/22	R30 R60 R90 R120			- 2)	1,8 1,5 1,1 0,8	3,0 2,4 1,7 1,4	3,5 2,8 1,8 1,3	- 2)
	FES-C-49/30	FBC-50/30	R30 R60 R90 R120			- 2)	1,3 1,0 0,7 0,6	2,9 2,4 1,8 1,6	3,1 2,5 1,9 1,6	3,1 2,5 1,9 1,6
	FES-C-54/33	FBC-50/30	R30 R60 R90 R120			- 2)	1,3 1,0 0,7 0,6	2,9 2,4 1,8 1,6	3,1 2,5 1,9 1,6	3,1 2,5 1,9 1,6
Partial factor				$\gamma_{Ms,fi}^{1)}$	[-]	1,0				

¹⁾ In absence of other national regulations.

²⁾ No performance assessed.

³⁾ Values also valid for stainless steel A4-70.

fischer Anchor Channel FES with fischer Channel Bolts FBC

Performance


Characteristic resistance under fire exposure

Annex C15


Appendix 33 / 34

Table C16.1: Minimum axis distance of the reinforcement under fire exposure

Anchor Channel FES-			C-28/15	C-38/17	H-S-29/20	H-S-38/23	C-40/25 H-40/22 H-40/22-P H-I-40/22	C-49/30 H50/30 H-50/30-P H-I-50/30	C-54/33 H-52/34 H-I-52/34
Minimum axis distance	R30	a [mm]	35	35	35	35	35	35	50
	R60		35	35	35	35	35	35	50
	R90		45	45	45	45	45	45	50
	R120		60	60	60	60	60	60	65



Fire exposure from one side only.



Fire exposure from more than one side.

fischer Anchor Channel FES with fischer Channel Bolts FBC

Performance
Characteristic resistance under fire exposure