

## DEKLARACJA WŁAŚCIWOŚCI UŻYTKOWYCH

### DoP 0182

dla systemu wklejanego fischer FIS V (Zaprawa do wklejania dodatkowych połączeń prętów zbrojeniowych)

PL

1. Niepowtarzalny kod identyfikacyjny typu wyrobu: DoP 0182
2. Zamierzone zastosowanie: System do wklejania prętów zbrojeniowych z zaprawą do stosowania w betonie. Zobacz załącznik, w szczególności aneksy B1- B11
3. Producent: fischerwerke GmbH & Co. KG, Otto-Hahn-Straße 15, 79211 Denzlingen, Niemcy
4. Upoważniony przedstawiciel: –
5. System(-y) oceny i weryfikacji stałości właściwości użytkowych: 1
6. Europejski dokument oceny: EAD 330087-00-0601  
Europejska ocena techniczna: ETA-08/0266; 2020-01-07  
Jednostka ds. oceny technicznej: DIBt- Deutsches Institut für Bautechnik  
Jednostka lub jednostki notyfikowane: 1343 MPA Darmstadt / 2873 TU Darmstadt
7. Deklarowane właściwości użytkowe:  
**Wytrzymałość mechaniczna i stabilność osadzenia (BWR 1)**  
Nośność charakterystyczna na wrywanie (nośności statyczne i quasi-statyczne): Siła wiązania wklejanego pręta zbrojeniowego: Aneksy C1  
Współczynnik redukujący: Aneksy C1  
  
Współczynnik wzmocnienia dla minimalnej długości zakotwienia: Aneksy C1

### Ochrona przeciwpożarowa (BWR 2)

Odporność ogniowa

Klasy (A1)

Odporność na działanie ognia:

Siła wiązania w podwyższonej temperaturze:

Aneksy C2, C3



8. Odpowiednia dokumentacja techniczna lub specjalna –  
dokumentacja techniczna:

Właściwości użytkowe określonego powyżej wyrobu są zgodne z zestawem deklarowanych właściwości użytkowych. Niniejsza deklaracja właściwości użytkowych wydana zostaje zgodnie z rozporządzeniem (UE) nr 305/2011 na wyłączną odpowiedzialność producenta określonego powyżej.

W imieniu producenta podpisać(-a):

ppa. Thilo Prg

Thilo Pregartner, Dr.-Ing.  
Tumlingen, 2020-01-21

i.V. P. Sch

Peter Schillinger, Dipl.-Ing.

Niniejsza Deklaracja Właściwości Użytkowych została przygotowana w różnych językach. W razie wątpliwości w interpretacji, wersja angielska jest zawsze miarodajna.

Załącznik zawiera dobrowolne i uzupełniające informacje w języku angielskim (neutralne językowo), a wykraczające poza wymagania prawne.

## Specific Part

### 1 Technical description of the product

The subject of this European technical assessment is the post-installed connection, by anchoring or overlap connection joint, of reinforcing bars (rebars) in existing structures made of normal weight concrete, using the injection mortar FIS V in accordance with the regulations for reinforced concrete construction.

Reinforcing bars with a diameter  $\phi$  from 8 to 28 mm or the fischer rebar anchor FRA of sizes M12 to M24 according to Annex A and the fischer injection mortar FIS V are used for the post-installed rebar connection. The steel element is placed into a drilled hole filled with injection mortar and is anchored via the bond between embedded reinforcing bar, injection mortar and concrete.

The product description is given in Annex A.

### 2 Specification of the intended use in accordance with the applicable European assessment Document

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the rebar connections of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

### 3 Performance of the product and references to the methods used for its assessment

#### 3.1 Mechanical resistance and stability (BWR 1)

| Essential characteristic                                        | Performance   |
|-----------------------------------------------------------------|---------------|
| Characteristic resistance under static and quasi-static loading | See Annex C 1 |

#### 3.2 Safety in case of fire (BWR 2)

| Essential characteristic | Performance           |
|--------------------------|-----------------------|
| Reaction to fire         | Class A1              |
| Resistance to fire       | See Annex C 2 and C 3 |

### 4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

In accordance with European Assessment Document EAD No. 330087-00-0601, the applicable European legal act is: [96/582/EC].

The system to be applied is: 1

Installation conditions and application examples reinforcing bars, part 1

Figure A1.1:

Overlap joint with existing reinforcement for rebar connections of slabs and beams




Figure A1.2:

Overlap joint with existing reinforcement at a foundation of a column or wall where the rebar is stressed





Figure A1.3:

End anchoring of slabs or beams (e.g. designed as simply supported)



Figures not to scale

Rebar connection with fischer injection mortar FIS V

Product description

Installation conditions and application examples reinforcing bars, part 1

Annex A 1

Appendix 2/ 21

Installation conditions and application examples reinforcing bars, part 2

Figure A2.1:  
Rebar connection for stressed primarily in compression





Figure A2.2:  
Anchoring of reinforcement to cover the enveloped line of acting tensile force in the bending member



Note to **figure A1.1 to A1.3** and **figure A2.1 to A2.2**

In the figures no traverse reinforcement is plotted, the transverse reinforcement shall comply with EN 1992-1-1: 2004+AC:2010.

Preparing of joints according to **Annex B 2**

Figures not to scale

Rebar connection with fischer injection mortar FIS V

**Product description**  
Installation conditions and application examples reinforcing bars, part 2


**Annex A 2**

Appendix 3/ 21

## Installation conditions and application examples fischer rebar anchor FRA, part 3


**Figure A3.1:**

Lap to a foundation of a column under bending.




**Figure A3.2:**

Lap of the anchoring of guardrail posts. In the anchor plate, the drill holes for the fischer rebar anchors FRA have to be designed as slotted holes with axial direction to the shear force.



**Figure A3.3:**

Lap of the anchoring of cantilevered building components. In the anchor plate, the drill holes for the fischer rebar anchors FRA have to be designed as slotted holes with axial direction to the shear load.



The required transverse reinforcement acc. to EN 1992-1-1:2004+AC:2010 is not shown in the figures. **The fischer rebar anchor FRA may be only used for axial tensile force.** The tensile force must be transferred by lap to the existing reinforcement of the building. The transfer of the shear force has to be ensured by suitable measure, e.g. by means of shear force or anchors with European Technical Assessment (ETA)

Figures not to scale

Rebar connection with fischer injection mortar FIS V

### Product description

Installation conditions and application examples fischer rebar anchors FRA, part 3



**Annex A 3**

Appendix 4/ 21


## Overview system components

### Injection cartridge (shuttle cartridge) FIS V with sealing cap



Sizes: 350ml, 360 ml, 390 ml, 585 ml, 950 ml, 1500 ml



**Imprint:** fischer FIS V or FIS VS Low Speed, processing notes, shelf-life, hazard code, curing times and processing times (depending on temperature), piston travel scale (optional), size, volume




### Injection cartridge (coaxial cartridge) FIS V with sealing cap; Sizes: 300 ml ,380 ml, 400 ml, 410 ml




**Imprint:** fischer FIS V or FIS VS Low Speed, processing notes, shelf-life, hazard code, curing times and processing times (depending on temperature), piston travel scale (optional), size, volume





### Static mixer FIS MR Plus for injection cartridges up to 410 ml



### Static mixer FIS UMR for injection cartridges from 585 ml



### Injection adapter and extension tube Ø 9 for static mixer FIS MR Plus; Injection adapter and extension tube Ø 9 or Ø 15 for static mixer FIS UMR



### Reinforcing bar (rebar) Sizes: $\phi 8$ , $\phi 10$ , $\phi 12$ , $\phi 14$ , $\phi 16$ , $\phi 20$ , $\phi 25$ , $\phi 28$



marking setting depth

### fischer rebar anchor FRA Sizes: M12, M16, M20, M24



### Blow out pump ABP



Figures not to scale

### Rebar connection with fischer injection mortar FIS V

#### Product description

Overview system components; Injection mortar, static mixer, injection adapter, reinforcing bar, rebar anchor FRA, blow out pump

## Annex A 4

Appendix 5/ 21

Properties of reinforcing bars (rebar)

Figure A5.1:



- The minimum value of related rip area  $f_{R,min}$  according to EN 1992-1-1:2004+AC:2010
- The maximum outer rebar diameter over the ribs shall be:
  - The nominal diameter of the rip  $\phi + 2 \cdot h$  ( $h \leq 0,07 \cdot \phi$ )
  - ( $\phi$ : Nominal diameter of the bar;  $h$ : rip height of the bar)

Table A5.1: Installation conditions for rebars

| Nominal diameter of the bar          |           | $\phi$ | 8 <sup>1)</sup>              |    | 10 <sup>1)</sup> |    | 12 <sup>1)</sup> |              | 14 | 16 | 20 | 25 | 28 |
|--------------------------------------|-----------|--------|------------------------------|----|------------------|----|------------------|--------------|----|----|----|----|----|
| Nominal drill hole diameter          | $d_0$     | [mm]   | 10                           | 12 | 12               | 14 | 14               | 16           | 18 | 20 | 25 | 30 | 35 |
| Drill hole depth                     | $h_0$     |        | $h_0 = l_v$                  |    |                  |    |                  |              |    |    |    |    |    |
| Effective embedment depth            | $l_v$     |        | acc. to static calculation   |    |                  |    |                  |              |    |    |    |    |    |
| Minimum thickness of concrete member | $h_{min}$ |        | $l_v + 30$<br>( $\geq 100$ ) |    |                  |    |                  | $l_v + 2d_0$ |    |    |    |    |    |

<sup>1)</sup> Both drill hole diameters can be used

Table A5.2: Materials of rebars

| Designation                                          | Reinforcing bar (rebar)                                                                                                                            |
|------------------------------------------------------|----------------------------------------------------------------------------------------------------------------------------------------------------|
| Reinforcing bar<br>EN 1992-1-1:2004+AC:2010, Annex C | Bars and de-coiled rods class B or C with<br>$f_{yk}$ and $k$ according to NDP or NCL of EN 1992-1-1/NA:2013<br>$f_{uk} = f_{tk} = k \cdot f_{yk}$ |

Figures not to scale

Rebar connection with fischer injection mortar FIS V


Product description  
Properties and materials of reinforcing bars (rebar)

Annex A 5

Appendix 6/ 21

## Properties of fischer rebar anchor FRA

Figure A6.1:



Head marking e.g.:  FRA (for stainless steel)

 FRA C (for high corrosion-resistant steel)

**Table A6.1: Installation conditions for fischer rebar anchors FRA**

| Threaded diameter                                       |                                | M12                          |     | M16          | M20 | M24 |
|---------------------------------------------------------|--------------------------------|------------------------------|-----|--------------|-----|-----|
| Nominal diameter                                        | $\phi$ [mm]                    | 12                           |     | 16           | 20  | 25  |
| Width across flat                                       | SW [mm]                        | 19                           |     | 24           | 30  | 36  |
| Nominal drill bit diameter                              | $d_0$ [mm]                     | 14 <sup>2)</sup>             | 16  | 20           | 25  | 30  |
| Drill hole depth ( $h_0 = l_{e,ges}$ )                  | $l_{e,ges}$ [mm]               | $l_v + l_e$                  |     |              |     |     |
| Effective embedment depth                               | $l_v$ [mm]                     | acc. to static calculation   |     |              |     |     |
| Distance concrete surface to welded joint               | $l_e$ [mm]                     | 100                          |     |              |     |     |
| Diameter of clearance hole in the fixture <sup>1)</sup> | Pre-positioned $\leq d_f$ [mm] | 14                           | 18  | 22           | 26  |     |
|                                                         | Push through $\leq d_f$ [mm]   | 18                           | 22  | 26           | 32  |     |
| Minimum thickness of concrete member                    | $h_{min}$ [mm]                 | $h_0 + 30$<br>( $\geq 100$ ) |     | $h_0 + 2d_0$ |     |     |
| Maximum torque moment for attachment of the fixture     | $\max T_{fix}$ [Nm]            | 50                           | 100 | 150          | 150 |     |

<sup>1)</sup> For bigger clearance holes in the fixture see EN 1992-4

<sup>2)</sup> Both drill bit diameters can be used

**Table A6.2: Materials of fischer rebar anchors FRA**

| Part | Description                           | Materials                                                                            |                                                                                                     |
|------|---------------------------------------|--------------------------------------------------------------------------------------|-----------------------------------------------------------------------------------------------------|
|      |                                       | FRA                                                                                  | FRA C                                                                                               |
| 1    | Reinforcing bar                       | B500B acc. to DIN 488-1:2009                                                         |                                                                                                     |
| 2    | Round bar with partial or full thread | Stainless steel acc. to EN 10088-1:2014                                              | High corrosion-resistant steel acc. to EN 10088-1:2014                                              |
| 3    | Washer                                | Stainless steel acc. to EN 10088-1:2014                                              | High corrosion-resistant steel acc. to EN 10088-1:2014                                              |
| 4    | Hexagon nut                           | Stainless steel acc. to EN 10088-1:2014, strength class 80; acc. to EN ISO 3506:2009 | High corrosion-resistant steel acc. to EN 10088-1:2014, strength class 80; acc. to EN ISO 3506:2009 |

Figures not to scale

Rebar connection with fischer injection mortar FIS V

### Product description

Properties and materials of fischer rebar anchors FRA

## Annex A 6

Appendix 7/ 21

## Specifications of intended use (part 1)

**Table B1.1:** Overview use and performance categories

| Anchorages subject to                                                                                                                                                                                         |                    | FIS V with ...                                                                                       |                                 |                                                                                                                 |                                 |
|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--------------------|------------------------------------------------------------------------------------------------------|---------------------------------|-----------------------------------------------------------------------------------------------------------------|---------------------------------|
|                                                                                                                                                                                                               |                    | Reinforcing bar<br> |                                 | fischer rebar anchor FRA<br> |                                 |
| Hammer drilling with standard drill bit<br>                                                                                  |                    | all sizes                                                                                            |                                 |                                                                                                                 |                                 |
| Hammer drilling with hollow drill bit (fischer "FHD", Heller "Duster Expert"; Bosch „Speed Clean“; Hilti "TE-CD, TE-YD")<br> |                    | Nominal drill bit diameter ( $d_0$ )<br>12 mm to 35 mm                                               |                                 |                                                                                                                 |                                 |
| Static and quasi static load, in                                                                                                                                                                              | uncracked concrete | all sizes                                                                                            | Tables:<br>C1.1<br>C1.2<br>C1.3 | all sizes                                                                                                       | Tables:<br>C1.1<br>C1.2<br>C1.3 |
|                                                                                                                                                                                                               | cracked concrete   |                                                                                                      |                                 |                                                                                                                 |                                 |
| Installation temperature                                                                                                                                                                                      |                    | $T_{i,min} = 0\text{ °C}$ to $T_{i,max} = +40\text{ °C}$                                             |                                 |                                                                                                                 |                                 |
| Fire exposure                                                                                                                                                                                                 |                    | all sizes                                                                                            | Annex C2                        | no performance assessed                                                                                         |                                 |

Rebar connection with fischer injection mortar FIS V

**Intended use**  
Specifications (part 1)

**Annex B 1**

Appendix 8/ 21

## Specifications of intended use

### Anchorage subject to:

- Static and quasi-static loads: reinforcing bar (rebar) size 8 mm to 28 mm
- Fire exposure

### Base materials:

- Compacted reinforced or unreinforced normal weight concrete without fibres according to EN 206:2013+A1:2016
- Strength classes C12/15 to C50/60 according to EN 206:2013+A1:2016
- Maximum chloride content of 0,40 % (CL 0.40) related to the cement content according to EN 206:2013+A1:2016
- Non-carbonated concrete

Note: In case of a carbonated surface of the existing concrete structure the carbonated layer shall be removed in the area of the post-installed rebar connection with a diameter of  $\phi + 60$  mm prior to the installation of the new rebar. The depth of concrete to be removed shall correspond to at least the minimum concrete cover in accordance with EN 1992-1-1 :2004+AC:2010. The foregoing may be neglected if building components are new and not carbonated and if building components are in dry conditions.

### Temperature Range:

- - 40°C to +80°C (max. short term temperature +80°C and max long term temperature +50°C).

### Installation temperature:

- 0 °C to +40 °C

### Use conditions (Environmental conditions) for fischer rebar anchors FRA

- Structures subject to dry internal conditions (fischer rebar anchors FRA and FRA C)
- Structures subject to external atmospheric exposure (including industrial and marine environment) and to permanently damp internal condition, if no particular aggressive conditions exist (fischer rebar anchors FRA and FRA C)
- Structures subject to external atmospheric exposure and to permanently damp internal condition, if other particular aggressive conditions exist (fischer rebar anchors FRA C)

Note: Particular aggressive conditions are e.g. permanent, alternating immersion in seawater or the splash zone of seawater, chloride atmosphere of indoor swimming pools or atmosphere with extreme chemical pollution (e.g. in desulphurization plants or road tunnels where de-icing materials are used).

### Design:

- Anchorages are designed under the responsibility of an engineer experienced in anchorages and concrete work.
- Verifiable calculation notes and drawings are prepared taking account of the forces to be transmitted.
- Design according to EN 1992-1-1:2004+AC:2010 and Annex B 3 and B 4.
- The actual position of the reinforcement in the existing structure shall be determined on the basis of the construction documentation and taken into account when designing.

### Installation:

- Dry or wet concrete
- Water filled holes, only with 380 ml, 400 ml or 410 ml cartridges
- Hole drilling by hammer drill, hollow drill or compressed air drill mode
- Overhead installation allowed
- The installation of post-installed rebar respectively fischer rebar anchor FRA shall be done only by suitable trained installer and under Supervision on site; the conditions under which an installer may be considered as suitable trained and the conditions for Supervision on site are up to the Member States in which the installation is done.
- Check the position of the existing rebars (if the position of existing rebars is not known, it shall be determined using a rebar detector suitable for this purpose as well as on the basis of the construction documentation and then marked on the building component for the overlap joint).

Rebar connection with fischer injection mortar FIS V

**Intended use**  
Specifications (part 2)


**Annex B 2**

Appendix 9/ 21

# General construction rules for post-installed rebars

Figure B3.1:

- Only tension forces in the axis of the rebar may be transmitted.
- The transfer of shear forces between new concrete and existing structure shall be designed additionally according to EN 1992-1-1:2004+AC:2010.
- The joints for concreting must be roughened to at least such an extent that aggregate protrude.



<sup>1)</sup> If the clear distance between lapped bars exceeds  $4 \phi$  then the lap length shall be increased by the difference between the clear bar distance and  $4 \phi$

- $c$  concrete cover of post-installed rebar
- $c_1$  concrete cover at end-face of existing rebar
- $c_{min}$  minimum concrete cover according to table B5.1 and to EN 1992-1-1:2004+AC:2010, Section 4.4.1.2
- $\phi$  nominal diameter of reinforcing bar
- $l_0$  lap length, according to EN 1992-1-1:2004+AC:2010
- $l_v$  effective embedment depth,  $\geq l_0 + c_1$
- $d_0$  nominal drill bit diameter, see Annex B 6

Figures not to scale

Rebar connection with fischer injection mortar FIS V

**Intended use**  
General construction rules for post-installed rebars


**Annex B 3**

Appendix 10/ 21

# General construction rules for post-installed rebar anchors FRA

Figure B4.1:

- Only tension forces in the axis of the FRA may be transmitted.
- The tension force must be transferred via an overlap joint to the reinforcement in the building part.
- The transmission of the shear load shall be ensured by appropriate additional measures, e.g. by shear lugs or by anchors with a European Technical Assessment (ETA).
- In the anchor plate, the holes for the tension anchor shall be executed as slotted holes with the axis in the direction of the shear force.



<sup>1)</sup> If the clear distance between lapped bars exceeds  $4 \phi$  then the lap length shall be increased by the difference between the clear bar distance and  $4 \phi$ .

|                    |                                                                                                 |
|--------------------|-------------------------------------------------------------------------------------------------|
| c                  | concrete cover of post-installed rebar anchor FRA                                               |
| c <sub>1</sub>     | concrete cover at end-face of existing rebar                                                    |
| c <sub>min</sub>   | minimum concrete cover according to table B5.1 and to EN 1992-1-1:2004+AC:2010, Section 4.4.1.2 |
| φ                  | nominal diameter of reinforcing bar                                                             |
| l <sub>0</sub>     | lap length, according to EN 1992-1-1:2004+AC:2010, Section 8.7.3                                |
| l <sub>e,ges</sub> | overall embedment depth, $\geq l_0 + l_e$                                                       |
| d <sub>0</sub>     | nominal drill bit diameter, see Annex B 6                                                       |
| l <sub>e</sub>     | length of the bonded in threaded part                                                           |
| t <sub>fix</sub>   | thickness of the fixture                                                                        |
| l <sub>v</sub>     | effective embedment depth                                                                       |

Figures not to scale


Rebar connection with fischer injection mortar FIS V

**Intended use**  
General construction rules for post-installed rebar anchors FRA

**Annex B 4**

Appendix 11/ 21

**Table B5.1:** Minimum concrete cover  $c_{min}^{1)}$  depending of the drilling method and the drilling tolerance

| Drilling method                                                                                                          | nominal diameter of reinforcing bar $\phi$ [mm] | Minimum concrete cover $c_{min}$ |                                | <br>Drilling aid |
|--------------------------------------------------------------------------------------------------------------------------|-------------------------------------------------|----------------------------------|--------------------------------|-----------------------------------------------------------------------------------------------------|
|                                                                                                                          |                                                 | Without drilling aid [mm]        | With drilling aid [mm]         |                                                                                                     |
| Hammer drilling with standard drill bit                                                                                  | < 25                                            | 30 mm + 0,06 $l_v \geq 2 \phi$   | 30 mm + 0,02 $l_v \geq 2 \phi$ |                                                                                                     |
|                                                                                                                          | $\geq 25$                                       | 40 mm + 0,06 $l_v \geq 2 \phi$   | 40 mm + 0,02 $l_v \geq 2 \phi$ |                                                                                                     |
| Hammer drilling with hollow drill bit (fischer "FHD", Heller "Duster Expert"; Bosch "Speed Clean"; Hilti "TE-CD, TE-YD") | < 25                                            | 30 mm + 0,06 $l_v \geq 2 \phi$   | 30 mm + 0,02 $l_v \geq 2 \phi$ |                                                                                                     |
|                                                                                                                          | $\geq 25$                                       | 40 mm + 0,06 $l_v \geq 2 \phi$   | 40 mm + 0,02 $l_v \geq 2 \phi$ |                                                                                                     |
| Compressed air drilling                                                                                                  | < 25                                            | 50 mm + 0,08 $l_v$               | 50 mm + 0,02 $l_v$             |                                                                                                     |
|                                                                                                                          | $\geq 25$                                       | 60 mm + 0,08 $l_v \geq 2 \phi$   | 60 mm + 0,02 $l_v \geq 2 \phi$ |                                                                                                     |

<sup>1)</sup> See Annex B3, figure B3.1 and Annex B4, figure B4.1

Note: The minimum concrete cover as specified in EN 1992-1-1:2004+AC:2010 must be observed.

**Table B5.2:** Dispensers and cartridge sizes corresponding to maximum embedment depth  $l_{v,max}$

| reinforcing bars (rebar) | rebar anchor FRA | Manual dispenser                 | Accu and pneumatic dispenser (small) | Pneumatic dispenser (large)      |
|--------------------------|------------------|----------------------------------|--------------------------------------|----------------------------------|
|                          |                  | Cartridge size                   |                                      |                                  |
| $\phi$ [mm]              | thread [M]       | < 500 ml                         |                                      | > 500 ml                         |
|                          |                  | $l_{v,max} / l_{e,ges,max}$ [mm] |                                      | $l_{v,max} / l_{e,ges,max}$ [mm] |
| 8                        | ---              | 1000                             | 1000                                 | 1800                             |
| 10                       | ---              |                                  | 1200                                 |                                  |
| 12                       | FRA 12           |                                  | 1500                                 |                                  |
| 14                       | ---              |                                  | 1300                                 |                                  |
| 16                       | FRA 16           | 700                              | 1000                                 | 2000                             |
| 20                       | FRA 20           |                                  | 700                                  |                                  |
| 25                       | FRA 24           |                                  |                                      |                                  |
| 28                       | ----             | 500                              |                                      |                                  |

Rebar connection with fischer injection mortar FIS V

**Intended use**

Minimum concrete cover;  
dispenser and cartridge sizes corresponding to maximum embedment depth

**Annex B 5**

Appendix 12/ 21

**Table B6.1:** Working times  $t_{work}$  and curing times  $t_{cure}$ 

| Temperature in the anchorage base [°C] | Maximum working time <sup>1)</sup><br>$t_{work}$ |                  | Minimum curing time <sup>2)</sup><br>$t_{cure}$ |                  |
|----------------------------------------|--------------------------------------------------|------------------|-------------------------------------------------|------------------|
|                                        | FIS V                                            | FIS VS Low Speed | FIS V                                           | FIS VS Low Speed |
| >±0 to +5                              | 13 min <sup>3)</sup>                             | ---              | 3 h                                             | 6 h              |
| >+5 to +10                             | 9 min <sup>3)</sup>                              | 20 min           | 90 min                                          | 3 h              |
| >+10 to +20                            | 5 min                                            | 10 min           | 60 min                                          | 2 h              |
| >+20 to +30                            | 4 min                                            | 6 min            | 45 min                                          | 60 min           |
| >+30 to +40                            | 2 min <sup>4)</sup>                              | 4 min            | 35 min                                          | 30 min           |

<sup>1)</sup> Maximum time from the beginning of the injection to rebar / FRA setting and positioning

<sup>2)</sup> For wet concrete the curing time must be doubled

<sup>3)</sup> If the temperature in the concrete falls below 10°C the cartridge has to be warmed up to +15°C.

<sup>4)</sup> If the temperature in the concrete exceeds 30 °C the cartridge has to be cooled down to +15°C up to 20°C

**Table B6.2:** Installation tools for drilling and cleaning the bore hole and injection of the mortar

| reinforcing bars (rebar)<br>$\phi$ [mm] | rebar anchor FRA<br>thread [M] | Drilling and cleaning                    |                                            |                                    |                                     | Injection                          |                               |
|-----------------------------------------|--------------------------------|------------------------------------------|--------------------------------------------|------------------------------------|-------------------------------------|------------------------------------|-------------------------------|
|                                         |                                | Nominal drill bit diameter<br>$d_0$ [mm] | Diameter of cutting edge<br>$d_{cut}$ [mm] | Steel brush diameter<br>$d_b$ [mm] | Diameter of cleaning nozzle<br>[mm] | Diameter of extension tube<br>[mm] | Injection adapter<br>[colour] |
| 8 <sup>1)</sup>                         | ---                            | 10                                       | $\leq 10,50$                               | 11,0                               | 11                                  | 9                                  | ---                           |
|                                         |                                | 12                                       | $\leq 12,50$                               | 12,5                               |                                     |                                    | nature                        |
| 10 <sup>1)</sup>                        | ---                            | 12                                       | $\leq 12,50$                               | 12,5                               |                                     |                                    | blue                          |
|                                         |                                | 14                                       | $\leq 14,50$                               | 15                                 | 15                                  | 9                                  | red                           |
| 12 <sup>1)</sup>                        | FRA 12 <sup>1)</sup>           | 14                                       | $\leq 14,50$                               | 15                                 |                                     |                                    | yellow                        |
|                                         |                                | 16                                       | $\leq 16,50$                               | 17                                 |                                     |                                    | green                         |
| 14                                      | ---                            | 18                                       | $\leq 18,50$                               | 19                                 | 19                                  | 9 or 15                            | black                         |
| 16                                      | FRA 16                         | 20                                       | $\leq 20,55$                               | 21,5                               |                                     |                                    | grey                          |
| 20                                      | FRA 20                         | 25                                       | $\leq 25,55$                               | 26,5                               |                                     |                                    | brown                         |
| 25                                      | FRA 24                         | 30                                       | $\leq 30,55$                               | 32                                 | 28                                  |                                    |                               |
| 28                                      | ---                            | 35                                       | $\leq 35,70$                               | 37                                 |                                     |                                    |                               |

<sup>1)</sup> Both drill bit diameters can be used

Rebar connection with fischer injection mortar FIS V

**Intended use**

Working times and curing times;

Installation tools for drilling and cleaning the bore hole and injection of the mortar

**Annex B 6**

Appendix 13/ 21

## Safety regulations






Review the Safety Data Sheet (SDS) before use for proper and safe handling!  
Wear well-fitting protective goggles and protective gloves when working with mortar FIS V / FIS VS Low Speed.  
Important: Observe the instructions for use provided with each cartridge.

## Installation instruction part 1; Installation with FIS V / FIS VS Low Speed

### Hole drilling

Note: Before drilling, remove carbonized concrete; clean contact areas (see Annex B 2)  
In case of aborted drill holes the drill hole shall be filled with mortar.

|    |                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                    |
|----|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| 1a | <p><b>Hammer drilling or compressed air drilling</b></p>  <p>Drill the hole to the required embedment depth using a hammer drill with carbide drill bit set in rotation hammer mode or a pneumatic drill.<br/>Drill bit sizes see table B6.2.</p>                                                                                                                                                                                                                                                 |
| 1b | <p><b>Hammer drilling with hollow drill bit</b></p>  <p>Drill the hole to the required embedment depth using a hammer drill with hollow drill bit in rotation hammer mode.<br/>Dust extraction conditions see drill hole cleaning annex B8.<br/>Drill bit sizes see table B6.2.</p>                                                                                                                                                                                                              |
| 2  |  <p>Measure and control concrete cover <math>c</math><br/>(<math>c_{\text{drill}} = c + \varnothing / 2</math>)<br/>Drill parallel to surface edge and to existing rebar.<br/>Where applicable use fischer drilling aid.</p> <p>For holes <math>l_v &gt; 20</math> cm use drilling aid.<br/>Three different options can be considered:<br/>A) fischer drilling aid<br/>B) Slat or spirit level<br/>C) Visual check</p> <p>Minimum concrete cover <math>c_{\text{min}}</math> see table B5.1</p> |

Rebar connection with fischer injection mortar FIS V





### Intended use

Safety regulations; Installation instruction part 1, hole drilling

## Annex B 7

## Installation instruction part 2; Installation with FIS V / FIS VS Low Speed

### Drill hole cleaning

|    |                                                                                     |                                                                                                                                                                                                                                                                                                                                                                                                                                              |
|----|-------------------------------------------------------------------------------------|----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
|    | <b>Hammer or compressed air drilling</b>                                            |                                                                                                                                                                                                                                                                                                                                                            |
| 3a |    | <b>Blowing</b><br>three times from the back of the hole with the appropriate nozzle (oil-free compressed air $\geq 6$ bar) until return air stream is free of noticeable dust.<br>Personal protective equipment must be used (see regulations Annex B7).                                                                                                                                                                                     |
|    |    | <b>Brushing (with power drill)</b><br>three times with the suitable brush size (brush diameter > drill hole diameter). Switch on the power drill after inserting the steel brush into the drill hole. The brush must produce a noticeable resistance when it is inserted into the drill hole. If this is not the case, use a new or larger brush.<br>If necessary, check with brush inspection template.<br>Suitable brushes see table B6.2. |
|    |    | <b>Blowing</b><br>three times from the back of the hole with the appropriate nozzle (oil-free compressed air $\geq 6$ bar) until return air stream is free of noticeable dust.<br>Personal protective equipment must be used. (see regulations Annex B7).                                                                                                                                                                                    |
| 3b | <b>Hammer drilling with hollow drill bit</b>                                        |                                                                                                                                                                                                                                                                                                                                                             |
|    |  | Use a suitable dust extraction system, e. g. fischer FVC 35 M or a comparable dust extraction system with equivalent performance data.<br>Drill the hole with hollow drill bit. The dust extraction system has to extract the drill dust nonstop during the drilling process and must be adjusted to maximum power.<br>No further drill hole cleaning necessary                                                                              |

Rebar connection with fischer injection mortar FIS V

#### Intended use




Installation instruction part 2, drill hole cleaning

#### Annex B 8

Appendix 15/ 21

### Installation instruction part 3; Installation with FIS V / FIS VS Low Speed

reinforcing bars (rebar) / fischer rebar anchor FRA and cartridge preparation

|   |                                                                                    |                                                                                                                                                                                                                                                             |
|---|------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| 4 |   | Before use, make asure that the rebar or the rebar anchor FRA is dry and free of oil or other residue.<br>Mark the embedment depth $l_v$ (e.g. with tape)<br>Insert rebar in borehole, to verify drill hole depth and setting depth $l_v$ resp. $l_{e,ges}$ |
| 5 |   | Twist off the sealing cap<br>Twist on the static mixer (the spiral in the static mixer must be clearly visible).                                                                                                                                            |
| 6 |   | Place the cartridge into a suitable dispenser.                                                                                                                                                                                                              |
| 7 |  | Press out approximately 10 cm of mortar until the resin is permanently grey in colour. Mortar which is not grey in colour will not cure and must be disposed.                                                                                               |

Rebar connection with fischer injection mortar FIS V

#### Intended use



Installation instruction part 3,  
reinforcing bars (rebar) / fischer rebar anchor FRA and cartridge preparation

**Annex B 9**





Appendix 16/ 21

## Installation instruction part 4; Installation with FIS V / FIS VS Low Speed

### Injection of the mortar; borehole depth ≤ 250 mm

|    |                                                                                   |                                                                                                                                                                                                                                                                                                                                                      |
|----|-----------------------------------------------------------------------------------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| 8a |  | <p>Inject the mortar from the back of the hole towards the front and slowly withdraw the mixing nozzle step by step with each trigger pull. Avoid bubbles.</p> <p>Fill holes approximately 2/3 full, to ensure that the annular gap between the rebar and the concrete will be completely filled with adhesive over the entire embedment length.</p> |
|    |  | <p>After injecting, release the dispenser. This will prevent further mortar discharge from the mixing nozzle.</p>                                                                                                                                                                                                                                    |

### Injection of the mortar; borehole depth > 250 mm

|    |                                                                                                              |                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                        |
|----|--------------------------------------------------------------------------------------------------------------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
|    |                             | <p>Assemble mixing nozzle FIS MR Plus or FIS UMR, extension tube and appropriate injection adapter (see table B6.2)</p>                                                                                                                                                                                                                                                                                                                                                                                                                                                |
| 8b | <p>Mortar level mark</p>   | <p>Mark the required mortar level <math>l_m</math> and embedment depth <math>l_v</math> resp. <math>l_{e,ges}</math> with tape or marker on the injection extension tube.</p> <p>a) Estimation:</p> $l_m = \frac{1}{3} * l_v \text{ resp. } l_m = \frac{1}{3} * l_{e,ges}$ <p>b) Precise equation for optimum mortar volume:</p> $l_m = l_v \text{ resp. } l_{e,ges} \left( (1,2 * \frac{d_s^2}{d_0^2} - 0,2) \right) [\text{mm}]$                                                                                                                                     |
|    |  <p>Mortar level mark</p> | <p>Insert injection adapter to back of the hole. Begin injection allowing the pressure of the injected adhesive mortar to push the injection adapter towards the front of the hole. Do not actively pull out!</p> <p>Fill holes approximately 2/3 full, to ensure that the annular gap between the rebar and the concrete will be completely filled with adhesive over the embedment length.</p> <p>When using an injection adapter continue injection until the mortar level mark <math>l_m</math> becomes visible.</p> <p>Maximum embedment depth see table B5.2</p> |
|    |                           | <p>After injecting, release the dispenser. This will prevent further mortar discharge from the mixing nozzle.</p>                                                                                                                                                                                                                                                                                                                                                                                                                                                      |

Rebar connection with fischer injection mortar FIS V

#### Intended use





Installation instruction part 4, mortar injection

**Annex B 10**

Appendix 17/ 21

## Installation instruction part 5; Installation with FIS V / FIS VS Low Speed

### Insert rebar / rebar anchor FRA

|    |                                                                                     |                                                                                                                                                                                                                                                                                                                                                                                             |
|----|-------------------------------------------------------------------------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| 9  |    | <p>Insert the rebar / rebar anchor FRA slowly twisted into the borehole until the embedment mark is reached.</p>                                                                                                                                                                                                                                                                            |
| 10 |    | <p>For overhead installation, support the rebar / rebar anchor FRA and secure it from falling till mortar started to harden, e.g. using wedges.</p>                                                                                                                                                                                                                                         |
| 11 |    | <p>After installing the rebar or FRA the annular gap must be completely filled with mortar.</p> <p>Proper installation</p> <ul style="list-style-type: none"> <li>• Desired embedment depth is reached <math>l_v</math>: embedment mark at concrete surface</li> <li>• Excess mortar flows out of the borehole after the rebar has been fully inserted up to the embedment mark.</li> </ul> |
| 12 |  | <p>Observe the working time "<math>t_{work}</math>" (see table B 6.1), which varies according to temperature of base material. Minor adjustments to the rebar / rebar anchor FRA position may be performed during the working time</p> <p>Full load may be applied only after the curing time "<math>t_{cure}</math>" has elapsed (see table B 6.1)</p>                                     |
| 13 |  | <p>Mounting the fixture,<br/>max <math>T_{fix}</math> see table A 6.1</p>                                                                                                                                                                                                                                                                                                                   |

Rebar connection with fischer injection mortar FIS V

#### Intended use

Installation instruction part 5, insert rebar / rebar anchor FRA

**Annex B 11**

Appendix 18/ 21

## Minimum anchorage length and minimum lap length

The minimum anchorage length  $l_{b,min}$  and the minimum lap length  $l_{o,min}$  according to EN 1992-1-1 shall be multiply by the relevant amplification factor  $\alpha_{lb}$  according to table C1.1.

**Table C1.1:** Amplification factor  $\alpha_{lb}$  related to concrete strength class and drilling method

| Concrete strength class | Drilling method                                                                                                          | Amplification factor $\alpha_{lb}$ |
|-------------------------|--------------------------------------------------------------------------------------------------------------------------|------------------------------------|
| C12/15 to C50/60        | Hammer drilling with standard drill bit                                                                                  | 1,0                                |
|                         | Hammer drilling with hollow drill bit (fischer "FHD", Heller "Duster Expert"; Bosch „Speed Clean“; Hilti "TE-CD, TE-YD") | 1,0                                |
|                         | Compressed air drilling                                                                                                  | 1,0                                |

**Table C1.2:** Bond efficiency factor  $k_b$  for hammer drilling, hollow drilling and compressed air drilling

| Hammer drilling, hollow drilling and compressed air drilling |                              |        |        |        |        |        |        |        |        |
|--------------------------------------------------------------|------------------------------|--------|--------|--------|--------|--------|--------|--------|--------|
| Rebar / rebar anchor FRA<br>$\phi$ [mm]                      | Bond efficiency factor $k_b$ |        |        |        |        |        |        |        |        |
|                                                              | Concrete strength class      |        |        |        |        |        |        |        |        |
|                                                              | C12/15                       | C16/20 | C20/25 | C25/30 | C30/37 | C35/45 | C40/50 | C45/55 | C50/60 |
| 8 to 28                                                      | 1,00                         |        |        |        |        |        |        |        |        |

**Table C1.3:** Design values of the bond strength  $f_{bd,PIR}$  in N/mm<sup>2</sup> for hammer drilling, hollow drilling, compressed air drilling and for good bond conditions

$$f_{bd,PIR} = k_b \cdot f_{bd}$$

$f_{bd}$ : Design value of the bond strength in N/mm<sup>2</sup> considering the concrete strength classes and the rebar diameter according to EN 1992-1-1: 2004+AC:2010  
(for all other bond conditions multiply the values by 0,7)

$k_b$ : Bond efficiency factor according to table C1.2

### Hammer drilling, hollow drilling and compressed air drilling

| Rebar / rebar anchor FRA<br>$\phi$ [mm] | bond strength $f_{bd,PIR}$ [N/mm <sup>2</sup> ] |        |        |        |        |        |        |        |        |
|-----------------------------------------|-------------------------------------------------|--------|--------|--------|--------|--------|--------|--------|--------|
|                                         | Concrete strength class                         |        |        |        |        |        |        |        |        |
|                                         | C12/15                                          | C16/20 | C20/25 | C25/30 | C30/37 | C35/45 | C40/50 | C45/55 | C50/60 |
| 8 to 28                                 | 1,6                                             | 2,0    | 2,3    | 2,7    | 3,0    | 3,4    | 3,7    | 4,0    | 4,3    |

Rebar connection with fischer injection mortar FIS V

#### Performance

Amplification factor  $\alpha_{lb}$ , bond efficiency factor  $k_b$ ,  
design values of the bond strength  $f_{bd,PIR}$

## Annex C 1

Appendix 19/ 21

|                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                              |      |                    |                      |                                         |            |
|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|------|--------------------|----------------------|-----------------------------------------|------------|
| <b>Table C2.1:</b> Essential characteristics of <b>tensile resistance</b> for <b>fischer rebar anchors FRA</b> under fire exposure                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                           |      |                    |                      |                                         |            |
| concrete strength classes C12/C15 to C50/60, according to EN 1992-4                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                          |      |                    |                      |                                         |            |
| <b>fischer rebar anchor FRA</b>                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                              |      | <b>M12</b>         | <b>M16</b>           | <b>M20</b>                              | <b>M24</b> |
| Stainless steel (FRA or FRA C)                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                               |      |                    |                      |                                         |            |
| Characteristic tensile resistance                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                            | R30  | $\sigma_{Rk,s,fi}$ | [N/mm <sup>2</sup> ] | 30                                      |            |
|                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                              | R60  |                    |                      | 25                                      |            |
|                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                              | R90  |                    |                      | 20                                      |            |
|                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                              | R120 |                    |                      | 16                                      |            |
| <div><b>Design value of the steel bearing capacity <math>\sigma_{Rd,s,fi}</math> under fire exposure for fischer rebar anchor FRA</b></div> <div>The design value of the steel bearing capacity <math>\sigma_{Rd,s,fi}</math> under fire exposure has to be calculated by the following equation:</div> <div><math display="block">\sigma_{Rd,s,fi} = \sigma_{Rk,s,fi} / \gamma_{M,fi}</math></div> <div>with:</div> <div><div><math>\sigma_{Rk,s,fi}</math></div><div>Characteristic tensile resistance according to table C2.1</div></div> <div><div><math>\gamma_{M,fi}</math></div><div>Partial factor according to EN 1992-1-2:2004+AC:2008</div></div> |      |                    |                      |                                         |            |
| Rebar connection with fischer injection mortar FIS V                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                         |      |                    |                      | <b>Annex C 2</b><br><br>Appendix 20/ 21 |            |
| <b>Performance</b><br>Design value of the steel bearing capacity $\sigma_{Rd,s,fi}$ under fire exposure for fischer rebar anchor FRA                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                         |      |                    |                      |                                         |            |

**Design values of the bond strength  $f_{bd,fi}$  under fire exposure for concrete strength classes C12/15 to C50/60 (all drilling methods)**

The design value of the bond strength  $f_{bd,fi}$  under fire exposure has to be calculated by the following equation:

$$f_{bd,fi} = k_{b,fi}(\theta) \cdot f_{bd} \cdot \frac{\gamma_c}{\gamma_{M,fi}}$$


If:  $\theta > 74\text{ }^{\circ}\text{C}$        $k_{b,fi}(\theta) = \frac{24,308 \cdot e^{-0,012 \cdot \theta}}{10} \leq 1.0$

If:  $\theta > 317\text{ }^{\circ}\text{C}$        $k_{b,fi}(\theta) = 0.0$

- $f_{bd,fi}$  = Design value of the bond strength in case of fire (in N/mm<sup>2</sup>)
- $(\theta)$  = Temperature in  $^{\circ}\text{C}$
- $k_{b,fi}(\theta)$  = Reduction factor under fire exposure
- $f_{bd}$  = Design value of the bond strength in N/mm<sup>2</sup> in cold condition according to table C1.3 considering the concrete classes, the rebar diameter, the drilling method and the bond conditions according to EN 1992-1-1:2004+AC:2010
- $\gamma_c$  = Partial factor according to EN 1992-1-1:2004+AC:2010
- $\gamma_{M,fi}$  = Partial factor according to EN 1992-1-2:2004+AC:2008

For evidence under fire exposure the anchorage length shall be calculated according to EN 1992-1-1:2004+AC:2010 Equation 8.3 using the temperature-dependent ultimate bond strength  $f_{bd,fi}$ .

**Figure C3.1:** Example graph of reduction factor  $k_{b,fi}(\theta)$  for concrete class C20/25 for good bond conditions



Rebar connection with fischer injection mortar FIS V

**Performance**  
Design values of bond strength  $f_{bd,fi}$  under fire exposure

**Annex C 3**

Appendix 21/ 21