

IZJAVA O LASTNOSTIH

DoP 0391

za fischer sistem za vbrizgavanje FIS V Plus (pritrjen pritrdilni element za uporabo v betonu)

SL

1. Enotna identifikacijska oznaka tipa proizvoda: **DoP 0391**
2. Predvidena uporaba: **Za vgradnjo v razpokan in nerazpokan beton, glej dodatek, zlasti priloge B1 - B14.**
3. Proizvajalec: **fischerwerke GmbH & Co. KG, Otto-Hahn-Straße 15, 79211 Denzlingen, Nemčija**
4. Pooblaščen zastopnik: **–**
5. Sistemi ocenjevanja in preverjanja nespremenljivosti lastnosti: **1**
6. Evropski ocenjevalni dokument: **EAD 330499-02-0601**
Evropska tehnična ocena: **ETA-20/0603; 2026-01-29**
Organ za tehnično ocenjevanje: **DIBt- Deutsches Institut für Bautechnik**
Priglašeni organi: **2873 TU Darmstadt**
7. Navedene lastnosti:
Mehanska odpornost in stabilnost (BWR 1)
Karakteristična odpornost na napetostno obremenitev (statična in kvazistatična obremenitev):
 - 1) Odpornost pri odpovedi jekla: glej dodatek, zlasti prilogah C1-C4
 - 2) Odpor na kombinirani izvlek in odpoved betonskega stožca: glej dodatek, zlasti prilogah C5-C11
 - 3) Odpornost na odpoved v betonski coni: glej dodatek, zlasti priloge C5
 - 4) Razdalja od roba betona za preprečevanje loma pod obremenitvijo: glej dodatek, zlasti priloge C5
 - 5) Robusnost: glej dodatek, zlasti prilogah C5 - C11
 - 6) Največji zatezni navor: glej dodatek, zlasti prilogah B3, B4, B5, B7
 - 7) Najmanjša razdalja do roba betona in razmik: glej dodatek, zlasti prilogah B3 - B9**Karakteristična odpornost proti strižni obremenitvi (statična in kvazistatična obremenitev):**
 - 8) Odpornost na odpoved jekla: glej dodatek, zlasti prilogah C1-C4
 - 9) Odpornost na neuspešno odstranitev: glej dodatek, zlasti priloge C5
 - 10) Odpornost na odpoved od roba betona: glej dodatek, zlasti priloge C5**Zamenjave pri kratkoročnem in dolgoročnem nalaganju:**
 - 11) Zamenjave pri kratkoročnem in dolgoročnem nalaganju: glej dodatek, zlasti prilogah C12, C13
 - 12) Odpornost betona, ojačenega z jeklenimi vlakni: NPD**Karakteristična odpornost in premiki za kategoriji seizmičnih lastnosti C1 in C2:**
 - 13) Odpornost na napetost, premiki, kategorija C1: glej dodatek, zlasti prilogah C14, C16, C17
 - 14) Odpornost na napetost, premiki, kategorija C2: glej dodatek, zlasti prilogah C15, C16, C18
 - 15) Odpornost na strižno obremenitev, premiki, kategorija C1: glej dodatek, zlasti prilogah C14, C16, C17
 - 16) Odpornost na strižno obremenitev, premiki, kategorija C2: glej dodatek, zlasti prilogah C15, C16, C18**Varnost v primeru požara (BWR 2)**
 - 17) Odzivnost na ogenj: Razred (A1)**Odpornost proti ognju:**
 - 18) Požarna odpornost pri odpovedi jekla (napetostna obremenitev): NPD
 - 19) Odpornost spojev v požarnih razmerah: NPD
 - 20) Požarna odpornost pri odpovedi jekla (strižna obremenitev): NPD**Higiena, zdravje in okolje (BWR 3)**
 - 21) Vsečina, emisije in / ali sproščanje nevarnih snovi: NPD
8. Ustrezna tehnična dokumentacija in/ali specifična tehnična dokumentacija: **–**

Lastnosti proizvoda, navedenega zgoraj, so v skladu z navedenimi lastnostmi. Za izdajo te izjave o lastnostih je v skladu z Uredbo (EU) št. 305/2011 odgovoren izključno proizvajalec, naveden zgoraj.

Podpisal za in v imenu proizvajalca:



Alexander Zanocco, Generalni direktor prodaje in Generalni direktor raziskav in razvoja



Dieter Pfaff, Vodja Mednarodne proizvodne federacije in upravljanja kakovosti

Tumlingen, 2026-03-01

Ta izjava o lastnostih je bila pripravljena v različnih jezikih. V primeru nerazumevanja, se vedno upošteva angleška različica.

Priloga vsebuje informacije v angleškem jeziku, ki presegajo zakonske zahteve.

Translation guidance Essential Characteristics and Performance Parameters for Annexes
Navodila za prevajanje. Bistvene značilnosti in parametri za pravilno delovanje priloge

Mechanical resistance and stability (BWR 1)		
Mehanska odpornost in stabilnost (BWR 1)		
Characteristic resistance to tension load (static and quasi-static loading):		
Karakteristična odpornost na napetostno obremenitev (statična in kvazistatična obremenitev):		
1	Resistance to steel failure: Odpornost pri odpovedi jekla:	$N_{Rk,s}$ [kN]
2	Resistance to combined pull- out and concrete cone failure: Odpor na kombinirani izvlek in odpoved betonskega stožca:	τ_{Rk} and/or $\tau_{Rk,100}$ [N/mm ²], ψ_c , ψ_{sus}^0 , $\psi_{sus,100}$ [-] (BF)
	Resistance to pull-out failure:	$N_{Rk,p}$ and/or $N_{Rk,p,100}$ [kN], ψ_c [-] (BEF)
3	Resistance to concrete cone failure: Odpornost na odpoved v betonski coni:	$c_{cr,N}$ [mm], $k_{cr,N}$, $k_{ucr,N}$ [-]
4	Edge distance to prevent splitting under load: Razdalja od roba betona za preprečevanje loma pod obremenitvijo:	$c_{cr,sp}$ [mm]
5	Robustness: Robusnost:	γ_{inst} [-]
6	Maximum installation torque: Največji zatezni navor:	$\max T_{inst}$ [Nm] (BF)
	Installation torque:	T_{inst} [Nm] (BEF)
7	Minimum edge distance,spacing and member thickness: Najmanjša razdalja do roba betona in razmik:	c_{min} , s_{min} , h_{min} [mm]
Characteristic resistance to shear load (static and quasi-static loading):		
Karakteristična odpornost proti strižni obremenitvi (statična in kvazistatična obremenitev):		
8	Resistance to steel failure: Odpornost na odpoved jekla:	$V_{Rk,s}^0$ [kN], $M_{Rk,s}^0$ [Nm], k_7 [-]
9	Resistance to pry-out failure: Odpornost na neuspešno odstranitev:	k_8 [-]
10	Resistance to concrete edge failure: Odpornost na odpoved od roba betona:	d_{nom} , l_f [mm]
Displacements under short-term and long-term loading:		
Zamenjave pri kratkoročnem in dolgoročnem nalaganju:		
11	Displacements factors under short-term and long-term loading: Zamenjave pri kratkoročnem in dolgoročnem nalaganju:	δ_0 , δ_∞ [mm/(N/mm ²)] or [mm/kN]
12	Resistance in steel fibre reinforced concrete: Odpornost betona, ojačenega z jeklenimi vlakni:	Description
Characteristic resistance and displacements for seismic performance categories C1 and C2:		
Karakteristična odpornost in premiki za kategoriji seizmičnih lastnosti C1 in C2:		
13	Resistance to tension for seismic performance category C1 Odpornost na napetost, premiki, kategorija C1:	$N_{Rk,s,C1}$ [kN] (all) $\tau_{Rk,C1}$ [N/mm ²] (BF) $N_{Rk,p,C1}$ [kN] (BEF)
14	Resistance to tension and displacements for seismic performance category C2 Odpornost na napetost, premiki, kategorija C2:	$N_{Rk,s,C2}$ [kN] (all) $\tau_{Rk,C2}$ [N/mm ²] (BF) $N_{Rk,p,C2}$ [kN] (BEF) $\delta_{N,C2(50\%)}$, $\delta_{N,C2(100\%)}$ [mm] (all)
15	Resistance to shear for seismic performance category C1 Odpornost na strižno obremenitev, premiki, kategorija C1:	$V_{Rk,s,C1}$ [kN] (all)
16	Resistance to shear load and displacements for seismic performance category C2 Odpornost na strižno obremenitev, premiki, kategorija C2:	$V_{Rk,s,C2}$ [kN] (all) $\delta_{V,C2(50\%)}$, $\delta_{V,C2(100\%)}$ [mm] (all)
Safety in case of fire (BWR 2)		
Varnost v primeru požara (BWR 2)		
17	Reaction to fire	Class
	Odzivnost na ogenj:	Razred (A1)
Resistance to fire		
Odpornost proti ognju:		
18	Fire resistance to steel failure (tension load): Požarna odpornost pri odpovedi jekla (napetostna obremenitev):	$N_{Rk,s,fi}$ [kN]
19	Bond resistance under fire conditions: Odpornost spojev v požarnih razmerah:	$k_{fi,p}(\theta)$ [-], $\tau_{Rk,fi}(\theta)$ [N/mm ²] (BF)
20	Fire resistance to steel failure under shear loading: Požarna odpornost pri odpovedi jekla (strižna obremenitev):	$V_{Rk,s,fi}$ [kN], $M_{Rk,s,fi}^0$ [Nm]
Hygiene, health and the environment (BWR 3)		
Higiena, zdravje in okolje (BWR 3)		
21	Content, emission and/or release of dangerous substances: Vsebina, emisije in / ali sproščanje nevarnih snovi:	Description/Level

Specific Part

1 Technical description of the product

The "fischer injection system FIS V Plus" is a bonded fastener consisting of a cartridge with injection mortar according to Annex A5 and a steel element according to Annex A1 to A4.

The steel element is placed into a drilled hole filled with injection mortar and is anchored via the bond between metal part, injection mortar and concrete.

The product description is given in Annex A.

2 Specification of the intended use in accordance with the applicable European Assessment Document

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the anchor of at least 50 and/or 100 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment

3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Characteristic resistance to tension load (static and quasi-static loading)	See Annex C1 to C11, B3 to B9
Characteristic resistance to shear load (static and quasi-static loading)	See Annex C1 to C4
Displacements under short-term and long-term loading	See Annex C12 to C13
Characteristic resistance and displacements for seismic performance categories C1 and C2	See Annex C14 to C18

3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire	Class A1
Resistance to fire	No performance assessed

3.3 Hygiene, health and the environment (BWR 3)

Essential characteristic	Performance
Content, emission and/or release of dangerous substances	No performance assessed

4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base


In accordance with EAD 330499-02-0601 the applicable European legal act is: [96/582/EC].

The system to be applied is: 1


Installation conditions part 1

fischer Anchor rod FIS A / RG (Anchor rod) and
commercial standard Threaded rod (Threaded rod)


Pre-positioned installation



Push through installation (annular gap filled with mortar)



Pre-positioned or push through installation with subsequently injected fischer filling disc
(annular gap filled with mortar)



Figures not to scale

h_0 = drill hole depth
 t_{fix} = thickness of fixture

h_{ef} = effective embedment depth

fischer injection system FIS V Plus


Product description
Installation conditions part 1

Annex A1
Appendix 3 / 41


Installation conditions part 2

fischer internal threaded anchor RG M I (fischer RG M I)

Pre-positioned installation



Pre-positioned installation with subsequently injected fischer filling disc (annular gap filled with mortar)



Figures not to scale

h_0 = drill hole depth
 t_{fix} = thickness of fixture

h_{ef} = effective embedment depth

fischer injection system FIS V Plus


Product description
Installation conditions part 2

Annex A2
Appendix 4 / 41


Installation conditions part 3

fischer internal threaded anchor FIS IG (fischer FIS IG)

Pre-positioned installation



Pre-positioned installation with subsequently injected fischer filling disc (annular gap filled with mortar)



Figures not to scale

h_0 = drill hole depth
 t_{fix} = thickness of fixture

h_{ef} = effective embedment depth


fischer injection system FIS V Plus

Product description
Installation conditions part 3

Annex A3
Appendix 5 / 41


Installation conditions part 4

Reinforcing bar




fischer rebar Anchor FRA (fischer FRA)

Pre-positioned installation



Push through installation (annular gap filled with mortar)



Figures not to scale

h_0 = drill hole depth	h_{ef} = effective embedment depth
t_{fix} = thickness of fixture	h_{nom} = overall fastener embedment depth in the concrete



fischer injection system FIS V Plus

Product description
Installation conditions part 4

Annex A4
Appendix 6 / 41

Overview system components part 1



Injection cartridge (shuttle cartridge) with sealing cap; Sizes: 360 ml, 825 ml



Imprint: fischer FIS V Plus or FIS VW Plus High Speed or FIS VS Plus Low Speed, processing notes, shelf-life, piston travel scale (optional), curing times and processing times (depending on temperature), hazard code, size, volume/weight




Injection cartridge (coaxial cartridge) with sealing cap; Sizes: 100 ml, 150 ml, 300 ml, 380 ml, 400 ml, 410 ml




Imprint: fischer FIS V Plus or FIS VW Plus High Speed or FIS VS Plus Low Speed, processing notes, shelf-life, piston travel scale (optional), curing times and processing times (depending on temperature), hazard code, size, volume/weight





Static mixer FIS MR Plus for injection cartridges up to 825 ml



Static mixer FIS JMR for injection cartridges of 825 ml



Injection adapter and extension tube Ø 9 for static mixer FIS MR Plus;
Injection adapter and extension tube Ø 9 or Ø 15 for static mixer FIS JMR



Cleaning brush BS



Blow-out pump AB G



Compressed-air cleaning tool ABP



Figures not to scale

fischer injection system FIS V Plus


Product description
Overview system components part 1;
cartridges / static mixer / cleaning tools / injection adapter

Annex A5
Appendix 7 / 41

Overview system components part 2

Anchor rod / Threaded rod

Size: M6, M8, M10, M12, M16, M20, M24, M27, M30




fischer RG M I

Size: M8, M10, M12, M16, M20




fischer FIS IG


Size: M5, M6, M8, M10, M12, M16, M20




Screw / Anchor rod / Threaded rod / washer / hexagon nut



fischer filling disc with injection adapter



fischer centering clip DD-S / DD-E



Reinforcing bar

Nominal diameter: $\phi 8$, $\phi 10$, $\phi 12$, $\phi 14$, $\phi 16$, $\phi 20$, $\phi 25$, $\phi 28$



fischer FRA, FRA HCR

Size: M12, M16, M20, M24



Figures not to scale

fischer injection system FIS V Plus

Product description

Overview system components part 2; metal parts, fischer centering clip, injection adapter

Annex A6

Appendix 8 / 41

Table A7.1: Materials				
Part	Designation	Material		
1	Injection cartridge	Mortar, hardener, filler		
	Steel grade	Steel zinc plated (zp, hdg)	Stainless steel R	High corrosion resistant steel HCR
			acc. to EN 10088-1:2023 Corrosion resistance class CRC III acc. to EN 1993-1-4:2006+A1:2015	acc. to EN 10088-1:2023 Corrosion resistance class CRC V acc. to EN 1993-1-4:2006+A1:2015
2	Anchor rod / Threaded rod	Property class 4.8, 5.8 or 8.8; EN ISO 898-1:2013 zp $\geq 5 \mu\text{m}$, EN ISO 4042:2022 or hot dip galvanised $\geq 40 \mu\text{m}$ EN ISO 10684:2004+AC:2009 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 12 \%$ fracture elongation ¹⁾	Property class 50, 70 or 80; EN ISO 3506-1:2020 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; 1.4062; 1.4662; 1.4462; EN 10088-1:2023 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 12 \%$ fracture elongation ¹⁾	Property class 50, 70 or 80; EN ISO 3506-1:2020 or property class HCR 70 with $f_{yk} \geq 560 \text{ N/mm}^2$; 1.4565; 1.4529; EN 10088-1:2023 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 12 \%$ fracture elongation ¹⁾
3	Washer ISO 7089:2000	zinc plated $\geq 5 \mu\text{m}$, EN ISO 4042:2022 or hot dip galvanised $\geq 40 \mu\text{m}$ EN ISO 10684:2004+AC:2009	1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2023	1.4565; 1.4529; EN 10088-1:2023
4	Hexagon nut	Property class 5 or 8 acc. EN ISO 898-2:2022 zinc plated $\geq 5 \mu\text{m}$, EN ISO 4042:2022 or hot dip galvanised $\geq 40 \mu\text{m}$ EN ISO 10684:2004+AC:2009	Property class 50, 70 or 80 acc. EN ISO 3506-2:2020 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2023	Property class 50, 70 or 80 acc. EN ISO 3506-2:2020 1.4565; 1.4529; EN 10088-1:2023
5	fischer RG M I / FIS IG	Property class 5.8 EN ISO 898-1:2013 zinc plated $\geq 5 \mu\text{m}$, EN ISO 4042:2022	Property class 70 EN ISO 3506-1:2020; 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2023	Property class 70 EN ISO 3506-1:2020 1.4565; 1.4529; EN 10088-1:2023
6	Commercial standard screw or Anchor rod / Threaded rod for fischer RG M I / FIS IG	Property class 5.8 or 8.8; EN ISO 898-1:2013 zinc plated $\geq 5 \mu\text{m}$, EN ISO 4042:2022 $A_5 > 8 \%$ fracture elongation	Property class 70 EN ISO 3506-1:2020 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2023 $A_5 > 8 \%$ fracture elongation	Property class 70 EN ISO 3506-1:2020 1.4565; 1.4529; EN 10088-1:2023 $A_5 > 8 \%$ fracture elongation
7	fischer filling disc similar to DIN 6319-G	zinc plated $\geq 5 \mu\text{m}$, EN ISO 4042:2022 or hot dip galvanised $\geq 40 \mu\text{m}$ EN ISO 10684:2004+AC:2009	1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2023	1.4565; 1.4529; EN 10088-1:2023
8	Rebar	EN 1992-1-1:2004 and AC:2010, Annex C Bars and de-coiled rods, class B or C with f_{yk} and k according to NDP or NCI according to EN 1992-1-1/NA; $f_{uk} = f_{tk} = k \cdot f_{yk} (A_5 > 8 \%)$ ¹⁾		
9	fischer FRA	Rebar part: Bars and de-coiled rods class B or C with f_{yk} and k according to NDP or NCI of EN 1992-1-1:2004+AC:2010 $f_{uk} = f_{tk} = k \cdot f_{yk} (A_5 > 8 \%)$ Threaded part: Property class 80 EN ISO 3506-1:2020	1.4401, 1.4404, 1.4571, 1.4578, 1.4439, 1.4362, 1.4062 acc. to EN 10088-1:2023 Corrosion resistance class CRC III acc. to EN 1993-1-4:2006+A1:2015 1.4565; 1.4529 acc. to EN 10088-1:2023 Corrosion resistance class CRC V acc. to EN 1993-1-4:2006+A1:2015 $f_{uk} \leq 1000 \text{ N/mm}^2$; fracture elongation $A_5 > 8 \%$	

¹⁾ Fracture elongation $A_5 > 8 \%$, for applications without requirements for seismic performance category C1 or C2

fischer injection system FIS V Plus	Annex A7 Appendix 9 / 41
Product description Materials	

Specifications of intended use part 1

Table B1.1: Overview use and performance categories

FIS V Plus with ...											
		Anchor rod Threaded rod	fischer RG M I		fischer FIS IG		Reinforcing bar		fischer FRA		
											
Hammer drilling with standard drill bit		all sizes									
Hammer drilling with hollow drill bit		Nominal drill bit diameter (d ₀) 12 mm to 35 mm									
(fischer „FHD“, Heller „Duster Expert“, Bosch „Speed Clean“, Hilti „TE-CD, TE-YD“, DreBo „D-Plus“, DreBo „D-Max“)											
Static and quasi static load, in	uncracked concrete	all sizes	Tables: C1.1 C5.1 C6.1 C7.1 C8.1 C12.1	all sizes	Tables: C2.1 C5.1 C9.1 C12.2	all sizes	Tables: C3.1 C5.1 C6.1 C9.1 C12.2	all sizes	Tables: C4.1 C5.1 C10.1 C13.1	all sizes	Tables: C4.2 C5.1 C11.1 C13.2
	cracked concrete	M8 to M30	-2)	-2)	φ 10 to φ 28		-2)	-2)			
Seismic performance category	C1 ¹⁾	M10 to M30	Tables: C14.1 C15.1 C16.1	All sizes	-2)	-2)	-2)	-2)	-2)	-2)	-2)
	C2 ¹⁾	M12 M16 M20	Tables: C15.1 C17.1 C18.1								
Use category	I1 dry or wet concrete	all sizes									
	I2 water filled hole	M12 to M30	all sizes	all sizes	-2)	-2)	-2)	-2)	-2)	-2)	-2)
Resistance to fire in concrete (only hammer drilling with standard / hollow drill bits)		-2	-2)	-2)	-2)	-2)	-2)	-2)	-2)	-2)	-2)
Installation direction		D3 (downward and horizontal and upwards (e.g. overhead) installation)									
Installation temperature		T _{i,min} = -10 °C to T _{i,max} = +40 °C									
In-service temperature	Temperature range I	-40 °C to +80 °C		(max. short term temperature +80 °C; max. long term temperature +50 °C)							
	Temperature range II	-40 °C to +120 °C		(max. short term temperature +120 °C; max. long term temperature +72 °C)							

¹⁾ Not for FIS VW Plus High Speed and FIS VS Plus Low Speed

²⁾ No performance assessed

fischer injection system FIS V Plus

Intended use
Specifications part 1

Annex B1

Appendix 10 / 41

Specifications of intended use part 2

Base materials:

- Compacted reinforced or unreinforced normal weight concrete without fibres of strength classes C12/15 to C50/60 according to EN 206:2013+A2:2021.

Use conditions (Environmental conditions):

- Fastener intended for use in structures subject to dry, internal conditions (all materials).
- For all other conditions according to EN 1993-1-4:2006+A1:2015 corresponding to corrosion resistance classes to **Annex A7 Table A7.1**.

Design:

- Fastenings are designed in accordance with:
EN 1992-4:2018.
- The structural design is conducted under responsibility of a designer experienced in the field of anchorages and concrete works.
- Verifiable calculation notes and drawings are to be prepared taking account of the loads to be anchored. The position of the fastener is indicated on the design drawings (e. g. position of the fastener relative to reinforcement or to supports, etc.).

Installation:

- Fastener installation is to be carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters of the site.
- Fastening depth should be marked and adhered to installation.
- Overhead installation is allowed (necessary equipment see installation instruction).

fischer injection system FIS V Plus	Annex B2 Appendix 11 / 41
Intended use Specifications part 2	


Table B3.1: Installation parameters for Anchor rods / Threaded rods

Anchor rods / Threaded rods		Thread	M6	M8	M10	M12	M16	M20	M24	M27	M30
Nominal drill hole diameter	d_0	[mm]	8	10	12	14	18	24	28	30	35
Drill hole depth	$h_0^{3)}$		$h_0 \geq h_{ef}$								
Effective embedment depth	$h_{ef, min}$		40	40 ²⁾	40 ²⁾	48	64	80	96	108	120
	$h_{ef, max}$		72	160	200	240	320	400	480	540	600
Simplified spacing and edge distance ¹⁾	$s=c$		40	40	45	55	65	85	105	125	140
Maximum diameter of the pre-positioned installation	d_f		7	9	12	14	18	22	26	30	33
clearance hole of the fixture	push through installation d_f		9	12	14	16	20	26	30	33	40
Minimum thickness of concrete member	h_{min}	$h_{ef} + 30 (\geq 100)$						$h_{ef} + 2d_0$			
Maximum installation torque	$\max T_{inst}$	[Nm]	5	10	20	40	60	120	150	200	300

1) Detailed calculation according to **Annex B8 and B9**.

2) $h_{ef, min} \geq 60$ for concrete C12/15 and C16/20


3) When using centering clips DD-S / DD-E, observe the deviating specifications as specified in **Table B11.1**.

Anchor rod / Threaded rod**Marking (on random place) fischer Anchor rod:**

Steel zinc plated PC ¹⁾ 8.8	• or +	Steel hot-dip PC ¹⁾ 8.8	•
High corrosion resistant steel HCR PC ¹⁾ 50	•	High corrosion resistant steel HCR PC ¹⁾ 70	-
High corrosion resistant steel HCR PC ¹⁾ 80	(	Stainless steel R property class 50	~
Stainless steel R property class 80	*		

Alternatively: Colour coding according to DIN 976-1: 2016

¹⁾ PC = property class

Installation conditions:**Threaded rods, washers and hexagon nuts may also be used if the following requirements are fulfilled:**

- Materials, dimensions and mechanical properties according to **Annex A7, Table A7.1**.
- Inspection certificate 3.1 according to EN 10204:2004, the documents have to be stored.
- Setting depth is marked.
- Steel load-bearing capacities for hot-dip galvanised parts are only valid if the threaded rod and nut are correctly paired. The strength class of the nut must be one strength class higher than that of the threaded rod ($\geq M12$ in combination with tolerance class 6AX in accordance with EN ISO 10684:2004+AC:2009 two strength classes higher). The pairing of undersized threaded rods (additional designation U according to EN ISO 10684) with oversized nuts (additional designation Z or X according to EN ISO 10684) is not permitted under any circumstances.

Figures not to scale

fischer injection system FIS V Plus

Intended use

Installation parameters Anchor rods / Threaded rods

Annex B3

Appendix 12 / 41

Table B4.1: Installation parameters for fischer RG M I							
fischer RG M I		Thread	M8	M10	M12	M16	M20
Diameter of Anchor	$d_{nom} = d_H$	[mm]	12	16	18	22	28
Nominal drill hole diameter	d_0		14	18	20	24	32
Drill hole depth	h_0		$h_0 \geq h_{ef} = L_H$				
Effective embedment depth ($h_{ef} = L_H$)	h_{ef}		90	90	125	160	200
Minimum spacing and minimum edge distance	s_{min} = c_{min}		55	65	75	95	125
Maximum diameter of clearance hole in the fixture	d_f		9	12	14	18	22
Minimum thickness of concrete member	h_{min}		120	125	165	205	260
Maximum screw-in depth	$l_{E,max}$		18	23	26	35	45
Minimum screw-in depth	$l_{E,min}$		8	10	12	16	20
Maximum installation torque	$\max T_{inst}$	[Nm]	10	20	40	80	120

fischer RG M I

Marking: Anchor size e. g.: **M10**
 Stainless steel → additional **R**; e.g.: **M10 R**
 High corrosion resistant steel → additional **HCR**; e.g.: **M10 HCR**

Retaining bolt or Anchor rod / Threaded rods (including nut and washer) must comply with the appropriate material and strength class of **Annex A7, Table A7.1**.

Installation conditions:

Figures not to scale

fischer injection system FIS V Plus	Annex B4 Appendix 13 / 41
Intended use Installation parameters fischer RG M I	



Table B5.1: Installation parameters for fischer FIS IG

fischer FIS IG		Thread	M5	M6	M8	M10	M12	M16	M20
Diameter of anchor	$d_{nom} = d_H$	[mm]	10	10	12	16	20	24	30
Nominal drill hole diameter	d_0		12	12	14	18	24	28	35
Drill hole depth	h_0 ¹⁾		$h_0 \geq h_{ef} = L_H$						
Effective embedment depth	$h_{ef, min}$		40 ²⁾	40 ²⁾	48	64	80	96	120
($h_{ef} = L_H$)	$h_{ef, max}$		200	200	240	320	400	480	600
Minimum spacing	s_{min}		according to Annex B8						
Minimum edge distance	c_{min}		according to Annex B8						
Diameter of clearance hole in the fixture	d_f		6	7	9	12	14	18	22
Minimum thickness of concrete member	h_{min} ¹⁾		$h_{ef} + 30 (\geq 100)$			$h_{ef} + 2d_0$			
Maximum screw-in depth	$l_{E, max}$		18	18	20	25	30	40	50
Minimum screw-in depth	$l_{E, min}$		8	8	10	12	14	19	23
Maximum installation torque	$\max T_{inst}$	[Nm]	5	5	10	20	40	80	120

1) When using centering clips DD-S / DD-E, observe the deviating specifications as specified in **Table B11.1**.

2) $h_{ef, min} \geq 60$ for concrete C12/15 and C16/20.

fischer FIS IG




Marking (at any location) Anchor rod:

High corrosion resistant steel HCR property class 70

Bolts or threaded rods (including nut and washer) must comply with the relevant material and strength class as specified in **Annex A7, Table A7.1**.

Installation conditions:



Figures not to scale

fischer injection system FIS V Plus

Intended use
Installation parameters fischer FIS IG

Annex B5

Appendix 14 / 41

Nominal diameter of the bar		ϕ	8 ²⁾		10 ²⁾		12 ²⁾		14	16	20	25	28
Nominal drill hole diameter	d_0	[mm]	10	12	12	14	14	16	18	20	25	30	35
Drill hole depth	h_0		$h_0 \geq h_{ef}$										
Effective embedment depth	$h_{ef,min}$		60	60	70	75	80	90	100	112			
	$h_{ef,max}$		160	200	240	280	320	400	500	560			
Simplified spacing and edge distance ¹⁾	$s = c$		40	45	55	60	65	85	110	130			
Minimum thickness of concrete member	h_{min}	$h_{ef} + 30$ (≥ 100)					$h_{ef} + 2d_0$						


1) Detailed calculation according to **Annex B8** and **B9**.
2) Both drill hole diameters can be used.

Reinforcing bar



- The minimum value of related rib area $f_{R,min}$ must fulfil the requirements of EN 1992-1-1:2011.
- The rib height must be within the range: $0,05 \cdot \phi \leq h_{rib} \leq 0,07 \cdot \phi$
(ϕ = Nominal diameter of the bar, h_{rib} = rib height).

Installation conditions:



Figures not to scale


Table B7.1: Installation parameters for fischer FRA

fischer FRA		Thread	M12 ²⁾		M16	M20	M24
Nominal diameter of the bar	φ	[mm]	12		16	20	25
Nominal drill hole diameter	d ₀		14	16	20	25	30
Drill hole depth	h ₀		h _{ef} + l _e = h _{nom}				
Effective embedment depth	h _{ef,min}		70		80	90	96
	h _{ef,max}		140		220	300	380
Distance concrete surface to welded joint	l _e		100				
Simplified spacing and edge distance ¹⁾	s = c		55		65	85	105
Maximum Diameter of clearance hole in the fixture	pre-positioned anchorage d _f		14		18	22	26
	push through anchorage d _f		18		22	26	32
Minimum thickness of concrete member	h _{min}		h ₀ + 30 (≥ 100)	h ₀ + 2d ₀			
Maximum installation torque	max T _{inst}	[Nm]	40		60	120	150

1) Detailed calculation according to **Annex B8** and **B9**.

2) Both drill hole diameters can be used.

fischer FRA




Marking frontal e.g:



FRA (for stainless steel);

FRA HCR (for high corrosion resistant steel HCR)

Installation conditions:



Figures not to scale

fischer injection system FIS V Plus

Intended use

Installation parameters fischer FRA

Annex B7

Appendix 16 / 41

Table B8.1: Minimum spacing and minimum edge distance for **Anchor rods / Threaded rods, reinforcing bars, fischer FIS IG and fischer FRA**

Anchor rods / Threaded rods			M6	M8	M10	-	-	-	M12	-	-	M16	-	
fischer FIS IG			-	-	-	M5	M6	M8	-	M10	-	-	M12	
Reinforcing bars / fischer FRA (nominal diameter)			φ	-	8	10	-	-	-	12	-	14	16	-
Minimum edge distance														
Uncracked / cracked concrete	C _{min}	[mm]	40	40	45	40	45	45	45	50	45	50	55	
Minimum spacing	s		according to Annex B9											
Minimum spacing														
Uncracked / cracked concrete	S _{min}	[mm]	40	40	45	40	45	55	55	65	60	65	85	
Minimum edge distance	c		according to Annex B9											
Required projecting area														
Uncracked concrete	C12/15 and	A _{sp,req}	[1000 mm ²]	-	11,3	18,3	5,0	5,0	7,8	31,0	11,3	-	33,8	18,4
Cracked concrete	C16/20			-	9,2	14,1	3,6	3,6	6,4	23,2	9,2	-	26,1	14,1
Uncracked concrete	≥C20/25			8,0	8,0	13,0	3,5	3,5	5,5	22,0	8,0	23,0	24,0	13,0
Cracked concrete				6,5	6,5	10,0	2,5	2,5	4,5	16,5	6,5	17,5	18,5	10,0
Anchor rods / Threaded rods			M20	-	M24	-	M27	-				M30		
fischer IG			-	M16	-	-	-	-	-	M20		-		
Reinforcing bars / fischer FRA (nominal diameter)			φ	20	-	-	25	-	28			-		
Minimum edge distance														
Uncracked / cracked concrete	C _{min}	[mm]	55	60	60	75	75	80	80	80				
Minimum spacing	s		according to Annex B9											
Minimum spacing														
Uncracked / cracked concrete	S _{min}	[mm]	85	105	105	120	120	140	140	140				
Minimum edge distance	c		according to Annex B9											
Required projecting area														
Uncracked concrete	C12/15 and	A _{sp,req}	[1000 mm ²]	54,2	30,3	56,3	-	66,9	-	36,7	90,1			
Cracked concrete	C16/20			51,5	23,3	42,9	-	51,4	-	28,2	69,0			
Uncracked concrete	≥C20/25			38,5	21,5	40,0	47,5	47,5	64,0	26,0	64,0			
Cracked concrete				29,5	16,5	30,5	36,5	36,5	49,0	20,0	49,0			

Splitting failure for minimum edge distance and spacing in dependence of the effective embedment depth h_{ef} .

For the calculation of minimum spacing and minimum edge distance of anchors in combination with different embedment depths and thicknesses of concrete members the following equation shall be fulfilled:

$$A_{sp,req} < A_{sp,t}$$

$A_{sp, req}$ = required projecting area

$A_{sp,t}$ = projecting area (according to **Annex B9**)

fischer injection system FIS V Plus


Intended use

Minimum spacing and edge distance for Anchor rods / Threaded rods, fischer FIS IG, reinforcing bars and fischer FRA

Annex B8


Appendix 17 / 41

Table B9.1: Projecting area $A_{sp,t}$ with concrete member thickness $h > h_{ef} + 1,5 \cdot c$ and $h \geq h_{min}$



Single fastener	$A_{sp,t} = (3 \cdot c) \cdot (h_{ef} + 1,5 \cdot c)$	[mm ²]	with $c \geq c_{min}$
Group of fastener with $s > 3 \cdot c$	$A_{sp,t} = (6 \cdot c) \cdot (h_{ef} + 1,5 \cdot c)$	[mm ²]	
Group of fastener with $s \leq 3 \cdot c$	$A_{sp,t} = (3 \cdot c + s) \cdot (h_{ef} + 1,5 \cdot c)$	[mm ²]	with $c \geq c_{min}$ and $s \geq s_{min}$

Table B9.2: Projecting area $A_{sp,t}$ with concrete member thickness $h \leq h_{ef} + 1,5 \cdot c$ and $h \geq h_{min}$



Single fastener	$A_{sp,t} = 3 \cdot c \cdot \text{existing } h$	[mm ²]	with $c \geq c_{min}$
Group of fastener with $s > 3 \cdot c$	$A_{sp,t} = 6 \cdot c \cdot \text{existing } h$	[mm ²]	
Group of fastener with $s \leq 3 \cdot c$	$A_{sp,t} = (3 \cdot c + s) \cdot \text{existing } h$	[mm ²]	with $c \geq c_{min}$ and $s \geq s_{min}$

Edge distance and axial spacing shall be rounded up to at least 5 mm.

Figures not to scale

Table B10.1: Parameters of the cleaning brush BS (steel brush with steel bristles)

The size of the cleaning brush refers to the drill hole diameter.

Nominal drill hole diameter d_0		8	10	12	14	16	18	20	24	25	28	30	32	35
Steel brush diameter BS d_b	[mm]	9	11	14	16	20		25	26	27	30	40		




Table B10.2: Maximum processing time of the mortar and minimum curing time
(During the curing time of the mortar the concrete temperature may not fall below the listed minimum temperature)

Temperature at anchoring base [°C]	Maximum processing time t_{work}			Minimum curing time ¹⁾ t_{cure}		
	FIS VW Plus High Speed	FIS V Plus	FIS VS Plus Low Speed	FIS VW Plus High Speed	FIS V Plus	FIS VS Plus Low Speed
-10 to -5 ²⁾	5 min	-	-	12 h	-	-
> -5 to 0 ²⁾	5 min	13 min	-	3 h	24 h	-
> 0 to 5 ²⁾	5 min	13 min	20 min	3 h	3 h	6 h
> 5 to 10	3 min	9 min	20 min	50 min	90 min	3 h
> 10 to 20	1 min	5 min	10 min	30 min	60 min	2 h
> 20 to 30	-	4 min	6 min	-	45 min	60 min
> 30 to 40	-	2 min	4 min	-	35 min	30 min

¹⁾ In wet concrete or water filled holes the curing times must be doubled.

²⁾ Minimal cartridge temperature +5°C.

Table B10.3: Conditions for use static mixer without an extension tube

Nominal drill hole diameter d_0		8	10	12	14	16	18	20	24	25	28	30	32	35
Drill hole depth h_0 by using	FIS MR Plus	≤90			≤120	≤140	≤150	≤160	≤190	≤210				
	FIS JMR	-	-	-	≤90	≤160	≤180	≤190	≤220	≤250				

fischer injection system FIS V Plus

Intended use

Cleaning brush (steel brush)
Processing time and curing time

Annex B10


Appendix 19 / 41

Table B11.1: Parameters of the fischer centering clip DD-S / DD-E								
Anchor rods / Threaded rods			M12	M16	M20	M24	M27	M30
fischer FIS IG			M8	M10	M12	M16	-	M20
fischer centering clip DD-S / DD-E			M12	M16	M20	M24	M27	M30
fischer centering clip DD-S	h_{DD-S}	[mm]	6,5	8,0	9,0	10,0	10,0	10,0
fischer centering clip DD-E	h_{DD-E}	[mm]	12,0	13,5	18,0	19,0	19,0	19,0
Drill hole depth	h_0	[mm]	$h_0 \geq h_{nom} + 3 \text{ mm}$					
Minimum thickness of concrete member	h_{min}	[mm]	$h_{nom} + 30$ (≥ 100)	$h_{nom} + 2d_0$				

The uppermost DD-S clip should be positioned approx. 5 - 10 mm below the concrete surface.
The effective embedment depth h_{ef} is calculated as follows when using the DD-S / DD-E clips.

$$h_{ef} = h_{nom} - h_{DD-E} - n \cdot h_{DD-S}$$

n = number of DD-S clips used










Figures not to scale

fischer injection system FIS V Plus	Annex B11 Appendix 20 / 41
Intended use fischer centering clip DD-S / DD-E	



Installation instructions part 1

Drilling and cleaning the hole (hammer drilling with standard drill bit)

1		Drill the hole. Nominal drill hole diameter d_0 and drill hole depth h_0 see Tables B3.1, B4.1, B5.1, B6.1 or B7.1.		
2		Clean the drill hole: For $h_{ef} \leq 12d$ and $d_0 < 18$ mm blow out the hole four times by hand.		For $h_{ef} > 12d$ and / or $d_0 \geq 18$ mm blow out the hole four times with oil-free compressed air ($p \geq 6$ bar). Use suitable compressed-air nozzle
3		Brush the drill hole four times. For $d_0 < 30$ mm brush process can be performed by hand. For deep holes use an extension. Use suitable brushes (see Table B10.1).		Brush the drill hole four times. For drill hole diameter ≥ 30 mm use a power drill. For deep holes use an extension. Use suitable brushes (see Table B10.1).
4		Clean the drill hole: For $h_{ef} \leq 12d$ and $d_0 < 18$ mm blow out the hole four times by hand.		For $h_{ef} > 12d$ and / or $d_0 \geq 18$ mm blow out the hole four times with oil-free compressed air ($p \geq 6$ bar). Use suitable compressed-air nozzle.

Go to step 5

Drilling and cleaning the hole (hammer drilling with hollow drill bit)

1		Check a suitable hollow drill (see Table B1.1) for correct operation of the dust extraction.	
2		Use a suitable dust extraction system, e.g.fischer FVC 35 M or a comparable dust extraction system with equivalent performance data Drill the hole with hollow drill bit. The dust extraction system has to extract the drill dust nonstop during the drilling process and must be adjusted to maximum power. Nominal drill hole diameter d_0 and drill hole depth h_0 see Tables B3.1, B4.1, B5.1, B6.1, B7.1.	

Go to step 5

fischer injection system FIS V Plus



Intended use
Installation instructions part 1

Annex B12

Appendix 21 / 41





Installation instructions part 2

Preparing the cartridge

5		Remove the sealing cap Screw on the static mixer Place the cartridge into the dispenser
6		Ensuring that the spiral inside the mixer is clearly visible.
7		Extrude approximately 10 cm of material out until the resin is evenly grey in colour. Do not use mortar that is not uniformly grey.

Go to step 8

Injection of the mortar







8		For $h_0 = h_{ef}$ fill approximately 2/3 of the drill hole with mortar. For $h_0 > h_{ef}$ more mortar is needed. Always begin from the bottom of the hole and avoid bubbles.
9		Push-through installation: the drill hole in the fixture must be also filled with mortar.
10		The conditions for mortar injection without extension tube can be found in Table B10.3.
		For overhead installation, deep holes ($h_0 > 250$ mm) or drill hole diameter ($d_0 \geq 30$ mm) use an injection-adapter.

Go to step 11




fischer injection system FIS V Plus	Annex B13 Appendix 22 / 41
Intended use Installation instructions part 2	

Installation instructions part 3

Installation of Anchor rods / Threaded rods, fischer RG M I and fischer FIS IG

11		Only use clean and oil-free metal parts. Push the Anchor rod / Threaded rods with the setting depth mark or fischer RG M I or fischer FIS IG down to the bottom of the hole, turning it slightly while doing so. No turning movement is permitted when using the DD-S / DD-E centering clips. After inserting the metal parts, excess mortar must be emerged around the anchor element.
12	 For overhead installations support the metal part with wedges (e.g. fischer centering wedges or fischer overhead clips).	 For push through installation fill the annular gap with mortar.
13	 Wait for the specified curing time t_{cure} see Table B10.2. The application with the anchor rod is shown as an example.	 Mounting the fixture $\max T_{inst}$ see Tables B3.1, B4.1 and B5.1.
Option	 After the minimum curing time is reached, the gap between metal part and fixture (annular clearance) may be filled with mortar via the fischer filling disc. Compressive strength $\geq 50 \text{ N/mm}^2$ (e.g. fischer injection mortars FIS HB, FIS SB, FIS V Plus, FIS EM Plus). ATTENTION: Using fischer filling disc reduces t_{fix} (usable length of the Anchor).	

Installation reinforcing bars and fischer FRA

11	 Only use clean and oil-free reinforcing bars or fischer FRA. Push the reinforcement bar or the fischer FRA with the setting depth mark into the filled hole up to the setting depth mark. Recommendation: Rotation back and forth of the reinforcement bar or the fischer FRA makes pushing easy.	
	 When the setting depth mark is reached, excess mortar must be emerged from the mouth of the drill hole. Wait for the specified curing time t_{cure} see Table B10.2.	 Mounting the fixture $\max T_{inst}$ see Table B7.1.

fischer injection system FIS V Plus

Intended use
Installation instructions part 3

Annex B14

Appendix 23 / 41

Table C1.1: Characteristic resistance to **steel failure** under **tension / shear loading** of **Anchor rods** and **Threaded rods**

Anchor rod / Threaded rod				M6	M8	M10	M12	M16	M20	M24	M27	M30	
Characteristic resistance to steel failure under tension loading ¹⁾													
Characteristic resistance $N_{Rk,s}$	Steel zinc plated	Property class	4.8	[kN]	8,0	14,6(13,2)	23,2(21,4)	33,7	62,8	98,0	141,2	183,6	224,4
			5.8		10,1	18,3(16,6)	29,0(26,8)	42,1	78,5	122,5	176,5	229,5	280,5
			8.8		16,1	29,2(26,5)	46,4(42,8)	67,4	125,6	196,0	282,4	367,2	448,8
	Stainless steel R and high corrosion resistant steel HCR	50	10,1		18,3	29,0	42,1	78,5	122,5	176,5	229,5	280,5	
		70	14,1		25,6	40,6	59,0	109,9	171,5	247,1	321,3	392,7	
		80	16,1		29,2	46,4	67,4	125,6	196,0	282,4	367,2	448,8	
Partial factors ¹⁾													
Partial factor $\gamma_{Ms,N}$	Steel zinc plated	Property class	4.8	[-]	1,50								
			5.8		1,50								
			8.8		1,50								
	Stainless steel R and high corrosion resistant steel HCR		50		2,86								
			70		1.87 / fischer HCR: 1.50 ³⁾								
			80		1,60								
Characteristic resistance to steel failure under shear loading ¹⁾													
without lever arm													
Characteristic resistance $V_{Rk,s}^0$	Steel zinc plated	Property class	4.8	[kN]	4,8	8,7(7,9)	13,9(12,8)	20,2	37,6	58,8	84,7	110,1	134,6
			5.8		6,0	10,9(9,9)	17,4(16,0)	25,2	47,1	73,5	105,9	137,7	168,3
			8.8		8,0	14,6(13,2)	23,2(21,4)	33,7	62,8	98,0	141,2	183,6	224,4
	Stainless steel R and high corrosion resistant steel HCR		50		5,0	9,1	14,5	21,0	39,2	61,2	88,2	114,7	140,2
			70		7,0	12,8	20,3	29,5	54,9	85,7	123,5	160,6	196,3
			80		8,0	14,6	23,2	33,7	62,8	98,0	141,2	183,6	224,4
Ductility factor		k ₇	[-]	1,0									
with lever arm													
Characteristic resistance $M_{Rk,s}^0$	Steel zinc plated	Property class	4.8	[Nm]	6,1	14,9(12,9)	29,9(26,5)	52,3	132,9	259,6	448,8	665,7	899,5
			5.8		7,6	18,7(16,1)	37,3(33,2)	65,4	166,2	324,6	561,0	832,2	1124,4
			8.8		12,2	29,9(25,9)	59,8(53,1)	104,6	265,9	519,3	897,6	1331,5	1799,0
	Stainless steel R and high corrosion resistant steel HCR		50		7,6	18,7	37,3	65,4	166,2	324,6	561,0	832,2	1124,4
			70		10,7	26,2	52,3	91,5	232,6	454,4	785,4	1165,0	1574,1
			80		12,2	29,9	59,8	104,6	265,9	519,3	897,6	1331,5	1799,0
Partial factors ²⁾													
Partial factor $\gamma_{Ms,V}$	Steel zinc plated	Property class	4.8	[-]	1,25								
			5.8		1,25								
			8.8		1,25								
	Stainless steel R and high corrosion resistant steel HCR		50		2,38								
			70		1.56 / fischer HCR: 1.25 ³⁾								
			80		1,33								

¹⁾ Values in brackets are valid for undersized threaded rods with smaller stress area A_s for hot dip galvanised threaded rods according to EN ISO 10684:2004+AC:2009.

2) In absence of other national regulations,

³⁾ Only admissible for high corrosion resistant steel HCR, acc. to **Table A7.1**.

fischer injection system FIS V Plus	Annex C1 Appendix 24 / 41
Performances Characteristic resistance to steel failure under tension / shear loading of Anchor rods and Threaded rods	

Table C2.1: Characteristic resistance to steel failure under tension / shear loading of fischer RG M I

fischer RG M I				M8	M10	M12	M16	M20	
Characteristic resistance to steel failure under tension loading									
Characteristic resistance with Screw or Threaded / Anchor rod $N_{Rk,s}$	Steel zinc plated	Property class of Screw or Threaded / Anchor rod	5.8	[kN]	18,3	29,0	42,1	78,3	122,4
			8.8		29,2	46,4	67,4	106,7	180,2
	Stainless steel R and High corrosion resistant steel HCR		70		25,6	40,6	59,0	109,6	171,3
Partial factors ¹⁾									
Partial factor $\gamma_{Ms,N}$	Steel zinc plated	Property class of Screw or Threaded / Anchor rod	5.8	[-]	1,50				
			8.8		1,50				
	Stainless steel R and High corrosion resistant steel HCR		70		1,87 / fischer HCR: 1,50 ²⁾				
Characteristic resistance to steel failure under shear loading									
Without lever arm									
Characteristic resistance with Screw or Threaded / Anchor rod $V^0_{Rk,s}$	Steel zinc plated	Property class of Screw or Threaded / Anchor rod	5.8	[kN]	10,9	17,4	25,2	47,1	73,5
			8.8		14,6	23,2	33,7	62,8	98,0
	Stainless steel R and High corrosion resistant steel HCR		70		12,8	20,3	29,5	54,9	85,7
Ductility factor			k_7	[-]	1,0				
With lever arm									
Characteristic resistance with Screw or Threaded / Anchor rod $M^0_{Rk,s}$	Steel zinc plated	Property class of Screw or Threaded / Anchor rod	5.8	[Nm]	18,7	37,3	65,4	166,2	324,6
			8.8		29,9	59,8	104,6	265,9	519,3
	Stainless steel R and High corrosion resistant steel HCR		70		26,2	52,3	91,5	232,6	454,4
Partial factors ¹⁾									
Partial factor $\gamma_{Ms,V}$	Steel zinc plated	Property class of Screw or Threaded / Anchor rod	5.8	[-]	1,25				
			8.8		1,25				
	Stainless steel R and High corrosion resistant steel HCR		70		1,56 / fischer HCR: 1,25 ²⁾				
¹⁾ In absence of other national regulations ²⁾ Only admissible for high corrosion resistant steel HCR, acc. to Table A7.1 .									

¹⁾ In absence of other national regulations

²⁾ Only admissible for high corrosion resistant steel HCR, acc. to **Table A7.1**.

fischer injection system FIS V Plus

Performances

Characteristic resistance to steel failure under shear loading of fischer RG M I

Annex C2

Appendix 25 / 41

Table C3.1: Characteristic resistance to steel failure under tension / shear loading of fischer FIS IG

fischer FIS IG					M5	M6	M8	M10	M12	M16	M20
Characteristic resistance to steel failure under tension loading											
Characteristic resistance with Screw or Threaded / Anchor rod $N_{Rk,s}$	Steel zinc plated	Property class of Screw or Threaded / Anchor rod	5.8	[kN]	7,1	10,1	18,3	29,0	42,1	78,3	122,4
			8.8		11,4	16,1	23,0	46,4	67,4	96,9	156,8
	Stainless steel R and High corrosion resistant steel HCR		70		9,9	14,1	25,6	40,6	59,0	109,6	171,3
Partial factors ¹⁾											
Partial factor $\gamma_{Ms,N}$	Steel zinc plated	Property class of Screw or Threaded / Anchor rod	5.8	[-]	1,50						
			8.8		1,50						
	Stainless steel R and High corrosion resistant steel HCR		70		1,87 / fischer HCR: 1,50 ²⁾						
Characteristic resistance to steel failure under shear loading											
Without lever arm											
Characteristic resistance with Screw or Threaded / Anchor rod $V_{Rk,s}^0$	Steel zinc plated	Property class of Screw or Threaded / Anchor rod	5.8	[kN]	4,3	6,0	10,9	17,4	25,2	47,1	73,5
			8.8		5,7	8,0	14,6	23,2	33,7	62,8	98,0
	Stainless steel R and High corrosion resistant steel HCR		70		5,0	7,0	12,8	20,3	29,5	54,9	85,7
Ductility factor			k ₇	[-]	1,0						
With lever arm											
Characteristic resistance with Screw or Threaded / Anchor rod $M_{Rk,s}^0$	Steel zinc plated	Property class of Screw or Threaded / Anchor rod	5.8	[Nm]	4,5	7,6	18,7	37,3	65,4	166,2	324,6
			8.8		7,2	12,2	29,9	59,8	104,6	265,9	519,3
	Stainless steel R and High corrosion resistant steel HCR		70		6,3	10,7	26,2	52,3	91,5	232,6	454,4
Partial factors ¹⁾											
Partial factor $\gamma_{Ms,V}$	Steel zinc plated	Property class of Screw or Threaded / Anchor rod	5.8	[-]	1,25						
			8.8		1,25						
	Stainless steel R and High corrosion resistant steel HCR		70		1,56 / fischer HCR: 1,25 ²⁾						

¹⁾ In absence of other national regulations.

²⁾ Only admissible for high corrosion resistant steel HCR, acc. to **Table A7.1**

fischer injection system FIS V Plus	Annex C3 Appendix 26 / 41
Performances Characteristic resistance to steel failure under shear loading of fischer FIS IG	

Table C4.1: Characteristic resistance to steel failure under tension / shear loading of reinforcing bars
--

Nominal diameter of the bar	ϕ	8	10	12	14	16	20	25	28
Characteristic resistance to steel failure under tension loading									
Characteristic resistance	$N_{Rk,s}$	[kN]	$A_s \cdot f_{uk}^{1)}$						
Characteristic resistance to steel failure under shear loading									
Without lever arm									
Characteristic resistance	$V^0_{Rk,s}$	[kN]	$k_6^{2)}) \cdot A_s \cdot f_{uk}^{1)}$						
Ductility factor	k_7	[-]	1,0						
With lever arm									
Characteristic resistance	$M^0_{Rk,s}$	[Nm]	$1,2 \cdot W_{el} \cdot f_{uk}^{1)}$						
¹⁾ f_{uk} respectively shall be taken from the specifications of the reinforcing bar. ²⁾ In accordance with EN 1992-4:2018 section 7.2.2.3.1: $k_6 = 0,6$ for fasteners made of carbon steel with $f_{uk} \leq 500 \text{ N/mm}^2$, $= 0,5$ for fasteners made of carbon steel with $500 \text{ N/mm}^2 < f_{uk} \leq 1000 \text{ N/mm}^2$, $= 0,5$ for fasteners made of stainless steel.									

Table C4.2: Characteristic resistance to steel failure under tension / shear loading of fischer FRA

fischer FRA			M12	M16	M20	M24
Characteristic resistance to steel failure under tension loading						
Characteristic resistance	$N_{Rk,s}$	[kN]	62,0	111,0	173,0	236,5
Partial factor¹⁾						
Partial factor	$\gamma_{Ms,N}$	[-]	1,4			
Characteristic resistance to steel failure under shear loading						
Without lever arm						
Characteristic resistance	$V^0_{Rk,s}$	[kN]	34,5	64,3	100,4	144,7
Ductility factor	k_7	[-]	1,0			
With lever arm						
Characteristic resistance	$M^0_{Rk,s}$	[Nm]	107,4	273,0	532,2	920,4
Partial factor¹⁾						
Partial factor	$\gamma_{Ms,V}$	[-]	1,5			

¹⁾ In absence of other national regulations.

fischer injection system FIS V Plus	Annex C4 Appendix 27 / 41
Performances Characteristic resistance to steel failure under tension / shear loading of reinforcing bars and fischer FRA	

Table C5.1: Characteristic resistance to concrete failure under tension / shear loading													
Size			All sizes										
Characteristic resistance to concrete failure under tension loading													
Installation factor		γ_{inst}	[-]	See annex C6 to C11 and C 17 to C18									
Factors for the compressive strength of concrete > C20/25													
Increasing factor ψ_c for cracked or uncracked concrete $\tau_{Rk}(X,Y) = \psi_c \cdot \tau_{Rk}(C20/25)$	C25/30	[-]		1,05									
	C30/37			1,10									
	C35/45			1,15									
	C40/50			1,19									
	C45/55			1,22									
	C50/60			1,26									
Splitting failure													
Edge distance	$h / h_{ef} \geq 2,0$	$C_{cr,sp}$	[mm]	1,0 h_{ef}				C12/15: 1,22 h_{ef}					
	$2,0 > h / h_{ef} > 1,3$			4,6 $h_{ef} - 1,8 h$				C12/15: 5,6 $h_{ef} - 2,2 h$					
	$h / h_{ef} \leq 1,3$			2,26 h_{ef}				C12/15: 2,75 h_{ef}					
Spacing		$S_{cr,sp}$		2 $C_{cr,sp}$									
Concrete failure													
Uncracked concrete		$k_{ucr,N}$	[-]	11,0									
Cracked concrete		$k_{cr,N}$		7,7									
Edge distance		$C_{cr,N}$	[mm]	1,5 h_{ef}									
Spacing		$S_{cr,N}$		2 $C_{cr,N}$									
Factors for sustained tension loading													
Temperature range			[-]	50 °C / 80 °C				72 °C / 120 °C					
Factor C12/15 and C16/20			Ψ_{SUS}^0	[-]	0,68				0,70				
Factor from $\geq C20/25$			$\Psi_{SUS}^0 = \Psi_{SUS,100}^0$	[-]	0,76				0,78				
Characteristic resistance to concrete failure under shear loading													
Installation factor		γ_{inst}	[-]	1,0									
Concrete pry-out failure													
Factor for pry-out failure		k_8	[-]	2,0									
Concrete edge failure													
Effective length of fastener in shear loading		l_f	[mm]	for $d_{nom} \leq 24$ mm: min (h_{ef} ; 12 d_{nom}) for $d_{nom} > 24$ mm: min (h_{ef} ; 8 d_{nom} ; 300 mm)									
Calculation diameters													
Size				M5	M6	M8	M10	M12	M16	M20	M24	M27	M30
Anchor rods and Threaded rods		d_{nom}	[mm]	-1)	6	8	10	12	16	20	24	27	30
fischer RG M I		d_{nom}		-1)	-1)	12	16	18	22	28	-1)	-1)	-1)
fischer FIS IG				8	10	12	16	20	24	30	-1)	-1)	-1)
fischer FRA		d_{nom}		-1)	-1)	-1)	-1)	12	16	20	25	-1)	-1)
Size (nominal diameter of the bar)			ϕ	8	10	12	14	16	20	25	28		
Reinforcing bar			d_{nom}	[mm]	8	10	12	14	16	20	25	28	
1) Size of Anchor type not part of the assessment													
fischer injection system FIS V Plus										Annex C5 Appendix 28 / 41			
Performances Characteristic resistance to concrete failure under tension / shear loading													

Table C6.1:	Characteristic resistance to combined pull-out and concrete failure for Anchor rods and Threaded rods and fischer FIS IG in hammer drilled holes; uncracked or cracked concrete C20/25; working life 50 years
--------------------	--

Anchor rod / Threaded rod			M6	M8	M10	M12	M16	M20	M24	M27	M30		
fischer FIS IG			-	-	M5 M6	M8	M10	M12	M16	-	M20		
Combined pullout and concrete cone failure													
Calculation diameter		d	[mm]	6	8	10	12	16	20	24	27	30	
Uncracked concrete													
Characteristic bond resistance in uncracked concrete C20/25													
Hammer-drilling with standard drill bit or hollow drill bit (dry or wet concrete)													
Temperature range	I: 50 °C / 80 °C		$\tau_{Rk,ucr}$	[N/mm ²]	9,0	16,0	16,0	15,0	14,0	12,0	11,0	10,0	9,0
	II: 72 °C / 120 °C				6,5	15,0	14,0	13,0	12,0	11,0	9,0	8,0	8,0
Hammer-drilling with standard drill bit or hollow drill bit (water filled hole)													
Temperature range	I: 50 °C / 80 °C		$\tau_{Rk,ucr}$	[N/mm ²]	- ¹⁾	- ¹⁾	- ¹⁾	9,5	8,5	8,0	7,5	7,0	7,0
	II: 72 °C / 120 °C				- ¹⁾	- ¹⁾	- ¹⁾	7,5	7,0	6,5	6,0	6,0	6,0
Installation factors													
Dry or wet concrete		γ_{inst}	[-]	1,0									
Water filled hole				- ¹⁾	- ¹⁾	- ¹⁾	1,2						
Cracked concrete													
Characteristic bond resistance in cracked concrete C20/25													
Hammer-drilling with standard drill bit or hollow drill bit (dry or wet concrete)													
Temperature range	I: 50 °C / 80 °C		$\tau_{Rk,cr}$	[N/mm ²]	- ¹⁾	5,5	6,0	6,5	6,0	5,5	5,0	5,0	4,5
	II: 72 °C / 120 °C				- ¹⁾	4,5	5,0	6,0	5,5	5,0	4,5	4,0	4,0
Hammer-drilling with standard drill bit or hollow drill bit (water filled hole)													
Temperature range	I: 50 °C / 80 °C		$\tau_{Rk,cr}$	[N/mm ²]	- ¹⁾	- ¹⁾	- ¹⁾	5,0	5,0	4,5	4,0	3,5	3,5
	II: 72 °C / 120 °C				- ¹⁾	- ¹⁾	- ¹⁾	4,0	4,0	4,0	3,5	3,0	3,0
Installation factors													
Dry or wet concrete		γ_{inst}	[-]	- ¹⁾	1,0								
Water filled hole				- ¹⁾	- ¹⁾	- ¹⁾	1,2						

1) No performance assessed

fischer injection system FIS V Plus

Performances

Characteristic resistance to combined pull-out and concrete failure for Anchor rod and Threaded rods; working life 50 years; concrete C20/25

Annex C6

Appendix 29 / 41

Table C7.1: Characteristic resistance to combined pull-out and concrete failure for Anchor rods, Threaded rods and fischer FIS IG in hammer drilled holes; uncracked or cracked concrete C20/25; working life 100 years

Anchor rod / Threaded rod				M6	M8	M10	M12	M16	M20	M24	M27	M30
fischer FIS IG				-	-	M5 M6	M8	M10	M12	M16	-	M20
Combined pullout and concrete cone failure												
Calculation diameter		d	[mm]	6	8	10	12	16	20	24	27	30
Uncracked concrete												
Characteristic bond resistance in uncracked concrete C20/25												
Hammer-drilling with standard drill bit or hollow drill bit (dry or wet concrete)												
Temperature range	I: 50 °C / 80 °C		$\tau_{Rk,100,ucr}$ [N/mm ²]	- ¹⁾	16,0	16,0	15,0	14,0	12,0	11,0	10,0	9,0
	II: 72 °C / 120 °C			- ¹⁾	15,0	14,0	13,0	12,0	11,0	9,0	8,0	8,0
Hammer-drilling with standard drill bit or hollow drill bit (water filled hole)												
Temperature range	I: 50 °C / 80 °C		$\tau_{Rk,100,ucr}$ [N/mm ²]	- ¹⁾	- ¹⁾	- ¹⁾	9,5	8,5	8,0	7,5	7,0	7,0
	II: 72 °C / 120 °C			- ¹⁾	- ¹⁾	- ¹⁾	7,5	7,0	6,5	6,0	6,0	6,0
Installation factors												
Dry or wet concrete		γ_{inst}	[-]	- ¹⁾	1,0							
Water filled hole				- ¹⁾	- ¹⁾	- ¹⁾	1,2					
Cracked concrete												
Characteristic bond resistance in cracked concrete C20/25												
Hammer-drilling with standard drill bit or hollow drill bit (dry or wet concrete)												
Temperature range	I: 50 °C / 80 °C		$\tau_{Rk,100,cr}$ [N/mm ²]	- ¹⁾	5,0	5,5	5,5	5,5	5,5	5,0	5,0	4,5
	II: 72 °C / 120 °C			- ¹⁾	4,5	5,0	5,0	5,0	5,0	4,0	4,0	4,0
Hammer-drilling with standard drill bit or hollow drill bit (water filled hole)												
Temperature range	I: 50 °C / 80 °C		$\tau_{Rk,100,cr}$ [N/mm ²]	- ¹⁾	- ¹⁾	- ¹⁾	4,5	4,5	4,5	4,0	3,5	3,5
	II: 72 °C / 120 °C			- ¹⁾	- ¹⁾	- ¹⁾	4,0	4,0	4,0	3,5	3,0	3,0
Installation factors												
Dry or wet concrete		γ_{inst}	[-]	- ¹⁾	1,0							
Water filled hole				- ¹⁾	- ¹⁾	- ¹⁾	1,2					
1) No performance assessed												
fischer injection system FIS V Plus									Annex C7 Appendix 30 / 41			
Performances												
Characteristic resistance to combined pull-out and concrete failure for Anchor rod and Threaded rods; working life 100 years; concrete C20/25												

Table C8.1: Characteristic resistance to combined pull-out and concrete failure for Anchor rods, Threaded rods and fischer FIS IG in hammer drilled holes; uncracked or cracked concrete C12/15 and C16/20; working life 50 years

Anchor rod / Threaded rod	M6	M8	M10	M12	M16	M20	M24	M27	M30
fischer FIS IG	-	-	M5 M6	M8	M10	M12	M16	-	M20

Combined pullout and concrete cone failure

Calculation diameter	d	[mm]	6	8	10	12	16	20	24	27	30
----------------------	---	------	---	---	----	----	----	----	----	----	----

Uncracked concrete

Characteristic bond resistance in uncracked concrete C12/15

Hammer-drilling with standard drill bit or hollow drill bit (dry or wet concrete)

Temperature range	I: 50 °C / 80 °C	$\tau_{RK,ucr}$	[N/mm ²]	-1)	12,5	12	11,5	10,5	10,0	9,0	8,5	8,0
	II: 72 °C / 120 °C			-1)	9,5	9,0	8,5	8,0	7,5	7,0	6,5	6,5

Hammer-drilling with standard drill bit or hollow drill bit (water filled hole)

Temperature range	I: 50 °C / 80 °C	$\tau_{RK,ucr}$	[N/mm ²]	-1)	-1)	-1)	9,0	7,5	7,0	4,0	3,5	3,5
	II: 72 °C / 120 °C			-1)	-1)	-1)	7,0	6,0	5,5	3,0	3,0	2,5

Installation factors

Dry or wet concrete	γ_{inst}	[-]	- ¹⁾	1,2
Water filled hole			- ¹⁾	1,4

Cracked concrete

Characteristic bond resistance in cracked concrete C12/15

Hammer-drilling with standard drill bit or hollow drill bit (dry or wet concrete)

Temperature range	I: 50 °C / 80 °C	$\tau_{RK,cr}$	[N/mm ²]	-1)	4,5	5,0	5,0	5,0	4,0	4,0	4,0	4,0
	II: 72 °C / 120 °C			-1)	3,5	3,5	3,5	3,5	3,0	3,0	3,0	3,0

Hammer-drilling with standard drill bit or hollow drill bit (water filled hole)

Temperature range	I: 50 °C / 80 °C	$\tau_{Rk,cr}$	[N/mm ²]	-1)	-1)	-1)	4,0	3,5	3,0	2,0	2,0	2,0
	II: 72 °C / 120 °C			-1)	-1)	-1)	3,0	2,5	2,5	1,5	1,5	1,5

Installation factors

Dry or wet concrete	γ_{inst}	[-]	- ¹⁾	1,2
Water filled hole			- ¹⁾	1,4

1) No performance assessed

fischer injection system FIS V Plus	Annex C8 Appendix 31 / 41
Performances Characteristic resistance to combined pull-out and concrete failure for Anchor rod and Threaded rods; working life 50 years; concrete C12/15	

Table C9.1: Characteristic resistance to combined pull-out and concrete failure for fischer RG M I in hammer drilled holes; uncracked concrete; working life 50 years

fischer RG M I			M8	M10	M12	M16	M20
Combined pullout and concrete cone failure							
Calculation diameter	d	[mm]	12	16	18	22	28
Uncracked concrete							
Characteristic bond resistance in uncracked concrete C20/25							
Hammer-drilling with standard drill bit or hollow drill bit (dry or wet concrete)							
Temperature range	I: 50 °C / 80 °C	$\tau_{Rk,ucr}$ [N/mm ²]	10,5	10,0	9,5	9,0	8,5
	II: 72 °C / 120 °C		9,0	8,0	8,0	7,5	7,0
Hammer-drilling with standard drill bit or hollow drill bit (water filled hole)							
Temperature range	I: 50 °C / 80 °C	$\tau_{Rk,ucr}$ [N/mm ²]	10,0	9,0	9,0	8,5	8,0
	II: 72 °C / 120 °C		7,5	6,5	6,5	6,0	6,0
Installation factors							
Dry or wet concrete	γ_{inst}	[-]	1,0				
Water filled hole			1,2				

fischer injection system FIS V Plus

Performances

Characteristic resistance to combined pull-out and concrete failure for fischer RG M I or fischer FIS IG; working life 50 years

Annex C9

Appendix 32 / 41

Table C10.1: Characteristic resistance to combined pull-out and concrete failure for reinforcing bars in hammer drilled holes; uncracked or cracked concrete; working life 50 years

Nominal diameter of the bar		ϕ	8	10	12	14	16	20	25	28	
Combined pullout and concrete cone failure											
Calculation diameter		d	[mm]	8	10	12	14	16	20	25	28
Uncracked concrete											
Characteristic bond resistance in uncracked concrete C20/25											
Hammer-drilling with standard drill bit or hollow drill bit (dry or wet concrete)											
Temperature range	I: 50 °C / 80 °C	$\tau_{Rk,ucr}$	[N/mm ²]	11,0	11,0	11,0	10,0	10,0	9,5	9,0	8,5
	II: 72 °C / 120 °C			9,5	9,5	9,0	8,5	8,5	8,0	7,5	7,0
Installation factor											
Dry or wet concrete		γ_{inst}	[-]	1,0							
Cracked concrete											
Characteristic bond resistance in cracked concrete C20/25											
Hammer-drilling with standard drill bit or hollow drill bit (dry or wet concrete)											
Temperature range	I: 50 °C / 80 °C	$\tau_{Rk,cr}$	[N/mm ²]	- ¹⁾	3,0	5,0	5,0	5,0	4,5	4,0	4,0
	II: 72 °C / 120 °C			- ¹⁾	3,0	4,5	4,5	4,5	4,5	4,0	3,5
Installation factor											
Dry or wet concrete		γ_{inst}	[-]	1,0							

¹⁾ No performance assessed

fischer injection system FIS V Plus

Performances
Characteristic resistance to combined pull-out and concrete failure for reinforcing bars;
working life 50 years

Table C11.1: Characteristic resistance to combined pull-out and concrete failure for fischer FRA in hammer drilled holes; uncracked or cracked concrete; working life 50 years

fischer FRA			M12	M16	M20	M24	
Combined pullout and concrete cone failure							
Calculation diameter		d	[mm]	12	16	20	25
Uncracked concrete							
Characteristic bond resistance in uncracked concrete C20/25							
Hammer-drilling with standard drill bit or hollow drill bit (dry or wet concrete)							
Temperature range	I: 50 °C / 80 °C	$\tau_{Rk,ucr}$	[N/mm ²]	11,0	10,0	9,5	9,5
	II: 72 °C / 120 °C			9,0	8,5	8,0	7,5
Installation factors							
Dry or wet concrete		γ_{inst}	[-]	1,0			
Cracked concrete							
Characteristic bond resistance in cracked concrete C20/25							
Hammer-drilling with standard drill bit or hollow drill bit (dry or wet concrete)							
Temperature range	I: 50 °C / 80 °C	$\tau_{Rk,cr}$	[N/mm ²]	5,0	5,0	4,5	4,0
	II: 72 °C / 120 °C			4,5	4,5	4,0	3,5
Installation factors							
Dry or wet concrete		γ_{inst}	[-]	1,0			

fischer injection system FIS V Plus

Performances

Characteristic resistance to combined pull-out and concrete failure for fischer FRA;
working life 50 years

Annex C11

Appendix 34 / 41

Table C12.1: Displacements for Anchor rods / Threaded rods or fischer FIS IG										
Anchor rod / Threaded rods	M6	M8	M10	M12	M16	M20	M24	M27	M30	
fischer FIS IG										
Displacement-Factors for tension loading ¹⁾										
Uncracked concrete; Temperature range I, II										
δ _{N0} -Factor	[mm/(N/mm ²)]	0,09	0,09	0,09	0,10	0,10	0,10	0,10	0,12	0,12
δ _{N∞} -Factor		0,10	0,10	0,10	0,12	0,12	0,12	0,13	0,13	0,14
Cracked concrete; Temperature range I, II										
δ _{N0} -Factor	[mm/(N/mm ²)]	- ³⁾	0,12	0,12	0,12	0,13	0,16	0,19	0,21	0,23
δ _{N∞} -Factor		- ³⁾	0,25	0,27	0,30	0,30	0,30	0,35	0,35	0,40
Displacement-Factors for shear loading ²⁾										
Uncracked or cracked concrete; Temperature range I, II										
δ _{V0} -Factor	[mm/kN]	0,11	0,11	0,11	0,10	0,10	0,09	0,09	0,08	0,07
δ _{V∞} -Factor		0,12	0,12	0,12	0,11	0,11	0,10	0,10	0,09	0,09
1) Calculation of effective displacement:					2) Calculation of effective displacement:					
δ _{N0} = δ _{N0} -Factor · τ					δ _{V0} = δ _{V0} -Factor · V					
δ _{N∞} = δ _{N∞} -Factor · τ					δ _{V∞} = δ _{V∞} -Factor · V					
τ = acting bond strength under tension loading					V = acting shear loading					
3) No performance assessed										

Table C12.2: Displacements for fischer RG M I						
fischer RG M I		M8	M10	M12	M16	M20
Displacement-Factors for tension loading ¹⁾						
Uncracked concrete; Temperature range I, II						
δ_{N0} -Factor	[mm/(N/mm ²)]	0,10	0,11	0,12	0,13	0,14
$\delta_{N\infty}$ -Factor		0,13	0,14	0,15	0,16	0,18
Displacement-Factors for shear loading ²⁾						
Uncracked concrete; Temperature range I, II						
δ_{V0} -Factor	[mm/kN]	0,12	0,12	0,12	0,12	0,12
$\delta_{V\infty}$ -Factor		0,14	0,14	0,14	0,14	0,14
1) Calculation of effective displacement: $\delta_{N0} = \delta_{N0}\text{-Factor} \cdot \tau$ $\delta_{N\infty} = \delta_{N\infty}\text{-Factor} \cdot \tau$ τ = acting bond strength under tension loading 2) Calculation of effective displacement: $\delta_{V0} = \delta_{V0}\text{-Factor} \cdot V$ $\delta_{V\infty} = \delta_{V\infty}\text{-Factor} \cdot V$ V: acting shear loading						
fischer injection system FIS V Plus						Annex C12 Appendix 35 / 41
Performances Displacements for Anchor rods / Threaded rods, fischer FIS IG and fischer RG M I						

Table C13.1: Displacements for reinforcing bars									
Nominal diameter of the bar	ϕ	8	10	12	14	16	20	25	28
Displacement-Factors for tension loading ¹⁾									
Uncracked concrete; Temperature range I, II									
δ_{N0} -Factor	[mm/(N/mm ²)]	0,09	0,09	0,10	0,10	0,10	0,10	0,10	0,11
$\delta_{N\infty}$ -Factor		0,10	0,10	0,12	0,12	0,12	0,12	0,13	0,13
Cracked concrete; Temperature range I, II									
δ_{N0} -Factor	[mm/(N/mm ²)]	– ³⁾	0,12	0,13	0,13	0,13	0,13	0,13	0,14
$\delta_{N\infty}$ -Factor		– ³⁾	0,27	0,30	0,30	0,30	0,30	0,35	0,37
Displacement-Factors for shear loading ²⁾									
Uncracked or cracked concrete; Temperature range I, II									
δ_{V0} -Factor	[mm/kN]	0,11	0,11	0,10	0,10	0,10	0,09	0,09	0,08
$\delta_{V\infty}$ -Factor		0,12	0,12	0,11	0,11	0,11	0,10	0,10	0,09
1) Calculation of effective displacement:					2) Calculation of effective displacement:				
$\delta_{N0} = \delta_{N0}\text{-Factor} \cdot \tau$					$\delta_{V0} = \delta_{V0}\text{-Factor} \cdot V$				
$\delta_{N\infty} = \delta_{N\infty}\text{-Factor} \cdot \tau$					$\delta_{V\infty} = \delta_{V\infty}\text{-Factor} \cdot V$				
τ = acting bond strength under tension loading					V: acting shear loading				
³⁾ No performance assessed									

Table C13.2: Displacements for fischer FRA

fischer FRA		M12	M16	M20	M24
Displacement-Factors for tension loading¹⁾					
Uncracked concrete; Temperature range I, II					
δ_{N0} -Factor	[mm/(N/mm ²)]	0,10	0,10	0,10	0,10
$\delta_{N\infty}$ -Factor		0,12	0,12	0,12	0,13
Cracked concrete; Temperature range I, II					
δ_{N0} -Factor	[mm/(N/mm ²)]	0,12	0,13	0,13	0,13
$\delta_{N\infty}$ -Factor		0,30	0,30	0,30	0,35
Displacement-Factors for shear loading²⁾					
Uncracked or cracked concrete; Temperature range I, II					
δ_{V0} -Factor	[mm/kN]	0,10	0,10	0,09	0,09
$\delta_{V\infty}$ -Factor		0,11	0,11	0,10	0,10
¹⁾ Calculation of effective displacement: $\delta_{N0} = \delta_{N0}\text{-Factor} \cdot \tau$ $\delta_{N\infty} = \delta_{N\infty}\text{-Factor} \cdot \tau$ τ = acting bond strength under tension loading			²⁾ Calculation of effective displacement: $\delta_{V0} = \delta_{V0}\text{-Factor} \cdot V$ $\delta_{V\infty} = \delta_{V\infty}\text{-Factor} \cdot V$ V : acting shear loading		

fischer injection system FIS V Plus

Performances

Displacements for reinforcing bars and fischer FRA

Annex C13

Appendix 36 / 41

Table C14.1: Characteristic resistance to **steel failure** under **tension / shear loading** of **Anchor rods** and **Threaded rods** under seismic action performance category **C1**

Anchor rod / Threaded rod			M10	M12	M16	M20	M24	M27	M30		
Characteristic resistance to steel failure under tension loading ¹⁾											
Anchor rods and Threaded rods, performance category C1 ²⁾											
Characteristic resistance $N_{Rk,s,C1}$	Steel zinc plated	Property class	4.8	[kN]	23,2(21,4)	33,7	62,8	98,0	141,2	183,6	224,4
			5.8		29,0(26,8)	42,1	78,5	122,5	176,5	229,5	280,5
			8.8		46,4(42,8)	67,4	125,6	196,0	282,4	367,2	448,8
	Stainless steel R and high corrosion resistant steel HCR		50		29,0	42,1	78,5	122,5	176,5	229,5	280,5
			70		40,6	59,0	109,9	171,5	247,1	321,3	392,7
			80		46,4	67,4	125,6	196,0	282,4	367,2	448,8
Characteristic resistance to steel failure under shear loading without lever arm ¹⁾											
Anchor rods, performance category C1 ²⁾											
Characteristic resistance $V_{Rk,s,C1}$	Steel zinc plated	Property class	4.8	[kN]	13,9(12,8)	20,2	37,6	58,8	84,7	110,1	134,6
			5.8		17,4(16,0)	25,2	47,1	73,5	105,9	137,7	168,3
			8.8		23,2(21,4)	33,7	62,8	98,0	141,2	183,6	224,4
	Stainless steel R and high corrosion resistant steel HCR		50		14,5	21,0	39,2	61,2	88,2	114,7	140,2
			70		20,3	29,5	54,9	85,7	123,5	160,6	196,3
			80		23,2	33,7	62,8	98,0	141,2	183,6	224,4
Threaded rods, performance category C1 ²⁾											
Characteristic resistance $V_{Rk,s,C1}$	Steel zinc plated	Property class	4.8	[kN]	9,7(9,0)	14,1	26,3	41,1	59,3	77,1	97,2
			5.8		12,1(11,2)	17,7	32,9	51,4	74,1	96,3	117,8
			8.8		16,2(15,0)	23,6	43,9	68,6	98,8	128,5	157,0
	Stainless steel R and high corrosion resistant steel HCR		50		10,1	14,7	27,4	42,8	61,7	80,3	98,1
			70		14,2	20,6	38,4	60,0	86,4	112,4	137,4
			80		16,2	23,6	43,9	68,6	98,8	128,5	157,0

¹⁾ Values in brackets are valid for undersized Threaded rods with smaller stress area A_s for hot dip galvanised Threaded rods according to EN ISO 10684:2004+AC:2009.

2) Partial factors for performance category C1 see **Table C16.1**; for Anchor rods the factor for steel ductility is 1,0

fischer injection system FIS V Plus

Performances

Characteristic resistance to steel failure under tension / shear loading for Anchor rods and Threaded rods under seismic action (performance category C1)

Annex C14

Appendix 37 / 41

Table C15.1: Characteristic resistance to steel failure under tension / shear loading for **Anchor rods** and **Threaded rods** under seismic action performance category **C2**

Anchor rod / Threaded rod				M10	M12	M16	M20	M24	M27	M30	
Characteristic resistance to steel failure under tension loading											
Anchor rods and Threaded rods, performance category C2 ¹⁾											
Characteristic resistance $N_{Rk,S,C2}$	Steel zinc plated	Property class	4.8	[kN]	-2)	30,3	56,5	88,2	-2)	-2)	-2)
			5.8		-2)	37,9	70,6	110,2	-2)	-2)	-2)
			8.8		-2)	60,6	113,0	176,4	-2)	-2)	-2)
	Stainless steel R and high corrosion resistant steel HCR		50		-2)	37,9	70,6	110,2	-2)	-2)	-2)
			70		-2)	53,1	98,9	154,3	-2)	-2)	-2)
			80		-2)	60,6	113,0	176,4	-2)	-2)	-2)

Characteristic resistance to steel failure under shear loading without lever arm

Anchor rods, performance category C2 ¹⁾

Characteristic resistance $V_{Rk,s,C2}$	Steel zinc plated	Property class	4.8	[kN]	-2)	13,3	28,2	45,2	-2)	-2)	-2)	
					-2)	16,6	35,3	56,5	-2)	-2)	-2)	
					-2)	22,2	47,1	75,4	-2)	-2)	-2)	
	Stainless steel R and high corrosion resistant steel HCR				50	-2)	13,9	29,4	47,1	-2)	-2)	-2)
					70	-2)	19,4	41,2	66,0	-2)	-2)	-2)
					80	-2)	22,2	47,1	75,4	-2)	-2)	-2)

Threaded rods, performance category C2 ¹⁾

[illegible]

¹⁾ Partial factors for performance category C2 see **Table C16.1**; for Anchor rods the factor for steel ductility is 1,0.

2) No performance assessed.

fischer injection system FIS V Plus

Performances

Characteristic resistance to steel failure under tension / shear loading for Anchor rods and Threaded rods under seismic action (performance category C2)

Annex C15

Appendix 38 / 41

Table C16.1: Partial factors for Anchor rods, Threaded rods under seismic action performance category C1 or C2

Anchor rod / Threaded rod			M10	M12	M16	M20	M24	M27	M30
Characteristic resistance to steel failure under tension loading ¹⁾									
Partial factor $\gamma_{Ms,N}$	Steel zinc plated	4.8	[-]	1,50					
		5.8		1,50					
		8.8		1,50					
	Stainless steel R and high corrosion resistant steel HCR	50		2,86					
		70		1,87 / fischer HCR: 1,50 ²⁾					
		80		1,60					
Characteristic resistance to steel failure under shear loading ¹⁾									
Partial factor $\gamma_{Ms,V}$	Steel zinc plated	4.8	[-]	1,25					
		5.8		1,25					
		8.8		1,25					
	Stainless steel R and high corrosion resistant steel HCR	50		2,38					
		70		1,56 / fischer HCR: 1,25 ²⁾					
		80		1,33					

¹⁾ In absence of other national regulations.
²⁾ Only admissible for high corrosion resistant steel HCR, acc. to **Table A7.1**.

Table C17.1: Characteristic resistance to **combined pull-out and concrete failure** for **Anchor rods and Threaded rods** in hammer drilled holes under seismic action performance category **C1**, **concrete ≥ C20/25**; **working life 50 and 100 years**

Anchor rod / Threaded rod			M10	M12	M16	M20	M24	M27	M30	
Combined pullout and concrete cone failure										
Characteristic bond resistance										
Hammer-drilling with standard drill bit or hollow drill bit (dry or wet concrete)										
Temperature range	I: 50 °C / 80 °C	$\tau_{Rk,C1}$	[N/mm ²]	4,5	5,5	5,5	5,5	4,5	4,0	4,0
	II: 72 °C / 120 °C			4,0	4,5	4,5	4,5	4,0	3,5	3,5
Hammer-drilling with standard drill bit or hollow drill bit (water filled hole)										
Temperature range	I: 50 °C / 80 °C	$\tau_{Rk,C1}$	[N/mm ²]	- ¹⁾	5,0	5,0	4,5	4,0	3,5	3,5
	II: 72 °C / 120 °C			- ¹⁾	4,0	4,0	4,0	3,5	3,0	3,0
Installation factors										
Dry or wet concrete		γ_{inst}	[-]	1,0						
Water filled hole				- ¹⁾	1,2					

¹⁾ No performance assessed.

Table C18.1: Characteristic resistance to combined pull-out and concrete failure for Anchor rods / Threaded rods in hammer drilled holes under seismic action performance category C2; concrete $\geq$ C20/25; working life 50 and 100 years

Anchor rod / Threaded rod		M12	M16	M20	
Combined pullout and concrete cone failure					
Characteristic bond resistance					
Hammer-drilling with standard drill bit or hollow drill bit (dry or wet concrete)					
Temperature range	I: 50 °C / 80 °C	$\tau_{Rk,C2}$ [N/mm ²]	1,5	1,3	2,1
	II: 72 °C / 120 °C		1,3	1,2	1,9
Hammer-drilling with standard drill bit or hollow drill bit (water filled hole)					
Temperature range	I: 50 °C / 80 °C	$\tau_{Rk,C2}$ [N/mm ²]	1,3	1,1	1,8
	II: 72 °C / 120 °C		1,1	1,0	1,6
Installation factors					
Dry or wet concrete	γ_{inst}	[-]	1,0		
Water filled hole			1,2		
Displacement-Factors for tension loading ¹⁾					
$\delta_{N,C2(50\%)-Factor}$	[mm/(N/mm ²)]	0,20	0,13	0,21	
$\delta_{N,C2(100\%)-Factor}$		0,38	0,18	0,24	
Displacement-Factors for shear loading ²⁾					
$\delta_{V,C2(50\%)-Factor}$	[mm/kN]	0,18	0,10	0,07	
$\delta_{V,C2(100\%)-Factor}$		0,25	0,14	0,11	

1) Calculation of effective displacement:

$$\delta_{N,C2(50\%)} = \delta_{N,C2(50\%)\text{-Factor}} \cdot \tau$$

$$\delta_{N,C2(100\%)} = \delta_{N,C2(100\%)\text{-Factor}} \cdot \tau$$

τ = acting bond strength under tension loading

2) Calculation of effective displacement:

$$\delta_{V,C2(50\%)} = \delta_{V,C2(50\%)\text{-Factor}} \cdot V$$

$$\delta_{V,C2(100\%)} = \delta_{V,C2(100\%)\text{-Factor}} \cdot V$$

V: acting shear loading

fischer injection system FIS V Plus

Performances

Characteristic resistance under seismic action (performance category C2) for Anchor rods; working life 50 and 100 years

Annex C18

Appendix 41 / 41