



Approval body for construction products and types of construction

Bautechnisches Prüfamt

An institution established by the Federal and Laender Governments



European Technical Assessment

ETA-14/0471 of 3 February 2015

according to Article 66 Paragraph 3 of Regulation (EU)

English translation prepared by DIBt - Original version in German language

General Part

Technical Assessment Body issuing the Deutsches Institut für Bautechnik European Technical Assessment: Trade name of the construction product fischer Injectionsystem FIS GREEN for masonry Product family Injectionsystem for use in masonry to which the construction product belongs fischerwerke GmbH & Co. KG Manufacturer Otto-Hahn-Straße 15 79211 Denzlingen DEUTSCHLAND fischerwerke Manufacturing plant This European Technical Assessment 22 pages including 3 annexes which form an integral part contains of this assessment This European Technical Assessment is Guideline for European technical approval of "Metal issued in accordance with Regulation (EU) Injection Anchors for Use in Masonry", ETAG 029, April No 305/2011, on the basis of 2013, used as European Assessment Document (EAD)

Deutsches Institut für Bautechnik Kolonnenstraße 30 B | 10829 Berlin | GERMANY | Phone: +49 30 78730-0 | Fax: +49 30 78730-320 | Email: dibt@dibt.de | www.dibt.de

No 305/2011.



European Technical Assessment ETA-14/0471 English translation prepared by DIBt

Page 2 of 22 | 3 February 2015

The European Technical Assessment is issued by the Technical Assessment Body in its official language. Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and shall be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may only be made with the written consent of the issuing Technical Assessment Body. Any partial reproduction has to be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission according to Article 25 Paragraph 3 of Regulation (EU) No 305/2011.



Page 3 of 22 | 3 February 2015

Specific Part

1 Technical description of the product

The fischer injectionsystem FIS GREEN for masonry is a bonded anchor (injection type) consisting of a mortar cartridge with fischer injection mortar, a perforated sieve sleeve and an anchor rod with hexagon nut and washer or an internal threaded rod in the range of M6 to M16. The steel elements are made of zinc coated steel, stainless steel or high corrosion resistant steel.

The anchor rod is placed into a drilled hole filled with injection mortar and is anchored via the bond between steel element, injection mortar and masonry and mechanical interlock.

The product description is given in Annex A.

2 Specification of the intended use in accordance with the applicable European Assessment Document

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the anchor of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment

3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Characteristic resistance for tension and shear loads	See Annex C 1 – C 3
Characteristic resistance for bending moments	See Annex C 4
Displacements under shear and tension loads	See Annex C 4
Reduction Factor for job site tests (β -Factor)	See Annex C 4
Edge distances and spacing	See Annex C 5

3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire	Anchorages satisfy requirements for Class A1
Resistance to fire	No performance determined (NPD)

3.3 Hygiene, health and the environment (BWR 3)

Regarding dangerous substances there may be requirements (e.g. transposed European legislation and national laws, regulations and administrative provisions) applicable to the products falling within the scope of this European Technical Assessment. In order to meet the provisions of Regulation (EU) No 305/2011, these requirements need also to be complied with, when and where they apply.



European Technical Assessment

ETA-14/0471

Page 4 of 22 | 3 February 2015

English translation prepared by DIBt

3.4 Safety in use (BWR 4)

The essential characteristics regarding Safety in use are included under the Basic Works Requirement Mechanical resistance and stability.

- 3.5 Protection against noise (BWR 5) Not applicable.
- 3.6 Energy economy and heat retention (BWR 6) Not applicable.

3.7 Sustainable use of natural resources (BWR 7)

The sustainable use of natural resources was not investigated.

3.8 General aspects

The verification of durability is part of testing the essential characteristics. Durability is only ensured if the specifications of intended use according to Annex B are taken into account.

4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

According to Decision of the Commission of 17 February 1997 (97/177/EC) (OJ L 073 of 14.03.97 p. 24-25), the system of assessment and verification of constancy of performance (see Annex V and Article 65 Paragraph 2 to Regulation (EU) No 305/2011) given in the following table applies.

Product	Intended use	Level or class	System
Metal injection anchors for use in masonry	For fixing and/or supporting to masonry, structural elements (which contributes to the stability of the works) or heavy units	_	1


5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable European Assessment Document

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited at Deutsches Institut für Bautechnik.

Issued in Berlin on 03 February 2015 by Deutsches Institut für Bautechnik


Uwe Bender Head of Department *beglaubigt:* Wittstock






Page 6 of European Technical Assessment ETA-14/0471 of 3 February 2015





Page 7 of European Technical Assessment ETA-14/0471 of 3 February 2015





Page 8 of European Technical Assessment ETA-14/0471 of 3 February 2015

English translation prepared by DIBt



Table A1: Materials

Part Designation		Material						
1	Mortar cartridge	Bio based mortar, hardener; fillers						
		Steel, zinc plated	Stainless steel A4	High corrosion- resistant steel c				
2	Threaded rod	Property class 5.8 or 8.8; ISO 898-1:2013 zinc plated \geq 5µm, EN ISO 4042 A2K or hot- dip galvanised EN ISO 10684:2004 $f_{uk} \leq$ 1000 N/mm ² $A_5 > 8\%$	$\begin{array}{c} \mbox{Property class 50, 70} \\ \mbox{or 80} \\ \mbox{EN ISO 3506:2009} \\ 1.4401; 1.4404; \\ 1.4578; 1.4571; \\ 1.4439; 1.4362; \\ 1.4062 \\ \mbox{EN 10088-1:2014} \\ f_{uk} \leq 1000 \ \mbox{N/mm}^2 \\ A_5 > 8\% \end{array}$	Property class 50 or 80 EN ISO 3506:2009 or property class 70 with f_{yk} = 560 N/mm ² 1.4565; 1.4529 EN 10088-1:2014 $f_{uk} \le 1000$ N/mm ² $A_5 > 8\%$				
3	Washer ISO 7089:2000	zinc plated ≥ 5µm, EN ISO 4042:1999 A2K or hot-dip galvanised ISO 10684:2004	1.4401; 1.4404; 1.4578;1.4571; 1.4439; 1.4362 EN 10088-1:2014	1.4565;1.4529 EN 10088-1:2014				
4	Hexagon nut	Property class 5 or 8; ISO 898-2:2013 zinc plated ≥ 5µm, ISO 4042:1999 A2K or hot-dip galvanised ISO 10684:2004	Property class 50, 70 or 80 ISO 3506:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4571; 1.4439; 1.4362 EN 10088-1:2014	Property class 50, 70 or 80 ISO 3506:2009 1.4565; 1.4529 EN 10088-1:2014				
5	Internal threaded anchor FIS E	Property class 5.8; ISO 898-1:2013 zinc plated ≥ 5µm, EN ISO 4042:1999 A2K	Property class 70 EN ISO 3506:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362 EN 10088-1:2014	Property class 70 EN ISO 3506-1:2009 1.4565; 1.4529 EN 10088-1:2014				
6	Perforated sleeve FIS H K		PP / PE					

fischer Injectionsystem FIS GREEN for masonry

Product description Materials

Annex A 4



Specifications of intended use

Anchorages subject to:

Static and quasi-static loads

Base materials:

- Solid brick masonry (Use category b) and autoclaved aerated masonry (Use category d), acc. to Annex B 7.
- Note: The characteristic resistance is also valid for larger brick sizes and higher compressive strength of the masonry unit.
 Hollow brick masonry (use category c), according to Annex B 7.
- Mortar strength class of the masonry M2,5 at minimum according to EN 998-2:2010.
- For other bricks in solid masonry and in hollow or perforated masonry, the characteristic resistance of the anchor may be determined by job site tests according to ETAG 029, Annex B under consideration of the β-factor according to Annex C 4, Table C4.

Temperature Range:

From - 40°C to +80°C (max. short term temperature +80°C and max. long term temperature +50°C)

Use conditions (Environmental conditions):

- · Dry and wet structure (regarding injection mortar).
- Structures subject to dry internal conditions (zinc coated steel, stainless steel or high corrosion resistant steel).
- Structures subject to external atmospheric exposure including industrial and marine environment (stainless steel or high corrosion resistant steel).
- Structures subject to permanently damp internal condition, if no particular aggressive conditions exist (stainless steel or high corrosion resistant steel).
- Structures subject to external atmospheric exposure and to permanently damp internal condition, if other particular aggressive conditions (high corrosion resistant steel) Note: Particular aggressive conditions are e.g. permanent, alternating immersion in seawater or the splash zone of seawater, chloride atmosphere of indoor swimming pools or atmosphere with extreme chemical pollution (e.g. in desulphurization plants or road tunnels where de-icing materials are used).

Design:

- The anchorages have to be designed in accordance with the ETAG 029, Annex C, Design method A under the responsibility of an engineer experienced in anchorages and masonry work.
- Verifiable calculation notes and drawings have to be prepared taking account the relevant masonry in the region of the anchorage, the loads to be transmitted and their transmission to the supports of the structure. The position of the anchor is indicated on the design drawings.

Installation:

- Dry or wet structures (use category d/d and use category w/w).
- Hole drilling by hammer drill mode.
- In case of aborted hole: The hole shall be filled with mortar
- Anchor installation carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters of the site.
- Fastening screws or threaded rods (including nut and washer) must comply with the appropriate material and property class of the fischer internal threaded anchor FIS E
- min. curing time see table B3
- Commercial standard threaded rods, washers and hexagon nuts may also be used if the following requirements are fulfilled:

material dimensions and mechanical properties of the metal parts according to the specifications are given in Annex A4, Table A1

conformation of material and mechanical properties of the metal parts by inspection certificate 3.1 according to EN 10204:2004, the documents shall be stored.

marking of the threaded rod with the envisage embedment depth. This may be done by the manufacturer of the rod or by a person on job site.

fischer Injectionsystem FIS GREEN for masonry

Intended Use Specifications


Annex B 1

Z6024.15

Page 10 of European Technical Assessment ETA-14/0471 of 3 February 2015

English translation prepared by DIBt





Marking:


Property class 8.8 or high corrosion-resistant steel C, property class 80: • Stainless steel A4, property class 50 and high corrosion-resistant steel C, property class 50: ••

Table B1.1: Installation parameters (threaded rod without perforated sleeve)

Size				M6	M8	M10	M12	M16
Nominal drill hole diar	neter	d _{nom} =d ₀	[mm]	8	10	12	14	18
Width across flat		SW	[mm]	10	13	17	19	24
Effective anchorage d	Effective anchorage depth ¹⁾				50 10			100
Depth of drill hole ho =	epth of drill hole $h_0 = h_{ef}$				200			
Maximum torque mon	nent	T _{inst,max}	[Nm]	4 10				
Max. torque moment	for aerated concrete	T _{inst,max}	[Nm]	1 2 4				
Diameter of clearance	Pre-position anchorage	d _f ≤	[mm]	7	9	12	14	18
hole in the fixture	Push through anchorage	d _f ≤	[mm]	9	11	14	16	20

¹⁾ $h_{ef,min} \le h_{ef} \le h_{ef,max}$ is possible.

fischer internal threaded anchor FIS E






Table B1.2: Installation parameters (internal threaded anchor FIS E without perforated sleeve)

high corrosion-resistant steel C: e.g. M8 C

Marking: size, e.g. M8

Size FIS E			11x85 M6	11x85 M8	15x85 M10	15x85 M12	
Nominal drill hole diameter	d _{nom} =d ₀	[mm]	14 18				
Depth of drill hole	h ₀	[mm]	90				
Effective anchorage depth	$L_H = h_{ef}$	[mm]	85				
Maximum torque moment	T _{inst, max}	[mm]	4 10				
Max. torque moment for aerated concrete	T _{inst, max}	[mm]	4				
Diameter of clearance hole in the fixture	d _f ≤	[mm]	7	9	12	14	
Screw-in depth	$L_{E,min}$	[mm]	6	8	10	12	

fischer Injectionsystem FIS GREEN for masonry

Intended Use

Installation parameters, part 1



Perforated sleeves FIS H 12x85; 16x85; 16x130; 20x85; 20x130; 20x200 K




Table B1.3: Installation parameters (threaded rod and internal threaded anchor with perforated sleeve; only pre-positioned anchorage)

Size FIS HK			12x85	16x85	16x130	20x85	20x130	20x200
Nominal drill hole diameter (d_0 = D_{Sleeve})	⁰ d _{nom} =d ₀ [mm]		12	16			20	
Depth of drill hole	h ₀	[mm]	90	90	135	90	135	205
Effective anchorage depth ¹⁾	h _{ef,min}	[mm]	85	85	110	85	110	180
Enective anchorage depth	h _{ef,max}	[mm]	85	85	130	85	130	200
Size of threaded rod		[-]	M6, M8	M8	M8, M10		M12,	M16
Size of internal threaded anchor		[-]		11x85		15x85		
Maximum torque moment threaded rod and internal threaded anchor	T _{inst,max}	[mm]	2			4		

¹⁾ $h_{ef,min} \le h_{ef} \le h_{ef,max}$ is possible.

Perforated sleeves FIS H 18x130/200 K and FIS H 22x130/200 K




Table B1.4: Installation parameters (threaded rod with perforated sleeve; pushthrough anchorage)

Size FIS HK			18x130/200	22x130/200	
Nominal drill hole diameter (d ₀ = D _{Sleeve})	d _{nom} =d ₀	[mm]	18	22	
Depth of drill hole	h ₀	[mm]	135 + t _{fix}		
Effective anchorage depth	h _{ef,min}	[mm]	130		
Size of threaded rod		[-]	M10 or M12	M16	
Maximum torque moment threaded rod	T _{inst,max}	[Nm]	4	4	
Diameter of clearance hole in the fixture	d _f ≤	[mm]	18	22	
Thickness of fixture	t _{fix.max}	[mm]	20	00	

fischer Injectionsystem FIS GREEN for masonry


Intended Use

Installation parameters, part 2.

Page 12 of European Technical Assessment ETA-14/0471 of 3 February 2015

English translation prepared by DIBt





Only for solid bricks and aerated concrete

Table B2: Parameters of steel brush

Drill hole diameter	d ₀	[mm]	8	10	12	14	16	18	20	22
Brush diameter	d _{b,} nom	[mm]	9	11	14	16	20	20	25	25

Table B3:Maximum processing time of the mortar and minimum curing time(During the curing time of the mortar the masonry temperature may not fall below the listed minimum temperature).

Temperature at			Minimum curing time ¹⁾		
anchoring base		base	t _{cure}		
	[°C]		[minutes]		
>±0	to	+5	6 hours		
>+5	to	+10	4 hours		
>+10	to	+20	90		
>+20	to	+30	60		
>+30	to	+40	30		

System-	Maximum processing
temperature	time t _{work}
(mortar) [°C]	[minutes]
+5	13
+10	9
+20	5
+30	4
+40	2

¹⁾ For wet masonry the curing time must be doubled.

fischer Injectionsystem FIS GREEN for masonry


Intended Use Steel brush

Processing times and curing times




1	→ (Ì	Remove the sealing cap.	■ ■ □ <u>→</u>)	Screw on the static mixer (the spiral in the static mixer must be clearly visible).
2		Place the cartridge into the dispenser.	<×	Press approx. 10 cm of material out until the resin is well mixed. Mortar which is not grey in colour will not cure and mus be disposed off.
Inst 3	tallation in solid brick a	nd aerated concrete (with Drill the hole. Depth of d		
J		h_0 and drill hole diamete Table B1.1 or B1.2		
4	2x		2x	Blow out the drill hole twice. Brush twice and blow out twice again.
5		Fill approx. 2/3 of the dril hole with mortar beginning from the bottom of the hole ¹⁾ . Avoid bubbles.		For push through installation (not FIS E) fill the annular gap also with mortar.
6		Insert the threaded rod o	r internal threaded ancho	readed rod for setting depth. r FIS E by hand using light mark, excess mortar must
7	Do not tour Minimum of see Table	uring time		iting the fixture. _{ax} see Table B1.1 or B1.2
¹⁾ Fo	or the exact quantity of m	ortar see manufacturer`s s	spezification.	






¹⁾ For the exact quantity of mortar see manufacturer's spezification.






Page 15 of European Technical Assessment ETA-14/0471 of 3 February 2015









 $^{1)}$ Other combinations can be used after job site tests acc. to ETAG 029, Annex B. The β - factor for this job site tests are given in Table C4

fischer Injectionsystem FIS GREEN for masonry

Intended Use Allocation of anchor rods, perforated sleeves and bricks, part 1

Annex B 8

Electronic copy of the ETA by DIBt: ETA-14/0471






Table B4.2: Allocation of anchor rods¹⁾, perforated sleeves¹⁾ and bricks

fischer Injectionsystem FIS GREEN for masonry

Intended Use Allocation of anchor rods, perforated sleeves and bricks, part 2



	Donoity o			Effective anchorage depth		Characteristic resistance [kN]					
	Density ρ [kg/dm³]		Anchor size or			N _{Rk} ¹⁾			•]	V _{Rk} ²⁾	
Driek	- Compressive	Classes	screw size in internal threaded	F	h	Temp. 24/40°C		Temp. 50/80°C		All	
Brick No.	strength f _b [N/mm ²]	Sleeve FIS HK	anchor	h _{ef,min} [mm]	h _{ef,max} [mm]	d/d	w/w	d/d	w/w	categorie	
			M6	50	85	1,5 (1,5)	0,9 (0,9)	1,5 (1,5)	0,9 (0,9)	4,0	
			M8	50	200	2,5 (2,5)	2,5 (2,5)	2,5 (2,5)	2,5 (2,5)	(2,5)	
115 -			M10	50	79	4,5 ((3,0)	4,5 ((3,0)	6,0	
R.	ρ≥1,8		M10	80	199	6,0 ((4,5)	6,0 (4,5)		(4,0)	
	$f_b \ge 20$	without	M10	200	200	12,0 ((11,0)	12,0 ((11,0)	12,0 (8,	
340	(f _b ≥10)		M12	50	79	4,0 (3,0)		4,0 (3,0)		// -	
1			M12	80	199	7,0(5,0)		7,0 (5,0)		5,5 (4,0)	
			M12	200	200	10,0 (7,0)		10,0 (7,0)		12,0 (11,	
			FIS E M6/8, FIS E M10/M12	85	85	6,0 (6,0 (4,5)		(4,5)	4,0 (2,5	
			M6	50	85	1,5 (1,5)	0,9 (0,9)	1,5 (1,5)	0,9 (0,9)	4,0 (3,0	
115			M8	50	200	2,5 ((2,5)	2,5 ((2,5)		
t.			M10	50	79	3,0 (3,0 (2,5)		5,5 (4,0)	
	ρ ≥ 1,8		M10	80	199	4,0 (3,0)		4,0 ((3,0)	5,5 (4,0)	
	$f_b \ge 20$	without	M10	200	200	12,0	(9,0)	12,0 (9,0)			
240	(f _b ≥10)		M12	50	79	3,0 (2,0)		3,0 (2,0)		7,0 (5,0)	
~			M12	80	199	4,5 (3,0)		4,5 (3,0)			
2			M12	200	200	12,0 (9,0)		12,0 (9,0)			
			FIS E M6/8, FIS E M10/M12	85	85	4,0 ((2,5)	4,0 ((2,5)	4,0 (3,0	
115 8		12x85	M6/8	85	85	8,0 (5,5)		4,5 (3,0)		4,5 (3,0	
48		16x85	M8/M10	85	85	4,5 ((3,5)	3,0 (2,0)			
30 3	ρ ≥ 1,8 f _b ≥ 20	20x85	M12/M16	85	85	12,0	(9,5)	8,0 (5,5)			
	(f _b ≥10)	16x130 18x130/200 20x130 22x130/200	M8/M10 M10/M12	110	130	4,5 (3,0)		2,5 (2,0)		5,5 (3,5)	
			M12/M16 M16	110	130	8,5 ((6,0)	5,0 ((3,5)	1	
108 *			M6	50	200	1,5	0,9	1,5	0,9	2,5	
· 25	ρ ≥ 1,8	without	M8	50	200	2	,0	2	,0	4,0	
- 20	f _b ≥ 20	without	M10	50	200	2	,0	2	,0		
4			M12	50	200	3,0 3,0			5,5		

² For design according to ETAG 029, Annex C: $N_{Rk} = N_{Rk,p} = N_{Rk,p} = N_{Rk,s}$ ²⁾ For design according to ETAG 029, Annex C: $V_{Rk} = V_{Rk,c} = V_{Rk,c} = V_{Rk,s}$

fischer Injectionsystem FIS GREEN for masonry

Performances

Characteristic values of resistance to tension load and shear load, part 1



Table C1.2: Chara perfo	acteristic va rated bricks		sistance to ter	nsion le	oads ar	nd to she	ear loads	s for	
•	Density_ρ				ctive ge depth				
	[kg/dm ³]		Anghanging an			N _R	V _{Rk} ²⁾		
Brick	Compressive strength f _b	Sleeve	Sharry and the second	h _{ef,min}	h _{ef,max}	Temp. 24/40°C	Temp. 50/80°C	All catego- ries	
No.	[N/mm ²]	FIS HK	anchor	[mm]	[mm]	d/d w/w	d/d w/w	1100	
5	ρ ≥ 1,4 f _b ≥ 8	12x85 16x85 20x85	M6/M8 M8/M10 M12/M16	85	85	3,5	2,0	2,5	
		12x85	M6/M8	85	85	3,5 (2,0)	2,0 (1,2)	4,5 (2,5)	
ar 115 -	ρ ≥ 1,4 f _b ≥ 20 (f _b ≥ 12)	16x85	M8/M10	85	85			8,0 (5,5)	
		20x85	M10, M12/M16,	85	85	5,5 (3,5)	3,5 (2,0)	7,5 (4,5)	
		16x130 18x130/200	M8/M10 M10/M12	110	130			8,0 (5,5)	
		20x130 22x130/200	M12/M16 M16	110	130	4,5 (2,5)	2,5 (1,5)	7,5 (4,5)	
		12x85	M6/M8	85	85	2	1,2	2,5	
370 41		16x85	M8/M10	85	85	1,5	0,9	3,0	
	ρ ≥ 0 ,6	20x85	M12,M16	85	85	2,0	1,2	1,5	
	p ≥ 0,0 f _b ≥ 8	16x130 18x130/200	M8/M10 M10/M12	130	130	2,5	1,5	3,0	
** 7		20x130 22x130/200	M12/M16 M16	110	130	2,0	1,2	1,5	
		20x200	M12/M16	180	200	2,5	1,5	1,5	
		12x85	M6, M8	85	85	3,5	2,0	4,0	
E E		16x85	M8,M10	85	85	3,5	2,0	5,5	
	ρ ≥ 0,9	20x85	M12, M16	85	85	4,0	2,5	6,0	
	f _b ≥10	16x130 18x130/200	M8/M10 M10/M12	110	130	4,5	2,5	5,5	
240 8		20x130 22x130/200	M12/M16 M16	110	130	3,5	2,0	6,0	

¹⁾ For design according to ETAG 029, Annex C: $N_{Rk} = N_{Rk,p} = N_{Rk,b} = N_{Rk,s}$ ²⁾ For design according to ETAG 029, Annex C: $V_{Rk} = V_{Rk,b} = V_{Rk,c} = V_{Rk,s}$

fischer Injectionsystem FIS GREEN for masonry

Performances

Characteristic values of resistance to tension load and shear load, part 2



Table C1.3: Characteristic values of resistance to tension loads and shear loads foraerated concrete										
				Effective anchorage depth		Characteristic resista				ance [kN]
	Density ρ [kg/dm³]	N _{Rk} ¹⁾				V _{Rk} ²⁾				
Brick	- Compressive strength f _b	Sleeve	Anchor size or screw size in internal threaded	h _{ef,min}	h _{ef,max}	Temp. 24/40°C		Temp. 50/80°C		All catego-
No.	[N/mm ²]	FIS HK	anchor	[mm]	[mm]	d/d	w/w	d/d	w/w	ries
			M6	100	200	1,5	1,2	1,5	1,2	
	ρ ≥ 350 f _b ≥ 2	without	M8	100	200	2,0	1,5	2,0	1,5	0,9
			M10	100	200	2,0	1,5	2,0	1,5	0,0
			M12	100	200	2,5	2,0	2,5	2,0	
			M16	100	200	2,5	2,0	2,5	2,0	1,2
175	ρ ≥ 500 f _b ≥ 4	without	M6	100	200	2,0	1,5	2,0	1,5	1,5
*			M8	100	200	2,5	2,0	2,5	2,0	
			M10	100	200	3,0	2,0	3,0	2,0	
*			M12	100	200	3,0	2,5	3,0	2,5	
9			M16	100	200	3,0	2,5	3,0	2,5	
			M6	100	200	2,5	2,0	2,5	2,0	
		without	M8	100	200	3,5	2,5	3,5	2,5	2,5
	ρ ≥ 650 f _b ≥ 6		M10	100	200	4,0	3,0	4,0	3,0	2,5
			M12	100	200	4,0	3,0	4,0	3,0	
			M16	100	200	4,0	3,0	4,0	3,0	2,0

 $^{1)}$ For design according to ETAG 029, Annex C: N_{Rk} = $N_{Rk,p}$ = $N_{Rk,b}$ = $N_{Rk,s}$ $^{2)}$ For design according to ETAG 029, Annex C: V_{Rk} = $V_{Rk,b}$ = $V_{Rk,c}$ = $V_{Rk,s}$

fischer Injectionsystem FIS GREEN for masonry

Performances

Characteristic values of resistance to tension loads and shear loads for aerated concrete, part 3



Table C2:	C2: Characteristic bending moments								
Size					M6	M8	M10	M12	M16
Charac- teristic bending moment M _{Rk,s}	Zinc-plated	Property	5.8	[Nm]	8	19	37	65	166
	steel	class	8.8	[Nm]	12	30	60	105	266
	Stainless	Property	50	[Nm]	8	19	37	65	166
	steel A4	class	70	[Nm]	11	26	52	92	232
	High	50	[Nm]	8	19	37	65	166	
	corrosion- resistant	corrosion- Property resistant class steel C	70 ¹⁾	[Nm]	11	26	52	92	232
			80	[Nm]	12	30	60	105	266

¹⁾ f_{uk} = 700 N/mm²; f_{yk} = 560 N/mm²

Displacements under tension load and shear load Table C3:

	N	δ _{N0}	δ_{N^∞}
	[kN]	[mm]	[mm]
Solid bricks ¹⁾	N _{Rk}	1,32	2,64
Perforated bricks ²⁾	$\frac{1}{1} \frac{1}{4} \frac{1}$	1,0	2,0
Aerated concrete	1,4 * γ _M	1,0	2,0

V	δ _{vo}	$\delta_{V\infty}$
[kN]	[mm]	[mm]
V _{Rk}	1,2	1,8
	1,9	2,85
1,4 * γ _M	2,93	4,4

¹⁾ Brick No.: 1; 2; 3; 4 ²⁾ Brick No.: 5; 6; 7; 8

β- factor for job site tests according to ETAG 029, Annex B Table C4:

Brick	Size	β- Factor						
No.		Temp 2	4°C/40°C	Temp 50°C/80°C				
		d/d	w/w	d/d	w/w			
	M6;M8	0,8	0,48	0,80	0,48			
1	M12x200	0,78	0,78	0,78	0,78			
	Other sizes	0,84	0,84	0,84	0,84			
	Other sizes	0,84	0,84	0,81	0,81			
2	M8x200	0,55	0,55	0,55	0,54			
	M6x50	0,84	0,51	0,84	0,51			
3	All sizes	0,84	0,84	0,51	0,5			
4	Other sizes	0,84	0,84	0,84	0,84			
4	M6x50	0,84	0,51	0,84	0,51			
5	All sizes	0,71	0,71	0,43	0,43			
6	All sizes	0,84	0,84	0,51	0,50			
7	Other sizes	0,84	0,84	0,51	0,51			
	20x130,20x200	0,67	0,67	0,41	0,4			
8	All sizes	0,84	0,84	0,51	0,50			
9	All sizes	1,0	0,79	1,0	0,79			

fischer Injectionsystem FIS GREEN for masonry

Performances

Characteristic bending moments; displacements; β- factors for job site tests

Table C5:



Min. Direction to bed joint \bot thickness of the \mathbf{S}_{cr} \mathbf{S}_{cr} \mathbf{S}_{min} \mathbf{S}_{min} Cmin h_{ef} masonry Brick No. [mm] members [mm] [mm] [mm] [mm] [mm] | [mm] 100 50 150 150 1, 2 100 80 240 240 150 200 300 300 100 85 255 255 h_{ef} + 30 (≥ 80) 3 130 100 390 390 4 50 100 150 150 5 all sizes 100 55 230 100 all sizes 115 240 6 7 all sizes 120 240 250 120 8 all sizes 115 240 9 80 115 240 all sizes s_a II Ο \odot S_{min} || Cmin s_{min} || = Minimum spacing anchor group parallel to bed joint s_{min}^{\perp} = Minimum spacing anchor group vertical to bed joint s_{cr}|| = Characteristic spacing anchor group parallel to bed joint s_{cr}^{\perp} = Characteristic spacing anchor group vertical to bed joint c_{cr} = c_{min} = Edge distance group of 2 anchors: $N_{Rk}^{g}=2x N_{Rk}$; $V_{Rk}^{g}=2x V_{Rk}$ group of 4 anchors: $N_{Rk}^{g}=4x N_{Rk} V_{Rk}^{g}=4x V_{Rk}$ fischer Injectionsystem FIS GREEN for masonry Annex C 5 Performances Edge distance and spacing

Edge distance and spacing (installation with and without sleeves)

8.06.04-328/14