

Technical Data Sheet

Injection Mortar FIS EM

Prepared on: 19.11.2008
Version: 4.1

Reviewed on: 05.12.2017

Printing Date: 05.12.2017
Page: 1 von 1

Product Description: High-performance epoxy mortar for concrete
Colour: dark-grey

Technical Data:

Product Data	Testing Method	Results
--------------	----------------	---------

Stability		
UV-resistance (sunlight)		not resistant
Temperature resistance		100 °C
Water resistance		resistant
Water absorption		after 14 days: 0.18 %
Cleaning agents		1% tenside solution no effects

Physical properties		
Shrinkage		< 0.01 %
Density		1.4 - 1.6 g/cm ³

Workability features		
Viscosity (20 °C)	Brookfield (Sp.7) 10 U/min	~ 100 Pas
Open time [min] +5 to +10 °C +10 to +20°C +20 to +30 °C +30 to +40 °C		120 30 14 7
Curing time [h] +5 to +10 °C +10 to +20°C +20 to +30 °C +30 to +40 °C		40 18 10 5
Shelf life		36 months