

Technical Data Sheet

Injection Mortar FIS SB High Speed

Prepared on: 12.02.2014
Version: 1.1

Reviewed on: 12.06.2014

Printing Date: 12.06.2014
Page: 1 von 1

Product Description: High performance hybrid mortar in shuttle cartridge,
styrene free
Colour: grey

Technical Data:

Product Data	Testing Method	Results
--------------	----------------	---------

Stability		
UV-resistance (sunlight)		resistant
Temperature resistance		150 °C
Water resistance		resistant
Water absorption		after 14 days: 0.8 %
Cleaning agents		1 % tenside solution no effects
Long-term behaviour (Freezing and thawing resistance)	EOTA part 5	approved suitability for outside applications

Physical properties		
Shrinkage		< 0.8 %
Hardness Shore A		after 45 min: > 85
pH-value		after 24 hours: > 12 (22 °C)
Density		1.7 - 1.9 g/cm ³

Workability features		
Viscosity (20 °C)	Brookfield (Sp.7) 10 U/min	120 – 160 Pas
Open time (10 – 20 °C)		4 – 5 min
Curing time (10 – 20 °C)		30 min
Shelf life		12 months