







Consistency	Powder
Number of Components	1
Grain size	≤ 2 mm
Wet mortar density	2 kg/l
Colour	Grey
Shelf life	Min. 12 months when stored dry, permanent stored < 30 °C and unopened
Packaging	25 kg paper bag with PE inlay
GISCODE	ZP1
Art.-No.	574217

Processing		
Processing temperature (Material, air and substrate)		5 °C to 30 °C
Mixing ratio mortar		2.8 l water per 25 kg bag
Mixing ratio 1 kg		0.11 l water per kg
Mixing time		3 min
Maturing time		1 min
Final mixing time		1 min
Working time*		60 min
Single layer min.		5 mm
Single layer max.		20 mm
Two layers max.		40 mm
Concrete outbreak		70 mm
Wet mortar consumption per 1 mm thickness		2 kg/m ²
Dry mortar consumption per 1 mm thickness		1.8 kg/m ²
Coverage of 25 kg bag		Approx. 2.8 m ² at 5 mm layer thickness
Application technique		Manual (Trowel), Wet Spray 
Approved machines		See machine list

*At 20 °C. Higher temperatures decrease the given times, while lower temperatures increase them.

Processing guidelines	
Preparation concrete surface	<ul style="list-style-type: none"> • Must not contain loose parts • Dust free and clean • Check for adequate adhesive tensile strength

	<ul style="list-style-type: none"> • Damp surface without puddles (Matt appearance) • Pre-wet surface at latest 2 h before work • Keep surface wet
Preparation reinforcement	<ul style="list-style-type: none"> • Any visible corrosion must be removed • Cleaning grade if corrosion protection used: SA 2½ • Basic Cleaning grade: SA 2
Processing indications	<ul style="list-style-type: none"> • Use tap water for mixing with mortar • Add CreNovate FCRM-RM R3 SR to bucket with water • Mix as long as described under processing and until free of lumps • Never add any substances to the mortar except tap water • Never add water after mortar has started to set • Only mechanical mixing of mortar • Dropped mortar must be thrown away
Subsequent processing	<ul style="list-style-type: none"> • Mortar must be protected against direct sunlight, strong wind, rain and frost for at least 48 h
Cleaning	<ul style="list-style-type: none"> • After use, clean tools with water immediately • Once cured, the product can only be removed mechanically
Safety / Disposal	For safety information related to transport, storage, handling, and disposal of the product, refer to the current Safety Data Sheet.

Please note that the data and information provided above are guidelines from laboratory and real-life experience and are not binding. This general information describes our products and their use, but due to varied working conditions, not every case can be covered. We recommend conducting tests or consulting us if in doubt. We provide information to outline our products and services, without guaranteeing specific properties or suitability for a particular purpose. Upon publication of a new version, the current Technical Data Sheet becomes invalid.