

Technical Data Sheet



Injection Mortar FIS RC II Low Speed

Prepared on: 08.10.2025
Version: 1.0

Reviewed on: -

Printing Date: 08.10.2025
Page: 1 von 2

Product Description: High performance hybrid mortar in shuttle cartridge,
styrene free
Colour: grey

Technical Data:

Product Data	Testing Method	Results
--------------	----------------	---------

Stability		
UV-resistance (sunlight)		resistant
Temperature resistance		120 °C
Water resistance		resistant
Water absorption		after 14 days: 0.8 %
Cleaning agents		1 % tenside solution no effects
Long-term behaviour (Freezing and thawing resistance)	EAD 330499	approved suitability for outside applications

Physical properties		
Shrinkage		< 0.9 %
Hardness Shore D		after 45 min: > 80
Density		1.6 - 1.8 g/cm ³
Thermal conductivity		0,73 W/mK
Contact resistance		1,8 x 10 ¹² Ωcm

Technical Data Sheet



Injection Mortar FIS RC II Low Speed

Prepared on: 08.10.2025
Version: 1.0

Reviewed on: -

Printing Date: 08.10.2025
Page: 2 von 2

Workability features		
Viscosity (20 °C)	Brookfield (Sp.7) 10 U/min	110 – 150 Pas
Open time -5 - 0 °C 1 - 5 °C 6 - 10 °C 11 - 20 °C 21 - 30 °C 31 - 40 °C		40 min 30 min 20 min 13 min 9 min 7 min
Curing time -5 - 0 °C 1 - 5 °C 6 - 10 °C 11 - 20 °C 21 - 30 °C 31 - 40 °C		120 h 48 h 24 min 120 min 60 min 45 min
Shelf life 360ml cartridge 825ml cartridge		24 months 18 months