

Curing times

FIS HB System temperature FIS HB (Mortar min. +5 °C) [°C]	Maximum processing time FIS HB t_{work} [min.]	Minimum curing time FIS HB ¹⁾ t_{cure} [min.]
-5 – -1	–	360
0 – +4	–	180
> +5 – +9	15	90
> +10 – +19	6	35
> +20 – +29	4	20
> +30 – +40	2	12

1) In wet concrete the curing times must be doubled.