

Curing times

FIS P 360 S Cartridge temperature (mortar) [°C]	Maximum processing time t_{work} [min.]	Temperature at anchoring base [°C]	Minimum curing time t_{cure}	
			[hrs.]	[min.]
		-5	8	-
		0	4	-
+5	14	+5	2	-
+20	5	+20	-	60
+30	3	+30	-	30
+40	2	+40	-	20

Please note: The curing times apply for dry anchoring bases, in damp anchoring bases they should be doubled.